

Synthesis and styrene copolymerization of novel halogen ring-substituted isobutyl phenylcyanoacrylates

Gabrielle Escalante, Victoria Escalante, Amanda A. Hartoun, Cynhia B. Hsu, Yousef A. Ibrahim, Will R. Jones, Charles Y. Jun, Madeleine M. Karpiuk, Eghe S. Obaseki, Phillip A. Osak, Jessica R. Schwartzwald, Ryan W. Sloan, Sara M. Rocus, William S. Schjerven and Gregory B. Kharas

DePaul University, Chemistry and Biochemistry Department, 1110 West Belden Avenue, Chicago, IL 60614-3214

ABSTRACT

Novel halogen ring-substituted isobutyl phenylcyanoacrylates, $RPhCH=C(CN)CO_2CH_2CH(CH_3)_2$, where R is 5-bromo-2,4-dimethoxy, 2-bromo-3-hydroxy-4-methoxy, 3-chloro-2,6-difluoro, 4-chloro-2,6-difluoro, 2,3,5-trichloro, 2,3,6-trichloro, 2,3,4-trifluoro, 2,3,5-trifluoro, 2,4,5-trifluoro, 2,4,6-trifluoro, 3,4,5-trifluoro, 2,3,5,6-tetrafluoro, 2,3,4,5,6-pentafluoro were synthesized by the piperidine catalyzed Knoevenagel condensation of ring-substituted benzaldehydes and isobutyl cyanoacetate and characterized by CHN analysis, IR, 1H and ^{13}C NMR. The acrylates were copolymerized with styrene in solution with radical initiation (ABCN) at 70°C. The compositions of the copolymers were calculated from nitrogen analysis.

*Address correspondence: Gregory B. Kharas, Chemistry and Biochemistry Department, DePaul University, Chicago, IL 60614-3214. Fax: 773-325-7421; E-mail: gkharas@depaul.edu

1. Introduction

Cyanoacrylates is family of vinyl monomers renowned for their high reactivity, instant adhesive properties, and wide-ranging applications [1–3]. Trisubstituted ethylenes (TSE), ring-functionalized (R^1) alkyl (R^2) phenylcyanoacrylates, $R^1\text{PhCH} = \text{C}(\text{CN})\text{CO}_2R^2$ (PCA) continue to attract attention as compounds with variety of applications [4–11]. Thus, methoxy ring-substituted methyl phenylcyanoacrylate, MPCA was used in synthesis of pyridotriazines and triazolopyridines [4]. Dimethylamino ring-substituted MPCA was examined among other cyanovinylheteroaromatics in relation to organic nonlinear optics [5]. There are a number of applications of ethyl phenylcyanoacrylate, EPCA and its ring-substituted derivatives which include studies of catalysis [6] and potential antimicrobial and antioxidant agents [7]. 2,4-Dimethoxyphenyl EPCA was used in design, synthesis and study of anticancer activity of novel benzothiazole analogues [8], in synthesis of thiazacridine derivatives as anticancer agents against breast and hematopoietic neoplastic cells [9] and in DABCO-catalyzed Knoevenagel condensation using hydroxy ionic liquid as a promoter [10]. This EPCA was involved in catalysis study of N,N'-dialkylimidazolium dimethyl phosphates [11], in synthesis and study of antimicrobial

activity of some cyanoacrylates [12], as well as in synthesis of antiproliferative active 2-aminobenzimidazole derivatives [13].

In regards to polymerization reactivity, previous studies showed that PCAs as all TSE monomers containing double bond substituents larger than fluorine have very low reactivity in radical homopolymerization due to polar and steric reasons [14]. Although steric difficulties preclude homopolymerization of such monomers, their copolymerization with a monosubstituted alkenes makes it possible to overcome these steric problems. Thus, copolymerization of electrophilic TSE monomers having double bonds substituted with halo, cyano, and carbonyl groups and electron-rich monosubstituted ethylenes such as styrene, *N*-vinylcarbazole, and vinyl acetate [15-17] show a tendency toward the formation of alternating copolymers - thus suggesting a way of functionalization of commercial polymers via introduction of isolated monomer units in copolymers. Earlier we have reported synthesis and styrene copolymerization of a number of halogen ring-substituted methyl [18], propyl [19, 20], and isopropyl [21-22] PCAs.

Our objectives in exploration of novel isobutyl phenylcyanoacrylates (IPCA) were twofold: (1) to utilize Knoevenagel condensation for synthesis of IPCA compounds with a variety of potentially reactive functional groups and (2) to explore feasibility of radical copolymerization with a commercial monomer styrene.

Thus, in continuation of our investigation of novel IPCA compounds we have prepared halogen ring-substituted isobutyl PCA, $RPhCH=C(CN)CO_2CH_2CH(CH_3)_2$, where R is 5-bromo-2,4-dimethoxy, 2-bromo-3-hydroxy-4-methoxy, 3-chloro-2,6-difluoro, 4-chloro-2,6-difluoro, 2,3,5-trichloro, 2,3,6-trichloro, 2,3,4-trifluoro, 2,3,5-trifluoro, 2,4,5-trifluoro, 2,4,6-

trifluoro, 3,4,5-trifluoro, 2,3,5,6-tetrafluoro, 2,3,4,5,6-pentafluoro, and explored the feasibility of their copolymerization with styrene. To the best of our knowledge, there have been no reports on either synthesis of these compounds, nor their copolymerization with styrene [23].

2. Experimental

2.1. Materials

5-bromo-2,4-dimethoxy, 2-bromo-3-hydroxy-4-methoxy, 3-chloro-2,6-difluoro, 4-chloro-2,6-difluoro, 2,3,5-trichloro, 2,3,6-trichloro, 2,3,4-trifluoro, 2,3,5-trifluoro, 2,4,5-trifluoro, 2,4,6-trifluoro, 3,4,5-trifluoro, 2,3,5,6-tetrafluoro, 2,3,4,5,6-pentafluorobenzaldehyde, isobutyl cyanoacetate, piperidine, styrene, 1,1'-azobis(cyclohexanecarbonitrile) (ABCN), and toluene supplied from Sigma-Aldrich Co., were used as received.


2.2. Instrumentation

Infrared spectra of the IPCA compounds and polymers (NaCl plates) were determined with an ABB FTLA 2000 FT-IR spectrometer. The melting points of the IPCA compounds were measured with TA (Thermal Analysis, Inc.) Model Q10 differential scanning calorimeter (DSC). ^1H and ^{13}C NMR spectra were obtained on 10-25% (w/v) IPCA solutions in CDCl_3 at ambient temperature using Avance 300 MHz spectrometer. CHN-elemental analyses of IPCA compounds and nitrogen analysis of the copolymers were performed by Midwest Microlab, LLC (IN).

3. Results and discussion

3.1. Synthesis and characterization of isobutyl phenylcyanoacrylates

All isobutyl phenylcyanoacrylates (IPCA) compounds were synthesized by Knoevenagel condensation [24] of appropriate benzaldehydes with isobutyl cyanoacetate, catalyzed by base, piperidine (Scheme 1).



Scheme 1. Synthesis of isobutyl R-phenylcyanoacrylates, where R is 5-bromo-2,4-dimethoxy, 2-bromo-3-hydroxy-4-methoxy, 3-chloro-2,6-difluoro, 4-chloro-2,6-difluoro, 2,3,5-trichloro, 2,3,6-trichloro, 2,3,4-trifluoro, 2,3,5-trifluoro, 2,4,5-trifluoro, 2,4,6-trifluoro, 3,4,5-trifluoro, 2,3,5,6-tetrafluoro, 2,3,4,5,6-pentafluoro.

The preparation procedure was essentially the same for all the monomers. In a typical synthesis, equimolar amounts of isobutyl cyanoacetate and an appropriate benzaldehyde were mixed in equimolar ratio in a 20 mL vial. A few drops of piperidine were added with stirring. The reactions was allowed to proceed 48 hrs at r.t. The product of the reaction was isolated by filtration and purified by crystallization from 2-propanol. The condensation reaction proceeded smoothly, yielding products, which were purified by conventional techniques. Melting points of the compounds in crystalline state were measured by DSC. The compounds were characterized by IR, ^1H and ^{13}C NMR spectroscopies. No

stereochemical analysis of the novel ring-substituted IPCA was performed since no stereoisomers (*E* or/and *Z*) of known configuration were available.

3.1.1. Isobutyl 5-bromo-2,4-dimethoxyphenylcyanoacrylate

Yield: 97%; mp 152°C; ¹H NMR: δ 8.6 (s, 1H, CH=), 8.5, 6.4 (2H, Ph), 4.1 (d, 2H, CH₂), 4.0 (s, 6H, CH₃O), 2.1 (m, 1H, CH), 1.2 (t, 3H, CH₃), 1.0 (d, 6H, CH₃); ¹³C NMR: δ 163 (C=O), 160 (HC=), 147, 133, 119, 115, 100, 95 (Ph), 116 (CN), 103 (C=), 72 (CH₂), 57, 56 (CH₃O), 28 (CH), 19 (CH₃); IR (cm⁻¹) 2964 (m, C-H), 2216 (m, CN), 1703 (s, C=O), 1663 (s, C=C), 1286 (s, C-O-CH₃), 959 (s, C-H out of plane). Anal. calcd. for C₁₆H₁₈BrNO₄: C, 52.19; H, 4.93; N, 3.80; Found: C, 51.27; H, 4.81; N, 3.46.

3.1.2. Isobutyl 2-bromo-3-hydroxy-4-methoxyphenylcyanoacrylate

Yield 92%; mp 135°C; ¹H NMR: δ 10.2 (s, 1H, OH), 8.6 (s, 1H, CH=), 8.0, 7.1 (2H, Ph), 4.1 (d, 2H, CH₂), 4.0 (s, 3H, CH₃O), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ¹³C NMR: δ 163 (C=O), 153 (HC=), 149, 123, 121, 111 (Ph), 116 (CN), 102 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR (cm⁻¹) 2972 (m, C-H), 2216 (m, CN), 1715 (s, C=O), 1583 (s, C=C), 1245 (s, C-O-CH₃), 943 (s, C-H out of plane). Anal. calcd. for C₁₅H₁₆BrNO₄: C, 50.87; H, 4.55; N, 3.95; Found: C, 52.02; H, 4.88; N, 3.89.

3.1.3. Isobutyl 3-chloro-2,6-difluorophenylcyanoacrylate

Yield 84%; mp 46°C; ¹H NMR: δ 8.2 (s, 1H, CH=), 7.5, 7.0 (s, 2H, Ph), 4.0 (d, 2H, CH₂), 2.0 (m, 1H, CH), 1.0 (d, 6H, CH₃); ¹³C NMR: δ 161 (C=O), 157 (HC=), 142, 134, 133, 113, 112 (Ph), 118 (CN), 104 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR (cm⁻¹) 2964 (m, C-H), 2223 (m, CN), 1732 (s, C=O), 1732 (s, C=C), 1269 (s, C-O-CH₃), 943 (s, C-H out of

plane). Anal. calcd. for $C_{14}H_{12}ClF_2NO_2$: C, 56.11; H, 4.04; N, 4.67; Found: C, 55.65; H, 4.54; N, 4.56.

3.1.4. Isobutyl 4-chloro-2,6-difluorophenylcyanoacrylate

Yield 81%; mp 50°C; 1H NMR: δ 8.2 (s, 1H, CH=), 7.1 (s, 2H, Ph), 4.1 (d, 2H, CH_2), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH_3); ^{13}C NMR: δ 163 (C=O), 158 (HC=), 141, 140, 114, 111, 109 (Ph), 116 (CN), 104 (C=), 73 (CH_2), 28 (CH), 19 (CH_3); IR (cm^{-1}) 3076 (m, C-H), 2224 (m, CN), 1726 (s, C=O), 1602 (s, C=C), 1272 (s, C-O- CH_3), 911 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}ClF_2NO_2$: C, 56.11; H, 4.04; N, 4.67; Found: C, 56.46; H, 4.39; N, 4.82.

3.1.5. Isobutyl 2,3,5-trichlorophenylcyanoacrylate

Yield 79%; mp 41°C; 1H NMR: δ 8.6 (s, 1H, CH=), 8.0, 7.7 (s, 2H, Ph), 4.1 (d, 2H, CH_2), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH_3); ^{13}C NMR: δ 161 (C=O), 150 (HC=), 135, 133, 128, (Ph), 114 (CN), 109 (C=), 73 (CH_2), 28 (CH), 19 (CH_3); IR: (cm^{-1}) 2928 (m, C-H), 2224 (m, CN), 1713 (s, C=O), 1582 (s, C=C), 1246 (s, C-O- CH_3), 876 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}Cl_3NO_2$: C, 50.56; H, 3.64; N, 4.21; Found: C, 52.46; H, 3.84; N, 4.81.

3.1.6. Isobutyl 2,3,6-trichlorophenylcyanoacrylate

Yield 82%; mp 59°C; 1H NMR: δ 8.2 (s, 1H, CH=), 7.6-7.2 (s, 2H, Ph), 4.2 (d, 2H, CH_2), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH_3); ^{13}C NMR: δ 161 (C=O), 151 (HC=), 146, 134, 132, 131, 129, 121 (Ph), 117 (CN), 113 (C=), 72 (CH_2), 28 (CH), 19 (CH_3); IR: (cm^{-1}) 2934 (m, C-H), 2236 (m, CN), 1732 (s, C=O), 1651 (s, C=C), 1286 (s, C-O- CH_3), 947, 814 (s,

C-H out of plane). Anal. calcd. for $C_{14}H_{12}Cl_3NO_2$: C, 50.56; H, 3.64; N, 4.21; Found: C, 49.90; H, 3.88; N, 4.96.

3.1.7. Isobutyl 2,3,4-trifluorophenylcyanoacrylate

Yield 72%; mp 74°C; 1H NMR: δ 8.4 (s, 1H, CH=), 8.2, 7.2 (s, 2H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 163 (C=O), 156 (HC=), 153, 149, 144, 142, 139, 123, 118, 114 (Ph), 115 (CN), 106 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2962 (m, C-H), 2228 (m, CN), 1732 (s, C=O), 1622 (s, C=C), 1254 (s, C-O-CH₃), 824 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}F_3NO_2$: C, 59.37; H, 4.27; N, 4.94; Found: C, 58.71; H, 4.72; N, 5.27.

3.1.8. Isobutyl 2,3,5-trifluorophenylcyanoacrylate

Yield 85%; 1H NMR: δ 8.5 (s, 1H, CH=), 7.9, 7.2 (s, 2H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 168 (C=O), 161 (HC=), 144, 122, 110, 108 (Ph), 114 (CN), 90 (C=), 73 (CH₂), 29 (CH), 20 (CH₃); IR: (cm⁻¹) 2939 (m, C-H), 2199 (m, CN), 1745 (s, C=O), 1618 (s, C=C), 1245 (s, C-O-CH₃), 970 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}F_3NO_2$: C, 59.37; H, 4.27; N, 4.94; Found: C, 60.26; H, 4.34; N, 5.13.

3.1.9. Isobutyl 2,4,5-trifluorophenylcyanoacrylate

Yield 91%; mp 49°C; 1H NMR: δ 8.4 (s, 1H, CH=), 8.3, 7.1 (s, 2H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 162 (C=O), 152 (HC=), 144, 137, 136, 134, 131, 129 (Ph), 117 (CN), 106 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2931 (m, C-H), 2226 (m, CN), 1728 (s, C=O), 1593 (s, C=C), 1266 (s, C-O-CH₃), 833 (s, C-H

out of plane). Anal. calcd. for $C_{14}H_{12}F_3NO_2$: C, 59.37; H, 4.27; N, 4.94; Found: C, 58.70; H, 4.68; N, 5.07.

3.1.10. Isobutyl 2,4,6-trifluorophenylcyanoacrylate

Yield 72%; mp 68°C; 1H NMR: δ 8.2 (s, 1H, CH=), 6.8 (s, 2H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 163 (C=O), 160 (HC=), 142, 113, 111, 107 (Ph), 115 (CN), 102 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2964 (m, C-H), 2231 (m, CN), 1732 (s, C=O), 1618 (s, C=C), 1254 (s, C-O-CH₃), 960 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}F_3NO_2$: C, 59.37; H, 4.27; N, 4.94; Found: C, 60.98; H, 4.95; N, 5.12.

3.1.11. Isobutyl 3,4,5-trifluorophenylcyanoacrylate

Yield 87%; mp 97°C; 1H NMR: δ 8.1 (s, 1H, CH=), 7.7 (s, 2H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 162 (C=O), 153 (HC=), 151, 149, 144, 141, 127 (Ph), 116 (CN), 106 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2934 (m, C-H), 2226 (m, CN), 1715 (s, C=O), 1593 (s, C=C), 1243 (s, C-O-CH₃), 945 (s, C-H out of plane). Anal. calcd. for $C_{14}H_{12}F_3NO_2$: C, 59.37; H, 4.27; N, 4.94; Found: C, 59.39; H, 4.57; N, 5.29.

3.1.12. Isobutyl 2,3,5,6-tetrafluorophenylcyanoacrylate

Yield 72%; 1H NMR: δ 8.3 (s, 1H, CH=), 7.3 (s, 1H, Ph), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ^{13}C NMR: δ 161 (C=O), 148 (HC=), 146, 144, 141, 113, 110 (Ph), 114 (CN), 110 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2962 (m, C-H), 2154 (m,

CN), 1732 (s, C=O), 1622 (s, C=C), 1254 (s, C-O-CH₃), 824 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄F₄NO₂: C, 55.82; H, 3.68; N, 4.65; Found: C, 56.36; H, 3.69; N, 4.87.

3.1.13. Isobutyl 2,3,4,5,6-pentafluorophenylcyanoacrylate

Yield 95%; ¹H NMR: δ 8.1 (s, 1H, CH=), 4.1 (d, 2H, CH₂), 2.1 (m, 1H, CH), 1.0 (d, 6H, CH₃); ¹³C NMR: δ 162 (C=O), 147 (HC=), 143, 142, 140, 113, 108 (Ph), 114 (CN), 106 (C=), 73 (CH₂), 28 (CH), 19 (CH₃); IR: (cm⁻¹) 2968 (m, C-H), 2233 (m, CN), 1736 (s, C=O), 1618 (s, C=C), 1265 (s, C-O-CH₃), 966 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₀F₅NO₂: C, 52.67; H, 3.16; N, 4.39; Found: C, 53.80; H, 3.89; N, 5.00.

3.2. Homopolymerization

An attempted homopolymerization of the IPCA compounds in the presence of ABCN did not produce any polymer as indicated by the lack of a precipitate in methanol. The inability of the monomers to polymerize is associated with steric difficulties encountered in homopolymerization of 1,1- and 1,2-disubstituted ethylenes [14]. Homopolymerization of ST under conditions identical to those in copolymerization experiments yielded 18.3% of polystyrene, when polymerized for 30 min.

3.3. Synthesis and characterization of styrene – IPCA copolymers


Copolymers of the styrene (ST) and the IPCA compounds, P(ST-co-IPCA) were prepared in 25-mL glass screw cap vials at ST/IPCA = 3 (mol) the monomer feed using 0.12 mol/L of ABCN at an overall monomer concentration 2.44 mol/L in 10 mL of toluene. The copolymerization was conducted at 70°C. After a predetermined time, the mixture was cooled to room temperature, and precipitated dropwise in methanol. The composition of the copolymers was determined based on the nitrogen content. The novel

synthesized IPCA compounds copolymerized readily with ST under free-radical conditions (Scheme 2) forming white flaky precipitates when their solutions were poured into methanol. The conversion of the copolymers was kept between 10 and 20% to minimize compositional drift (Table 1).

Table 1. Copolymerization of isobutyl phenylcyanoacrylates with styrene.

R	Yield ^a (wt%)	N (wt%)	ST in copol. (mol%)	IPCA in copol. (mol%)
5-Bromo-2,4-dimethoxy	11.4	1.95	77.1	22.9
2-Bromo-3-hydroxy-4-methoxy	11.2	1.68	81.7	18.3
3-Chloro-2,6-difluoro	11.6	2.15	77.2	22.8
4-Chloro-2,6-difluoro	12.8	2.67	68.3	31.7
2,3,5-Trichloro	13.4	2.29	72.9	27.1
2,3,6-Trichloro	13.5	0.83	92.9	7.1
2,3,4-Trifluoro	12.0	1.26	88.8	11.2
2,3,5-Trifluoro	15.2	1.57	85.4	14.6
2,4,5-Trifluoro	11.5	2.64	70.4	29.6
2,4,6-Trifluoro	10.3	2.55	71.9	28.1
3,4,5-Trifluoro	14.2	2.47	73.2	26.8
2,3,5,6-Petrafluoro	15.4	1.26	88.6	11.4
2,3,4,5,6-Pentafluoro	12.3	2.23	74.8	25.2

Nitrogen elemental analysis showed that between 7.1 and 31.7 mol% of IPCA is present in the copolymers, which is indicative of relatively high reactivity of the IPCA monomers towards ST radical which is typical of ring-substituted PCA esters [18-22]. Since IPCA monomers do not homopolymerize, the most likely structure of the copolymers would be isolated alternating IPCA monomer ($y = 1$) units with short ST sequences ($x > 1$) (Scheme 2).



Scheme 2. Copolymerization of ST and the ring-substituted isobutyl

phenylcyanoacrylates, $RPhCH = C(CN)CO_2CH_2CH(CH_3)_2$, $R = 5\text{-bromo-}2,4\text{-dimethoxy, } 2\text{-bromo-}3\text{-hydroxy-}4\text{-methoxy, } 3\text{-chloro-}2,6\text{-difluoro, } 4\text{-chloro-}2,6\text{-difluoro, } 2,3,5\text{-trichloro, } 2,3,6\text{-trichloro, } 2,3,4\text{-trifluoro, } 2,3,5\text{-trifluoro, } 2,4,5\text{-trifluoro, } 2,4,6\text{-trifluoro, } 3,4,5\text{-trifluoro, } 2,3,5,6\text{-tetrafluoro, } 2,3,4,5,6\text{-pentafluoro.}$

The copolymers prepared in the present work are all soluble in ethyl acetate, THF, DMF and $CHCl_3$ and insoluble in methanol, ethyl ether, and petroleum ether.

4 Conclusions

Novel halogen ring-substituted isobutyl phenylcyanoacrylates,

$RPhCH = C(CN)CO_2CH_2CH(CH_3)_2$, where R is 5-bromo-2,4-dimethoxy, 2-bromo-3-hydroxy-4-methoxy, 3-chloro-2,6-difluoro, 4-chloro-2,6-difluoro, 2,3,5-trichloro, 2,3,6-trichloro, 2,3,4-trifluoro, 2,3,5-trifluoro, 2,4,5-trifluoro, 2,4,6-trifluoro, 3,4,5-trifluoro, 2,3,5,6-tetrafluoro, 2,3,4,5,6-pentafluoro were synthesized and copolymerized with styrene.

The compositions of the copolymers were calculated from nitrogen analysis.

Acknowledgments

The authors are grateful to acknowledge that the project was partly supported by Chicago Society of Coating Technology (CSCT).

References

- [1] Klemarczyk, P.; Guthrie, J. Advances in anaerobic and cyanoacrylate adhesives. In *Advances in Structural Adhesive Bonding*, 1st ed.; Dillard, D., Ed.; Woodhead Publishing Limited: Cambridge, UK, 2010; pp. 96–131, ISBN 978-1-84569-435-7.
- [2] Shantha, K.L.; Thennarasu, S.; Krishnamurti, N. Developments and applications of cyanoacrylate adhesives. *J. Adhes. Sci. Technol.* 1989, 3, 237–260.
- [3] J.M. Korde and B. Kandasubramanian, Biocompatible alkyl cyanoacrylates and their derivatives as bio-adhesives, *Biomaterials Science*, 10.1039/C8BM00312B, 6, 7, (1691-1711), (2018).
- [4] Zaki MEA, Fathalla OA, Swelam SA, Aly HF (2004) Synthesis of pyrido[2,1-c][1,2,4]triazine, 1,2,4-triazolo[4,3-a]pyridine and 2-(pyrazolyl)nicotinonitrile and their effect on *Biomphalaria alexandrina* snail enzymes. *Acta Poloniae Pharmaceutica* 61: 55-64.
- [5] Matsuoka M, Takao M, Kitao T, Fujiwara T, Nakatsu K (1990) Cyanovinylheteroaromatics for Organic Nonlinear Optics. *Molecular Crystals and Liquid Crystals*, 182A: 71-79.
- [6] Burate PA, Javle BR, Desale PH, Kinage AK (2019) Amino acid amide based ionic liquid as an efficient organo-catalyst for solvent-free Knoevenagel condensation at room temperature. *Catalysis Letters* 149(9): 2368-2375.
- [7] Medyouni R, Hamdi N, Ben Said R, Al-Ayed AS, Zagrouba F (2013) Clean procedure and DFT study for the synthesis of 2-amino-3-ethoxycarbonyl-4-(aryl)-4H-

pyrano-[3,2-c]-chromene-5-ones derivatives: A novel class of potential antimicrobial and antioxidant agents. *Journal of Chemistry* 2013: 1-4.

- [8] Hassan AY, Sarg MT, Hussein EM (2019) Design, synthesis and anticancer activity of novel benzothiazole analogues. *Journal of Heterocyclic Chemistry* 56(4): 1437-1457.
- [9] Moacyr JB, De Melo R, Wanessa LB, De Sena, RO, De Moura, Iris TT et al. (2017). Synthesis and anticancer evaluation of thiazacridine derivatives reveals new selective molecules to hematopoietic neoplastic cells. *Combinatorial Chemistry & High Throughput Screening* 20(8): 713.
- [10] Meng D, Qiao Y, Wang X, Wen W, Zhao S (2018) DABCO-catalyzed Knoevenagel condensation of aldehydes with ethyl cyanoacetate using hydroxy ionic liquid as a promoter. *RSC Advances* 8(53): 30180-30185.
- [11] Brica S, Freimane L, Kulikovska L, Zicmanis A (2017) N,N'-dialkylimidazolium dimethyl phosphates - promising media and catalysts at the same time for condensation reactions. *Chemical Science International Journal* 19(4): 1-9.
- [12] Bhuiyan M, Mosharef H, Rahman KM, Alam MA, Mahmud M (2013) Microwave assisted Knoevenagel condensation: synthesis and antimicrobial activities of some α -cyanoacrylates. *Pakistan Journal of Scientific and Industrial Research, Series A: Physical Sciences* 56(3): 131-137.
- [13] Nowicka A, Liszkiewicz H, Nawrocka WP, Wietrzyk J, Kempinska K, Drys A (2014)

- Synthesis and antiproliferative activity in vitro of new 2-aminobenzimidazole derivatives. Reaction of 2-arylideneaminobenzimidazole with selected nitriles containing active methylene group. *Central European Journal of Chemistry* 12(10): 1047-1055.
- [14] Odian, G. *Principles of Polymerization*, 4th Ed., Wiley-Interscience: New York, 2004.
- [15] Hall, H. K., Jr.; Padias, A. B. *J. Polym. Sci. Part A: Polym. Chem.* **2004**, 42, 2845-2858.
- [16] Hall, H. K. Jr.; Ykman, P. *Macromolecules*. 1977, 10, 464.
- [17] Kharas, G. B. *Trisubstituted Ethylene Copolymers. In Polymeric Materials Encyclopedia*, Salamone, J.C., (Ed.) CRC Press: Boca Raton, FL, 11, 8405, 1996.
- [18] Novel Copolymers of Styrene. 17. Ring-Trisubstituted Methyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, A. Shahbein, M.J. Ascitto, L.E. Blanc, S.M. Bostrom, S.S. Cherala, R. Li, S.S. Perisa, A. Santi, W. Tam, and C. Wolfe. *J. Macromol. Sci.* A51(11) 849-853 (2014).
- [19] Synthesis and Styrene Copolymerization of New Halogen and Methoxy Ring-Trisubstituted Propyl Cyanophenylpropenoates. Y.L. Soto, E.A. Baumgartner, F.R. Bertolotti, E.F. Gardner, B.M. Hofsteadter, A. Hrvat, A. Jackunas, A.J. Jagla, J.V. Winter, D.S. Ostrovsky, W.S. Schjerven, G.B. Kharas. *Int. J. Chem.*, 11 (2) 60-66 (2019). <https://doi.org/10.5539/ijc.v11n2p60>

- [20] Synthesis and Styrene Copolymerization of Novel Chloro and Fluoro Ring-Trisubstituted Propyl Cyanophenylpropenoates. J. Bates, A.L. Krider, S.A. Malik, D.P. May, M. Stryelkina, C.G. Williams, D.T. Wood, S.M. Rocus, G.B. Kharas. *Inter. J. Chem.* 11(1), 79-83 (2019). <https://doi.org/10.5539/ijc.v11n1p79>
- [21] Synthesis and vinyl benzene copolymerization of novel trisubstituted ethylenes: 15. Halogen and methoxy ring-substituted isopropyl 2-cyano-3-phenyl-2-propenoates. G.B. Kharas, A. Cimino, S. Flieger, P.M. Whelpley, D. Ebner, R. Groy, C.R. Savittieri, N. Shinde, K.L. Thomas, S.M. Rocus, W.S. Schjerven. *Designed Monomers and Polymers*, 23(1) 75-82 (2020). <https://doi.org/10.1080/15685551.2020.1782556>
- [22] Synthesis and styrene copolymerization of novel halogen ring-substituted isopropyl 2-cyano-3-phenyl-2-propenoates. Cimino, Alessandra; Kharas, Gregory B. Abstracts of Papers, 259th ACS National Meeting & Exposition, Philadelphia, PA, United States, March 22-26, (2020), POLY-0387. <https://doi.org/10.1021/scimeetings.0c05713>
- [23] SciFinder; Chemical Abstracts Service: Columbus, OH; <https://scifinder.cas.org> (accessed November 14, 2020).
- [24] Smith, M. B.; March, J. *Addition to Carbon-Hetero Multiple Bonds*, In March's Advanced Organic Chemistry, J. Wiley & Sons: New York, Ch.16, 1225 (2001).