Influence of a Cu-zirconia interface structure on CO₂ adsorption and activation

Lars Gell, Aku Lempelto, Toni Kiljunen, and Karoliina Honkala^{a)}

*Department of Chemistry, Nanoscience Center, P.O. Box 35 (YN) FI-40014,
University of Jyväskylä, Finland*

(Dated: 3 March 2021)

CO₂ adsorption and activation on a catalyst is a key elementary step for CO₂ conversion to various valuable products. In the present computational study, we screened different Cu-ZrO₂ interface structures and analysed the influence of the interface structure on CO₂ binding strength using density functional theory calculations. Our results demonstrate that a Cu nanorod favours one position on both tetragonal and monoclinic ZrO₂ surfaces, where the bottom Cu atoms are placed close the lattice oxygens. CO₂ prefers a bent bidentate configuration at the interface and the molecule is clearly activated being negatively charged. Straining of the Cu nanorod influences CO₂ adsorption energy but does not change the preferred nanorod position on zirconia. Altogether, our results highlight that CO₂ adsorption and activation depend sensitively on the chemical composition and atomic structure of the interface used in the calculations. This structure sensitivity may potentially impact further catalytic steps and the overall computed reactivity profile.

Keywords: heterogeneous catalysis, density functional theory, CO₂ activation, metal-oxide interface

---

^{a)}karoliina.honkala@jyu.fi

I. INTRODUCTION

Chemical transformations of CO_2 into fuels and platform chemicals have been identified as a highly promising approach to alleviate anthropogenic CO_2 providing a waste-value approach to upgrade CO_2 into building block and value-added products for chemical industry.¹⁻³ Due to the highly oxidized state, thermodynamic stability, and unreactive nature of CO_2 , economical, active, and selective catalysts are mandatory and the chemical conversion and the economical utilization of CO_2 is a notable scientific and technical challenge.¹

Numerous experimental and computational studies have shown that CO_2 reduction takes place at a metal-oxide interface,⁴⁻¹⁰ which is also an active domain for many other industrially important catalytic reactions¹¹ such as the water-gas-shift reaction^{12,13} and CO oxidation^{14,15} just to mention but a few. These reactions have been reported to take place over a variety of metal-oxide interfaces with diverse chemical nature and composition e.g., Au-TiO₂,¹⁵⁻¹⁷ Cu-ZnO,^{4,9} Rh-ZrO₂,^{13,18} FeO-Pt,¹⁹ Pd-Co₃O₄,^{20,21} Pt-SiO₂^{22,23}, and others²⁴. As the experimental characterization of interface structures at the atomic level is demanding, density functional theory (DFT) modelling is extensively used to obtain microscopic information about chemical and structural properties of interfaces^{4,13,15,17,25,26} and to establish structure-performance relationships²⁵. While the catalyst models used in DFT calculations must be firmly based on real catalytic systems, simplifications are mandatory to reduce the computational burden. The key feature of a catalyst to be captured by the model is an active site. Typically, the employed models vary depending on the chemical composition and nature of the active site. For metal-only active sites, periodic surface slab models are commonly used,²⁷⁻³⁰ whereas active sites consisting of a metal-oxide interface are often represented by oxide-supported metal clusters^{8,31-34} or infinitely long nanorods^{13,15,25,26}.

Among the possible chemical transformations, CO_2 conversion to methanol is particularly interesting due to the potential of methanol as a future energy carrier.^{2,35} While Cu/ZnO/Al₂O₃ catalysts are commonly used in industry to produce methanol from CO and they have also been successfully applied to CO_2 reduction to methanol,^{2,5,36,37} ZrO₂ supported or promoted Cu catalysts have been identified as promising alternatives due to their higher selectivities and turn over frequencies towards methanol.^{5,6,38-40} Recent studies indicate that a reaction mechanism and selectivity are determined by adsorption energies of key reaction intermediates.^{5,8,26,31} Two central reaction steps, namely H₂ dissociation^{41,42}

and CO₂ activation, are strongly associated to the Cu-ZrO₂ interface.^{5,38,43} The reaction is inferred to be structure sensitive on Cu and the synergy between Cu and support oxides is responsible for enhanced reactivity^{4,5,44–48}. In calculations, however, adsorption characteristics may sensitively depend on a constructed catalyst model, and small differences between relatively similar active sites may introduce large variations in adsorption energies as shown, e.g., for CO adsorption zirconia supported metal clusters.³³ Computationally CO₂ conversion to methanol has been recently studied employing a Cu₃₈ cluster model supported on a *m*-ZrO₂($\bar{1}11$) surface⁸ and a Cu nanorod model, which is composed of three layers of stacked Cu(100) facets on *t*-ZrO₂(101)²⁶. A similar nanorod model was also used for a Au-MgO interface to address a water-gas-shift reaction.¹² In another computational study, the catalytic properties of various metal-MgO interfaces were considered using rods that also consist of (100) terminated slices but cut in a different orientation to better match the symmetry of MgO(100).²⁵ CO₂ reduction on SiO₂ and TiO₂ supported Pt was, in turn, investigated using a Pt₂₅ cluster, also composed of stacked (100) facets and exposing (111) microfacets towards the interface.³¹ A differently shaped Rh nanorod, terminated by (111) facets on each side was employed for a water-gas-shift reaction on ZrO₂¹³ and a similar model was used for Au-TiO₂ to address CO oxidation¹⁵ as well as low temperature H₂ oxidation⁴⁹. As one would expect, the symmetry and periodicity of the underlying support oxide naturally influences the interface and must therefore be considered. For highly symmetric oxide surfaces, such as MgO(100), the orientation of a deposited nanorod has a vanishingly small impact on the interface. For less symmetric oxides, the position and orientation of the nanorod can substantially change the interface structure. For example, a monoclinic ZrO₂($\bar{1}11$) surface displays a less symmetric crystal structure than a tetragonal ZrO₂(101) surface. One more feature that may affect interface reactivity is strain effects²⁵, which together with defects in catalytic metal particles have been suggested to significantly impact on catalytic efficiency.^{25,50,51} This is hardly surprising as it is well established from the numerous studies that straining of metal surfaces changes their reactivity observed as shifts in d-band centers.^{30,52} Artificial strain effects may emerge in the construction of atomic models for metal – oxide interfaces, because the lattice mismatch between metal and oxide will introduce strain along the nanorod as it has to meet the periodicity set for the support surface.

In this study, we focus on CO₂ adsorption and activation on various Cu-ZrO₂ interface structures to shed light on the influence of the interface properties on CO₂ binding.

Specifically, we considered two Cu nanorod models with different geometries as well as both tetragonal ($t\text{-ZrO}_2(101)$) and monoclinic ($m\text{-ZrO}_2(\bar{1}11)$) zirconia surfaces. A comprehensive screening of nanorod positions was performed on the oxide and CO_2 characteristics were analysed for differently strained interfaces. The adsorption process was broken down to distinct electronic contributions, and they were used to attempt to establish general trends between interface structure and its ability to adsorb and activate CO_2 .

II. COMPUTATIONAL METHODS

All density functional theory (DFT) calculations were carried out using the BEEF-vdW exchange-correlation functional⁵³ in the projector-augmented wave (PAW)⁵⁴ formalism as implemented in the GPAW⁵⁵ package. The core electrons of all elements were described by PAW setups in the frozen-core approximation. A maximum spacing of 0.18 Å was used for the real-space grid basis, and the reciprocal space was sampled at the Γ point. Periodic boundary conditions were used in two directions. A Hubbard U correction⁵⁶ of 2.0 eV was applied to the d-orbitals of the zirconium atoms. The geometry optimizations were performed using the BFGS algorithm as implemented in the Atomic Simulation Environment (ASE).⁵⁷ The computed electronic structures were analyzed by the Bader partitioning method⁵⁸ using code written by Tang *et al.*⁵⁹ to obtain the distribution of partial charges on individual atoms. The density of states was analyzed to locate the d-band centers for the purpose of investigating their importance to the reactivity of the Cu nanorods according to the d-band model.⁶⁰

The interface models were built by placing a Cu nanorod over the most stable facets of monoclinic and tetragonal zirconia surfaces, $m\text{-ZrO}_2(\bar{1}11)$ and $t\text{-ZrO}_2(101)$, as supports (see Fig. 1 for an overview). We adopted two Cu nanorod models, similar to those that have been used in previous publications,^{13,25,26} to be used in the present study. Both models have an equal number of atoms, and they display a (111) facet towards the reactive Cu-zirconia interface. The nanorod structures differ by the facet via which they are attached to the zirconia support. The bottom interface is either a (100) facet or a (111) facet; hence we will call them here the (100) and (111) models, respectively. As Figs. 1 and S1 show, the (100) model has a more gently sloping reactive interface than the (111) model. Under the reaction conditions of CO_2 conversion to methanol, the most common exposed Cu surfaces

FIG. 1. The optimized minimum energy structures of a Cu nanorod on tetragonal or monoclinic zirconia supports. a) (100)/ t -ZrO₂, b) (111)/ t -ZrO₂, c) (100)/ m -ZrO₂, d) (111)/ m -ZrO₂.

are (111) and (100) of which (111) is slightly more stable.⁶¹

A. Model system screening

Figure 1 illustrates the catalytic model systems for both nanorod models and supports. Screening of the rod position was carried out by displacing the nanorods in two directions on the support: along and perpendicular to the nanorod, while keeping the orientation fixed. To scan the surface, we used a grid of 0.7 Å steps along the nanorod axis, and 1.1 Å or 1.5 Å steps perpendicular to the nanorod for the t -ZrO₂ or m -ZrO₂, respectively. The CO₂

binding was studied by attaching the molecule to one of the bottom-row Cu atoms at the reactive interface.

The oxide support was described by a slab model, the thickness of which was set to two stoichiometric layers. This approximation is necessary to reduce the computational burden especially in the larger cells (see below). We consider the two-layer model sufficient to reveal general trends when comparing the nanorod models, and justified, since in preliminary evaluations with two to four layers, the Cu-zirconia binding energy showed only minor variation. We also determined that the d-band centers of the interfacial copper atoms varied insignificantly between different slab thicknesses. However, the CO₂ adsorption energy depends on slab thickness and Test calculations showed that a thicker slab would enhance the binding. In geometry optimizations, the bottom layer of the zirconia slab was kept frozen to its initial bulk geometry, while the top zirconia layer, the Cu nanorod, and the possible CO₂ adsorbate were allowed to relax until the maximum residual force was reduced below 0.02 eV Å⁻¹.

B. Strain of the nanorod

With the present DFT model, we obtain a bulk Cu lattice constant of 3.69 Å which leads to 2.61 Å nearest-neighbor Cu-Cu distance prior to modifications. The nanorods were created by repeating periodic Cu₈ minimum nanorod units having length of one atom. Our computationally determined zirconia lattice constants can be found from Table S1. To explore possible implications of the artificial strain on the metal-oxide interface, we studied five different nanorod lengths on tetragonal ZrO₂ and three on monoclinic ZrO₂ surfaces, see Table S2 for numerical details of the cell sizes.

Because the calculations have to be periodic along the length of the rod, the Cu-Cu distance modified in that direction was always adjusted accordingly to meet the periodicity of the given surface unit cell. We define the strain as positive when the nanorod is stretched and negative when it is compressed relative to the computationally optimized bulk Cu lattice constant. The nanorods illustrated in Fig. 1 are those with the lowest strains, with *t*-ZrO₂ support producing a -0.72 % and *m*-ZrO₂ a -1.02 % strain. Overall, the strain varies from -7.3 to +8.1 % between the different surface models investigated.

C. Energy decomposition

The energy decomposition was set to characterize different contributions in the adsorption of CO_2 at the catalytic sites. First, the adsorption energy of CO_2 was computed from the total energies as

$$\Delta E_{\text{ads}} = E_{\text{CO}_2/\text{Cu}/\text{ZrO}_2} - E_{\text{Cu}/\text{ZrO}_2} - E_{\text{CO}_2}, \quad (1)$$

where $E_{\text{CO}_2/\text{Cu}/\text{ZrO}_2}$ stands for the full system, $E_{\text{Cu}/\text{ZrO}_2}$ for the bare ZrO_2 -supported Cu nanorod, and E_{CO_2} for the gas-phase (linear, inactivated) CO_2 . The gas-phase reference was computed in a large non-periodic cell. We will use the adsorption energy difference $\Delta\Delta E_{\text{ads}}$ to compare the different interface model systems. Then, to exclude the contribution of atomic relaxations from the above CO_2 -Cu/ ZrO_2 bond strength, we computed the total electronic interaction energy as

$$\Delta E_{\text{el}}^{\text{tot}} = E_{\text{CO}_2/\text{Cu}/\text{ZrO}_2} - E_{\text{Cu}/\text{ZrO}_2}^* - E_{\text{CO}_2}^*. \quad (2)$$

Here, asterisks stand for reference configurations, where all the atomic positions were fixed to those optimized for the full system. The adsorption and electronic interaction energies in Eqs. (1) and (2) thus differ by an energy penalty required by the deformation of the catalyst and the CO_2 molecule upon adsorption. Again, for comparison, we define $\Delta\Delta E_{\text{el}}^{\text{tot}}$ to assess the difference between the models.

The electronic interaction energies between the CO_2 molecule and the catalyst components Cu and ZrO_2 were separated according to

$$\Delta E_{\text{el}}^{\text{Cu}} = E_{\text{CO}_2/\text{Cu}}^* - E_{\text{Cu}}^* - E_{\text{CO}_2}^*, \quad (3)$$

$$\Delta E_{\text{el}}^{\text{Zr}} = E_{\text{CO}_2/\text{ZrO}_2}^* - E_{\text{ZrO}_2}^* - E_{\text{CO}_2}^*. \quad (4)$$

Again, the atomic coordinates of the CO_2 and the isolated Cu nanorod and ZrO_2 were fixed to those optimized for the full system. Summing Eqs. (3) and (4) together accounts for the pairwise contributions to the three-body interaction in Eq. (2). Finally, to account for the missing contribution to the total electronic interaction, we define an excess energy

$$\Delta E_{\text{exc}} = \Delta E_{\text{el}}^{\text{tot}} - \Delta E_{\text{el}}^{\text{Cu}} - \Delta E_{\text{el}}^{\text{Zr}}, \quad (5)$$

which describes the change in electronic interaction energy due to the synergy effect of the metal-oxide interface.

III. RESULTS AND DISCUSSION

A. Binding of the minimum-strain Cu nanorods on ZrO_2 supports

To evaluate how the structure and position of a nanorod on a zirconia support influences the catalytic properties of the formed interface, we carefully analyzed the binding of the two nanorods by screening their positions on the zirconia. The heat-maps given in Fig. 2 show how the binding energy of a nanorod depends on its position on the surface. Specifically, we plot the relative energies of both (100) and (111) models with respect to their most stable structures on both tetragonal (a and b) and monoclinic (c and d) supports. We find that the variation of the nanorod position along its length has only a minor influence on the binding energy whereas moving the nanorod in the perpendicular direction across the zirconia surface introduces substantial energy changes. On $t\text{-ZrO}_2$, the energy difference between the most stable and the least stable nanorod position is 1.4 eV for the (100) model and 2.0 eV for the (111) model. On $m\text{-ZrO}_2$ the corresponding value is 2.2 eV for both models.

We ascribe the large positional effect on the energy to the strong interaction between the bottom Cu atoms and the surface O anions. Figs. 1 and S2 display the energetically most favourable interface structures for the (100) and (111) models on both tetragonal and monoclinic zirconia. Careful visual inspection of the several interface structures indicate that the edge Cu atoms are attracted to surface oxygens and they avoid the positions directly above the Zr atoms. We anticipate that the positional effect would decrease with increasing nanorod width. The heat maps in Fig. 2 show that the favourable binding zone for Cu nanorods on zirconia is very narrow. Thus wider nanorods would always spread out over unfavourable areas of the zirconia as well, which weakens the overall binding to the underlying support. The fact that the relative energy increases steeply in heat maps when Cu atoms move to Zr top sites may also have implications for binding characteristics of larger Cu nanoparticles on zirconia. Interface structures, where the Cu edge atoms reside on Zr top sites should statistically appear less often as they are energetically costly and thus nanoparticles would prefer to create interfaces similar to those shown in Figs. 1 and S2 (For a top view of the binding interface, see Fig. S3).

More detailed comparison of energies of the two models shows that the (111) model is

FIG. 2. Variation of the binding energy of a Cu nanorod across the studied zirconia surfaces: a) (100)/ t -ZrO₂, b) (111)/ t -ZrO₂, c) (100)/ m -ZrO₂, and d) (111)/ m -ZrO₂. The nanorods are oriented along the y -axis (vertical in the figure).

more stable than the (100) model. On t -ZrO₂, the relative stability of the models differ by 0.11 eV per nanorod unit, while on m -ZrO₂ the difference as large as 0.32 eV. In the gas-phase, the (111) model is 0.33 eV/nanorod unit more stable than the (100) model. However, as this energy difference decreases on the tetragonal zirconia surface, it implies that the interaction with the support stabilises particularly the (100) Cu nanorod. We link the surface-specific stabilization effect to the Cu–O distances, which are shorter on tetragonal zirconia than on monoclinic zirconia, see Fig. S4 a) and S5. The relative stabilities of (100) and (111) nanorods on zirconia surfaces are 0.37 eV/nanorod unit and 0.24 eV/nanorod unit, respectively and they further demonstrate the ability of the tetragonal surface to better stabilise Cu than the monoclinic surface. Even when considering the adsorption of a single

Cu atom, we see that adsorption is about 0.3 eV more exothermic on tetragonal zirconia. These are in line with a previous experimental study³⁹, which reports stronger Cu–ZrO₂ interactions on tetragonal zirconia than on monoclinic. To gain more detail understanding for the energy variation seen in the heat map plots and to link the binding energy to the microscopic structure, we plotted the energy change with respect to the most stable (111)-ZrO₂ structure versus the average minimum Cu-O distance between the bottom Cu atoms and topmost surface anions for different nanorod positions over both surfaces. Figs. S4 a and S5 clearly display that the (111) model is more stable than the (100) model and for both nanorod models the shorter distance corresponds to more stable structure. Furthermore, the average distance of the entire Cu nanorod (bottom) from the zirconia is 2.5 Å on *t*-ZrO₂ and 3.1 Å on *m*-ZrO₂. The shorter average C-O distances and shorter nanorod-oxide distance can be explained with more exposed and symmetrically sitting lattice oxygens on the tetragonal surface. The optimization of bottom Cu atom positions with respect to surface oxygens is more challenging on the monoclinic surface owing to the larger asymmetry the surface and the fact that the surface anions are located deeper in the topmost surface layer. Additionally, we note that structural deformations in Cu nanorods originating from the interaction with the zirconia support show no correlation with the relative energy of the system as can be seen from Figure S4 b).

B. Strain effects on nanorod binding

A less optimal oxide surface cell size in calculations can introduce artificial strain effects on the nanorod and these, in turn, can influence the computed adsorption characteristics. Therefore, we analyzed strain effects more closely, for computational details see Table S2. First, the position of the differently strained nanorods were screened over both zirconia surfaces. We find that the preferred nanorod positions are almost identical to those given in Figs. 1, S2, and S3 for the ideal interfaces, and thus we limit our study on the most stable nanorod positions. In particular, we aim to understand changes in nanorod binding energies due to strain and elucidate the difference between the tetragonal and monoclinic ZrO₂ surfaces with special emphasis on the tetragonal surface.

The last column in Table I shows that the total binding energy (ΔE_b) is more exothermic for the (100) model and the tetragonal surface than for the (111) model and the monoclinic

FIG. 3. A thermodynamic cycle for the binding energy decomposition for a Cu nanorod on ZrO_2 .

surface, but it follows no obvious trend. To understand the origin of this variation better, the thermodynamic cycle (see schematic Figure 3) was devised to analyse the different components. The cycle divides the Cu– ZrO_2 binding energy into four contributions. The first three steps constitute the changes in the gas-phase nanorod and the last one measures the pure electronic interaction with zirconia. Step 1 describes the change for the optimisation of interatomic Cu–Cu distances whereas step 2 gives the energy change originating from strain effects and step 3 represents the energy change due to structure deformation arising from the interaction between the nanorod and zirconia. The remaining contribution, step 4, defines the pure electronic binding interaction between the deformed Cu nanorod and zirconia.

The energy changes accompanying the thermodynamic steps are collected in Table I. Overall the contributions from steps 1–3 are small compared to step 4, which dominates. The slight energy decrease seen in step 1 for all the models indicates that the Cu bulk lattice constant is not optimal for the gas-phase nanorod. In fact, the Cu–Cu distance decreases from the bulk value 2.61 Å to 2.58 Å for both nanorod models on *m*- ZrO_2 , and to 2.55 (2.57) Å for the (100) model ((111) model) on *t*- ZrO_2 . Other minor variations in Cu–Cu distances and energies in step 1 originate from the differences in the computational cell shapes. As expected, increasing strain leads to positive (endothermic) energy change in step 2 as mainly also does nanorod deformation in step 3. While irregularities introduced by the support make it difficult to predict clear trends, the larger strain is accompanied by

TABLE I. Nanorod binding energies (in eV) at each stage of the thermodynamic cycle shown in Fig. 3. ΔE_b stands for binding energy of a nanorod to the zirconia surface and step5 in the thermodynamic cycle. To facilitate comparison, the energies are divided by the number of rod units in the corresponding cell.

ZrO ₂	Nanorod Strain (%)	Step 1	Step 2	Step 3	Step 4	ΔE_b	
<i>t</i> -ZrO ₂	(100)	-7.34	-0.034	+0.159	-0.363	-1.069	-1.306
		-2.71	-0.034	+0.002	-0.005	-1.025	-1.061
		-0.72	-0.034	+0.021	+0.007	-1.108	-1.113
		+4.24	-0.034	+0.220	+0.014	-1.183	-0.983
		+8.10	-0.034	+0.456	+0.055	-1.256	-0.779
	(111)	-7.34	-0.012	+0.205	-0.199	-0.871	-0.877
		-2.71	-0.012	+0.003	+0.035	-0.994	-0.968
		-0.72	-0.012	+0.008	+0.102	-1.010	-0.912
		+4.24	-0.012	+0.168	+0.045	-1.039	-0.838
		+8.10	-0.012	+0.390	+0.120	-1.136	-0.638
<i>m</i> -ZrO ₂	(100)	-1.02	-0.019	+0.008	+0.067	-0.787	-0.741
	(111)	-4.02	-0.012	+0.035	+0.002	-0.714	-0.579
		-1.02	-0.012	+0.001	+0.009	-0.743	-0.673
		+5.57	-0.012	+0.225	+0.072	-0.898	-0.667

stronger deformation and this is especially clear for the two most strained (100) rods.

Cu nanorod binding energy on zirconia is dominated by electronic interaction (step 4), which is more exothermic for *t*-ZrO₂ than for *m*-ZrO₂ resulting most likely from the shorter Cu–O distance as suggested also for the minimum strain interfaces. As illustrated in Fig. S6, the introduced strain correlates well with the electronic interaction energy, where the compression of the nanorod decreases the electronic interaction between Cu and zirconia, while the expansion of the nanorod enhances it. No clear correlation is seen when attempting to link binding energies to strain. Multiple factors may contribute to this, the main reason being the irregular structural deformations during structure optimization. The d-band-center analysis supports the stronger interaction between Cu and tetragonal zirconia as the shifts in the d-band center are larger for tetragonal than monoclinic surfaces. The net shift, see

FIG. 4. Front and side views of the most stable CO₂ adsorption geometry at the minimum-strain Cu-*t*-ZrO₂ interfaces for the (100) model (panels a and c) and the (111) model (b and d).

Table S3, is to lower energies and it is dominated by the "ligand" effect introduced by the oxide, whereas the "strain" effect, including deformation, constitutes minor contribution.

C. CO₂ adsorption and activation

In order to estimate the significance of an interface site to CO₂ adsorption and activation, we conducted a thorough screening of the available sites for the structures explored in section III A. We find that the CO₂ adsorbs preferably in a bent configuration for the minimum-strain interface structures as shown in Figs. 4 and 5. Our results also demonstrate that adsorption energies depend sensitively on the nanorod model and the interface structure.

Figure 4 displays the minimum-strain Cu-*t*-ZrO₂ interface for which the most exothermic CO₂ adsorption energies were computed to be -1.01 and -0.52 eV for the (100) and (111) models, respectively. The adsorption energies for other interfacial sites along these interfaces can be found from Table S4. A previous DFT study²⁶ reports as large as a -1.78 eV adsorption energy for the CO₂ with the (100) model. We associate the large difference with two factors, firstly a $+0.41$ eV gas-phase correction was applied to CO₂,²⁶ and secondly, to

FIG. 5. Front and side views of the most stable CO_2 adsorption geometry at the minimum-strain $\text{Cu}-m\text{-ZrO}_2$ interfaces for the (100) model (panels a and c) and the (111) model (b and d).

the fact that the employed interface model has substantial, 5.08 %, strain, which strongly impacts CO_2 adsorption as discussed below. Figure 5 illustrates the CO_2 adsorption on the $\text{Cu}-m\text{-ZrO}_2$ interface, where the computed CO_2 adsorption energies are -1.38 eV for the (100) nanorod and -0.44 eV for the (111) nanorod. For a $\text{Cu}_{38}-m\text{-ZrO}_2(\bar{1}11)$ interface, CO_2 absorption energy is -1.86 eV⁸ being substantially more exothermic than what we found in this work. This time, the observed adsorption energy difference is attributed on one hand to the different exchange and correlation functional, and on the other hand to the 38-atom cluster geometry. In another computational work, an adsorption energy of -0.69 eV was reported for a slightly thinner (111)-type Cu nanorod on a stepped $m\text{-ZrO}_2(\bar{2}12)$ surface,⁷ where the CO_2 is at the interface but binds only to the Cu atoms.

The most stable CO_2 adsorption geometries are structurally similar for both zirconia surfaces and nanorod models. CO_2 prefers a bidendate geometry, i.e., it binds to the Cu via the carbon atom and has both oxygen atoms pointing down towards the support cations with the O-C-O angle being close to 120° . A substantial deviation from the linear gas-phase structure and a slight, 0.14 Å, elongation of the C-O bonds clearly indicate CO_2 activation. This is further supported by the Bader charge analysis showing that the CO_2

molecule gains $1.2 |e|$ upon adsorption, which is in line with the previously reported value.⁸ Interaction between CO₂ and the interface introduces structural deformations to the Cu nanorods. While in the case of the *t*-ZrO₂ surface, the distortion of Cu edge is minor, on *m*-ZrO₂ CO₂ clearly pulls out one Cu atom from the both nanorods, see Fig. 5.

Table II summarizes the energy contributions defined in Eqs. (1)–(5) and displays the origin of the variation of CO₂ adsorption energies from one minimum-strain interface to the other. We first focus on electronic interaction energies, which exclude all the structural deformations. For example, the adsorption energy difference ($\Delta\Delta E_{\text{ads}}$) between the (100) and (111) models is 0.49 eV for the tetragonal surface, whereas the pure electronic, aka binding, interaction energy difference, $\Delta\Delta E_{\text{el}}^{\text{tot}}$, shows a larger, 0.75 eV, value. Interestingly, for the monoclinic surface $\Delta\Delta E_{\text{ads}}$ is larger than $\Delta\Delta E_{\text{el}}^{\text{tot}}$ (0.9 vs 0.5 eV). The opposite behaviour is ascribed to nonidentical atomic relaxations for different CO₂-interface systems. In general, we attribute the observed adsorption energy differences to different electronic interaction energies, which are clearly more exothermic for the (100) model on both tetragonal and monoclinic zirconia. The interaction energies from the CO₂-Cu and CO₂-ZrO₂ subsystems, which measure the binding between CO₂ and metal and CO₂ and oxide, do not indicate that one nanorod model or zirconia crystal structure is favoured over the other. The substantial synergy between the Cu and zirconia is demonstrated by the exothermic values of ΔE_{exc} for all the studied system.

Next, a CO₂ adsorption site at the (111)-ZrO₂ interface is further explored by moving the nanorod across the oxide surfaces. Fig. 6 displays the heat maps summarizing the energy variation with respect to the most stable adsorption structure at the interface. The plots show, that for many nanorod positions, CO₂ does not either adsorb at all or adsorption is energetically very unfavourable. In order to interpret the heat map information, we analyzed the calculated CO₂ adsorption structures. For a favourable CO₂ adsorption, it seems to be crucial to have lattice Zr cations sufficiently close to the Cu edge to ensure that the oxygens of the CO₂ molecule can interact with them. The nanorod positions, where surface anions are closer to the Cu edge than the Zr cations lead to unfavourable CO₂ adsorption due to repulsive interactions between the oxygen atoms and anions. The central role of the zirconia support is further highlighted by the fact that, without the support, CO₂ only physisorbs maintaining a linear structure on a Cu(111) surface as well as on our (111) and (100) nanorods. This agrees well with the previous DFT results, which also demonstrate

TABLE II. CO₂ adsorption energies (ΔE_{ads}) and electronic interaction energies ($\Delta E_{\text{el}}^{\text{tot}}$, $\Delta E_{\text{el}}^{\text{Cu}}$, $\Delta E_{\text{el}}^{\text{Zr}}$, and ΔE_{exc}), defined in Eqs. (2)–(5) for different models and strain values. All the energy values are given in eV.

ZrO ₂	nanorod	Strain (%)	ΔE_{ads}	$\Delta E_{\text{el}}^{\text{tot}}$	$\Delta E_{\text{el}}^{\text{Cu}}$	$\Delta E_{\text{el}}^{\text{Zr}}$	ΔE_{exc}
<i>t</i> -ZrO ₂	(100)	−0.72	−1.01	−6.30	−2.49	−1.76	−2.05
		+4.24	−1.17	−6.39	−2.86	−1.63	−1.89
		−7.34	−1.91	−6.02	−2.34	−1.55	−2.13
	(111)	−2.71	−0.51	−5.84	−2.38	−1.85	−1.60
		−0.72	−0.52	−5.55	−2.58	−1.50	−1.47
		+4.24	−0.71	−5.98	−2.49	−1.63	−1.87
<i>m</i> -ZrO ₂	(100)	+8.10	−1.33	−6.27	−2.17	−1.39	−2.71
		−1.02	−1.38	−6.06	−2.13	−1.63	−2.30
		−4.02	−0.89	−5.79	−1.88	−1.72	−2.18
	(111)	−1.02	−0.44	−5.57	−1.78	−1.62	−2.18
		+5.57	−1.34	−5.81	−2.69	−1.70	−1.42

CO₂ physisorption on Cu(111) and Cu(533) surfaces.^{28,37}

CO₂ adsorption on the bare zirconia surface leads to carbonate (CO₃) formation with the lattice oxygen. We find this process exothermic by −0.57 eV on *t*-ZrO₂ and by −0.59 eV on *m*-ZrO₂. In the case of a (111) model, the carbonate formation is thermodynamically slightly more favourable than CO₂ adsorption at the interface, which makes these two simultaneous reactions competing. On the other hand, CO₂ adsorption at the interface is clearly preferred to carbonate formation for the (100) model. Previously computed⁶² carbonate formation energy on the same monoclinic zirconia surface is about −1.13 eV, which is substantially more exothermic than the value reported here. We ascribe this energy difference to the different exchange and correlation functional and to the thicker zirconia slab, not computationally feasible for the present screening study. Note that under the reaction conditions, zirconia is partially covered by OH groups, which are known to react with CO₂ to create an extremely stable formate species.^{6,13,62,63}

We close the discussion on CO₂ adsorption and activation by considering that at the strained metal-oxide interfaces. Similar to the minimum-strained nanorods, CO₂ is acti-

FIG. 6. Heat maps for CO₂ adsorption upon varying the position of the (111) nanorod across the a) *t*-ZrO₂ and b) *m*-ZrO₂ surfaces. The nanorod lies parallel to the vertical axis and is moved along the horizontal axis. The energy difference is given with respect to the most stable adsorption structure. The vertical axis numbers represent Cu edge atoms to which CO₂ was attempted to bind. Gray color corresponds to the nanorod positions, which do not bind or activate CO₂.

vated via electron transfer and the molecule adopts a bent adsorption configuration. The bidentate binding is preferred, while monodentate geometries also appear at slightly higher energies. CO₂ adsorption energies and the electronic interaction energy components for the strained interfaces are presented in Table II. While the data does not allow to make comprehensive conclusions for all the interfaces, we can say that for the (111) model the straining and compressing of the nanorod leads to more exothermic electronic interaction energies. However, one has to be careful with the nanorods exposed to larger ($\pm > 7\%$) strain, as they experienced significant structural deformations during the atomic structure optimization, which reduced the atomic coordination number of some Cu atoms, typically those interacting with the C atom leading to enhanced CO₂ adsorption. Therefore, these systems are largely omitted from the detailed discussion. In general, adsorption and total electronic interaction energies do not correlate. This means that adsorption energy difference and total electronic interaction energy difference, $\Delta\Delta E_{\text{ads}}$ and $\Delta\Delta E_{\text{el}}^{\text{tot}}$, differ for a considered system pair. Again, this can be attributed to diverse deformations of the nanorod and the molecule giving system-specific positive deformation energies. In addition, we see for all the systems strong synergy between metal and oxide, which is reflected by exothermic values of

ΔE_{exc} and highlights the unique nature of the interface. Table II also shows that interfaces built from the (100) nanorod give more exothermic CO_2 adsorption energies than its (111) counterpart.

In order to understand the variation of CO_2 adsorption energy from one system to the other, we performed d-band center analysis separately to each steps in the thermodynamic cycle. The formation of a metal-oxide interface has been considered as a two-step process²⁵ including the "strain" and "ligand" contributions similar to bimetallic systems.⁶⁴ The "strain" effects include both changes in Cu-Cu distances along the nanorod as well as structural deformation of the nanorod due to interaction with zirconia whereas the ligand effect describes the electronic interactions between Cu and zirconia. The first three steps in the thermodynamic cycle contribute to the shift of the d-band center due to strain effects $\Delta\epsilon_d^{\text{strain}}$ while the shift of the d-band center for step 4 ($\Delta\epsilon_d^{\text{ligand}}$) measures the change resulting from the ligand effect. The overall impact of the support to the Cu nanorod is a clear shift of a d-band center to lower energies for all the models, see Table S3 explicit numerical values. The ligand effects clearly dominate and the negative value of $\Delta\epsilon_d^{\text{ligand}}$ for all the interface models highlight that binding interaction between the Cu and zirconia shifts the d-band center to lower energies. The contribution of the strain effects to the shift of the d-band center is negligible being positive for some interfaces and negative for some others. Table S3 shows that CO_2 adsorption energies can not be rationalized with the shift of the d-band center as no correlation can be established between the adsorption energy and the total shift in the d-band center. We believe that the complex metal-oxide interaction effects at the interface together with structural deformations, especially in the case of the less stable (100) rod, make the d-band model insufficient to explain CO_2 adsorption energies.

Altogether, our DFT results highlight that CO_2 adsorption and activation depends sensitively on the atomic structure and composition making only few site geometries favourable for CO_2 . Moreover, care must be taken when building computational interface models as artificial strain enhances CO_2 adsorption and similar effects might be present for reaction intermediates as well, let alone that the possible strain effects may affect the activation barriers for elementary steps taking place at the interface. Structure sensitivity of CO_2 adsorption suggests that not all the Cu- ZrO_2 interfaces at real-world catalytic systems are active towards CO_2 chemistry. This is because supported nanoparticles present various interface sites with different composition and atomic structure and their direct structural

optimization is infeasible.

IV. CONCLUSIONS

We have investigated the properties of a Cu-ZrO₂ interface and its ability to adsorb and activate CO₂ using density functional theory calculations. Specifically, two Cu nanorod models were explored on *m*-ZrO₂($\bar{1}11$), and *t*-ZrO₂(101) surfaces. We observed that the (111) nanorod model is always more stable than the (100) one regardless of whether it is supported by zirconia or not. Tetragonal ZrO₂ stabilises both nanorod models more than the monoclinic ZrO₂, which is likely due to the more exposed oxygen anions of the *t*-ZrO₂(101) surface. Our calculations demonstrate that the stability of the nanorod depends sensitively on its local chemical environment on ZrO₂ and results from the fact that Cu atoms avoid the interaction with surface cations and prefer to minimize a Cu-anion nearest neighbour distance. Compression along the nanorod enhances binding to the zirconia while tension of the nanorod weakens the interaction with the studied oxide surfaces.

Our results demonstrate that the employed Cu-ZrO₂ interface model significantly impacts the adsorption characteristics of the CO₂ molecule. In general, the interfaces built using the (100) nanorod adsorb CO₂ more strongly compared to the interfaces created with the (111) nanorods. The activation of CO₂ is seen as increased Bader charge and a bent adsorption configuration. Applying strain to the nanorod enhances electronic interaction with the CO₂, which is not always reflected in more exothermic adsorption energies due to structural deformation effects. The excess interaction energy originating from the synergy between the metal and the support is strongly exothermic for the all studied systems, highlighting the importance of the metal-oxide interface. Furthermore, depending on how the nanorod is positioned on the ZrO₂, CO₂ might not adsorb at the interface at all.

Overall, not only the chemical composition but also the diverse structural features of an interface can impact the adsorption characteristics of reacting molecules and consequently the computed activity and selectivity profiles. Therefore, when building computational models for catalytic reactions taking place at the metal-oxide interface, care should be taken in constructing interfaces and identifying interfacial active sites.

SUPPLEMENTARY MATERIAL

See supplementary material for details on the construction and the structure of the atomic models, and the d-band shifts for the thermodynamic cycle.

ACKNOWLEDGMENTS

The work was funded by Academy of Finland projects 329977 and 307623 and University of Jyväskylä. The electronic structure calculations were made possible by the computational resources provided by the CSC — IT Center for Science, Espoo, Finland (<https://www.csc.fi/en/>) and Finnish Grid and Cloud Infrastructure.

DATA AVAILABILITY

The data that support the findings of this study are available from the corresponding author upon reasonable request.

REFERENCES

- ¹S. Roy, A. Cherevotan, and S. C. Peter, *ACS Ener. Lett.* **3**, 1938 (2018).
- ²B. M. Tackett, E. Gomez, and J. G. Chen, *Nat. Catal.* **2**, 381 (2019).
- ³R. P. Ye, J. Ding, W. Gong, M. D. Argyle, Q. Zhong, Y. Wang, C. K. Russell, Z. Xu, A. G. Russell, Q. Li, M. Fan, and Y. G. Yao, *Nat. Comm.* **10**, 5698 (2019).
- ⁴S. Kattel, P. J. Ramírez, J. G. Chen, J. A. Rodriguez, and P. Liu, *Science* **355**, 1296 (2017).
- ⁵S. Kattel, P. Liu, and J. G. Chen, *J. Am. Chem. Soc.* **139**, 9739 (2017).
- ⁶N. Scotti, F. Bossola, F. Zaccheria, and N. Ravasio, *Catalysts* **10**, 168 (2020).
- ⁷Q.-L. Tang, Q.-J. Hong, and Z.-P. Liu, *J. Catal.* **263**, 114 (2009).
- ⁸K. Larmier, W.-C. C. Liao, S. Tada, E. Lam, R. Verel, A. Bansode, A. Urakawa, A. Comas-Vives, and C. Copéret, *Angew. Chem. Int. Ed.* **56**, 2318 (2017).
- ⁹M. Zabilskiy, V. L. Sushkevich, D. Palagin, M. A. Newton, F. Krumeich, and J. A. van Bokhoven, *Nat. Comm.* **11**, 2409 (2020).
- ¹⁰Y. Wang, S. Kattel, W. Gao, K. Li, P. Liu, J. G. Chen, and H. Wang, *Nat. Comm.* **10**, 1166 (2019).
- ¹¹Q. Fu and T. Wagner, *Surf. Sci. Rep.* **62**, 431 (2007).
- ¹²Z.-J. Zhao, Z. Li, Y. Cui, H. Zhu, W. F. Schneider, W. N. Delgass, F. Ribeiro, and J. Greeley, *J. Catal.* **345**, 157 (2017).
- ¹³M. M. Kauppinen, M. M. Melander, A. S. Bazhenov, and K. Honkala, *ACS Catal.* **8**, 11633 (2018).
- ¹⁴Y. Y. Wu, N. A. Mashayekhi, and H. H. Kung, *Catal. Sci. Technol.* **3**, 2881 (2013).
- ¹⁵I. X. Green, W. Tang, M. Neurock, and J. T. Yates, *Science* **333**, 736 (2011).
- ¹⁶M. Boronat and A. Corma, *Dalton Trans.* **39**, 8538 (2010).
- ¹⁷P. Schlexer, D. Widmann, R. J. Behm, and G. Pacchioni, *ACS Catal.* **8**, 6513 (2018).
- ¹⁸H. Tao, C. Choi, L.-X. Ding, Z. Jiang, Z. Hang, M. Jia, Q. Fan, Y. Gao, H. Wang, A. W. Robertson, S. Hong, Y. Jung, S. Liu, and Z. Sun, *Chem* **5**, 204 (2019).
- ¹⁹Q. Fu, W.-X. Li, Y. Yao, H. Liu, H.-Y. Su, D. Ma, X.-K. Gu, L. Chen, Z. Wang, H. Zhang, B. Wang, and X. Bao, *Science* **328**, 1141 (2010).
- ²⁰J.-Y. Luo, M. Meng, X. Li, X.-G. Li, Y.-Q. Zha, T.-D. Hu, Y.-N. Xie, and J. Zhang, *J. Catal.* **254**, 310 (2008).

- ²¹J. Shen, R. E. Hayes, and N. Semagina, *Catal. Today* **360**, 435 (2021).
- ²²N. T. S. Phan, M. Van Der Sluys, and C. W. Jones, *Adv. Synt. Catal.* **348**, 609 (2006).
- ²³V. Polshettiwar, C. Len, and A. Fihri, *Coord. Chem. Rev.* **253**, 2599 (2009).
- ²⁴Z.-c. Zhang, B. Xu, and X. Wang, *Chem. Soc. Rev.* **43**, 7870 (2014).
- ²⁵P. Mehta, J. Greeley, W. N. Delgass, and W. F. Schneider, *ACS Catal.* **7**, 4707 (2017).
- ²⁶S. Polierer, J. Jelic, S. Pitter, and F. Studt, *J. Phys. Chem. C* **123**, 26904 (2019).
- ²⁷J. K. Nørskov, T. Bligaard, J. Rossmeisl, and C. H. Christensen, *Nat. Chem.* **1**, 37 (2009).
- ²⁸D. Kopač, B. Likozar, and M. Huš, *Appl. Surf. Sci.* **497**, 143783 (2019).
- ²⁹I. A. Pašti and S. V. Mentus, *Electrochim. Acta* **55**, 1995 (2010).
- ³⁰M. Mavrikakis, B. Hammer, and J. K. Nørskov, *Phys. Rev. Lett.* **81**, 2819 (1998).
- ³¹S. Kattel, B. Yan, J. G. Chen, and P. Liu, *J. Catal.* **343**, 115 (2016).
- ³²M. M. Kauppinen, V. Korpelin, A. M. Verma, M. M. Melander, and K. Honkala, *J. Chem. Phys.* **151**, 164302 (2019).
- ³³A. S. Bazhenov and K. Honkala, *J. Phys. Chem. C* **123**, 7209 (2019).
- ³⁴Y. Yang, J. Evans, J. A. Rodriguez, M. G. White, and P. Liu, *Phys. Chem. Chem. Phys.* **12**, 9909 (2010).
- ³⁵G. A. Olah, *Angew. Chem. Int. Ed.* **52**, 104 (2013).
- ³⁶M. Behrens, F. Studt, I. Kasatkin, S. Kuhl, M. Havecker, F. Abild-Pedersen, S. Zander, F. Girgsdies, P. Kurr, B.-L. Kniep, M. Tovar, R. W. Fischer, J. K. Nørskov, and R. Schlögl, *Science* **336**, 893 (2012).
- ³⁷L. C. Grabow and M. Mavrikakis, *ACS Catal.* **1**, 365 (2011).
- ³⁸S. Kattel, B. Yan, Y. Yang, J. G. Chen, and P. Liu, *J. Am. Chem. Soc.* **138**, 12440 (2016).
- ³⁹T. Witoon, J. Chalorngtham, P. Dumrongbunditkul, M. Chareonpanich, and J. Limtrakul, *Chem. Eng. J.* **293**, 327 (2016).
- ⁴⁰Y. Nitta, O. Suwata, Y. Ikeda, Y. Okamoto, and T. Imanaka, *Catal. Lett.* **26**, 345 (1994).
- ⁴¹K. D. Jung and A. T. Bell, *J. Catal.* **193**, 207 (2000).
- ⁴²I. A. Fisher and A. T. Bell, *J. Catal.* **178**, 153 (1998).
- ⁴³I. A. Fisher, H. C. Woo, and A. T. Bell, *Catal. Lett.* **44**, 11 (1997).
- ⁴⁴F. Arena, G. Italiano, K. Barbera, S. Bordiga, G. Bonura, L. Spadaro, and F. Frusteri, *Appl. Catal. A Gen.* **350**, 16 (2008).
- ⁴⁵F. Arena, G. Mezzatesta, G. Zafarana, G. Trunfio, F. Frusteri, and L. Spadaro, *J. Catal.* **300**, 141 (2013).

- ⁴⁶J. D. Grunwaldt, A. M. Molenbroek, N. Y. Topsøe, H. Topsøe, and B. S. Clausen, *J. Catal.* **194**, 452 (2000).
- ⁴⁷A. Le Valant, C. Comminges, C. Tisseraud, C. Canaff, L. Pinard, and Y. Pouilloux, *J. Catal.* **324**, 41 (2015).
- ⁴⁸J. Zhong, X. Yang, Z. Wu, B. Liang, Y. Huang, and T. Zhang, *Chem. Soc. Rev.* **49**, 1385 (2020).
- ⁴⁹I. X. Green, W. Tang, M. Neurock, and J. T. Yates Jr., *Angew. Chem. Int. Edit.* **50**, 10186 (2011).
- ⁵⁰I. Kasatkin, P. Kurr, B. Kniep, A. Trunschke, and R. Schlögl, *Angew. Chem. Int. Ed.* **46**, 7324 (2007).
- ⁵¹M. M. Günter, T. Ressler, B. Bems, C. Büscher, T. Genger, O. Hinrichsen, M. Muhler, and R. Schlögl, *Catal. Lett.* **71**, 37 (2001).
- ⁵²S. Sakong and A. Groß, *Surf. Sci.* **525**, 107 (2003).
- ⁵³J. Wellendorff, K. T. Lundgaard, A. Møgelhøj, V. Petzold, D. D. Landis, J. K. Nørskov, T. Bligaard, and K. W. Jacobsen, *Phys. Rev. B* **85**, 235149 (2012).
- ⁵⁴P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- ⁵⁵J. Enkovaara, C. Rostgaard, J. J. Mortensen, J. Chen, M. Dułak, L. Ferrighi, J. Gavnholt, C. Glinsvad, V. Haikola, H. A. Hansen, H. H. Kristoffersen, M. Kuisma, A. H. Larsen, L. Lehtovaara, M. Ljungberg, O. Lopez-Acevedo, P. G. Moses, J. Ojanen, T. Olsen, V. Petzold, N. A. Romero, J. Stausholm-Møller, M. Strange, G. A. Tritsarlis, M. Vanin, M. Walter, B. Hammer, H. Häkkinen, G. K. H. Madsen, R. M. Nieminen, J. K. Nørskov, M. Puska, T. T. Rantala, J. Schiøtz, K. S. Thygesen, and K. W. Jacobsen, *J. Phys. Cond. Mat.* **22**, 253202 (2010).
- ⁵⁶S. L. Dudarev, G. A. Botton, S. Y. Savrasov, C. J. Humphreys, and A. P. Sutton, *Phys. Rev. B* **57**, 1505 (1998).
- ⁵⁷A. H. Larsen, J. J. Mortensen, J. Blomqvist, I. E. Castelli, R. Christensen, M. Dułak, J. Friis, M. N. Groves, B. Hammer, C. Hargus, E. D. Hermes, P. C. Jennings, P. B. Jensen, J. Kermode, J. R. Kitchin, E. L. Kolsbjerg, J. Kubal, K. Kaasbjerg, S. Lysgaard, J. B. Maronsson, T. Maxson, T. Olsen, L. Pastewka, A. Peterson, C. Rostgaard, J. Schiøtz, O. Schütt, M. Strange, K. S. Thygesen, T. Vegge, L. Vilhelmsen, M. Walter, Z. Zeng, and K. W. Jacobsen, *J. Phys. Condens. Mat.* **29**, 273002 (2017).

- ⁵⁸R. F. W. Bader, *Atoms in Molecules: A Quantum Theory*, edited by R. F. W. Bader, International series of monographs on chemistry (Oxford University Press, Oxford, 1990).
- ⁵⁹W. Tang, E. Sanville, and G. Henkelman, *J. Phys. Condens. Matter* **21**, 084204 (2009).
- ⁶⁰B. Hammer and J. K. Nørskov, *Surf. Sci.* **343**, 211 (1995).
- ⁶¹P. L. Hansen, J. B. Wagner, S. Helveg, J. R. Rostrup-Nielsen, B. S. Clausen, and H. Topsøe, *Science* **295**, 2053 (2002).
- ⁶²S. Kouva, J. Andersin, K. Honkala, J. Lehtonen, L. Lefferts, and J. Kanervo, *Phys. Chem. Chem. Phys.* **16**, 20650 (2014).
- ⁶³A. S. Bazhenov and K. Honkala, *Top. Catal.* **60**, 382 (2017).
- ⁶⁴J. R. Kitchin, J. K. Nørskov, M. A. Barteau, and J. G. Chen, *Phys. Rev. Lett.* **93**, 156801 (2004).