

Synthesis and styrene copolymerization of novel trisubstituted ethylenes:

8. Halogen ring-disubstituted 2-methoxyethyl phenylcyanoacrylates

Julianne Cappas, Emma Caraus, Sharad Chandra, Jacqueline A. Flores, Emily F. Jorgensen, Spozmai N. Khan, Emilia Kulka, Eiden Lami, Grace A. McGee, Gazmend Sadiku, Rami Sakka, Laith M. Shaban, Mariam Shaikh, Sara M. Rocus, William S. Schjerven, and Gregory B. Kharas

DePaul University, Chemistry and Biochemistry Department, 1110 West Belden Avenue, Chicago, IL 60614-3214

Abstract

Novel trisubstituted ethylenes, halogen ring-disubstituted 2-methoxyethyl phenylcyanoacrylates, $R\text{PhCH}=\text{C}(\text{CN})\text{CO}_2\text{CH}_2\text{CH}_2\text{OCH}_3$ (where R is 2-fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy) were prepared and copolymerized with styrene. The ethylenes were synthesized by the piperidine catalyzed Knoevenagel condensation of ring-substituted benzaldehydes and 2-methoxyethyl cyanoacetate, and characterized by CHN analysis, IR, ^1H and ^{13}C NMR. All the ethylenes

were copolymerized with styrene in solution with radical initiation (ABCN) at 70°C. The compositions of the copolymers were calculated from nitrogen analysis.

Keywords: ring-substituted phenylcyanoacrylates, Knoevenagel condensation, radical copolymerization, styrene copolymers

1. Introduction

Cyanoacrylates is family of vinyl monomers renowned for their high reactivity, instant adhesive properties, and wide-ranging applications [1–3]. Trisubstituted ethylenes (TSE), ring-functionalized phenylcyanoacrylates, $R^1\text{PhCH} = \text{C}(\text{CN})\text{CO}_2\text{R}^2$ (PCA) continue to attract attention as compounds with variety of applications [4–13]. Thus, methoxy ring-substituted methyl phenylcyanoacrylate, MPCA was used in synthesis of pyridotriazines and triazolopyridines [4]. Dimethylamino ring-substituted MPCA was examined among other cyanovinylheteroaromatics in relation to organic nonlinear optics [5]. There are a number of applications of ethyl phenylcyanoacrylate, EPCA and its ring-substituted derivatives, which include studies of catalysis [6] and potential antimicrobial and antioxidant agents [7]. 2,4-Dimethoxyphenyl EPCA was used in design, synthesis and study of anticancer activity of novel benzothiazole analogues [8], in synthesis of thiazacridine derivatives as anticancer agents against breast and hematopoietic neoplastic cells [9] and in DABCO-catalyzed Knoevenagel condensation using hydroxy ionic liquid as a promoter [10]. This EPCA was involved in catalysis study of N,N'-dialkylimidazolium dimethyl phosphates [11], in

synthesis and study of antimicrobial activity of some cyanoacrylates [12], as well as in synthesis of antiproliferative active 2-aminobenzimidazole derivatives [13].

In regards to polymerization reactivity, previous studies showed that PCAs as all TSE monomers containing double bond substituents larger than fluorine have very low reactivity in radical homopolymerization due to polar and steric reasons [14]. Although steric difficulties preclude homopolymerization of such monomers, their copolymerization with a monosubstituted alkenes makes it possible to overcome these steric problems. Thus, copolymerization of electrophilic TSE monomers having double bonds substituted with halo, cyano, and carbonyl groups and electron-rich monosubstituted ethylenes such as styrene, N-vinylcarbazole, and vinyl acetate [15-17] show a tendency toward the formation of alternating copolymers - thus suggesting a way of functionalization of commercial polymers via introduction of isolated monomer units in copolymers.

Earlier we have reported synthesis and styrene copolymerization a number of halogen ring-disubstituted PCAs, such esters as methyl [18,19], ethyl [20], propyl [21-23], isopropyl [24-26], butyl [27, 28], and isobutyl [29].

Our objectives in exploration of novel 2-methoxyethyl phenylcyanoacrylates (MEPA) were twofold: (1) to utilize Knoevenagel condensation for synthesis of MEPA compounds with a variety of potentially reactive functional groups and (2) to explore feasibility of radical copolymerization with a commercial monomer styrene.

Thus, in continuation of our investigation of novel TSE compounds we have prepared halogen ring-disubstituted 2-methoxyethyl phenylcyanoacrylates, $RPhCH=C(CN)CO_2CH_2CH_2OCH_3$, where R is 2-fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-

fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy), and explored the feasibility of their copolymerization with styrene. To the best of our knowledge there have been no reports on either synthesis of these compounds, nor their copolymerization with styrene [30].

2. Experimental

2.1. Materials

2-Fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy - substituted benzaldehydes, 2-methoxyethyl cyanoacetate ($\geq 98.0\%$), piperidine (99%), styrene ($\geq 99\%$), 1,1'-azobis(cyclohexanecarbonitrile) (98%), (ABCN), and toluene (98%) supplied from Sigma-Aldrich Co., were used as received.

2.2. Instrumentation


Infrared spectra of the MEPA compounds and polymers (NaCl plates) were determined with an ABB FTLA 2000 FT-IR spectrometer. The melting points of the MEPA compounds were measured with TA (Thermal Analysis, Inc.) Model Q10 differential scanning calorimeter (DSC). ^1H and ^{13}C NMR spectra were obtained on 10-25% (w/v) MEPA solutions in CDCl_3 at ambient temperature using Avance 300 MHz spectrometer. CHN-

elemental analyses of MEPA compounds and nitrogen analysis of the copolymers were performed by Midwest Microlab, LLC (IN).

3. Results and discussion

3.1. Synthesis and characterization of 2-methoxyethyl phenylcyanoacrylates

All MEPA compounds were synthesized by Knoevenagel condensation [31] of appropriate benzaldehydes with 2-methoxyethyl cyanoacetate, catalyzed by base, piperidine (Scheme 1).



Scheme 1. Synthesis of 2-methoxyethyl phenylcyanoacrylates where R is 2-fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy.

The preparation procedure was essentially the same for all the MEPA compounds. In a typical synthesis, equimolar amounts of 2-methoxyethyl cyanoacetate and an appropriate benzaldehyde were mixed in equimolar ratio in a 20 mL vial. A few drops of piperidine were added with stirring. The product of the reaction was isolated by filtration and purified by crystallization from 2-propanol. The condensation reaction proceeded smoothly, yielding products, which were purified by conventional techniques. The compounds were

characterized by IR, ^1H and ^{13}C NMR spectroscopies. No stereochemical analysis of the novel alkoxy ring-substituted MEPA was performed since no stereoisomers (*E* or/and *Z*) of known configuration were available.

3.1.1. 2-Methoxyethyl 2-fluoro-3-methoxyphenylcyanoacrylate

Yield: 74%; ^1H NMR: δ 8.6 (s, 1H, CH=), 8.0-7.1 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.9 (s, 3H, PhOCH₃), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ^{13}C NMR: δ 164 (C=O), 154 (HC=), 143, 135, 131, 125, 112, 106 (Ph), 116 (CN), 105 (C=), 74 (OCH₂), 65 (OCOCH₂), 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2943 (m, C-H), 2228 (m, CN), 1734 (s, C=O), 1580 (s, C=C), 1277 (s, C-O-CH₃), 784, 721 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 54.74; H, 4.61; N, 4.87.

3.1.2. 2-Methoxyethyl 2-fluoro-4-methoxyphenylcyanoacrylate

Yield: 83%; ^1H NMR: δ 8.5 (s, 1H, CH=), 7.9-6.6 (m, 3H, Ph), 4.5, 4.4 (t, 2H, OCOCH₂), 3.9 (s, 3H, PhOCH₃), 3.7, 3.6 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ^{13}C NMR: δ 168-163 (C=O), 146 (HC=), 130, 118, 114-111 (Ph), 116 (CN), 102 (C=), 74, 70 (OCH₂), 66 (OCOCH₂), 62, 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2935 (m, C-H), 2222 (m, CN), 1749 (s, C=O), 1620 (s, C=C), 1275 (s, C-O-CH₃), 843, 814 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 58.74; H, 4.87; N, 4.89.

3.1.3. 2-Methoxyethyl 2-fluoro-5-methoxyphenylcyanoacrylate

Yield 91%; ^1H NMR: δ 8.5 (s, 1H, CH=), 7.9-7.0 (m, 3H, Ph), 4.5, 4.4 (t, 2H, OCOCH₂), 3.9, 3.8 (s, 3H, PhOCH₃), 3.7, 3.6 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ^{13}C NMR: δ 166, 164 (C=O), 158, 156 (HC=), 146, 124, 123, 120, 115, 110 (Ph), 117 (CN), 104 (C=), 74

(OCH₂), 70, 66 (OCOCH₂), 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2943 (m, C-H), 2228 (m, CN), 1734 (s, C=O), 1580 (s, C=C), 1277 (s, C-O-CH₃), 784, 721 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 54.74; H, 4.61; N, 4.87.

3.1.4. 2-Methoxyethyl 2-fluoro-6-methoxyphenylcyanoacrylate

Yield 85%; ¹H NMR: δ 8.3, 8.4 (s, 1H, CH=), 7.6-6.7 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.9 (s, 3H, PhOCH₃), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ¹³C NMR: δ 165, 163, 162 (C=O), 160 (HC=), 146, 136, 134, 125, 110, 109, 108 (Ph), 115, 114 (CN), 107 (C=), 74, 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2943 (m, C-H), 2230 (m, CN), 1732 (s, C=O), 1616 (s, C=C), 1261 (s, C-O-CH₃), 785, 756 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 57.97; H, 4.82; N, 4.88.

3.1.5. 2-Methoxyethyl 3-fluoro-4-methoxyphenylcyanoacrylate

Yield 74%; ¹H NMR: δ 8.1 (s, 1H, CH=), 8.0-7.0 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 4.0 (s, 3H, PhOCH₃), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ¹³C NMR: δ 166, 163 (C=O), 154, 153 (HC=), 130, 129, 125, 118, 1115 (Ph), 116 (CN), 101 (C=), 74, 70 (OCH₂), 66 (OCOCH₂), 62, 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2938 (m, C-H), 2222 (m, CN), 1749 (s, C=O), 1609 (s, C=C), 1283 (s, C-O-CH₃), 874, 818, 744 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 57.75; H, 4.72; N, 4.91.

3.1.6. 2-Methoxyethyl 4-fluoro-3-methoxyphenylcyanoacrylate

Yield 79%; ^1H NMR: δ 8.2 (s, 1H, CH=), 7.9-7.1 (m, 3H, Ph), 4.5, 4.4 (t, 2H, OCOCH₂), 4.0 (s, 3H, PhOCH₃), 3.8, 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃); ^{13}C NMR: δ 165, 164 (C=O), 158, 157, 154 (HC=), 149, 134, 128, 126, 125, 114 (Ph), 117 (CN), 103, 102 (C=), 74, 70 (OCH₂), 65, 62 (OCOCH₂), 59 (OCH₃), 56 (PhOCH₃); IR: (cm⁻¹) 2941 (m, C-H), 2224 (m, CN), 1751 (s, C=O), 1595 (s, C=C), 1265 (s, C-O-CH₃), 858, 783, 762 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₄: C, 60.21; H, 5.05; N, 5.02; Found: C, 57.44; H, 4.85; N, 4.91.

3.1.7. 2-Methoxyethyl 2-fluoro-5-methylphenylcyanoacrylate

Yield 79%; ^1H NMR δ 8.5 (s, 1H, CH=), 7.7-7.0 (m, 3H, Ph), 5.2 (s, 2H, PhCH₂), 4.5, 4.3 (t, 2H, OCOCH₂), 3.6 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃), 2.4 (s, 3H, PhCH₃); ^{13}C NMR: δ 163 (C=O), 158 (HC=), 148, 137, 136, 130, 124, 120 (Ph), 116 (CN), 104 (C=), 74, 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 20 (PhCH₃); IR: (cm⁻¹) 2932 (m, C-H), 2226 (m, CN), 1734 (s, C=O), 1609 (s, C=C), 1236 (s, C-O-CH₃), 824, 764, 714 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₃: C, 63.87; H, 5.36; N, 5.32; Found: C, 59.80; H, 5.16; N, 4.90.

3.1.8. 2-Methoxyethyl 2-fluoro-6-methylphenylcyanoacrylates

Yield 89%; ^1H NMR δ 8.3 (s, 1H, CH=), 7.5-6.9 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃), 2.4 (s, 3H, PhCH₃); ^{13}C NMR: δ 165 (C=O), 150 (HC=), 143, 140, 135, 133, 126, 123 (Ph), 116 (CN), 104 (C=), 74, 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 21 (PhCH₃); IR: (cm⁻¹) 2934 (m, C-H), 2233 (m, CN), 1750 (s,

C=O), 1614 (s, C=C), 1256 (s, C-O-CH₃), 862, 827, 787 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₃: C, 63.87; H, 5.36; N, 5.32; Found: C, 60.80; H, 5.19; N, 5.28.

3.1.9. 2-Methoxyethyl 3-fluoro-4-methylphenylcyanoacrylate

Yield 83%; ¹H NMR δ 8.2 (s, 1H, CH=), 7.8-7.3 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.6 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃), 2.4 (s, 3H, PhCH₃); ¹³C NMR: δ 166 (C=O), 154 (HC=), 136, 134, 133, 127, 126, 115 (Ph), 117 (CN), 104 (C=), 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 25 (PhCH₃); IR: (cm⁻¹) 2932 (m, C-H), 2224 (m, CN), 1754 (s, C=O), 1607 (s, C=C), 1277 (s, C-O-CH₃), 874, 824, 781 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₃: C, 63.87; H, 5.36; N, 5.32; Found: C, 66.76; H, 5.44; N, 5.78.

3.1.10. 2-Methoxyethyl 4-fluoro-2-methylphenylcyanoacrylates

Yield 91%; ¹H NMR δ 8.5 (s, 1H, CH=), 8.3-6.9 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃), 2.5 (s, 3H, PhCH₃); ¹³C NMR: δ 163 (C=O), 153 (HC=), 144, 135, 131, 127, 119, 114 (Ph), 116 (CN), 104 (C=), 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 20 (PhCH₃); IR: (cm⁻¹) 2932 (m, C-H), 2226 (m, CN), 1751 (s, C=O), 1591 (s, C=C), 1244 (s, C-O-CH₃), 866, 824 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₃: C, 63.87; H, 5.36; N, 5.32; Found: C, 60.82; H, 5.14; N, 5.54.

3.1.11. 2-Methoxyethyl 4-fluoro-3-methylphenylcyanoacrylates

Yield 76%; ¹H NMR δ 8.2 (s, 1H, CH=), 7.9-7.1 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, OCH₃), 2.3 (s, 3H, PhCH₃); ¹³C NMR: δ 163 (C=O), 153 (HC=), 145, 144, 136, 131, 127, 119 (Ph), 116 (CN), 104 (C=), 70 (OCH₂), 66 (OCOCH₂), 59 (OCH₃), 20 (PhCH₃); IR: (cm⁻¹) 2932 (m, C-H), 2224 (m, CN), 1751 (s,

C=O), 1589 (s, C=C), 1250 (s, C-O-CH₃), 827 (s, C-H out of plane). Anal. calcd. for C₁₄H₁₄FNO₃: C, 63.87; H, 5.36; N, 5.32; Found: C, 61.80; H, 5.22; N, 5.13.

3.1.12. 2-Methoxyethyl 4-fluoro-3-phenoxyphenylcyanoacrylates

Yield 83%; ¹H NMR δ 8.1 (s, 1H, CH=), 7.7-7.0 (m, 3H, Ph), 4.4 (t, 2H, OCOCH₂), 3.6 (t, 2H, OCH₂), 3.4 (s, 3H, CH₃O); ¹³C NMR δ 163 (C=O), 156 (HC=), 145, 134, 130, 127, 125, 121, 118 (Ph), 117 (CN), 101 (C=), 74 (OCH₂), 66 (OCOCH₂), 59 (OCH₃); IR (cm⁻¹): 2934 (m, C-H), 2224 (m, CN), 1761 (s, C=O), 1589 (s, C=C), 1254 (s, C-O-CH₃), 822, 756 (s, C-H out of plane). Anal. Calcd. for C₁₉H₁₆FNO₄: C, 66.86; H, 4.72; N, 4.10; Found: C, 65.54; H, 4.52; N, 4.71.

3.1.13. 2-Methoxyethyl 5-iodo-2-methoxyphenylcyanoacrylates

Yield 79%; mp 117.5°C; ¹H NMR δ 8.4 (s, 1H, CH=), 8.2-6.7 (m, 3H, Ph), 4.5 (t, 2H, OCOCH₂), 3.8 (s, 3H, PhCH₃), 3.7 (t, 2H, OCH₂), 3.4 (s, 3H, CH₃O), 2.6 (s, 3H, PhCH₃); ¹³C NMR δ 160 (C=O), 155 (HC=), 143, 138, 123, 114 (Ph), 117 (CN), 103 (C=), 74 (OCH₂), 64 (OCOCH₂), 59 (OCH₃), 55 (PhOCH₃); IR (cm⁻¹): 2949 (m, C-H), 2214 (m, CN), 1730 (s, C=O), 1583 (s, C=C), 1246 (s, C-O-CH₃), 818, 762 (s, C-H out of plane). Anal. Calcd. for C₁₄H₁₄INO₄: C, 43.43; H, 3.64; N, 3.62; Found: C, 44.30; H, 3.74; N, 3.62.


3.2. Homopolymerization

An attempted homopolymerization of the MEPA compounds in the presence of ABCN did not produce any polymer as indicated by the lack of a precipitate in methanol. The inability of the monomers to polymerize is associated with steric difficulties encountered

in homopolymerization of 1,1- and 1,2-disubstituted ethylenes [14]. Homopolymerization of styrene (ST) under conditions identical to those in copolymerization experiments yielded 18.3% of polystyrene, when polymerized for 30 min.

3.3. Synthesis and characterization of styrene – MEPA copolymers

Copolymers of the ST and the MEPA compounds, P(ST-co-MEPA) were prepared in 25-mL glass screw cap vials at ST/MEPA = 3 (mol) the monomer feed using 0.12 mol/L of ABCN at an overall monomer concentration 2.44 mol/L in 10 mL of toluene. The copolymerization was conducted at 70°C. After a predetermined time, the mixture was cooled to room temperature, and precipitated dropwise in methanol. The composition of the copolymers was determined based on the nitrogen content (cyano group in MEPA monomers). The novel synthesized MEPA compounds copolymerized readily with ST under free-radical conditions (Scheme 2) forming white flaky precipitates when their solutions were poured into methanol. The conversion of the copolymers was kept between 10 and 20% to minimize compositional drift (Table 1).



Scheme 2. Copolymerization of ST and phenoxy ring-substituted 2-methoxyethyl phenylcyanoacrylates, $RPhCH = C(CN)CO_2CH_2CH_2OCH_3$. R is 2-fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-

3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy.

Table 1. Copolymerization of Styrene and 2-Methoxyethyl phenylcyanoacrylates.

R	Yield ^a (wt%)	N (wt%)	ST in copol. (mol%)	MEPA in copol. (mol%)
2-Fluoro-3-methoxy	11.5	2.36	75.1	24.9
2-Fluoro-4-methoxy	14.1	2.22	77.2	22.8
2-Fluoro-5-methoxy	13.2	2.43	74.1	25.9
2-Fluoro-6-methoxy	14.2	2.35	75.3	24.7
3-Fluoro-4-methoxy	13.0	2.28	76.3	23.7
4-Fluoro-3-methoxy	11.8	2.2	77.5	22.5
2-Fluoro-5-methyl	12.9	2.65	71.8	28.2
2-Fluoro-6-methyl	11.5	1.83	82.8	17.2
3-Fluoro-4-methyl	12.9	2.42	75.2	24.8
4-Fluoro-2-methyl	14.5	1.98	81.0	19.0
4-Fluoro-3-methyl	11.3	2.06	80.0	20.0
4-Fluoro-3-phenoxy	12.5	1.99	77.7	22.3
5-Iodo-2-methoxy	14.7	2.11	72.7	27.3

Nitrogen elemental analysis showed that between 17.2 and 28.2 mol% of MEPA is present in the copolymers prepared at ST/MEPA = 3 (mol), which is indicative of relatively high reactivity of the MEPA monomers towards ST radical which is typical of phenoxy ring-substituted phenylcyanoacrylates [18-29]. Since MEPA monomers do not homopolymerize, the most likely structure of the copolymers would be isolated MEPA monomer units alternating with short ST sequences (Scheme 2).

The copolymers prepared in the present work are all soluble in ethyl acetate, THF, DMF and CHCl₃ and insoluble in methanol, ethyl ether, and petroleum ether.

4 Conclusions

Novel trisubstituted ethylenes, ring-substituted 2-methoxyethyl phenylcyanoacrylates, $R\text{PhCH}=\text{C}(\text{CN})\text{CO}_2\text{CH}_2\text{CH}_2\text{OCH}_3$ (where R is 2-fluoro-3-methoxy, 2-fluoro-4-methoxy, 2-fluoro-5-methoxy, 2-fluoro-6-methoxy, 3-fluoro-4-methoxy, 4-fluoro-3-methoxy, 2-fluoro-5-methyl, 2-fluoro-6-methyl, 3-fluoro-4-methyl, 4-fluoro-2-methyl, 4-fluoro-3-methyl, 4-fluoro-3-phenoxy, 5-iodo-2-methoxy) were prepared and copolymerized with styrene.

Acknowledgments

The authors are grateful to acknowledge that the project was partly supported by Chicago Society of Coating Technology (CSCT).

References

- [1] Klemarczyk, P.; Guthrie, J. Advances in anaerobic and cyanoacrylate adhesives. In *Advances in Structural Adhesive Bonding*, 1st ed.; Dillard, D., Ed.; Woodhead Publishing Limited: Cambridge, UK, 2010; pp. 96–131, ISBN 978-1-84569-435-7.
- [2] Shantha, K.L.; Thennarasu, S.; Krishnamurti, N. Developments and applications of cyanoacrylate adhesives. *J. Adhes. Sci. Technol.* 1989, 3, 237–260.
- [3] J.M. Korde and B. Kandasubramanian, Biocompatible alkyl cyanoacrylates and their derivatives as bio-adhesives, *Biomaterials Science*, 10.1039/C8BM00312B, 6, 7, (1691-1711), (2018).
- [4] Zaki MEA, Fathalla OA, Swelam SA, Aly HF (2004) Synthesis of pyrido[2,1-c][1,2,4]triazine, 1,2,4-triazolo[4,3-a]pyridine and 2-(pyrazolyl)nicotinonitrile and their

effect on *Biomphalaria alexandrina* snail enzymes. *Acta Poloniae Pharmaceutica* 61: 55-64.

- [5] Matsuoka M, Takao M, Kitao T, Fujiwara T, Nakatsu K (1990) Cyanovinylheteroaromatics for Organic Nonlinear Optics. *Molecular Crystals and Liquid Crystals*, 182A: 71-79.
- [6] Burate PA, Javle BR, Desale PH, Kinage AK (2019) Amino acid amide based ionic liquid as an efficient organo-catalyst for solvent-free Knoevenagel condensation at room temperature. *Catalysis Letters* 149(9): 2368-2375.
- [7] Medyouni R, Hamdi N, Ben Said R, Al-Ayed AS, Zagrouba F (2013) Clean procedure and DFT study for the synthesis of 2-amino-3-ethoxycarbonyl-4-(aryl)-4H-pyrano-[3,2-c]-chromene-5-ones derivatives: A novel class of potential antimicrobial and antioxidant agents. *Journal of Chemistry* 2013: 1-4.
- [8] Hassan AY, Sarg MT, Hussein EM (2019) Design, synthesis and anticancer activity of novel benzothiazole analogues. *Journal of Heterocyclic Chemistry* 56(4): 1437-1457.
- [9] Moacyr JB, De Melo R, Wanessa LB, De Sena, RO, De Moura, Iris TT et al. (2017). Synthesis and anticancer evaluation of thiazacridine derivatives reveals new selective molecules to hematopoietic neoplastic cells. *Combinatorial Chemistry & High Throughput Screening* 20(8): 713.

- [10] Meng D, Qiao Y, Wang X, Wen W, Zhao S (2018) DABCO-catalyzed Knoevenagel condensation of aldehydes with ethyl cyanoacetate using hydroxy ionic liquid as a promoter. *RSC Advances* 8(53): 30180-30185.
- [11] Brica S, Freimane L, Kulikovska L, Zicmanis A (2017) N,N'-dialkylimidazolium dimethyl phosphates - promising media and catalysts at the same time for condensation reactions. *Chemical Science International Journal* 19(4): 1-9.
- [12] Bhuiyan M, Mosharef H, Rahman KM, Alam MA, Mahmud M (2013) Microwave assisted Knoevenagel condensation: synthesis and antimicrobial activities of some α -cyanoacrylates. *Pakistan Journal of Scientific and Industrial Research, Series A: Physical Sciences* 56(3): 131-137.
- [13] Nowicka A, Liszkiewicz H, Nawrocka WP, Wietrzyk J, Kempinska K, Drys A (2014) Synthesis and antiproliferative activity in vitro of new 2-aminobenzimidazole derivatives. Reaction of 2-arylideneaminobenzimidazole with selected nitriles containing active methylene group. *Central European Journal of Chemistry* 12(10): 1047-1055.
- [14] Odian, G. *Principles of Polymerization*, 4th Ed., Wiley-Interscience: New York, 2004.
- [15] Hall, H. K., Jr.; Padias, A. B. *J. Polym. Sci. Part A: Polym. Chem.* **2004**, *42*, 2845-2858.
- [16] Hall, H. K. Jr.; Ykman, P. *Macromolecules.* 1977, *10*, 464.

- [17] Kharas, G. B. *Trisubstituted Ethylene Copolymers. In Polymeric Materials Encyclopedia*, Salamone, J.C., (Ed.) CRC Press: Boca Raton, FL, 11, 8405, 1996.
- [18] Novel Copolymers of Styrene. 11. Some Ring-Substituted Methyl 2-Cyano-3-phenyl-2-propenoates. G.B. Kharas, S.E. Chavez, A.N. Luna, E.E. Lusk, D.P. Mendez, D.S. O'Rourke, C.S. Roat, S.G. Robinson, G.S. Stamelos, J.D. Schoenburg, D.H. Vinanzaca, S. Zermeno, M.P. O'Mara. *J. Macromol. Sci.* A51 (1), 1-5 (2014).
- [19] Novel Copolymers of Styrene. 12. Halogen Ring-Substituted Methyl 2-Cyano-3-Phenyl-2-Propenoates. C.E. Karver, E.S. Molina, E.T. Economos, J.C. Fuentes, S.M. Kaitson, S. Kogan, G. Levi, J.K. Marcus, S. Mei, S.C. Reinsalu, K. Rico, M.M. Zuzek, G.B. Kharas. *J. Macromol. Sci.* A51(2) 101-105 (2014).
- [20] Novel Copolymers of Styrene. 8. Haloalkyl Ring-substituted Ethyl 2-Cyano-3-phenyl-2-propenoates. G.B. Kharas, B.M. Fitzpatrick, M.C. Francis, C. Gallardo, J.L. Gehle, G.M. Giovannini, M.E. Giovannini, J.K. Jerzewski, S.L. LaFary, L.N. Lessor, D.E. Macias. *J. Macromol. Sci.* A50 (4) 370-374 (2013).
- [21] Novel Copolymers of Styrene. 6. Some Ring-Disubstituted Propyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, L.A. Alyahya, S. M. Rocus, A. Ismail, R. Juarez, A. Kavaliauskaite, K.Y. Lechuga, A.C. Leeper, and G.C. Lenti. *J. Macromol. Sci.* A53(12) 725-728 (2016).
- [22] Novel Copolymers of Styrene. 8. Fluoro Ring-Disubstituted Propyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, Y.L. Soto, E.L. Divino, M. Donovan, M.D.

- Dotson, S.A. Slazyk, D. Kishawi, J.H. Kittle, S. Logvinenko, B.M. McClarty, J.L. Pierce, and C.J. Smith. *J. Macromol. Sci. A*54(1) 1-5 (2017).
- [23] Synthesis and Radical Copolymerization of Novel Phenyl-Disubstituted Cyanoacrylates. C.R. Savittieri, S.M. Tinsley, A.J. Diehn, F. Hai, K.E. Humanski, E.J. Kempke, B.Y. Killam, J. Kozeny, E.W. Makhoul, M.C. Obert, A.C. Parisi, V.C. Parrilli, and G.B. Kharas. *Acad. J Polym Sci.* 2019; 2(5): 555597.
DOI:10.19080/AJOP.2019.02.555597.
- [24] Synthesis and Styrene Copolymerization of Novel Fluoro and Oxy Ring-Disubstituted Isopropyl Phenylcyanoacrylates. A.R. Krause, H.E. Aynessazian, M.C. Gonzalez, A.M. Khan, L.R. Lieberman, M.H. McNicholas, N.M. Pelsi, Z.S. Pierard, S.M. Rocus, W.S. Schjerven, G.B. Kharas. (2019) ChemRxiv (20.11.2019).
<https://doi.org/10.26434/chemrxiv.10279751.v1>
- [25] Synthesis and styrene copolymerization of novel halogen, alkoxy, and alkyl ring-disubstituted isopropyl 2-cyano-3-phenyl-2-propenoates. K.M. Hussain, R.M. Breault, N.J. Caporusso, C.J. Cu, K.J. Decker, T.K. Gill, E.K. Gray, C.J. Homsy, M.F. Kanji, R.M. Stone, J.L. Zepeda, S.M. Rocus, W.S. Schjerven, G.B. Kharas. ChemRxiv (04.10.2019). <https://doi.org/10.26434/chemrxiv.9932393>
- [26] Synthesis and styrene copolymerization of novel ring-disubstituted isopropyl cyanoacrylates. P.M. Whelpley, S. Bajramovic, D.M. Bracamontes, G.A. Buechner, A.D. Eremin, E.J. Kowalczyk, D.D. Lender, R. McCann, W.S. Schjerven, G.B. Kharas. ChemRxiv (24.09.2019). <https://doi.org/10.26434/chemrxiv.9891161.v1>

- [27] Novel Copolymers of Styrene. 7. Some Ring-Disubstituted Butyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, H. Feng, I.S. Shouib, C. Tong, A. Tsang, D. Velazquez, A.C. Williamson, E.B. Yokana, and A.M. Zekic. *J. Macromol. Sci.* A53(1) 1-5 (2016).
- [28] Novel Copolymers of Styrene. 9. Fluorine Ring-Disubstituted Butyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, W.S. Schjerven, U.A. Baray, S. Chan, M.T. Cole, A.F. Haddad, J.A. Lucente, K.J. Patterson, A. Ralko, K.N. Reget, C.A. Shamblen, and E.M. Whitmore. *J. Macromol. Sci.* A53(4) 191-195 (2016).
- [29] Synthesis and styrene copolymerization of novel fluoro and iodomethoxy ring-disubstituted isobutyl phenylcyanoacrylates. Umamah Alam, Magen A. Higgs, Kelly C. Ho, Kristin N. Huffman, Alexis L. Johnson, Paulina Kapica, Melanie A. Knight, Ashley Lehan, Christina Guyn, Briana N. Hryhorysak, Sara M. Rocus, William S. Schjerven and Gregory B. Kharas. ChemRxiv (17.09.2020)
<https://doi.org/10.26434/chemrxiv.11401347.v7>
- [30] SciFinder; Chemical Abstracts Service: Columbus, OH; <https://scifinder.cas.org>
(Accessed December 24, 2020).
- [31] Smith, M. B.; March, J. Addition to Carbon-Hetero Multiple Bonds, In March's Advanced Organic Chemistry, J. Wiley & Sons: New York, Ch.16, 1225, 2001.