Abnormal Effect of Phase Transition on Thermal Transport in Soft Porous Crystals

Penghua Ying, Jin Zhang,^{*} and Zheng Zhong^{*}

School of Science, Harbin Institute of Technology, Shenzhen 518055, PR China

E-mail: jinzhang@hit.edu.cn; zhongzheng@hit.edu.cn

Abstract

Soft porous crystals (SPCs) or flexible metal-organic frameworks have great potential in gas storage and separation applications, in which SPCs can undergo phase transition due to external stimulus. Thus, understanding the effect of phase transition on the thermal transport in SPCs becomes extremely crucial, because the latent heat generated in aforementioned applications is needed to be effectively removed. In this paper, taking the isorecticular DUT series as an example, the thermal transport property of SPCs during the phase transition from the large pore (lp) phase to the narrow pore (np) phase is comprehensively investigated by molecular dynamics simulations together with the Green-Kubo method. According to our calculations, all DUT structures exhibit an ultralow thermal conductivity smaller than $0.2 \text{ Wm}^{-1}\text{K}^{-1}$. In addition, we find that the effect of phase transition on the thermal transport property of different DUT materials considered here strongly depends on their porosity. As for DUT-48, its lp phase has a thermal conductivity larger than that of its np phase. However, in other DUT materials, i.e, DUT-47, DUT-49, DUT-50, and DUT-151 the thermal transport property of their lp phase is found to be weaker than that of their np phase. This complicated effect of phase transition on thermal transport in SPCs can be explained by

a porosity-dominated competition mechanism between the increased volumetric heat capacity and the aggravated phonon scattering during the phase transition process.

1. Introduction

Soft porous crystals (SPCs), coined by Kitagawa and colleagues in 2009,¹ refer to the flexible metal-organic frameworks (MOFs) or porous coordination polymers which own bistable or multistable phases with long-range crystal order.¹⁻⁵ The different phases of SPCs can switch to each other due to external physical and chemical stimulation such as mechanical pressure, gas adsorption, temperature, electric fields and light.^{4,6} A typical process of this structural transition is associated with the stepwise expansion and contraction between the large pore (lp) and narrow pore (np) phases of SPCs. Other terms have also been used to describe the SPCs processing this dynamic behavior, which includes flexible frameworks,² stimuli-responsive materials,⁴ and nanoscale metamaterials.⁷ When compared with the rigid adsorbents, this dynamic behavior of SPCs makes them promising materials for new applications in gas storage and separation.⁸⁻¹⁰ A very recent example among these applications is the novel negative gas adsorption (NGA) phenomenon of DUT-49,¹¹ in which a drop in the amount of adsorbed particles is observed with increasing vapor pressure. On the basis of reticular synthesis,¹² Krause and colleagues proposed a general network architecture design criterion for the NGA transition in isorecticular DUT materials,^{13,14} among which DUT-50,¹³ and DUT-160¹⁴ are found to exhibit an NGA behavior similar to that of DUT-49.¹¹ Several thermodynamic models have been developed to unravel the conditions determining the NGA in SPCs.¹⁵⁻¹⁷ In our recent work,¹⁸ the influence of phase transition on the mechanical properties of isorecticular DUT series has been comprehensively investigated by molecular dynamics (MD) simulations together with continuum mechanical models.

In spite of the fact that MOFs possess many unique properties, the thermal conductivity of MOFs is usually extremely low, which is typically smaller than $2 \text{ Wm}^{-1}\text{K}^{-1}$ at room

temperature,^{19–21} due to their ultra-porous structure²² and weak coordination bond.²³ The property of extralow thermal conductivity is considered as the bottleneck of MOFs in energy-related applications such as adsorbent-based fuel tanks for methane or hydrogen-powered vehicles.²⁴ Hence, it is crucial to obtain a more fundamental understanding of the nature and mechanism of the thermal transport in SPCs, which will facilitate their applications as practical industrial adsorbents. However, compared with the gas adsorption property, the study of heat transfer in SPCs is still in its very early stage. To data, only the thermal conductivity of some conventional SPCs such as MOF-5,^{23–26} ZIF-8,^{27–32} and HKUST-1^{21,33,34} has been investigated in detail by experimental or computational approaches, while the thermal transport properties of the aforementioned DUT series remain unknown. In addition, the existing studies mainly focus on the influence of gas and water adsorption,^{29,34} framework architecture,^{24,28,35–37} defects,³³ and physical environment including pressure¹⁸ and temperature²⁰ on the thermal conductivity of SPCs, little attention has been paid to the evolution of the thermal transport properties of SPCs during their dynamic process, i.e., the phase transition. To the best of our knowledge, there are only two studies regarding the effect of phase transition on the thermal transport in SPCs using MD simulations. For example, by using MD simulations, Sezginel et al.³⁸ studied the effect of pore expansion on the thermal conductivity of idealized materials, while Lemaire et al.³⁹ compared the thermal conductivity of anisotropical MIL-53(Al) within different phases. The thermal conductivity of these two MOF materials is found to be strongly dependent on the crystal orientation, since these materials have different porosity distributions along three crystal directions. It is worth mentioning that these initial studies^{38,39} ignored the impact of volume concentration due to the phase transition,¹³ which, however, may have a great impact on the thermal conductivity.^{28,30} Moreover, these studies only focus on some specific anisotropic SPCs, e.g., MIL-53(Al), which can not reveal the broad picture of the nature and mechanism behind the phase-dependent thermal transport properties of SPCs. Specifically, apart from the anisotropical SPCs, the cubic SPCs such as ZIF-8 and DUT series are also usually synthe-

sized in experiments and have great potentials in some specific applications.^{5,40} However, the effect of phase transition on the thermal transport in these cubic SPCs still remains unknown.

In this paper, taking the isorecticular DUT series as an example, we study the effect of phase transition on thermal conductivity of SPCs by using MD simulations together with Green-Kubo method. Five DUT crystals including DUT-48, DUT-49, DUT-50, and DUT-151 are considered in our work. In contrast to the previous finding that the SPCs with larger density possess a larger thermal conductivity,^{18,21,30} we demonstrate here that the np phase of DUT-48 crystal after phase transition has a larger density but owns a smaller thermal conductivity. As for other DUT crystals including DUT-47, DUT-49, DUT-50, and DUT-151, the np phase after phase transition is found to have a higher thermal conductivity, which are as expected. This complicated effect of phase transition on thermal transport in different SPCs is explained by the volumetric heat capacity and vibrational density of states (VDOS) analysis.

2. Methodology

2.1 Simulation models

Figure 1: Atomic structures of isorecticular DUT materials. Cu, O, C, N and H atoms are colored in brown, red, gray, cyan, and white, respectively.

Atomic structures of five isorecticular DUT materials considered here, i.e., DUT-48, -47, -49, -50, and -151 are plotted in Figure 1. The ligand backbone of isorecticular DUT crystals expands from one to four units of 1,4-substituted phenylene to achieve the general network architecture design for DUT-48, DUT-49, DUT-50, and DUT-151, respectively. An exception in DUT series is DUT-47 that has one unit of 2,6-substituted naphthalene, leading to an intermediate ligand length between DUT-48 and DUT-49. For the specific details of their crystal structures, we refer the readers to the original synthetic report.¹³ For all DUT materials considered here, we adopt a $2 \times 2 \times 2$ supercell with periodic boundaries along three mutually perpendicular directions. As a result, DUT-48, DUT-47, DUT-49, DUT-50, and DUT-151 models considered in the present study contain 1488, 1632, 1728, 1968, and 2208 atoms, respectively. The size selection of these DUT materials can safely exclude the size

effect and, meanwhile, improve the computational efficiency, since MOFs usually possess an extremely short phonon mean free path.²⁵

The interactions between atoms in isorecticular DUT crystals were described by the MOF-FF force field⁴¹ with the potential parameters extracted from the work reported by Krause et al..¹³ The MOF-FF force field, which is a force field derived from first-principle calculations, has been proven to be reliable in describing the mechanical and thermal properties of SPCs, such as NGA behavior,^{14,42} mechanical stability,¹⁸ and thermal expansion of isorecticular DUT series.⁴³ The porosity and density of DUTs were calculated by the open-source code Zeo++^{44,45} with a probe sphere radius of 2.0 Å. The iRASPA package⁴⁶ was used for visualization of all atomic structures.

2.2 Thermal conductivity calculations

The thermal conductivity of isorecticular DUT series was calculated by equilibrium MD simulations together with Green-Kubo method.^{47,48} The Green-Kubo method is based on the fluctuation-dissipation theorem,⁴⁹ which calculates the running thermal conductivity tensor k_{uv} by integrating the heat current autocorrelation function (HCACF) over a given correlation time t :

$$k_{uv}(t) = \frac{V}{k_B T^2} \int_0^t \langle J_u(0) J_v(t) \rangle dt. \quad (1)$$

Here, k_B , T , and V are, respectively, the Boltzmann's constant, the temperature, and the volume of the simulation box. $\langle J_u(0) J_v(t) \rangle$ is the average HCACF over different time origins with J being heat current. Since the isorecticular DUT series investigated in this work are cubic crystals, their thermal properties are isotropic in three axial directions. Therefore, Equation 1 can be further simplified into

$$k(t) = \frac{V}{k_B T^2} \int_0^t \langle J(0) J(t) \rangle dt. \quad (2)$$

All MD simulations were performed by using the publicly available simulation code LAMMPS,⁵⁰ in which the velocity Verlet algorithm was used to integrate the standard Newton equations of motion. The time step was set as 0.5 fs in MD simulations for all structures. During the MD simulation process, sufficient relaxation was performed before thermal conductivity calculations. The energy minimization was first performed by conjugate gradient method. After that, the obtained structures were relaxed at 300K and 0 GPa in the NPT ensemble (constant number of particles, pressure, and temperature) for 0.5 ns and, subsequently, at 300K in the NVT ensemble (constant number of particles, volume, and temperature) for another 0.5 ns. Here, the Nose-Hoover thermostat was applied to control the temperature and pressure. The thermal conductivity calculations were performed in the NVE ensemble (constant volume without thermostat). A correlation of 40 ps was adopted for all DUT crystals. The running thermal conductivity would converge around 30 ps of correlation time. Thus, the thermal conductivity of all DUT crystals was obtained by averaging the values obtained at the final 10 ps. Twenty independent calculations were conducted to avoid possible statistic error and then used to obtain the average thermal conductivity of DUTs considered here.

2.3 Volumetric heat capacity and vibrational analysis

The volumetric heat capacity was calculated here to explain the major factor responsible for the change in the thermal conductivity of isorecticular DUT crystals. It is noted that although the term of PV , i.e., the product of pressure P and volume V fluctuates greatly in MD simulations,⁵¹ the change of its magnitude is very small and thus can be safely ignored.⁵² Under this circumstance, we directly calculated here the heat capacity $C_V(T)$ on the basis of change in the internal energy $U(T)$:

$$C_V(T) \cong \frac{U(T + \Delta T) - U(T - \Delta T)}{2V\Delta T}, \quad (3)$$

where T and ΔT are set as 300 K and 25 K, respectively, to obtain the volumetric heat capacity of isorecticular DUT crystals at room temperature. A simulation with 2 million steps corresponding to 1 ns in the NVT ensemble was performed to achieve the gradual heating process from 275 K to 325 K in MD simulations. The raw data of the obtained internal energy was averaged every 5 ps to reduce noise. Afterwards, the volumetric heat capacity can be obtained by performing a linear fitting to the obtained $U - T$ curves.

We also calculated the VDOS to further provide a microscopic insight into the lattice vibrations of DUT crystals. The VDOS was calculated by taking the Fourier transform to the atomic velocity autocorrelation function (VACF) shown as follows

$$\text{VDOS}(\sigma) = \int \gamma(t) e^{-2\pi i \sigma t} dt, \quad (4)$$

where σ is the frequency, i is the imaginary unit, $\gamma(t) = \frac{\langle \sum_i v_i(0) \cdot v_i(t) \rangle}{\langle \sum_i v_i(0) \cdot v_i(0) \rangle}$ is the VACF. Here, $v_i(t)$ and $v_0(t)$ are, respectively, velocities of i th atom at time t and the initial time. In the present study, the VACF was calculated with a simulation of over 10 ps after the structure has reached its equilibrium stage. During this simulation, the velocity information at each 10th time step was collected for calculating the VACF.

3. Results and discussion

3.1 Ligand dependence of the thermal conductivity

Figure 2: (a) Running thermal conductivity of isorecticular DUT crystals as a function of correlation time. (b) Calculated thermal conductivity and (c) framework VDOS distribution of isorecticular DUT crystals. Here, the thermal conductivity was calculated as the average value of 20 independent simulation raw data sets. (d) Atomic VDOS distributions of DUT-49.

The original lp structures of DUT crystals are first considered here. The running thermal conductivity of five DUT materials is shown in Figure 2(a) as a function of the correlation time. From this figure we can see that although the thermal conductivity of DUTs fluctuates at the initial stage of simulations, it tends to a steady value at the final 10 ps. Thus, as mentioned in Sec. 2.2, the averaged value at the final 10 ps was taken as the steady thermal conductivity. The obtained thermal conductivity of five DUT materials considered here is compared in Figure 2(b) and listed in Table 1. It is found that DUT-48 has the highest thermal conductivity of $0.183 \text{ Wm}^{-1}\text{K}^{-1}$, followed by $0.160 \text{ Wm}^{-1}\text{K}^{-1}$ of DUT-49, $0.152 \text{ Wm}^{-1}\text{K}^{-1}$ of DUT-47, and $0.111 \text{ Wm}^{-1}\text{K}^{-1}$ of DUT-50. DUT-151 is found to possess the

lowest thermal conductivity of $0.073 \text{ Wm}^{-1}\text{K}^{-1}$. Our results indicate that when compared with some other SPCs, the present isorecticular DUT crystals can be treated as thermal insulators since they have a relatively low thermal conductivity smaller than $0.2 \text{ Wm}^{-1}\text{K}^{-1}$. The low thermal conductivity observed in the present DUTs is close to the value ($0.138 - 0.174 \text{ Wm}^{-1}\text{K}^{-1}$) extracted from their ZIF counterparts,^{27,28} but is much smaller than some other SPCs such as MOF-5 ($0.31 \text{ Wm}^{-1}\text{K}^{-1}$),^{24,25} and HKUST-1 ($1.65 \text{ Wm}^{-1}\text{K}^{-1}$).^{33,34} Moreover, it is found that the thermal conductivity of DUT crystals generally decreases with increasing ligand length. For example, when the ligand length increases from one unit of phenylene in DUT-48 to four units of phenylene in DUT-151, the thermal conductivity is found to decline from $0.180 \text{ Wm}^{-1}\text{K}^{-1}$ to $0.071 \text{ Wm}^{-1}\text{K}^{-1}$. The similar ligand length-dependent thermal conductivity is also observed in previous studies of IRMOF series.^{21,36} The only exception is DUT-47 that possesses a ligand shorter than DUT-49 (see Figure 1(b)), but has a thermal conductivity ($0.152 \text{ Wm}^{-1}\text{K}^{-1}$) slightly lower than that of DUT-49 ($0.160 \text{ Wm}^{-1}\text{K}^{-1}$). The unique thermal transport property detected in DUT-47 materials may stem from their different ligand backbone structure comprised of 2,6-substituted phenylene, which may cause a lattice vibrational mode slightly different from that of their counterparts with the ligand backbone constructed by 1,4-substituted phenylene. To further reveal the difference of lattice vibration among different DUTs considered here, we compared their VDOS distributions in Figure 2(c). It can be clearly observed that the VDOS of DUT-47 is different from other DUT crystals. For example, the VDOS peaks of DUT-47 locate around 15 THz and 38 THz, which are much higher than the values of other four DUTs. Moreover, in DUT-48, -49, -50 and -151, the VDOS intensity is found to decrease with increasing ligand length especially around the frequency of 30 THz. This result indicates that the thermal conductivity is inversely proportional to the ligand length, which is consistent with the ligand dependence of thermal conductivity directly exacted from MD simulations of DUT materials (see Figure 2).

To explain the origin of ultralow thermal conductivity observed in DUT crystals, we

decompose the VDOS of the overall framework into each group of atoms. The VDOS distribution for the framework atoms of DUT-49 is plotted in Figure 2(d), while those of other DUT crystals considered here are plotted in Figure S1 (see the Supporting Information). We consider a complete thermal transport path, which starts from the metal atom Cu, then passes through O, C, and N atoms in the ligand backbone, and finally returns to metal atom Cu. The H atom is omitted here, because it is not included in the thermal transport path.¹⁸ It is noted here that to distinguish different carbons in DUTs, the carbon atom connecting to Cu and O atoms in carboxylate moieties is termed as C1, while that in the carbon ring of phenylene bridge (or the naphthalene bridge of DUT-47) is termed as C2. The previous studies have proven that the small overlap between the atomic VDOS of the main energy carriers of MOF materials (such as Zn and N in ZIF materials) is responsible for their poor thermal transport properties.^{18,23,27} As shown in Figures 2(d) and S1, the VDOS distribution of Cu atom in all DUT crystals considered here mainly locates at the low frequency below 20 THz, while the other atoms have a broader VDOS distribution. To more directly quantify the overlap in VDOS along atomic bonds in DUT crystals, we calculate the following similarity index $\gamma_{\alpha-\beta}$:⁵³

$$\gamma_{\alpha-\beta} = \frac{\int f_{\alpha}(\sigma)f_{\beta}(\sigma)dT}{\sqrt{\int f_{\alpha}^2(\sigma)f_{\beta}^2(\sigma)dT}}, \quad (5)$$

which is a measure of the correlation in an atomic bond between the spectra $f_a(\sigma)$ of atom α and the spectra $f_b(\sigma)$ of atom β in a certain frequency range. By using this definition, in Figure S2 we plot the similarity index of atomic bonds in isorecticular DUT crystals. Because the DUT crystals share the similar framework architecture, the similarity indexes of all DUT crystals are found to be very close to each other. Specifically, as for a DUT material, the similarity index of atomic chain in the thermal transport path follows the order $\gamma_{\text{Cu-O}}$ (0.774-0.786) $>$ $\gamma_{\text{C1-C2}}$ (0.676-0.700) and $\gamma_{\text{C2-N}}$ (0.627-0.711) $>$ $\gamma_{\text{O-C1}}$ (0.470-0.493), indicating a very large overlap in Cu-O chain especially when compared to the O-C1 chain. From the above lattice vibrational analysis, we can see that, in addition to the effect of thermal

transport resistance at the interface between the metal node and the linkers (corresponding to Cu-O chain here),²³ the large phonon mismatch of the O-C1 chain in the ligand backbone can further reduce the thermal conductivity of isorecticular DUT crystals. This should be one important reason explaining the much lower thermal conductivity of isorecticular DUT series when compared to their HKUST-1 and MOF-5 counterparts, since HKUST-1 and MOF-5 do not contain the O-C1 chains existing in the isorecticular DUT series.

Table 1: Structural Parameters and Calculated Properties of lp and np Phases of Isorecticular DUT Crystals.^a

DUT Crystals	$V (\text{\AA}^3)$	$\rho (\text{g cm}^{-3})$	$\eta (\%)$	$k (\text{W m}^{-1} \text{K}^{-1})$	$C_V (\text{KJ m}^{-3} \text{K}^{-1})$
DUT-48(lp)	62537	0.444	78.8	0.180	981
DUT-48(np)	25868	0.789	55.4	0.164	1716
DUT-47(lp)	78180	0.379	81.4	0.157	868
DUT-47(np)	41681	0.728	59.8	0.173	1630
DUT-49(lp)	96047	0.321	83.6	0.163	743
DUT-49(np)	46070	0.675	62.7	0.192	1532
DUT-50(lp)	139918	0.243	87.3	0.114	581
DUT-50(np)	58582	0.585	66.6	0.169	1378
DUT-151(lp)	194574	0.187	90.1	0.071	469
DUT-151(np)	75962	0.489	71.5	0.182	1221

^aThe structure properties (volume V , density ρ , and probe-occupiable void fraction η , i.e., the porosity) were determined from the structures after energy minimization at 0 K. The thermal conductivity k and volumetric heat capacity C_V are simulated at room temperature of 300 K.

According to the classical phonon-gas model, the thermal conductivity of a crystal can be written as:^{54,55}

$$k = \frac{1}{3} C_V v_g l_{eff}, \quad (6)$$

where C_V is the volumetric heat capacity, v_g is the group velocity of phonon, and l_{eff} is the mean free path of phonon. This model suggests that the thermal conductivity of a crystal is proportional to its volumetric heat capacity, phonon group velocity and phonon mean free path. Table 1 shows the structural parameters (lattice volume, density, and porosity) and the calculated thermal properties (thermal conductivity and volumetric heat capacity) of lp

and np phases of DUT crystals. It is found that the thermal conductivity of DUT crystals within the lp phase increases generally with growing volumetric heat capacity as shown in Figure S3. Because the volumetric heat capacity of DUT crystals is proportional to the density and is inversely proportional to the porosity as plotted in Figure S4, the decreased volumetric heat capacity from DUT-48 to DUT-151 is thus responsible for the evolution of thermal conductivity of isorecticular DUT crystals with different ligands as shown in Figure 2(b). Moreover, the thermal conductivity of isorecticular DUT crystals with different densities or porosities graphically shown in Figures 3(b) and S5 is found to decrease with decreasing density or with increasing pore size. The same density or porosity dependence of thermal conductivity is also observed in previous studies of the idealized MOFs.³⁶

3.2 Influence of phase transition on the thermal conductivity

Figure 3: (a) Free energy-versus-volume curves of DUT-49 obtained by $P - V$ EOS method, and the inset shows the atomic structures of DUT-49(lp) and DUT-49(np). (b) A comparison of the thermal conductivity between lp and np phases of isorecticular DUT crystals. (c) Thermal conductivity and volumetric heat capacity of lp and np phases of isorecticular DUT crystals as a function of the density.

The pressure-versus-volume equations of state ($P - V$ EOS) method was applied to obtain the np phase of DUT crystals. This method has been widely used in previous studies in investigating the mechanical instability and dynamic effects of SPCs.^{13,16,18,42,56–61} The theories and simulation details of the $P - V$ EOS method are provided in the Supporting Information. Taking DUT-49 as an example, Figure 3(a) shows the free energy evolution with shrinking volume. Two extreme points correspond to the lp and np phases of DUT-49, i.e., DUT-49(lp) and DUT-49(np), respectively. As shown in the atomic structures presented in Figure 3(a), the phase transition of DUT series is driven by the buckling of their ligands.¹⁸ The calculated thermal conductivity of the transformed np structures of various DUT materials is shown in Figure 3(b) together with the result of their parent lp counterparts. Meanwhile, the corresponding specific values of the obtained thermal conductivity are also listed in Table 1. It is found that expect DUT-48 whose np phase has a thermal conductivity ($0.164 \text{ Wm}^{-1}\text{K}^{-1}$) smaller than that of its lp phase ($0.180 \text{ Wm}^{-1}\text{K}^{-1}$), the thermal conductivity of transformed np phase of all other DUT materials is higher than that of their parent lp phase. Specially, as for DUT-50 and DUT-151, the thermal conductivity of their np phase after the phase transition can be, respectively, 48% and 156% larger than the value of their parent lp phase. Moreover, among all DUT crystals considered here, the np structure of DUT-49, i.e., DUT-49(np) shows the highest thermal conductivity of $0.192 \text{ Wm}^{-1}\text{K}^{-1}$. In Figure 3(c), we graphically show the thermal conductivity (k) and the volumetric heat capacity (C_V) as a function the density (ρ) of both two phases of different isorecticular DUT crystals considered here. Form this figure, we find that C_V increases linearly with growing ρ in both lp and np phases of DUTs. However, as for lp and np phases their k exhibits different relations with ρ . It is found that k of lp phase increases generally with growing ρ , while k of np phase seems to be independent of ρ , which fluctuates around $0.16 \text{ Wm}^{-1}\text{K}^{-1}$. Among all DUT materials considered here, if we specifically compare among DUT-49(np), DUT-47(np), and DUT-48(np), we can find a counter-intuitive phenomenon, which corresponds to the decrease of k with growing ρ and C_V . This phenomenon is in contrast to the existing understanding that

the thermal conductivity of MOF materials increases as their density grows.²¹ Our results indicate that the thermal conductivity of isorecticular DUT crystals after phase transition is not solely determined by the volumetric heat capacity. The phonon properties such as the phonon group velocity and phonon mean free path would also have a crucial effect on the thermal transport in DUT crystals.

Figure 4: (a) Framework VDOS of lp and np phases of DUT-49. (b) Similarity index γ of the chains in lp and np phases of DUT-49. (c) Similarity index γ in atomic chains of lp and np phases of DUT-49

To investigate different thermal transport properties observed in lp and np structures of DUTs, we compare the VDOS distribution of the lp and np phases of DUT-49 in Figure 4(a). The results of other DUT crystals considered here are shown in Figure S6. As for all DUT crystals, more modes/peaks are observed in the VDOS distribution of their np phase. To further evaluate the change in VDOS overlap caused by the phase transition, we compare the similarity index of lp and np phases of DUT-49 in Figures 4(b-c). A similar comparison of other DUT crystals is shown in Figure S7. In general, the similarity index of atomic bonds in lp phase of all DUT crystals is larger than that of atomic bonds in the np phase, which corresponds to a decrease of the VDOS overlap after phase transition. This result

indicates that compared to their lp counterparts, the np structures possess a higher thermal resistance and more significant phonon scattering between atomic bonds, which would thus weaken the thermal transport properties. Very recently, Lamiare et al.³⁹ demonstrated that the VDOS overlap between atomic bonds in the np phase of MIL-53(Al) is much larger than that of its lp counterpart, which is in contrary to the case of isorecticular DUT crystals discussed here. This difference observed between these two MOF materials might originate from their different mechanisms of phase transition. The phase transition of DUT crystals is accompanied by the buckling of their ligand backbones^{13,14,28} as shown in Figure 3(b), while the ligand backbones of MIL-53(Al) keep straight at both lp and np phases. Since more phonon scattering exists in the buckled ligand compared with the pristine straight ligand,⁶² DUT crystals after phase transition are thus expected to possess a smaller thermal conductivity.

Figure 5: Mechanical properties including (a) Young's modulus, (b) shear modulus, and (c) bulk modulus of lp and np phases of isorecticular DUT crystals. The inset shows the deformation mode corresponding to each modulus. (d) Spatial dependence of Young's modulus of lp and np phases of DUT-49.

It is known that materials with low elastic modulus have flattened phonon dispersion curves, which correspond to low phonon group velocities in these materials. According to Equation 6, the thermal conductivity is directly proportional to the phonon group velocity. Thus, the materials with lower elastic modulus are expected to possess a lower thermal conductivity.^{63–65} Here, we adopt the stress-fluctuation method⁶⁶ to calculate the elastic constants and mechanical properties of lp and np phases of five isorecticular DUT crystals. The theory of the stress-fluctuation method and simulation detail of the mechanical properties are given in the Supporting Information. Due to the very high symmetry of their lattice structures, the cubic isorecticular DUT crystals only have three independent elastic constants, which are C_{11} , C_{12} , and C_{44} as listed in Table S1. The corresponding mechanical properties including Young's modulus, shear modulus, and bulk modulus of lp and np phases of

different isorecticular DUT crystals considered here are compared in Figure 5. As for DUT materials with lp phase, their Young’s modulus, shear modulus, and bulk modulus are found to decrease from 21.0 GPa, 8.7 GPa, and 12.0 GPa of DUT-48 with a porosity of 78.8% to 4.7 GPa, 1.8 GPa, and 4.0 GPa of DUT-151 with a porosity of 90.1%. As shown in Figures 5(a-c), the elastic moduli of np phase of all DUT crystals are generally found to be smaller than those of its lp counterpart. The only exception is the bulk modulus of DUT-151, whose np phase possess a value slightly larger than that of its lp phase. The weaker mechanical properties generally observed in the np phase of DUTs can be attributed to the predistorted structure of the buckled ligand backbone of DUT materials, which exhibits the higher compressibility when compared to the straight ligand backbone of the parent lp phase.^{28,67} We also plot the spatial dependence of Young’s modulus of DUT-49 in Figure 5(d). The corresponding results of other DUT materials are shown in Figure S8. From Figures 5(d) and S8 we can see that the softening in Young’s modulus induced by the phase transition is independent of crystal direction. From the above results we can see that the reduced elastic moduli of DUTs from lp phase to np phase will reduce the phonon velocity, which will result in a lower thermal conductivity of isorecticular DUT crystals after the phase transition.

Figure 6: (top) Schematics illustrating the competitive mechanism between enhanced phonon scattering and increased volumetric heat capacity after phase transition of isoreticular DUT materials. (bottom) Evaluation parameter α of five DUT materials as a function of their porosity.

From the above discussion, we can see that the phase transition of DUT crystals from the parent lp phase to the transformed np phase can affect the thermal transport by changing the volumetric heat capacity and also the phonon properties including phonon scattering intensity and phonon group velocity. On one hand, the volume shrink induced by the phase transition will result in a great increase in the volumetric heat capacity, which can enhance the thermal conductivity of DUTs. On the other hand, the ligand buckling accompanied with the phase transition can aggravate the phonon scattering and cause a reduction in phonon group velocity, which will weaken the thermal transport property of DUTs. The mechanism of the competition between above two effects on the thermal conductivity of DUTs after phase transition is schematically shown in Figure 6. Since the thermal conductivity of DUT-48 is reduced after phase transition (see Figure 3), the increased phonon plays the dominated role. However, in other DUTs including DUT-47, DUT-49, DUT-50, and DUT-151, the effect of

volumetric heat capacity becomes dominated, which results in a higher thermal conductivity observed in their transformed np phase. To clearly measure the influence of phase transition on the thermal conductivity of DUT materials considered here, we introduce a evaluation parameter α defined as $\alpha = (k_{np} - k_{lp})/k_{lp}$, where k_{lp} and k_{np} are values of the thermal conductivity of lp and np phases of DUT materials, respectively. Thus, $\alpha > 0$ indicates that phase transition would enhance the thermal transport properties, while $\alpha < 0$ indicates the opposite effect. We graphically show α of DUT materials with different porosities in Figure 6. It is found that the value of α increases with growing porosity. Moreover, the largest enhancement in the thermal conductivity is found in DUT-151 after the phase transition, which can be attributed to the fact that its ultra-porous DUT crystal can result in great increase of its volumetric heat capacity after phase transition.

4. Conclusion

Taking the isorecticular DUT material e.g., DUT-48, DUT-47, DUT-49, DUT-50, and DUT-151 as an example, in this paper we comprehensively investigate the effect of phase transition on the thermal transport in SPCs by using MD simulations together with the Green-Kubo method. It is shown that the pristine DUT materials have a very low thermal conductivity smaller than $0.2 \text{ Wm}^{-1}\text{K}^{-1}$. The ultralow thermal conductivity observed in DUTs can be attributed to the thermal transport resistance in the O-C chain observed in the present VDOS analysis as well as the interface between metal node and organic linker reported previously. Regarding the influence of phase transition, the thermal conductivity of transformed np phase of DUT-48 is slightly smaller than that of its parent lp phase. However, as for other DUT materials, i.e., DUT-47, DUT-49, DUT-50, and DUT-151, the np phase exhibits a higher thermal conductivity. Especially, the thermal conductivity of np phase of DUT-151 can be up to 155.8% larger than that of its lp phase. This complicated effect of phase transition on thermal conductivity of isorecticular DUT materials is explained by the

competitive mechanism between the enhanced phonon scattering and the increased volumetric heat capacity after phase transition. As for the DUT with a relatively small porosity such as DUT-48, the enhanced phonon scattering is dominated, leading to a lower thermal conductivity of its np phase. However, the increased volumetric heat capacity becomes the dominated effect in other DUT materials with a relatively large porosity, which results in the increase of thermal conductivity after phase transition. Overall, we find that although the density of some SPCs can be greatly increased after phase transition, their thermal conductivity can be significantly reduced in this process. This finding can greatly expand current knowledge about the thermal conductivity of MOFs that is previously found to grow usually with increasing density.

Acknowledgement

This study was supported by the National Key R&D Program of China (no.2018YFB1502602) and the National Natural Science Foundation of China (nos.11932005, 11772106).

Supporting Information Available

VDOS distribution for the framework atoms of DUT crystals; the similar index between atomic bonds in DUT crystals; the volumetric-dependent and porosity-dependent thermal conductivity of lp phase of DUT crystals; the volumetric heat capacity of DUT crystals with different densities and porosities; comparison of the framework VDOS, similarity index γ between atomic chains; spatial dependence of Young's modulus of lp and np phases of DUT crystals.

References

- (1) Horike, S.; Shimomura, S.; Kitagawa, S. Soft porous crystals. *Nature chemistry* **2009**, *1*, 695.
- (2) Schneemann, A.; Bon, V.; Schwedler, I.; Senkovska, I.; Kaskel, S.; Fischer, R. A. Flexible metal–organic frameworks. *Chemical Society Reviews* **2014**, *43*, 6062–6096.
- (3) Evans, J. D.; Bon, V.; Senkovska, I.; Lee, H.-C.; Kaskel, S. Four-dimensional metal–organic frameworks. *Nature Communications* **2020**, *11*, 1–11.
- (4) Coudert, F.-X. Responsive metal–organic frameworks and framework materials: under pressure, taking the heat, in the spotlight, with friends. *Chemistry of Materials* **2015**, *27*, 1905–1916.
- (5) Krause, S.; Hosono, N.; Kitagawa, S. Chemistry of Soft Porous Crystals–Structural Dynamics and Gas Adsorption Properties. *Angewandte Chemie* **2020**,
- (6) Ghoufi, A.; Benhamed, K.; Boukli-Hacene, L.; Maurin, G. Electrically induced breathing of the MIL-53 (Cr) metal–organic framework. *ACS central science* **2017**, *3*, 394–398.
- (7) Coudert, F.-X.; Evans, J. D. Nanoscale metamaterials: meta-MOFs and framework materials with anomalous behavior. *Coordination Chemistry Reviews* **2019**, *388*, 48–62.
- (8) Mason, J. A.; Oktawiec, J.; Taylor, M. K.; Hudson, M. R.; Rodriguez, J.; Bachman, J. E.; Gonzalez, M. I.; Cervellino, A.; Guagliardi, A.; Brown, C. M., et al. Methane storage in flexible metal–organic frameworks with intrinsic thermal management. *Nature* **2015**, *527*, 357–361.
- (9) Sato, H.; Kosaka, W.; Matsuda, R.; Hori, A.; Hijikata, Y.; Belosludov, R. V.; Sakaki, S.; Takata, M.; Kitagawa, S. Self-accelerating CO sorption in a soft nanoporous crystal. *Science* **2014**, *343*, 167–170.

- (10) Van Assche, T. R.; Baron, G. V.; Denayer, J. F. Molecular separations with breathing metal–organic frameworks: modelling packed bed adsorbers. *Dalton Transactions* **2016**, *45*, 4416–4430.
- (11) Krause, S.; Bon, V.; Senkovska, I.; Stoeck, U.; Wallacher, D.; Többsens, D. M.; Zander, S.; Pillai, R. S.; Maurin, G.; Coudert, F.-X., et al. A pressure-amplifying framework material with negative gas adsorption transitions. *Nature* **2016**, *532*, 348–352.
- (12) Yaghi, O. M.; O’Keeffe, M.; Ockwig, N. W.; Chae, H. K.; Eddaoudi, M.; Kim, J. Reticular synthesis and the design of new materials. *Nature* **2003**, *423*, 705–714.
- (13) Krause, S.; Evans, J. D.; Bon, V.; Senkovska, I.; Iacomi, P.; Kolbe, F.; Ehrling, S.; Troschke, E.; Getzschmann, J.; Többsens, D. M., et al. Towards general network architecture design criteria for negative gas adsorption transitions in ultraporous frameworks. *Nature communications* **2019**, *10*, 1–12.
- (14) Krause, S.; Evans, J. D.; Bon, V.; Senkovska, I.; Ehrling, S.; Iacomi, P.; Többsens, D. M.; Wallacher, D.; Weiss, M. S.; Zheng, B., et al. Engineering micromechanics of soft porous crystals for negative gas adsorption. *Chemical Science* **2020**, *11*, 9468–9479.
- (15) Evans, J. D.; Krause, S.; Kaskel, S.; Sweatman, M. B.; Sarkisov, L. Exploring the thermodynamic criteria for responsive adsorption processes. *Chemical science* **2019**, *10*, 5011–5017.
- (16) Vanduyfhuys, L.; Rogge, S.; Wieme, J.; Vandenbrande, S.; Maurin, G.; Waroquier, M.; Van Speybroeck, V. Thermodynamic insight into stimuli-responsive behaviour of soft porous crystals. *Nature communications* **2018**, *9*, 1–9.
- (17) Vanduyfhuys, L.; Van Speybroeck, V. Unraveling the thermodynamic conditions for negative gas adsorption in soft porous crystals. *Communications Physics* **2019**, *2*, 1–10.

- (18) Ying, P.; Zhang, J.; Zhong, Z. Pressure-induced phase transition of isorecticular MOFs: Mechanical instability due to ligand buckling. *Microporous and Mesoporous Materials* **2020**, 110765.
- (19) Erickson, K. J.; Léonard, F.; Stavila, V.; Foster, M. E.; Spataru, C. D.; Jones, R. E.; Foley, B. M.; Hopkins, P. E.; Allendorf, M. D.; Talin, A. A. Thin film thermoelectric metal–organic framework with high Seebeck coefficient and low thermal conductivity. *Advanced Materials* **2015**, *27*, 3453–3459.
- (20) Gunatilleke, W. D.; Wei, K.; Niu, Z.; Wojtas, L.; Nolas, G.; Ma, S. Thermal conductivity of a perovskite-type metal–organic framework crystal. *Dalton Transactions* **2017**, *46*, 13342–13344.
- (21) Wieme, J.; Vandenbrande, S.; Lamaire, A.; Kapil, V.; Vanduyfhuys, L.; Van Speybroeck, V. Thermal Engineering of Metal–Organic Frameworks for Adsorption Applications: A Molecular Simulation Perspective. *ACS applied materials & interfaces* **2019**, *11*, 38697–38707.
- (22) Maurin, G.; Serre, C.; Cooper, A.; Férey, G. The new age of MOFs and of their porous-related solids. *Chemical Society Reviews* **2017**, *46*, 3104–3107.
- (23) Wieser, S.; Kamencek, T.; Dürholt, J. P.; Schmid, R.; Bedoya-Martínez, N.; Zojer, E. Identifying the Bottleneck for Heat Transport in Metal–Organic Frameworks. *Advanced Theory and Simulations* **2020**, 2000211.
- (24) Han, L.; Budge, M.; Greaney, P. A. Relationship between thermal conductivity and framework architecture in MOF-5. *Computational materials science* **2014**, *94*, 292–297.
- (25) Huang, B.; McGaughey, A.; Kaviani, M. Thermal conductivity of metal-organic framework 5 (MOF-5): Part I. Molecular dynamics simulations. *International journal of heat and mass transfer* **2007**, *50*, 393–404.

- (26) Huang, B.; Ni, Z.; Millward, A.; McGaughey, A.; Uher, C.; Kaviani, M.; Yaghi, O. Thermal conductivity of a metal-organic framework (MOF-5): Part II. Measurement. *International Journal of Heat and Mass Transfer* **2007**, *50*, 405–411.
- (27) Zhang, X.; Jiang, J. Thermal conductivity of zeolitic imidazolate framework-8: A molecular simulation study. *The Journal of Physical Chemistry C* **2013**, *117*, 18441–18447.
- (28) Ying, P.; Zhang, J.; Zhang, X.; Zhong, Z. Impacts of Functional Group Substitution and Pressure on the Thermal Conductivity of ZIF-8. *The Journal of Physical Chemistry C* **2020**, *124*, 6274–6283.
- (29) Wei, W.; Huang, J.; Li, W.; Peng, H.; Li, S. Impacts of Ethanol and Water Adsorptions on Thermal Conductivity of ZIF-8. *The Journal of Physical Chemistry C* **2019**, *123*, 27369–27374.
- (30) Sørensen, S. S.; Østergaard, M. B.; Stepniewska, M.; Johra, H.; Yue, Y.; Smedskjaer, M. M. Metal–Organic Framework Glasses Possess Higher Thermal Conductivity than Their Crystalline Counterparts. *ACS Applied Materials & Interfaces* **2020**, *12*, 18893–18903.
- (31) Huang, J.; Fan, A.; Xia, X.; Li, S.; Zhang, X. In Situ Thermal Conductivity Measurement of Single-Crystal Zeolitic Imidazolate Framework-8 by Raman-Resistance Temperature Detectors Method. *ACS nano* **2020**, *14*, 14100–14107.
- (32) Cui, B.; Audu, C. O.; Liao, Y.; Nguyen, S. T.; Farha, O. K.; Hupp, J. T.; Grayson, M. Thermal conductivity of zif-8 thin-film under ambient gas pressure. *ACS applied materials & interfaces* **2017**, *9*, 28139–28143.
- (33) Islamov, M.; Babaei, H.; Wilmer, C. E. Influence of Missing Linker Defects on the Thermal Conductivity of Metal–Organic Framework HKUST-1. *ACS Applied Materials & Interfaces* **2020**,

- (34) Babaei, H.; DeCoster, M. E.; Jeong, M.; Hassan, Z. M.; Islamoglu, T.; Baumgart, H.; McGaughey, A. J.; Redel, E.; Farha, O. K.; Hopkins, P. E., et al. Observation of reduced thermal conductivity in a metal-organic framework due to the presence of adsorbates. *Nature communications* **2020**, *11*, 1–8.
- (35) Babaei, H.; Wilmer, C. E. Mechanisms of heat transfer in porous crystals containing adsorbed gases: Applications to metal-organic frameworks. *Physical review letters* **2016**, *116*, 025902.
- (36) Babaei, H.; McGaughey, A. J.; Wilmer, C. E. Effect of pore size and shape on the thermal conductivity of metal-organic frameworks. *Chemical science* **2017**, *8*, 583–589.
- (37) Sezginel, K. B.; Asinger, P. A.; Babaei, H.; Wilmer, C. E. Thermal transport in interpenetrated metal-organic frameworks. *Chemistry of Materials* **2018**, *30*, 2281–2286.
- (38) Sezginel, K. B.; Lee, S.; Babaei, H.; Wilmer, C. E. Effect of Flexibility on Thermal Transport in Breathing Porous Crystals. *The Journal of Physical Chemistry C* **2020**, *124*, 18604–18608.
- (39) Lemaire, A.; Wieme, J.; Hoffman, A. E.; Van Speybroeck, V. Atomistic insight in the flexibility and heat transport properties of the stimuli-responsive metal-organic framework MIL-53 (Al) for water-adsorption applications using molecular simulations. *Faraday Discussions* **2020**,
- (40) Rogge, S. M.; Bavykina, A.; Hajek, J.; Garcia, H.; Olivos-Suarez, A. I.; Sepúlveda-Escribano, A.; Vimont, A.; Clet, G.; Bazin, P.; Kapteijn, F., et al. Metal-organic and covalent organic frameworks as single-site catalysts. *Chemical Society Reviews* **2017**, *46*, 3134–3184.
- (41) Bureekaew, S.; Amirjalayer, S.; Tafipolsky, M.; Spickermann, C.; Roy, T. K.; Schmid, R. MOF-FF-A flexible first-principles derived force field for metal-organic frameworks. *physica status solidi (b)* **2013**, *250*, 1128–1141.

- (42) Evans, J. D.; Bocquet, L.; Coudert, F.-X. Origins of negative gas adsorption. *Chem* **2016**, *1*, 873–886.
- (43) Evans, J. D.; Dürholt, J. P.; Kaskel, S.; Schmid, R. Assessing negative thermal expansion in mesoporous metal–organic frameworks by molecular simulation. *Journal of Materials Chemistry A* **2019**, *7*, 24019–24026.
- (44) Willems, T. F.; Rycroft, C. H.; Kazi, M.; Meza, J. C.; Haranczyk, M. Algorithms and tools for high-throughput geometry-based analysis of crystalline porous materials. *Microporous and Mesoporous Materials* **2012**, *149*, 134–141.
- (45) Ongari, D.; Boyd, P. G.; Barthel, S.; Witman, M.; Haranczyk, M.; Smit, B. Accurate characterization of the pore volume in microporous crystalline materials. *Langmuir* **2017**, *33*, 14529–14538.
- (46) Dubbeldam, D.; Calero, S.; Vlugt, T. J. iRASPA: GPU-accelerated visualization software for materials scientists. *Molecular Simulation* **2018**, *44*, 653–676.
- (47) Green, M. S. Markoff random processes and the statistical mechanics of time-dependent phenomena. II. Irreversible processes in fluids. *The Journal of Chemical Physics* **1954**, *22*, 398–413.
- (48) Kubo, R. Statistical-mechanical theory of irreversible processes. I. General theory and simple applications to magnetic and conduction problems. *Journal of the Physical Society of Japan* **1957**, *12*, 570–586.
- (49) Haile, J.; Johnston, I.; Mallinckrodt, A. J.; McKay, S. Molecular dynamics simulation: elementary methods. *Computers in Physics* **1993**, *7*, 625–625.
- (50) Plimpton, S. Fast parallel algorithms for short-range molecular dynamics. *Journal of computational physics* **1995**, *117*, 1–19.

- (51) Gaillac, R.; Pullumbi, P.; Beyer, K. A.; Chapman, K. W.; Keen, D. A.; Bennett, T. D.; Coudert, F.-X. Liquid metal–organic frameworks. *Nature materials* **2017**, *16*, 1149–1154.
- (52) Yang, Y.; Shin, Y. K.; Li, S.; Bennett, T. D.; van Duin, A. C.; Mauro, J. C. Enabling computational design of ZIFs using ReaxFF. *The Journal of Physical Chemistry B* **2018**, *122*, 9616–9624.
- (53) Hoffman, A. E.; Vanduyfhuys, L.; Nevjestic, I.; Wieme, J.; Rogge, S. M.; Depauw, H.; Van Der Voort, P.; Vrielinck, H.; Van Speybroeck, V. Elucidating the vibrational fingerprint of the flexible metal–organic framework MIL-53 (Al) using a combined experimental/computational approach. *The Journal of Physical Chemistry C* **2018**, *122*, 2734–2746.
- (54) Kittel, C.; McEuen, P.; McEuen, P. *Introduction to solid state physics*; Wiley New York, 1996; Vol. 8.
- (55) Zhang, Z. M.; Zhang, Z. M.; Luby, *Nano/microscale heat transfer*; Springer, 2007.
- (56) Rogge, S. M.; Waroquier, M.; Van Speybroeck, V. Unraveling the thermodynamic criteria for size-dependent spontaneous phase separation in soft porous crystals. *Nature communications* **2019**, *10*, 1–10.
- (57) Wieme, J.; Lejaeghere, K.; Kresse, G.; Van Speybroeck, V. Tuning the balance between dispersion and entropy to design temperature-responsive flexible metal-organic frameworks. *Nature communications* **2018**, *9*, 1–10.
- (58) Demuynck, R.; Rogge, S. M.; Vanduyfhuys, L.; Wieme, J.; Waroquier, M.; Van Speybroeck, V. Efficient construction of free energy profiles of breathing metal–organic frameworks using advanced molecular dynamics simulations. *Journal of chemical theory and computation* **2017**, *13*, 5861–5873.

- (59) Keupp, J.; Schmid, R. Molecular dynamics simulations of the “breathing” phase transformation of MOF nanocrystallites. *Advanced Theory and Simulations* **2019**, *2*, 1900117.
- (60) Vervoorts, P.; Keupp, J.; Schneemann, A.; Hobday, C. L.; Daisenberger, D.; Fischer, R. A.; Schmid, R.; Kieslich, G. Configurational Entropy Driven High-Pressure Behaviour of a Flexible Metal–Organic Framework (MOF). *Angewandte Chemie* **2020**,
- (61) Rogge, S. M.; Waroquier, M.; Van Speybroeck, V. Reliably modeling the mechanical stability of rigid and flexible metal–organic frameworks. *Accounts of chemical research* **2018**, *51*, 138–148.
- (62) Zhang, J. Phase transformation in two-dimensional covalent organic frameworks under compressive loading. *Physical Chemistry Chemical Physics* **2018**, *20*, 29462–29471.
- (63) Kim, W. Strategies for engineering phonon transport in thermoelectrics. *Journal of Materials Chemistry C* **2015**, *3*, 10336–10348.
- (64) Lin, S.; Li, W.; Li, S.; Zhang, X.; Chen, Z.; Xu, Y.; Chen, Y.; Pei, Y. High thermoelectric performance of Ag₉GaSe₆ enabled by low cutoff frequency of acoustic phonons. *Joule* **2017**, *1*, 816–830.
- (65) Luu, S. D.; Supka, A. R.; Nguyen, V. H.; Vo, D.-V. N.; T. Hung, N.; Wojciechowski, K. T.; Fornari, M.; Vaqueiro, P. Origin of low thermal conductivity in In₄Se₃. *ACS Applied Energy Materials* **2020**,
- (66) Parrinello, M.; Rahman, A. Strain fluctuations and elastic constants. *The Journal of Chemical Physics* **1982**, *76*, 2662–2666.
- (67) Redfern, L. R.; Robison, L.; Wasson, M. C.; Goswami, S.; Lyu, J.; Islamoglu, T.; Chapman, K. W.; Farha, O. K. Porosity dependence of compression and lattice rigidity

in metal-organic framework series. *Journal of the American chemical society* **2019**, *141*, 4365–4371.

Graphical TOC Entry