Synthesis and styrene copolymerization of novel trisubstituted ethylenes:
8. Dichloro and difluoro ring-substituted octyl phenylcyanoacrylates

Christian Ibarra, Andy N. La, Victoria Orban, Taha Raziuddin, Amir Sedighzadeh, Amina Torlo, Ania Tyrawa, Peter A. Wild Crea, Jessica E. Youngs, Stephanie Block, David C. Dainko, Sara M. Rocus, William S. Schjerven, and Gregory B. Kharas

DePaul University, Chemistry and Biochemistry Department, 1110 West Belden Avenue, Chicago, IL 60614-3214

Abstract

Novel trisubstituted ethylenes, dichloro and difluoro ring-substituted octyl phenylcyanoacrylates, RPhCH=C(CN)CO₂CH₂(CH₂)₆CH₃ (where R is 2,3-dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 2,6-difluoro, 3,4-difluoro, 3,5-difluoro) were prepared and copolymerized with styrene. The ethylenes were synthesized by the piperidine catalyzed Knoevenagel condensation of ring-substituted benzaldehydes and octyl cyanoacetate, and characterized by CHN analysis, IR, ¹H and ¹³C NMR. All the ethylenes were copolymerized with styrene in solution with radical initiation (ABCN) at 70°C. The compositions of the copolymers were calculated from nitrogen analysis.

1. Introduction

Cyanoacrylates is family of vinyl monomers renowned for their high reactivity, instant adhesive properties, and wide-ranging applications [1–3]. Trisubstituted ethylenes (TSE), ring-functionalized (R^1) alkyl (R^2) phenylcyanoacrylates, R^1 PhCH = C(CN)CO₂R² (PCA) continue to attract attention as compounds with variety of applications [4-11]. Thus, methoxy ring-substituted methyl phenylcyanoacrylate, MPCA was used in synthesis of pyridotriazines and triazolopyridines [4]. Dimethylamino ring-substituted MPCA was examined among other cyanovinylheteroaromatics in relation to organic nonlinear optics [5]. There are a number of applications of ethyl phenylcyanoacrylate, EPCA and its ringsubstituted derivatives which include studies of catalysis [6] and potential antimicrobial and antioxidant agents [7]. 2,4-Dimethoxyphenyl EPCA was used in design, synthesis and study of anticancer activity of novel benzothiazole analogues [8], in synthesis of thiazacridine derivatives as anticancer agents against breast and hematopoietic neoplastic cells [9] and in DABCO-catalyzed Knoevenagel condensation using hydroxy ionic liquid as a promoter [10]. This EPCA was involved in catalysis study of N,N'-dialkylimidazolium dimethyl phosphates [11], in synthesis and study of antimicrobial activity of some cyanoacrylates [12], as well as in synthesis of antiproliferative active 2-aminobenzimidazole derivatives [13]. Methoxyphenyl octyl cyanoacrylate was synthesized and evaluated for UV-filter activity [14].

In regards to polymerization reactivity, previous studies showed that PCAs as all TSE monomers containing double bond substituents larger than fluorine have very low reactivity in radical homopolymerization due to polar and steric reasons [15]. Although steric

difficulties preclude homopolymerization of such monomers, their copolymerization with a monosubstituted alkenes makes it possible to overcome these steric problems. Thus, copolymerization of electrophylic TSE monomers having double bonds substituted with halo, cyano, and carbonyl groups and electron-rich monosubstituted ethylenes such as styrene, N-vinylcarbazole, and vinyl acetate [16-18] show a tendency toward the formation of alternating copolymers - thus suggesting a way of functionalization of commercial polymers via introduction of isolated monomer units in copolymers. Earlier we have reported synthesis and styrene copolymerization of a number of dichloro and difluoro ring-substituted methyl [19-21], ethyl [22], propyl [23-25], isopropyl [26, 27], butyl [28, 29], isobutyl [30, 31], and 2-methoxyethyl [32] PCAs.

Our objectives in exploration of novel octyl phenylcyanoacrylates (OPCA) were twofold:

(1) to utilize Knoevenagel condensation for synthesis of OPCA compounds with a variety of potentially reactive functional groups and (2) to explore feasibility of radical copolymerization with a commercial monomer styrene.

Thus, in continuation of our investigation of novel TSE compounds we have prepared octyl dichloro and difluoro ring-substituted cyanoacrylates,

RPhCH=C(CN)CO₂CH₂(CH₂)₆CH₃, where R is 2,3-dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 2,6-difluoro, 3,4-difluoro, 3,5-difluoro, and explored the feasibility of their copolymerization with styrene. To the best of our knowledge there have been no reports on either synthesis of these compounds, nor their copolymerization with styrene [33].

2. Experimental

2.1. Materials

2,3-Dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 2,6-difluoro, 3,4-difluoro, 3,5-difluorobenzaldehydes, octyl cyanoacetate (≥98.0%), piperidine (99%), styrene (≥99%), 1,1'-azobis(cyclohexanecarbonitrile) (98%), (ABCN), and toluene (98%) supplied from Sigma-Aldrich Co., were used as received.

2.2. Instrumentation

Infrared spectra of the OPCA compounds and polymers (NaCl plates) were determined with an ABB FTLA 2000 FT-IR spectrometer. The melting points of the OPCA compounds were measured with TA (Thermal Analysis, Inc.) Model Q10 differential scanning calorimeter (DSC). ¹H and ¹³C NMR spectra were obtained on 10-25% (w/v) OPCA solutions in CDCl₃ at ambient temperature using Avance 300 MHz spectrometer. CHN-elemental analyses of OPCA compounds and nitrogen analysis of the copolymers were performed by Midwest Microlab, LLC (IN).

3. Results and discussion

3.1. Synthesis and characterization of octyl phenylcyanoacrylates

All octyl phenylcyanoacrylates (OPCA) compounds were synthesized by Knoevenagel condensation [34] of appropriate benzaldehydes with octyl cyanoacetate, catalyzed by base, piperidine (Scheme 1).

Scheme 1. Synthesis of octyl phenylcyanoacrylates where R is 2,3-dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 2,6-difluoro, 3,4-difluoro, 3,5-difluoro.

The preparation procedure was essentially the same for all the monomers. In a typical synthesis, equimolar amounts of octyl cyanoacetate and an appropriate benzaldehyde were mixed in equimolar ratio in a 20 mL vial. A few drops of piperidine were added with stirring. The product of the reaction was isolated by filtration and purified by crystallization from 2-propanol. The condensation reaction proceeded smoothly, yielding products, which were purified by conventional techniques. The compounds were characterized by IR, ¹H and ¹³C NMR spectroscopies. No stereochemical analysis of the novel oxy ring-substituted OPCA was performed since no stereoisomers (*E* or/and *Z*) of known configuration were available.

3.1.1. Octyl 2,3-dichlorophenylcyanoacrylate

Yield 82%; mp 111.3°C; ¹H NMR δ8.7 (s, 1H, CH=), 8.1-7.2 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 2.3-1.8 (q, 2H, OCH₂C<u>H</u>₂), 1.6-1.5 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ163 (C=O), 154 (HC=), 134-128 (Ph), 116 (CN), 107 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29 (O(CH₂)₃(<u>C</u>H₂)₂), 28 (OCH₂<u>C</u>H₂), 26

(O(CH₂)₂CH₂), 23 (CH₂CH₃), 14 (CH₃); IR (cm⁻¹): 2928 (m, C-H), 2228 (m, CN), 1734 (s, C=O), 1612 (s, C=C), 1280 (s, C-O-CH₃), 758 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁Cl₂NO₂: C, 61.03; H, 5.97; N, 3.95; Found: C, 61.81; H, 6.17; N, 4.04.

3.1.2. *Octyl* 2,4-dichlorophenylcyanoacrylate.

Yield 81%; mp 38.5°C; ¹H NMR δ 8.6 (s, 1H, CH=), 8.3-7.4 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂CH₂), 1.6-1.5 (m, 6H, OCH₂CH₂(CH₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(CH₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ 162 (C=O), 150 (HC=), 140, 138, 131, 129 (Ph), 116, (CN), 107 (C=), 68 (OCH₂), 32 (O(CH₂)₅CH₂), 29 (O(CH₂)₃(CH₂)₂), 28 (OCH₂CH₂), 26 (O(CH₂)₂CH₂), 23 (CH₂CH₃), 14 (CH₃); IR (cm⁻¹): 2933 (m, C-H), 2228 (m, CN), 1724 (s, C=O), 1616 (C=C), 1257 (s, C-O-CH₃), 823 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁Cl₂NO₂: C, 61.03; H, 5.97; N, 3.95; Found: C, 58.88; H, 5.80; N, 4.59.

3.1.3. Octyl 2,5-dichlorophenylcyanoacrylate.

Yield 87%; mp 60.4°C; ¹H NMR δ8.6 (s, 1H, CH=), 8.2-7.2 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.9-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.5-1.3 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ162 (C=O), 150 (HC=), 137-129 (Ph), 116 (CN), 107 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29 (O(CH₂)₃(<u>C</u>H₂)₂), 28 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 13 (CH₃); IR (cm⁻¹): 2937 (m, C-H), 2224 (m, CN), 1733 (s, C=O), 1622 (C=C), 1272 (s, C-O-CH₃), 774 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁Cl₂NO₂: C, 61.03; H, 5.97; N, 3.95; Found: C, 60.85; H, 6.42; N, 4.46.

3.1.4. Octyl 2,6-dichlorophenylcyanoacrylate.

Yield 82%; ¹H NMR δ8.3 (s, 1H, CH=), 7.5-7.2 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.9-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.5-1.3 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ162 (C=O), 152 (HC=), 134-129 (Ph), 115 (CN), 101 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29 (O(CH₂)₃(<u>C</u>H₂)₂), 28 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 13 (CH₃); IR (cm⁻¹): 2929 (m, C-H), 2204 (m, CN), 1743 (s, C=O), 1629 (C=C), 1276 (s, C-O-CH₃), 783 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁Cl₂NO₂: C, 61.03; H, 5.97; N, 3.95; Found: C, 59.35; H, 6.13; N, 3.91.

3.1.5. Octyl 3,4-dichlorophenylcyanoacrylate.

Yield 72%; mp 102.8°C; ¹H NMR δ 8.2 (s, 1H, CH=), 8.1-7.6 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂CH₂), 1.5-1.4 (m, 6H, OCH₂CH₂(CH₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(CH₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ 162 (C=O), 152 (HC=), 138-129 (Ph), 116 (CN), 105 (C=), 67 (OCH₂), 32 (O(CH₂)₅CH₂), 29.3 (O(CH₂)₃(CH₂)₂), 28.5 (OCH₂CH₂), 26 (O(CH₂)₂CH₂), 23 (CH₂CH₃), 14 (CH₃); IR (cm⁻¹): 2952 (m, C-H), 2227 (m, CN), 1719 (s, C=O), 1612 (s, C=C), 1273 (s, C-O-CH₃), 868 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁Cl₂NO₂: C, 61.03; H, 5.97; N, 3.95; Found: C, 59.74; H, 6.01; N, 3.94.

3.1.6. *Octyl* **2,3-***difluorophenylcyanoacrylate*.

Yield 87%; mp 95.8°C; ¹H NMR δ8.5 (s, 1H, CH=), 8.2-7.1 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 2.1-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.5-1.4 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ162 (C=O), 153 (HC=), 152-120 (Ph), 117 (CN), 107 (C=), 68 (OCH₂), 33 (O(CH₂)₅CH₂), 29.3 (O(CH₂)₃(CH₂)₂), 28.5 (OCH₂CH₂), 26 (O(CH₂)₂CH₂), 23 (CH₂CH₃), 14 (CH₃); IR (cm⁻¹): 2927 (m, C-H), 2228 (m, CN),

1727 (s, C=O), 1611 (s, C=C), 1247 (s, C-O-CH₃), 803 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 65.70; H, 6.68; N, 4.39.

Yield 77%; mp 112.2°C; ¹H NMR δ 8.5 (s, 1H, CH=), 7.3-6.8 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.5-1.4 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ 163 (C=O), 153 (HC=), 150, 132-114 (Ph), 116 (CN), 104 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29.3 (O(CH₂)₃(<u>C</u>H₂)₂), 28.5 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 13 (CH₃); IR (cm⁻¹): 2927 (m, C-H), 2225 (m, CN), 1724 (s, C=O), 1607 (s, C=C), 1273 (s, C-O-CH₃), 852 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 66.72; H, 6.69; N, 4.43.

3.1.8. Octyl 2,5-difluorophenylcyanoacrylate.

3.1.7. Octyl 2,4-difluorophenylcyanoacrylate.

Yield 91%; ¹H NMR δ8.5 (s, 1H, CH=), 8.1-7.1 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.5-1.4 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ163 (C=O), 157 (HC=), 162, 145-117 (Ph), 116 (CN), 107 (C=), 67 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29.3 (O(CH₂)₃(<u>C</u>H₂)₂), 28.5 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 13 (CH₃); IR (cm⁻¹): 2931 (m, C-H), 2229 (m, CN), 1737 (s, C=O), 1614 (s, C=C), 1256 (s, C-O-CH₃), 823 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 66.61; H, 6.81; N, 4.68.

3.1.9. Octyl 2,6-difluorophenylcyanoacrylate.

Yield 72%; ¹H NMR δ8.3 (s, 1H, CH=), 7.7-6.9 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂CH₂), 1.5-1.4 (m, 6H, OCH₂CH₂(CH₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(CH₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ163 (C=O), 159 (HC=), 161, 133-111 (Ph), 116 (CN), 103 (C=), 67 (OCH₂), 32 (O(CH₂)₅ CH₂), 29.3 (O(CH₂)₃(CH₂)₂), 28.5 (OCH₂CH₂), 26 (O(CH₂)₂CH₂), 23 (CH₂CH₃), 13 (CH₃); IR (cm⁻¹): 2930 (m, C-H), 2224 (m, CN), 1733 (s, C=O), 1627 (s, C=C), 1272 (s, C-O-CH₃), 806 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 69.00; H, 7.07; N, 4.70.

3.1.10. Octyl 3,4-difluorophenylcyanoacrylate.

Yield 87%; mp 92.7°C; ¹H NMR δ8.2 (s, 1H, CH=), 8.0-7.1 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.7-1.8 (q, 2H, OCH₂C<u>H</u>₂), 1.6-1.5 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ163 (C=O), 152 (HC=), 154, 130-118 (Ph), 116 (CN), 103 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29 (O(CH₂)₃(<u>C</u>H₂)₂), 28 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 13 (CH₃); IR (cm⁻¹): 2933 (m, C-H), 2228 (m, CN), 1717 (s, C=O), 1598 (s, C=C), 1283 (s, C-O-CH₃), 827 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 64.15; H, 6.58; N, 4.56.

3.1.11. Octyl 3,5-difluorophenylcyanoacrylate.

Yield 82%; mp 89.5°C; ¹H NMR δ 8.2 (s, 1H, CH=), 7.7-6.9 (m, 3H, Ph), 4.3 (t, 2H, CO₂CH₂), 1.8-1.7 (q, 2H, OCH₂C<u>H</u>₂), 1.6-1.5 (m, 6H, OCH₂CH₂(C<u>H</u>₂)₃), 1.4-1.2 (m, 4H, O(CH₂)₅(C<u>H</u>₂)₂), 0.9 (t, 3H, CH₃); ¹³C NMR δ 163 (C=O), 152 (HC=), 162, 133-108

(Ph), 115 (CN), 107 (C=), 68 (OCH₂), 32 (O(CH₂)₅ <u>C</u>H₂), 29 (O(CH₂)₃(<u>C</u>H₂)₂), 28 (OCH₂<u>C</u>H₂), 26 (O(CH₂)₂<u>C</u>H₂), 23 (<u>C</u>H₂CH₃), 14 (CH₃); IR (cm⁻¹): 2925 (m, C-H), 2228 (m, CN), 1737 (s, C=O), 1620 (s, C=C), 1271 (s, C-O-CH₃), 767 (s, C-H out of plane). Anal. Calcd. for C₁₈H₂₁F₂NO₂: C, 67.27; H, 6.59; N, 4.36; Found: C, 68.50; H, 7.28; N, 4.68.

3.2. Homopolymerization

An attempted homopolymerization of the OPCA compounds in the presence of ABCN did not produce any polymer as indicated by the lack of a precipitate in methanol. The inability of the monomers to polymerize is associated with steric difficulties encountered in homopolymerization of 1,1- and 1,2-disubstituted ethylenes [15]. Homopolymerization of ST under conditions identical to those in copolymerization experiments yielded 18.3% of polystyrene, when polymerized for 30 min.

3.3. Synthesis and characterization of styrene – OPCA copolymers

Copolymers of the ST and the OPCA compounds, P(ST-co-OPCA) were prepared in 25-mL glass screw cap vials at ST/OPCA = 3 (mol) the monomer feed using 0.12 mol/L of ABCN at an overall monomer concentration 2.44 mol/L in 10 mL of toluene. The copolymerization was conducted at 70°C. After a predetermined time, the mixture was cooled to room temperature, and precipitated dropwise in methanol. The composition of the copolymers was determined based on the nitrogen content (cyano group in OPCA). The novel synthesized OPCA compounds copolymerized readily with ST under free-radical conditions (Scheme 2) forming white flaky precipitates when their solutions were

poured into methanol. The conversion of the copolymers was kept between 10 and 20% to minimize compositional drift (Table 1).

Scheme 2. Copolymerization of ST and the octyl phenylcyanoacrylates, where R is 2,3-dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 3,5-difluoro.

Table 1. Copolymerization of styrene and octyl phenylcyanoacrylates.

R	Yield ^a (wt%)	N (wt%)	ST in copol. (mol%)	OPCA in copol. (mol%)
2,3-Dichloro	13.1	2.44	67.9	32.1
2,4-Dichloro	18.2	2.45	67.6	32.4
2,5-Dichloro	10.1	2.17	73.7	26.3
2,6-Dichloro	11.2	1.87	79.1	20.9
3,4-Dichloro	12.5	2.21	72.9	27.1
2,3-Difluoro	11.8	2.94	59.9	40.1
2,4-Difluoro	13.8	2.36	72.4	27.6
2,5-Difluoro	15.8	2.45	70.7	29.3
2,6-Difluoro	12.2	1.86	80.6	19.4
3,4-Difluoro	16.1	1.93	79.5	20.5
3,5-Difluoro	11.8	2.58	68.1	31.9

Nitrogen elemental analysis showed that between 19.4 and 40.1 mol% of OPCA is present in the copolymers prepared at ST/ OPCA = 3 (mol), which is indicative of relatively high reactivity of the OPCA monomers towards ST radical which is typical of ring-substituted OPCA [18-26]. Since OPCA monomers do not homopolymerize, the most likely structure of the copolymers would be isolated OPCA monomer units alternating with short ST sequences (Scheme 2).

The copolymers prepared in the present work are all soluble in ethyl acetate, THF, DMF and CHCl₃ and insoluble in methanol, ethyl ether, and petroleum ether.

4 Conclusions

Novel trisubstituted ethylenes, dichloro and difluoro octyl phenylcyanoacrylates, RPhCH=C(CN)CO₂CH₂(CH₂)₆CH₃ (where R is 2,3-dichloro, 2,4-dichloro, 2,5-dichloro, 2,6-dichloro, 3,4-dichloro, 2,3-difluoro, 2,4-difluoro, 2,5-difluoro, 3,4-difluoro, 3,5-difluoro) were prepared and copolymerized with styrene.

Acknowledgments

The authors are grateful to acknowledge that the project was partly supported by Chicago Society of Coating Technology (CSCT).

References

[1] Klemarczyk, P.; Guthrie, J. Advances in anaerobic and cyanoacrylate adhesives. In Advances in Structural Adhesive Bonding, 1st ed.; Dillard, D., Ed.; Woodhead Publishing Limited: Cambridge, UK, 2010; pp. 96–131, ISBN 978-1-84569-435-7.

- [2] Shantha, K.L.; Thennarasu, S.; Krishnamurti, N. Developments and applications of cyanoacrylate adhesives. J. Adhes. Sci. Technol. 1989, 3, 237–260.
- [3] J.M. Korde and B. Kandasubramanian, Biocompatible alkyl cyanoacrylates and their derivatives as bio-adhesives, Biomaterials Science, 10.1039/C8BM00312B, 6, 7, (1691-1711), (2018).
- [4] Zaki MEA, Fathalla OA, Swelam SA, Aly HF (2004) Synthesis of pyrido[2,1-c][1,2,4]triazine, 1,2,4-triazolo[4,3-a]pyridine and 2-(pyrazolyl)nicotinonitrile and their effect on Biomphalaria alexandrina snail enzymes. Acta Poloniae Pharmaceutica 61: 55-64.
- [5] Matsuoka M, Takao M, Kitao T, Fujiwara T, Nakatsu K (1990)
 Cyanovinylheteroaromatics for Organic Nonlinear Optics. Molecular Crystals and
 Liquid Crystals, 182A: 71-79.
- [6] Burate PA, Javle BR, Desale PH, Kinage AK (2019) Amino acid amide based ionic liquid as an efficient organo-catalyst for solvent-free Knoevenagel condensation at room temperature. Catalysis Letters 149(9): 2368-2375.
- [7] Medyouni R, Hamdi N, Ben Said R, Al-Ayed AS, Zagrouba F (2013) Clean procedure and DFT study for the synthesis of 2-amino-3-ethoxycarbonyl-4-(aryl)-4H-pyrano-[3,2-c]-chromene-5-ones derivatives: A novel class of potential antimicrobial and antioxidant agents. Journal of Chemistry 2013: 1-4.

- [8] Hassan AY, Sarg MT, Hussein EM (2019) Design, synthesis and anticancer activity of novel benzothiazole analogues. Journal of Heterocyclic Chemistry 56(4): 1437-1457.
- [9] Moacyr JB, De Melo R, Wanessa LB, De Sena, RO, De Moura, Iris TT et al. (2017).
 Synthesis and anticancer evaluation of thiazacridine derivatives reveals new
 selective molecules to hematopoietic neoplastic cells. Combinatorial Chemistry &
 High Throughput Screening 20(8): 713.
- [10] Meng D, Qiao Y, Wang X, Wen W, Zhao S (2018) DABCO-catalyzed Knoevenagel condensation of aldehydes with ethyl cyanoacetate using hydroxy ionic liquid as a promoter. RSC Advances 8(53): 30180-30185.
- [11] Brica S, Freimane L, Kulikovska L, Zicmanis A (2017) N,N'-dialkylimidazolium dimethyl phosphates promising media and catalysts at the same time for condensation reactions. Chemical Science International Journal 19(4): 1-9.
- [12] Bhuiyan M, Mosharef H, Rahman KM, Alam MA, Mahmud M (2013) Microwave assisted Knoevenagel condensation: synthesis and antimicrobial activities of some α-cyanoacrylates. Pakistan Journal of Scientific and Industrial Research, Series A: Physical Sciences 56(3): 131-137.
- [13] Nowicka A, Liszkiewicz H, Nawrocka WP, Wietrzyk J, Kempinska K, Drys A (2014)

 Synthesis and antiproliferative activity in vitro of new 2-aminobenzimidazole

 derivatives. Reaction of 2-arylideneaminobenzimidazole with selected nitriles

- containing active methylene group. Central European Journal of Chemistry 12(10): 1047-1055.
- [14] Synthesis and evaluation of octocrylene-inspired compounds for UV-filter activity. Polonini, Hudson C.; Lopes, Rosangela S.; Beatriz, Adilson; Gomes, Roberto S.; Silva, Adriano O.; de Lima, Ricardo V.; Nunes, Glaucia A.; Brandao, Marcos Antonio F.; Raposo, Nadia R. B.; de Lima, Denis P. Quimica Nova (2014), 37(6), 1004-1009.
- [15] Odian, G. *Principles of Polymerization*, 4th Ed., Wiley-Interscience: New York, 2004.
- [16] Hall, H. K., Jr.; Padias, A. B. J. Polym. Sci.Part A: Polym. Chem. 2004, 42, 2845-2858.
- [17] Hall, H. K. Jr.; Ykman, P. Macromolecules. 1977, 10, 464.
- [18] Kharas, G. B. Trisubstituted Ethylene Copolymers. In Polymeric Materials Encyclopedia, Salamone, J.C., (Ed.) CRC Press: Boca Raton, FL, 11, 8405, 1996.
- [19] Novel Copolymers of Trisubstituted Ethylenes and Styrene 5. Ring-disubstituted Methyl 2-Cyano-3-phenyl-2-propenoates. K.Kim, M. Morales, M.J. Scully, C.D. Seitz, A.-M. Sikora, A.M. Spaulding, R.Sudman, A.C. Sullivan, G.B. Kharas, K.Watson. Designed Monomers and Polymers, 2, 333-341 (1999).
- [20] Novel Copolymers of Trisubstituted Ethylenes with Styrene 7. Halogen ringdisubstituted methyl 2-cyano-3-phenyl-2-propenoates. G.B. Kharas, K. Kim, K.C.

- Beinlich, S.B. Benington, S.K. Brennan, M. Morales, N.E. Ruano, D.Y. Won, E. Adibu, and K. Watson. Polym. Bull., 45, 351-357 (2000).
- [21] Novel Copolymers of Styrene. 16. Halogen Ring-Disubstituted Methyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, S.E. Chavez, H. Browning, J. Sepe, M.E. Romanelli, M. Susnis, G. Choquegonzales, K. Fuentes, R. Treneva, and C. Murphy. J. Macromol. Sci. A51(10) 751-755 (2014).
- [22] Novel Copolymers of Styrene. 7. Dihalogen Ring-substituted Ethyl 2-Cyano-3-phenyl-2-propenoates and Styrene. G.B. Kharas, A.A. Delgado, K. Aco, L.M. Cardenas, M.L. Lopez, A.D. Mazerat, P.D. Merageas, D.M. Perone, M.D. Pickering, C.S. Samuelson, C.L. Shelly. J. Macromol. Sci. A50 (4) 365-369 (2013).
- [23] Novel Copolymers of Styrene. 9. Chloro and Fluoro Ring-Disubstituted Propyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, W.S. Schjerven, F.A.S. Aldakheel, E.J. Crespo, Z.M. Gaskell, K.J.M. Jordan, J.D. Knight, A.R. Moses, and A.H.A. Niyazi. J. Macromol. Sci. A54(2) 67-70 (2017).
- [24] Novel Copolymers of Styrene. 10. Bromo and Chloro Ring-Disubstituted Propyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, J. Bates, A.T. Boyd, J.N. Burke, J.L. Crosby, S.B. Sundquist, C.C. Zoleta, A.K. Zurek, and P.L. Bromby II. J. Macromol. Sci. A54(6) 372-375 (2017).
- [25] Synthesis and Radical Copolymerization of Novel Phenyl-Disubstituted
 Cyanoacrylates. C.R. Savittieri, S.M. Tinsley, A.J. Diehn, F. Hai, K.E. Humanski, E.J.
 Kempke, B.Y. Killam, J. Kozeny, E.W. Makhoul, M.C. Obert, A.C. Parisi, V.C.
 Parrilli, and G.B. Kharas. Acad. J Polym Sci. 2019; 2(5): 555597.

DOI:10.19080/AJOP.2019.02.555597

- [26] Synthesis and styrene copolymerization of novel ring-disubstituted isopropyl cyanoacrylates. P.M. Whelpley, S. Bajramovic, D.M. Bracamontes, G.A. Buechner, A.D. Eremin, E.J. Kowalczyk, D.D. Lender, R. McCann, W.S. Schjerven, G.B. Kharas. ChemRxiv (24.09.2019).
 https://doi.org/10.26434/chemrxiv.9891161.v1
- [27] Synthesis and Styrene Copolymerization of Novel Dihalogen Ring-Substituted
 Isopropyl Cyanophenylacrylates. S. Flieger, P.M. McCaw, S. Mouradkhanian, B.
 Pedroza, M.M. Peffley, R.L. Pride, P.R. Ramirez, M.S. Rogers, B. Romanov, M.
 Saleh, C. Soler, L.D. Warnick, Sara M. Rocus, W.S. Schjerven, and G.B. Kharas.
 ChemRxiv (19.12.2019). https://doi.org/10.26434/chemrxiv.11336852.v1
- [28] Novel Copolymers of Styrene. 10. Halogen Ring-substituted Butyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, H. Feng, S.G. Robinson, A. Eduardo, K.M.A. Carlson, V. Djordjevic, E. Dominguez, K.M. English, R.J. Hudson, and D.B. Kennedy. J. Macromol. Sci. A53(5) 253-257 (2016).
- [29] Novel Copolymers of Styrene. 11. Fluoro Ring-substituted Butyl 2-Cyano-3-Phenyl-2-Propenoates. G.B. Kharas, W.S. Schjerven, L.M. Maurer, G.C. Mcgee, M.E. Mcgovern, L.E. Palaciaos, H.M. Pollard-Durodola, R.E. Riccio, and J. Weingard. J. Macromol. Sci. A53(5) 258-261 (2016).
- [30] Synthesis and styrene copolymerization of novel dibromo and dichloro ringdisubstituted isobutyl phenylcyanoacrylates. Daniah H. Ibrahim, Chris J. Lee, Daniel N. Madock, Marcin Marciniak, Miguel A. Montero, Juan Orozco, Viany Ortiz, Mica

- C. Robles, Sara M. Rocus, William S. Schjerven and Gregory B. Kharas. ChemRxiv (25.09.2020) https://doi.org/10.26434/chemrxiv.11401347.v8
- [31] Synthesis and styrene copolymerization of novel fluoro and chloro ring-disubstituted isobutyl phenylcyanoacrylates. Christopher D. Ahlers, Aisha A. Ahmed, Umamah Alam, Alima A. Sajwani, Megan V. Salloum, Makayla A. Schneider, Heysel M. Serra, Richard C. Tanawath, Gabriella L. Triolo, Marisol Velazquez, Sara M. Rocus, William S. Schjerven, Gregory B. Kharas. ChemRxiv (06.10.2020)
 https://doi.org/10.26434/chemrxiv.11401347.v9
- [32] Synthesis and styrene copolymerization of novel trisubstituted ethylenes: 9. Ring-disubstituted 2-methoxyethyl 2-cyano-3-phenyl-2-propenoates. Ehab Abdelhamid, Hussein Abourahma, Julia Bellino, Joshua S.M. Bowser, Lourdes De Anda, Richard E. DeMaria, Erika Galeczka, Madeline Martin, Abdulrafey Nasir, Alexis Pawlak, Ashley Pezza, Rachel Quade, Anna Schell, Valerie Tafoya, Bhavi D. Vashi, Sabah I. Vikaruddin, Sophia L. Zygowski, Sara M. Rocus, William S. Schjerven, and Gregory B. Kharas. ChemRxiv. Preprint. (10.02.2021). https://doi.org/10.26434/chemrxiv.13262660.v9
- [33] SciFinder; Chemical Abstracts Service: Columbus, OH; https://scifinder.cas.org (accessed March 16, 2021).
- [34] Smith, M. B.; March, J. *Addition to Carbon-Hetero Multiple Bonds*, In March's Advanced Organic Chemistry, J. Wiley & Sons: New York, Ch.16, 1225, **2001**.