

Cite this: DOI: 00.0000/xxxxxxxxxx

# Polymer degradation through chemical change: A quantum-based test of inferred reactions in irradiated polydimethylsiloxane

Matthew P. Kroonblawd,<sup>\*a</sup> Nir Goldman,<sup>a</sup> Amitesh Maiti,<sup>a</sup> and James P. Lewicki<sup>a</sup>

Received Date

Accepted Date

DOI: 00.0000/xxxxxxxxxx

Chemical reaction schemes are key conceptual tools for interpreting the results of experiments and simulations, but often carry implicit assumptions that remain largely unverified for complicated systems. Established schemes for chemical damage through crosslinking in irradiated silicone polymers comprised of polydimethylsiloxane (PDMS) date to the 1950's and correlate small-molecule off-gassing with specific crosslink features. In this regard, we use a somewhat reductionist model to develop a general conditional probability and correlation analysis approach that tests these types of causal connections between proposed experimental observables to reexamine this chemistry through quantum-based molecular dynamics (QMD) simulations. Analysis of the QMD simulations suggests that the established reaction schemes are qualitatively reasonable, but lack strong causal connections under a broad set of conditions that would enable making direct quantitative connections between off-gassing and crosslinking. Further assessment of the QMD data uncovers a strong (but nonideal) quantitative connection between exceptionally hard-to-measure chain scission events and the formation of silanol (Si-OH) groups. Our analysis indicates that conventional notions of radiation damage to PDMS should be further qualified and not necessarily used ad hoc. In addition, our efforts enable independent quantum-based tests that can inform confidence in assumed connections between experimental observables without the burden of fully elucidating entire reaction networks.

## 1 Introduction


Chemical degradation of polymer materials is thought to arise from atomic-scale chemical reactions that alter networks through a range of processes including formation of crosslinks, chain scission, rearrangement, and abstraction/alteration of side groups. These reactions can adversely impact macroscale properties leading to irreversible changes in mechanical moduli, permanent set, embrittlement, or breaking under load that ultimately render components unfit for purpose.<sup>1,2</sup> Polydimethylsiloxane (PDMS) is the primary constituent of silicones, which are ubiquitous in commercial, industrial, and medical contexts as oils, elastomers, and foams.<sup>3</sup> The wide adoption of PDMS-based materials owes to their highly tunable mechanical response with favorable long-time characteristics, chemical inertness, thermal stability, and shape-filling factor. Despite these characteristics, PDMS is not impervious to chemical damage and it can interact with other materials. Common vectors for degradation arise from the ready uptake of environmental water<sup>4-7</sup> or absorption of radiation.<sup>7-12</sup> Understanding the degradation responses of PDMS has enormous practical applications, ranging from assessing environmental im-

pacts<sup>13-15</sup> to establishing models for the aging and lifetime prediction of silicone components.<sup>4-12,16,17</sup>

Ionizing radiation is a common cause for polymer degradation that can arise during component sterilization,<sup>1,18,19</sup> as a consequence of planned operation conditions, and as a driver in accelerated aging studies.<sup>7-12</sup> In 1955, Charlesby proposed<sup>20</sup> a set of reaction schemes for crosslinking in irradiated PDMS that were quickly refined by others<sup>21,22</sup> and were based on IR vibrational spectroscopy, titration, mass spectra of off-gassing species, and chromatography (see Figure 1). These reactions respectively connect the evolution of hydrogen (H<sub>2</sub>), methane (CH<sub>4</sub>), and ethane (C<sub>2</sub>H<sub>6</sub>) with the formation of silethylene (Si-C-C-Si), silmethylene (Si-C-Si), and silicon-silicon (Si-Si) crosslinks. Here, Si-C-C-Si links are thought to form from the joining of two under-coordinated methyl side groups (Si-CH<sub>2</sub>). Producing these sites emits two H atoms (Si-CH<sub>3</sub> → Si-CH<sub>2</sub> + H) that combine stoichiometrically to make H<sub>2</sub>. Similarly, producing Si-C-Si links emits an H atom (Si-CH<sub>3</sub> → Si-CH<sub>2</sub> + H) and a CH<sub>3</sub> group (Si-CH<sub>3</sub> → Si + CH<sub>3</sub>) that combine stoichiometrically to make CH<sub>4</sub>. Direct Si-Si linking can arise from the loss of two CH<sub>3</sub> side groups (Si-CH<sub>3</sub> → Si + CH<sub>3</sub>) that combine stoichiometrically to make C<sub>2</sub>H<sub>6</sub>.

The reaction schemes of Charlesby have formed the basis for interpreting a wide range of experiments and modeling results

<sup>a</sup> Physical and Life Sciences Directorate, Lawrence Livermore National Laboratory, Livermore, CA 94550, United States; E-mail: kroonblawd1@llnl.gov



**Fig. 1** Standard reaction schemes for formation of Si-Si, methyl, and ethyl cross links in irradiated PDMS.

in the ensuing decades and are generally uncontested. A recent comprehensive review by Palsule et al.<sup>2</sup> highlights these reactions among other chemical routes to different crosslinking and back-biting motifs. The reaction schemes in Figure 1 indeed form a chemically reasonable hypothesis for interpreting experiments. At the same time, it is well understood that imprecision in the available experimental diagnostics can lead to large uncertainties in the quantification of crosslinking and other network alterations. Consequently, while this simple reaction scheme is pragmatic, its unqualified use neglects the possibility for systematic errors in the assumption that this mechanism comprises the main routes to evolution of observed gases and crosslinks.

Vibrational spectra offer a sensitive test for the presence of crosslinking groups, but it is difficult to quantify crosslink populations with high precision. Interpreting IR or Raman intensities invokes considerations of absorptivity and optical path lengths along with concentration (the quantity of interest). Complicated spectra with overlapping peaks can further exacerbate these difficulties. Modern NMR methods also suffer from some of these drawbacks. Mass spectra peak intensities are typically reconciled to a standard, giving only reliable relative measurements. Thus, making quantitative comparisons between mass, vibrational, and NMR spectra to count crosslinking events is fraught with unknowns.

In addition, unlike polymer crosslinking, it is comparatively difficult to directly detect and quantify chain scission events in experiments. Radiation damage leads to a net formation of crosslinks in PDMS, measured as a decrease in average chain length, onset of gelation, or enhancement of mechanical modulus. However, scission reactions not directly connected to the proposed crosslinking schemes can also take place. Scission

events also open alternative channels for network alterations<sup>23</sup> and can combine with crosslinking to result in complex dynamic changes in molecular weight distributions.<sup>8,9</sup> Most experimental routes to estimate crosslinking and scission rely on fitting bulk-integrated data to rigid model forms,<sup>8,9,24–26</sup> such as Tobolsky's two-network model,<sup>27</sup> and thus do not provide a direct route to quantify populations of specific crosslink types nor their possible correlation with scission reactions. Some of the most advanced experiments that quantify scissions do so via isotopic tagging of silanol groups, which are treated as a proxy for the event of interest.<sup>28</sup>

Direct comparison of populations is far cleaner in computer-based simulations of reactions based on quantum-mechanical descriptions of atomic interactions. These simulations have uncovered a number of complicated reactive processes in PDMS materials including potential synergies between multiple degradation factors.<sup>7,10,11,17,29–35</sup> Quantum-based molecular dynamics (QMD) takes as input a suitable initial-boundary value problem and evolves the system trajectory according to the dynamically evolving Born-Oppenheimer potential energy surface given by the electronic structure. This captures the ensuing chemical reactions as a direct consequence, with the primary difficulty resting on analyzing these simulations and interpreting underlying events for chemical significance.

In this work, we focus on characterizing chemical changes in pure PDMS through an atomistic modeling approach utilizing chains of dodecamethylpentasiloxane (DMPS), a methyl-terminated PDMS backbone with five silicon centers as an analog for the amorphous polymer. DMPS has previously been chosen as a somewhat simplified model as it includes enough monomer units to provide physical-chemical insights on local chemical reac-

tivity while allowing for the reactive phase space to be explored more effectively on the timescales of our simulations.<sup>17</sup> In using this approach, we can help bound the actual PDMS degradation chemistry in the context of Charlesby’s reaction schemes for crosslink formation in Figure 1. Hundreds of QMD simulations are used to predict the dynamic reaction cascades that follow from initial ionization events, which are modeled with a primary knock-on atom (PKA) approach<sup>36</sup> using an established simulation protocol.<sup>11</sup> The simulations probe reaction cascades under ideal vacuum conditions and in the presence of environmental water, which is a common and potentially reactive contaminant<sup>7,10,17,31,37,38</sup> that is difficult to eliminate in experiments.

Simulations in this work are assessed from two perspectives. The first is an ensemble-based time history analysis and the second a probabilistic analysis. The first approach quantifies the production of reaction intermediates, stable small molecules, and populations of polymer network features such as crosslinks and scissions. These ensemble-averaged response functions are analogous to “bulk” or system-integrated measures of the sort probed in most experiments, yielding for instance the amount of gas evolved. While this is useful information, QMD simulations can provide a direct exploration of the chemical reaction networks including causal dependencies, which is neglected by the ensemble time history analysis approach.

We therefore develop here a complimentary second approach, which takes the form of a general event-based conditional probability and correlation analysis framework. It casts QMD data in a way that provides a straightforward route to test the underlying assumptions of an established hypothesis and make direct connections to experimental observables. This allows one to quantify causal connections between reactive events without fully deducing the complete reaction network and also test the suitability of treating specific events as proxies for other events. Our method allows us to quantitatively assess reliance on the Charlesby scheme for experimental analysis. Application of this analysis framework reveals that Charlesby’s schemes are qualitatively correct, but also shows that causal linking of events may be insufficient to quantitatively determine the number of crosslinks formed from off-gassing data. Further extension of the method yields a possible proxy for difficult-to-measure chain scission events under certain circumstances. The present results are discussed in the context of the extensive body of literature for PDMS radiolytic chemistry.

## 2 Methods

### 2.1 QMD Simulations

High-throughput QMD simulations<sup>39</sup> were performed using the self-consistent charge (SCC) DFTB method<sup>40,41</sup> as implemented in the DFTB+ code.<sup>42</sup> The DFTB total energy is derived from an expansion of the Kohn-Sham energy<sup>43</sup> about a reference electronic density to second order in charge fluctuations and is evaluated as

$$E_{\text{DFTB}} = E_{\text{BS}} + E_{\text{Coul}} + E_{\text{Rep}} + E_{\text{Disp}}. \quad (1)$$


Here  $E_{\text{BS}}$  is the electronic band structure energy evaluated in a tight-binding framework<sup>44</sup> with a minimal atomic orbital ba-

sis,  $E_{\text{Coul}}$  captures electrostatic interactions between fluctuating partial charges, and  $E_{\text{Rep}}$  and  $E_{\text{Disp}}$  are empirical repulsion and dispersion terms. We used the DFTB parameter set pbc-0-3 (available at <http://www.dftb.org>), a typical off-the-shelf parameter set for silicon-containing systems that we previously applied to study siloxane chemistry.<sup>10,11,17</sup> Universal force field dispersion terms<sup>45</sup> were used for  $E_{\text{Disp}}$ . The electronic structure was evaluated without spin polarization at the  $\Gamma$ -point only using Fermi-Dirac thermal smearing<sup>46</sup> and an SCC accuracy threshold of  $2.7 \times 10^{-5}$  eV ( $10^{-6}$  H). Specific thermal smearing energies (temperatures) are noted below. All simulations were performed using extended Lagrangian Born-Oppenheimer dynamics (XL-BOMD).<sup>47–50</sup>

Our simulations consisted of a cubic 3D-periodic cell that contained four chains of DMPS, where dry and wet conditions were considered. The wet case simulation cell included 10 H<sub>2</sub>O molecules that were initially randomly distributed among the four DMPS chains. A multistep procedure was used to bring the system to the PDMS average bulk density of 0.965 g·cm<sup>-3</sup> and to equilibrate it at 300 K prior to simulations to predict primary radiation damage. First, the four DMPS chains (and H<sub>2</sub>O for the wet case) were placed in a cubic cell with side length 20 Å. This cell was then isotropically compressed by reducing the cell length to 13.836 Å (14.356 Å with H<sub>2</sub>O) at a constant rate of 1.0 Å·ps<sup>-1</sup>. Following this, a 20 ps isothermal-isochoric (*NVT*) simulation was performed and 100 configurations were extracted every 100 fs during the last 10 ps as independent starting points for simulations of radiation damage. QMD trajectories for system preparation were integrated using the LAMMPS code<sup>51</sup> with forces and stresses evaluated by DFTB+. The temperature was set to 300 K through a Nosé-Hoover-style thermostat,<sup>52,53</sup> the electron temperature was set equal to the instantaneous ionic temperature, and the XL-BOMD dynamics were integrated with a 0.2 fs time step and four SCC cycles per step.

Similar to our previous work,<sup>11</sup> we adopted a PKA approach to initiate chemical reactions of the form given in Figure 1. With this approach, a randomly selected atom or group of atoms in a thermal configuration is imparted with a large “recoil” kinetic energy through assignment of a random velocity of set magnitude. We take a representative recoil energy to be 50 eV, which is  $\mathcal{O}(10)$  times greater than typical bond dissociation energies in PDMS and is similar in magnitude to ultraviolet radiation. Three types of PKA groups were considered including (1) entire methyl side groups (denoted “Me”), (2) single hydrogen atoms on a methyl side group (denoted “Me-H”), and (3) single hydrogen atoms on an H<sub>2</sub>O molecule (denoted “H<sub>2</sub>O-H”). We do not consider PKA events that induce chain scission directly via recoil of backbone atoms as our focus is on testing Charlesby’s reaction schemes. Such events were recently explored in our earlier work<sup>11</sup> and are predicted to lead to qualitatively similar reaction cascades. By simulating the above three types of PKA events, we can effectively explore all possible irradiation events in the context of Charlesby’s reaction schemes without performing direct calculation of absorption cross-sections, which can require substantial effort<sup>54</sup> and is the subject of future work.

Reaction cascades following from a PKA event were sampled



**Fig. 2** Ensemble-average maximum atom speed in simulations exciting hydrogen at three different PKA recoil energies.

through ensembles of statistically independent, 21 ps long *NVE* simulations. The reaction cascade is characterized by an initial ballistic portion followed by establishment of local thermal equilibrium at a high temperature. Thermal relaxation due to conduction of the resulting heat spike in nm-sized regions is expected to be on the order of 10s of picoseconds or more for materials with a glass-like thermal conductivity ( $\approx 0.5 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ ) such as PDMS.<sup>55,56</sup> Figure 2 shows ensemble-average maximum atom speeds reached following hydrogen atom PKA excitation at three different recoil energies in PDMS. The initial ballistic portion of the trajectory only lasts a few hundred femtoseconds and is followed by the onset of local equilibrium within 1 ps. Hydrogen excitation leads to the highest maximum atom speeds as this PKA group has the lowest mass. Energy conserving integration of the ballistic portion requires a very small time step, which is unnecessary and computationally expensive for the equilibrium portion. Based on Figure 2 and an assessment of energy conservation, we set the time step to 0.05 fs for H-atom excitation and 0.10 fs for Me-group excitation during the first 1 ps of the trajectory and used a larger 0.20 fs time step for the remaining 20 ps.

A given ensemble had 100 independent simulations, each starting from one of the 100 independent starting configurations, and had one specific group type (Me, Me-H, or H<sub>2</sub>O-H) selected for PKA excitation. The single excited group was chosen at random from among those of the chosen type in a given simulation. (There were 60 unique Me groups, 180 unique Me-H atoms, and 20 unique H<sub>2</sub>O-H atoms in the system.) Five ensembles were considered, one for each PKA group type under dry and wet conditions, leading to 500 independent trajectories and a total of 10.5 ns of combined QMD trajectory. All cascade QMD simulations were performed with the standalone DFTB+ code using *NVE* XL-BOMD dynamics. The electron temperature was set to 2000 K, consistent with the system-average kinetic energy, and full SCC convergence was enforced each time step. Trajectory snapshots were recorded every 10 fs for subsequent chemical analysis.

**Table 1** Atom separation distance criteria in Ångström for chemical analysis

|    | Si   | O    | C    | H    |
|----|------|------|------|------|
| Si | 2.55 | 2.00 | 2.20 | 1.80 |
| O  | 2.00 | 1.80 | 1.80 | 1.30 |
| C  | 2.20 | 1.80 | 1.80 | 1.30 |
| H  | 1.80 | 1.30 | 1.30 | 1.00 |

## 2.2 Chemical Analysis

Dynamic changes to chemical bonding were determined through post-processing of trajectories in the PKA simulations using separation distance cutoffs and a time-symmetric lifetime criteria. Bond distance cutoffs are collected in Table 1 and were chosen to be somewhat larger than equilibrium lengths for single bonds of a given interaction type obtained from DFTB-optimized geometries of representative small molecules. The lifetime criterion was set to  $\tau_B = 50$  fs, which is several times larger than the typical oscillation period of the fastest bond vibrations in the system.

Bonding between atoms was tracked through time and was recorded at each time step as an adjacency graph. (The adjacency graph was initialized based on pre-PKA thermalization runs.) Changes to the system's adjacency graph were recorded only when certain criteria were met. A bond was considered to be broken between two atoms at a given time step if the pair were considered bonded on the previous time step and the atoms were separated by more than the cutoff distance for the past  $\tau_B = 50$  fs. Similarly, a bond was considered to have formed between two atoms at a given time step if the pair were considered unbonded on the previous time step and the atoms were separated by less than the cutoff distance for the past  $\tau_B = 50$  fs. Forwards and backwards application of lifetime criteria serves to filter out transients and is essential for detailed balance.<sup>57</sup> A more rigorous yet computationally demanding definition of bonding could assess the trajectory for oscillatory behaviors<sup>58</sup> or explicitly connect to the electronic structure via bond orders.<sup>59</sup>


We considered both all-atom and backbone-only adjacency graphs. The former is useful for identifying small molecules and the latter specifically isolates the polymer network. The backbone-only adjacency graph was determined from the all-atom one by first removing all hydrogen atom nodes and their corresponding bonds (edges), followed by deleting any remaining nodes (atoms) that had only one bond.<sup>11</sup> This serves to effectively remove side groups and other highly undercoordinated terminal atoms. Individual molecules and backbones were identified as connected components of the respective (undirected) adjacency graphs through a depth-first search.

A reduced-order descriptor was used to identify small molecules of specific types. These descriptors were integer-valued length-14 vectors with components corresponding to the population of each atom type and bond type contained in a given molecular connected component. That is,



$$D = (N_{\text{Si}}, \dots, N_{\text{H}}, N_{\text{Si-Si}}, N_{\text{Si-O}}, \dots, N_{\text{H-H}}), \quad (2)$$

where quantities such as  $N_{\text{Si}}$  denote the number of silicon atoms

### Methyl Links



### Ethyl Links



**Fig. 3** Topology definitions and examples for identification of methyl (Si-C-Si) and ethyl (Si-C-C-Si) carbon-containing crosslink junctions. Snapshots of example backbones were rendered using the OVITO code<sup>62</sup> and the approach described in Ref. 11. Atoms are colored yellow, red, and cyan for Si, O, and C.

and  $N_{\text{Si-Si}}$  denote the number of silicon-silicon bonds in the component, etc. Such descriptors are widely used, but are rarely reported on in detail. A common pitfall is that they are highly degenerate when applied to large molecules, often failing to distinguish isomers and other kinds of chemically unique molecular topological features. Such pitfalls could be partially avoided with bond environment descriptors<sup>60</sup> if applied to molecular connected components, through spectral graph metrics,<sup>61</sup> or eliminated entirely through checking graph isomorphism.<sup>11</sup> We apply simple descriptors of the style in Eq. 2 only to quantify populations of small molecules such as  $\text{H}_2$ ,  $\text{CH}_4$ , and  $\text{C}_2\text{H}_6$ , and are thus not in a regime where degeneracy presents significant problems. We used a multi-step approach for backbone chemical analysis, discussed below.

The reaction scheme in Figure 1 yields specific backbone crosslinking motifs. Rapid screening for these features on the backbone adjacency graphs can be performed efficiently without rigorous differentiation of unique backbone topologies through isomorphism checks. We identify methyl and ethyl links by finding 3-center angles and 4-center dihedrals with specific features on the backbone adjacency graphs following Figure 3. Methyl (Si-C-Si) links were found as angles between connected atoms A, B, and C with the requisite ordering of element types and where atom B had exactly two bonds to heavy atoms  $N_B = 2$ . Atoms A and C could have one or more bonds to heavy atoms, but A and C were required to not be bonded to each other. Ethyl (Si-C-C-Si) links were found as proper dihedrals between connected atoms A, B, C, and D with the requisite ordering of element types and where atoms B and C had exactly two bonds to heavy atoms  $N_B = 2$ . Atoms A and D could have one or more bonds to heavy atoms, but the following bond pairs were prohibited: A-C, B-D, and A-D. Silicon-silicon crosslinking (Si-Si) was quantified through counting the number of Si-Si bonds on the backbone adjacency graphs.

## 2.3 Statistical Analysis

Statistics were gathered on specific chemical changes through ensemble-average time history analysis and event-based probabilities. We define  $f_\alpha^{\text{sim}}(t_i)$  as the time history for some property  $\alpha$  in a given independent simulation with discrete time stepping (e.g., the number of  $\text{CH}_4$  molecules). The ensemble-average time history is then obtained as

$$f_\alpha(t_i) = \frac{1}{N_{\text{sim}}} \sum f_\alpha^{\text{sim}}(t_i) \quad (3)$$

and the associated error is taken to be the standard error

$$\text{SE}_\alpha(t_i) = \sqrt{\frac{\sigma_\alpha^2(t_i)}{N_{\text{sim}}}} \quad (4)$$

computed from the variance  $\sigma_\alpha^2(t_i)$  over the  $N_{\text{sim}}$  simulations at time  $t_i$ . Given that  $N_{\text{sim}} = 100$ , the sample mean can reasonably be expected to follow the normal distribution.

We define time-independent events  $E$  and their probabilities  $P$  based on the complete time histories of individual simulations. The definition for event  $A$  is

$$E_A^{\text{sim}} = \begin{cases} 1 & f_\alpha^{\text{sim}}(t_i) \geq 1 \text{ for any } t_i \\ 0 & \text{otherwise} \end{cases} \quad (5)$$

which, for example, could track whether at least one  $\text{CH}_4$  molecule forms in a simulation. The unconditional probability of event  $A$  in an ensemble of  $N_{\text{sim}}$  simulations is thus

$$P(A) = \frac{1}{N_{\text{sim}}} \sum E_A^{\text{sim}}. \quad (6)$$

Similarly, one can define the simultaneous occurrence of events  $A$  and  $B$  in same simulation as

$$E_{A+B}^{\text{sim}} = \begin{cases} 1 & E_A^{\text{sim}} = 1 \text{ and } E_B^{\text{sim}} = 1 \\ 0 & \text{otherwise} \end{cases} \quad (7)$$

As an example, this might track whether at least one  $\text{CH}_4$  molecule and one Si-C-Si link formed. The joint unconditional probability for events  $A$  and event  $B$  is thus

$$P(A \text{ and } B) = \frac{1}{N_{\text{sim}}} \sum E_{A+B}^{\text{sim}} \quad (8)$$

From these relations, one has the definition for the *conditional probability* that event  $B$  occurs given event  $A$  occurred:

$$P(B|A) = \frac{P(A \text{ and } B)}{P(A)}. \quad (9)$$

Events are statistically independent iff

$$P(A \text{ and } B) = P(A)P(B), \quad (10)$$

or equivalently if  $P(A) = P(A|B)$ . Within the event-based description, an apt measure for the “strength” of a given *linear* relationship between events  $A$  and  $B$  is given by the correlation coefficient



$\rho(A,B)$  defined as

$$\rho(A,B) = \frac{P(A \text{ and } B) - P(A)P(B)}{\sqrt{P(A)[1 - P(A)]P(B)[1 - P(B)]}}. \quad (11)$$

Confidence intervals for  $\rho(A,B)$  were determined via bootstrapping with 10000 resamplings of a given 100-simulation ensemble.

Event-based conditional probability analysis applied to QMD simulations offers a route to independently test whether assumptions regarding causal linking are well-founded, such as the simplified reaction schemes in Figure 1. In particular, Equation 9 can help justify using certain events (or quantities) as proxies for different events (or quantities). Event  $B$  is a good proxy for event  $A$  if  $|\rho(A,B)|$  is sufficiently high, which expressed in terms of conditional probabilities is  $P(A) < P(A|B)$  and  $P(A|B) \rightarrow 1.0$ . A perfect proxy pair is one for which  $|\rho(A,B)| = 1.0$ , or equivalently if  $P(A|B) = 1.0$  and  $P(B|A) = 1.0$ . Given some initial chemical intuition or hypothesis to define pertinent events, an event-based probability analysis is substantially less complicated than constructing a full reaction network and facilitates making direct connections to experimental observables.

## 3 Results and Discussion


### 3.1 Crosslinking Events

#### 3.1.1 Time-Dependent Production of Intermediates

The first step in the proposed crosslinking reactions (see Figure 1) is the loss of hydrogen or methyl side groups. Ensemble-average populations of these intermediate species (H and CH<sub>3</sub>) were computed from the five different ensembles of PKA simulations and are shown in Figure 4. The ensembles are characterized by whether the simulation cell is dry or wet and the excitation group type (Me, Me-H, and H<sub>2</sub>O-H), with the last type only applying to wet configurations. The bond lifetime criteria is  $\tau_B = 50$  fs, so time  $t = 0.05$  ps is the earliest time that chemical changes register in trajectories and is taken as the time origin in the plots.

Exciting whole methyl groups (Me) is expected to make CH<sub>3</sub> and exciting hydrogen atoms on methyl groups (Me-H) is expected to make H. The last type with excited hydrogen atoms on environmental water (H<sub>2</sub>O-H) is expected to initially generate an H/OH pair. In all cases, the populations at  $t = 0.05$  ps are consistent with excitation group. Exciting Me-H and H<sub>2</sub>O-H leads to an initial H population of  $\approx 1$  and CH<sub>3</sub> population of  $\approx 0$ . Similarly, exciting Me leads to initial CH<sub>3</sub> population of  $\approx 1$  and H population of  $\approx 0$ . Following this, all cases exhibit a maximum in  $0.1 \leq t \leq 1.0$  ps, coinciding with the end of the ballistic regime. Populations of these species decay practically to zero within the time scale of the simulations.

Perhaps surprisingly, all three excitation types are very effective at producing H, yielding an average maximum of 2.5 per simulation regardless of excitation group. All three excitation types can also produce CH<sub>3</sub>, although in this case Me excitation is more effective. Taking the dry case as an example in panel (c), Me excitation leads to a maximum CH<sub>3</sub> population of 0.9 whereas Me-H leads to a maximum CH<sub>3</sub> population of 0.4. Interpreted as



**Fig. 4** Ensemble-average population time histories for intermediate species H and CH<sub>3</sub>, namely (a) H under dry conditions, (b) H under wet conditions, (c) CH<sub>3</sub> under dry conditions, and (d) CH<sub>3</sub> under wet conditions. Note the logarithmic time scale.


a probability, nearly every Me excitation makes a stable (if short-lived) CH<sub>3</sub>. The double CH<sub>3</sub> peaks for Me excitation and single delayed CH<sub>3</sub> peak for H excitation for both wet and dry conditions indicates that CH<sub>3</sub> is also an intermediate product of subsequent reactions that follow the very initial reactive states induced by PKA recoil.

Water has only one subtle effect on these intermediate time histories. Comparison of panels (c) and (d) shows that environmental water modestly suppresses CH<sub>3</sub> production when exciting Me groups. In contrast, the presence of water does not seem to suppress H populations relative to the dry case. There is largely no difference in initial production between exciting H on Me compared to H on H<sub>2</sub>O. Both H-excitation types lead to H and CH<sub>3</sub> population curves that agree within standard error bounds in panels (b) and (d).

The lifetimes for CH<sub>3</sub> predicted here are very short compared to electron spin resonance measurements in cryogenic (77 K) radiolysis experiments using both X-ray<sup>63</sup> and  $\gamma$ -ray sources.<sup>64</sup> At such low temperatures, these species can exist as radicals for hours.<sup>63</sup> Subsequent warming to 195 K and room temperature led to rapid disappearance of these radicals,<sup>64</sup> indicating a very strong temperature-dependent kinetics. Spin trapping chemical agents are needed to observe CH<sub>3</sub> radicals above 77 K.<sup>65</sup> Considering that our system is closed and the local temperature is in excess of 1000 K, picosecond-scale kinetics is not unreasonable and in qualitative agreement with the available experiments.

#### 3.1.2 Time-Dependent Small Molecule Production

Final off-gassing products in the proposed crosslinking reactions (see Figure 1) include H<sub>2</sub>, CH<sub>4</sub>, and small quantities of C<sub>2</sub>H<sub>6</sub>. The



**Fig. 5** Ensemble-average population time histories for stable small molecule species including (a)  $\text{H}_2$  under dry conditions, (b)  $\text{H}_2$  under wet conditions, (c)  $\text{CH}_4$  under dry conditions, (d)  $\text{CH}_4$  under wet conditions, (e)  $\text{C}_2\text{H}_6$  under dry conditions, and (f)  $\text{C}_2\text{H}_6$  under wet conditions.

ensemble-average time histories for  $\text{H}_2$ ,  $\text{CH}_4$ , and  $\text{C}_2\text{H}_6$  populations are shown in Figure 5 for the various cases. In nearly all cases (both wet and dry), a stable plateau for each species concentration is reached within a few picoseconds, indicating that the underlying gas-evolving reactions take place very quickly. Species  $\text{H}_2$  and  $\text{CH}_4$  are formed in roughly similar quantities whereas the quantity of  $\text{C}_2\text{H}_6$  is lower by about an order of magnitude. For instance, only a single  $\text{C}_2\text{H}_6$  molecule is generated across 100 simulations with Me-H excitation. This is largely consistent with experimental measurements discussed below, which find substantially less  $\text{C}_2\text{H}_6$  compared to  $\text{H}_2$  and  $\text{CH}_4$ .

There is a high degree of similarity among the  $\text{H}_2$  time histories for the different cases shown in panels (a) and (b). Exciting Me is approximately twice as effective at generating  $\text{H}_2$  than exciting H atoms under both wet and dry conditions. Water has negligible impact on final populations for a given excitation type within computed errors. We also determine no difference between exciting Me-H or  $\text{H}_2\text{O-H}$ .

In contrast, time histories for  $\text{CH}_4$  in panels (c) and (d) show distinctly different trends than  $\text{H}_2$ . Under dry conditions, both Me and Me-H excitation generate the same amounts of  $\text{CH}_4$ . Under wet conditions,  $\text{CH}_4$  production is unchanged when exciting Me compared to dry conditions, but is modestly suppressed when exciting Me-H.  $\text{H}_2\text{O-H}$  yields quite different trends than exciting Me-H, and is the most effective excitation type for generating  $\text{CH}_4$ .

Experimental measurements of small molecule off-gassing were made in a number of independent studies that considered different radiation sources and PDMS molecular weights.<sup>20–22,64,66–68</sup> Relative concentrations of  $\text{H}_2$ ,  $\text{CH}_4$ , and  $\text{C}_2\text{H}_6$  referenced to the  $\text{H}_2$  concentration  $[\text{H}_2]$  measured in these experiments are collected in Table 2, along with information on the form of the PDMS material sample, the radiation source (reactor piles,  $^{60}\text{Co}$   $\gamma$ -rays, or high-energy electrons  $e^-$ ), and headspace gases exposed to the sample (if known). These are compared to analogous values predicted here from QMD, which correspond to the ensemble-average results at time  $t = 21$  ps in Figure 5. Recent experiments on engineering silicones with complex compositions can off-gas additional volatile species,<sup>16</sup> though we restrict our discussion to pure PDMS materials here.

Quantitative trends among the experiments are difficult to discern. Results from Zack et al.<sup>66</sup> on hexamethyldisiloxane oil show little difference in off-gassing products between a  $^{60}\text{Co}$   $\gamma$ -ray source and the environment of a reactor pile. At the same time, the results of Zack et al. differ from the measurements by Warrick et al.<sup>68</sup> of  $^{60}\text{Co}$ -irradiated octamethylcyclotetrasiloxane and those by Charlesby<sup>20</sup> of pile-irradiated high-molecular-weight silicone. The results of Warrick et al. and Charlesby also differ from each other.

Significant spread is seen for relative  $\text{CH}_4$  production despite similar radiation sources and inert  $\text{N}_2$  atmosphere, as seen by comparing the experiments of St. Pierre et al.,<sup>67</sup> Dewhurst and St. Pierre,<sup>22</sup> and Miller.<sup>21</sup> Perhaps interestingly, those experiments show similar relative production of  $\text{C}_2\text{H}_6$ . The original source documenting the MeV-range electron irradiation experiments noted in Ref. 64 could not be located, but those results clearly fall within the spread of the other studies.

The present QMD modeling results and experiments are broadly consistent, exhibiting a significant (yet similar) spread of values. The minimum  $[\text{CH}_4]/[\text{H}_2]$  and  $[\text{C}_2\text{H}_6]/[\text{H}_2]$  populations over the five QMD ensembles are respectively 0.95 and 0.00, while the corresponding maximums are 2.62 and 0.12. This is quite similar to the respective experimental minima (0.86 and 0.00) and maxima (2.33 and 0.71). In particular, there are some experiments in which large amounts of  $\text{H}_2$  and  $\text{CH}_4$  form with no detectable  $\text{C}_2\text{H}_6$  whereas large quantities of  $\text{C}_2\text{H}_6$  form in others.

### 3.1.3 Time-Dependent Crosslink Formation

Figure 6 shows ensemble-averaged time histories for formation of specific crosslink features under the five cases considered. The panels are arranged to facilitate direct comparison to Figure 5 in the context of the reaction schemes given in Figure 1. For instance, production of  $\text{H}_2$  in Figure 5(a) is connected to formation of ethyl crosslinks (Si-C-C-Si) in Figure 6(a) under the same set of conditions.

**Table 2** Populations of small molecule species in irradiated PDMS materials relative to observed  $[H_2]$  concentrations

| QMD (this work) |                        |                          |                |                  |                                     |
|-----------------|------------------------|--------------------------|----------------|------------------|-------------------------------------|
| Material        | Excitation             | Headspace                | $[CH_4]/[H_2]$ | $[C_2H_6]/[H_2]$ |                                     |
| Pentamer        | Me                     | Vacuum (ideal)           | 1.24           | 0.12             |                                     |
| Pentamer        | Me-H                   | Vacuum (ideal)           | 2.10           | 0.03             |                                     |
| Pentamer        | Me                     | H <sub>2</sub> O         | 0.94           | 0.05             |                                     |
| Pentamer        | Me-H                   | H <sub>2</sub> O         | 2.21           | 0.05             |                                     |
| Pentamer        | H <sub>2</sub> O-H     | H <sub>2</sub> O         | 2.62           | 0.00             |                                     |
| Experiment      |                        |                          |                |                  |                                     |
| Material        | Rad. Source            | Headspace                | $[CH_4]/[H_2]$ | $[C_2H_6]/[H_2]$ | Ref.                                |
| Dimer           | <sup>60</sup> Co       | Vacuum ( $<10^{-6}$ atm) | 2.23           | 0.00             | Zach et al. 66                      |
| Dimer           | Pile                   | Vacuum ( $<10^{-6}$ atm) | 2.33           | 0.01             | Zach et al. 66                      |
| Dimer           | 800 kVp e <sup>-</sup> | N <sub>2</sub>           | 2.00           | 0.57             | Dewhurst & St. Pierre 22            |
| Pentamer        | 800 kVp e <sup>-</sup> | N <sub>2</sub>           | 1.52           | 0.71             | St. Pierre et al. 67                |
| Cyclotetramer   | <sup>60</sup> Co       | Sealed (unspecified)     | 1.76           | 0.14             | Warrick et al. 68                   |
| Silicone        | Pile                   | Sealed (unspecified)     | 1.16           | 0.30             | Charlesby 20                        |
| Silicone        | 2 MeV e <sup>-</sup>   | Unknown                  | 1.38           | 0.24             | Ormerod & Charlesby <sup>a</sup> 64 |
| Silicone        | 800 kVp e <sup>-</sup> | N <sub>2</sub>           | 0.86           | 0.61             | Miller <sup>b</sup> 21              |

<sup>a</sup>Reported in reference from private communications with W. Davison and D. Lloyd.

<sup>b</sup>Values correspond to measurements at 25 °C.

The time history response is characterized by well-converged plateaus under wet conditions and more slowly converging plateaus in dry conditions for all three crosslink types. The apparent rate of convergence is slower than those for the H<sub>2</sub>, CH<sub>4</sub>, and C<sub>2</sub>H<sub>6</sub> populations. Methyl and ethyl links are rapidly formed in 30% or fewer PKA events and Si-Si links are produced in 10% or fewer PKA events. These crosslink populations are approximately half the size of the corresponding small molecule species populations in Figure 5.

Wet conditions suppress both types of carbon crosslinking, consistent with earlier DFTB modeling results of radiation-induced reactions in phenylated siloxanes<sup>10</sup> and arguments based on DFT-computed reaction barriers.<sup>7</sup> Direct Si-Si linking is also lower in wet simulations, although these differences are similar in magnitude to the computed errors. Water suppresses Si-C-Si formation more than Si-C-C-Si formation. Exciting Me-H under dry conditions is the most effective combination for producing *both* Si-C-Si and Si-C-C-Si links; this is at least twice as effective as exciting Me groups directly. Conversely, exciting Me under dry conditions is the most effective combination for producing Si-Si links.

It is substantially more difficult to accurately quantify the different types of crosslinking in experiments than it is to measure small-molecule off-gassing. The small subset of experiments that quantified relative Si-C-C-Si, Si-C-Si, and Si-Si crosslink populations are listed in Table 3. These are compared to analogous values predicted here from QMD, which correspond to the ensemble-average results at time  $t = 21$  ps in Figure 6.

Among the experiments, the measurements of Dewhurst and St. Pierre<sup>22</sup> are perhaps the most direct. They analyzed non-volatile products of irradiated hexamethyldisiloxane through liquid chromatography to deduce crosslink populations. In comparison, Miller<sup>21</sup> deduced these ratios from a combination of relative IR intensities (sensitive to Si-C-Si and Si-C-C-Si) and titration with bromine Br<sub>2</sub>, which reacts quickly with Si-Si bonds. Bueche<sup>24</sup> quantified radiation-induced changes to average molec-

ular weights in dodecamethylpentasiloxane oil as a measure for crosslinking, but their technique did not yield specific crosslink type ratios. Their complimentary IR measurements did not detect Si-C-C-Si links.


Modern NMR techniques provide what is perhaps the most direct experimental route to quantify crosslinking in PDMS. Chemically specific crosslinking motifs were elucidated in  $\gamma$ -irradiated PDMS through a series of <sup>13</sup>C and <sup>29</sup>Si NMR experiments by Hill et al.<sup>23,69</sup> in samples under vacuum at cryogenic (77 K) and room temperature. Two principle findings from these studies were that (1) many of the crosslinks in PDMS arose from formation of Si-O-Si crosslinks (following main chain scission) that are not considered in the Charlesby mechanism, and (2) there was no evidence for Si-Si linking. While their experiments did detect Si-C-Si and Si-C-C-Si links, overlaps in spectral peaks prevented quantifying populations of the latter. These results indicate that caution should be exercised in interpreting crosslinking ratios from experiments such as sol-dose that measure only populations of generic “mechanically relevant” crosslinks with no chemical specificity.

The above experiments were performed under vacuum or N<sub>2</sub> atmosphere, so the QMD results without water are the cleanest point for comparison. As discussed above, QMD predicts that environmental water will have a substantial impact on crosslinking, which manifests markedly in the relative ratios. The QMD ensemble with Me excitation in vacuum yielded ratios very similar to the tabulated experiments. In contrast, H excitation yields results closer to Hill et al. that found little to no Si-Si linking. The wide (and sometimes conflicting) range of experimental results highlights the complexity of chemistry in this system. One interpretation of the present modeling results for small molecule production and crosslinking suggests that both environmental factors—it is difficult to completely eliminate water in samples—and the chemical groups initially excited by radiation could play a role in this spread.



**Table 3** Populations of cross-links in irradiated PDMS materials relative to observed [Si-C-C-Si] concentrations

| QMD (this work) |                        |                  |                       |                     |                                       |
|-----------------|------------------------|------------------|-----------------------|---------------------|---------------------------------------|
| Material        | Excitation             | Headspace        | [Si-C-Si]/[Si-C-C-Si] | [Si-Si]/[Si-C-C-Si] |                                       |
| Pentamer        | Me                     | Vacuum (ideal)   | 3.25                  | 2.50                |                                       |
| Pentamer        | Me-H                   | Vacuum (ideal)   | 1.26                  | 0.13                |                                       |
| Pentamer        | Me                     | H <sub>2</sub> O | 2.33                  | 1.67                |                                       |
| Pentamer        | Me-H                   | H <sub>2</sub> O | 0.63                  | 0.06                |                                       |
| Pentamer        | H <sub>2</sub> O-H     | H <sub>2</sub> O | 0.38                  | 0.15                |                                       |
| Experiment      |                        |                  |                       |                     |                                       |
| Material        | Rad. Source            | Headspace        | [Si-C-Si]/[Si-C-C-Si] | [Si-Si]/[Si-C-C-Si] | Ref.                                  |
| Dimer           | 800 kvp e <sup>-</sup> | N <sub>2</sub>   | 3.33                  | 1.67                | Dewhurst & St. Pierre <sup>a</sup> 22 |
| Silicone        | 800 kvp e <sup>-</sup> | N <sub>2</sub>   | 3.60                  | 2.22                | Miller <sup>a</sup> 21                |

<sup>a</sup>Values correspond to measurements at 25 °C.**Fig. 6** Ensemble-average population time histories for crosslinks including (a) Si-C-C-Si links under dry conditions, (b) Si-C-C-Si links under wet conditions, (c) Si-C-Si links under dry conditions, (d) Si-C-Si links under wet conditions, (e) Si-Si links under dry conditions, and (f) Si-Si links under wet conditions.


### 3.1.4 Conditional Probabilities

Figure 7 captures the conditional and unconditional probabilities for events linked to small molecule off-gassing and crosslink

formation. Here, event  $A$  is a formation probability for a particular small molecule gas type (denoted “gas”) and event  $B$  is the formation probability for a particular crosslink type (denoted “link”). Roughly speaking, it is easier to measure gas evolution than crosslink formation in experiments. The probabilities are organized in a given panel from top to bottom and left to right as  $P(\text{gas})$ ,  $P(\text{gas}|\text{link})$ ,  $P(\text{link})$ ,  $P(\text{link}|\text{gas})$ . Recall that  $P(\text{gas}|\text{link})$  is interpreted as the probability for event “gas” given knowledge that event “link” occurred. Specific event definitions are given in the caption. In all cases,  $P(\text{gas}) \neq P(\text{gas}|\text{link})$  and  $P(\text{link}) \neq P(\text{link}|\text{gas})$ , indicating the defined events are not independent. In general, event  $A$  is a good proxy for event  $B$  if  $P(B) < P(B|A)$  and  $P(B|A) = 1.0$ . Thus,  $P(\text{link}|\text{gas})$  is of most use for identifying easy-to-measure experimental proxies. At the same time  $P(\text{gas}|\text{link})$  is chemically informative, but the causal relationship is less useful.

Focusing first on Figure 7(a), the comparison is structured to test connections between H<sub>2</sub> off-gassing and Si-C-C-Si crosslinking. The unconditional probabilities follow  $P(\text{H}_2) > P(\text{Si-C-C-Si})$  and differ by a factor of six for Me excitation and 1.5 for either type of H excitation, which could indicate many other reaction channels for H<sub>2</sub> production with Me excitation. The conditional probability  $P(\text{H}_2|\text{Si-C-C-Si})$  is as much as 0.86, indicating that many H<sub>2</sub> molecules are connected to Si-C-C-Si crosslinking events. Conversely, while the conditional probability  $P(\text{Si-C-C-Si}) < P(\text{Si-C-C-Si}|\text{H}_2)$  and thus meets our criteria for a proxy, the value of  $P(\text{Si-C-C-Si}|\text{H}_2)$  is never greater than 0.47 (e.g., much less than the ideal value of 1). This implies there must be many other chemical events that produce H<sub>2</sub> without ever generating a Si-C-C-Si cross link. Thus, H<sub>2</sub> formation may not be a good proxy for Si-C-C-Si formation. Additional correlation analysis described below is required to determine whether a statistically significant relationship exists between these two events.

Figure 7(b) is structured to test connections between CH<sub>4</sub> off-gassing and Si-C-Si crosslinking. For all cases  $P(\text{CH}_4) > P(\text{Si-C-Si})$ , with difference factors ranging from 1.9 to 8.3 that are greatest in wet conditions. The conditional probability  $P(\text{CH}_4|\text{Si-C-Si})$  is no less than 0.71 and is 1.0 for the case with wet conditions and Me excitation. Forming Si-C-Si makes forming CH<sub>4</sub> much more likely, and there is an even stronger causal relationship than was seen for H<sub>2</sub> and Si-C-C-Si links. In contrast, the conditional probability  $P(\text{Si-C-Si}|\text{CH}_4)$  is never greater than 0.46, indicating



**Fig. 7** Unconditional and conditional probabilities for crosslink formation in PKA simulations with different excitation types and system conditions.  $P(A)$  is the unconditional probability for event  $A$  and  $P(A|B)$  is the conditional probability for event  $A$  given knowledge that event  $B$  occurred. (a) Probability at least one  $H_2$  molecule is formed and at least one Si-C-C-Si link is formed. (b) Probability at least one  $CH_4$  molecule is formed and at least one Si-C-Si link is formed. (c) Probability at least one  $C_2H_6$  molecule is formed and at least one Si-Si link is formed.

that  $CH_4$  is formed through other routes besides crosslink formation. As with  $H_2$ , so we find that  $CH_4$  formation may not be a good proxy for Si-C-Si formation, with the relationship requiring further interrogation.

Lastly, Figure 7(c) tests connections between  $C_2H_6$  off-gassing and Si-Si crosslinking. The unconditional probability to form  $C_2H_6$  is much lower than  $H_2$  or  $CH_4$  and is zero in the case of  $H_2O$ -H excitation. In contrast, the unconditional formation probability for Si-Si crosslinking is more similar to the Si-C-Si and Si-C-C-Si formation probabilities within the predicted spread. The conditional probability follows  $P(C_2H_6|Si-Si) > P(C_2H_6)$  for Me excitation, but both probabilities are very low. The direction for the inequality is reversed for Me-H excitation. While the conditional probability  $P(Si-Si|C_2H_6) > P(Si-Si)$  for Me excitation, it is never greater than 0.43, indicating that only some crosslinks are connected to  $C_2H_6$  off-gassing. With H excitation,  $P(Si-Si|C_2H_6) = 0$  even though  $P(Si-Si) \approx 0.1$ , suggesting that none of the evolved  $C_2H_6$  is tied to Si-Si crosslinking. Thus,  $C_2H_6$  and Si-Si formation are almost certainly not good proxies for each other and there must be other chemical events that produce Si-Si crosslinks.


Correlation coefficients for the events defined in Figure 7 were computed using Equation 11 and are collected in Figure 8. Confidence intervals for the correlation coefficients were computed via bootstrapping with 10000 resamplings of each 100-simulation ensemble. In this representation, there exists a statistically significant positive (negative) correlation between events  $A$  and  $B$  with 95% certainty if the entire 95% confidence interval indicated by the box is above (below) zero. For instance, focusing on panel (a), one can see that there exists a statistically significant correlation between  $H_2$  and Si-C-C-Si links with Me excitations in dry environments, but not in wet environments.

From the correlation confidence intervals, it is clear that there is a modest positive and statistically significant correlation between  $H_2$  and  $CH_4$  off-gassing and their respective crosslinking events for the majority of the conditions studied. This is unlike


the correlation between  $C_2H_6$  off-gassing and Si-Si linking, which shows no statistical significance for any excitation/humidity combination and is formally undefined for  $H_2O$ -H excitation given that some of the underlying probabilities are zero. We note that even for the apparent positive relationship between  $H_2$  and  $CH_4$  gases and crosslinks, there are some excitation/humidity combinations that yield insignificant correlations. In the case of  $H_2$ , it is the two wet cases with excitations centered on PDMS that have insignificant correlations. In contrast, there is no systematic trend for which cases exhibit significant correlations between  $CH_4$  and Si-C-Si links; two cases are insignificant, one being Me excitation in dry environment and the other between  $H_2O$ -H excitation in wet environment.

As  $P(link|gas) > P(link)$  and  $\rho(gas, link)$  is statistically significant in the majority of cases involving  $H_2$  and  $CH_4$ , it is clear that these specific off-gassing products are causally connected to specific crosslinks. However,  $P(link|gas)$  and  $\rho(gas, link)$  are rarely unity, which is what one would expect if every gas molecule were traced to a crosslink-forming event and vice-versa. Taken together with the fact that there are some excitation/humidity conditions that yield insignificant correlations, the conditional probabilities  $P(link|gas)$  computed for the present QMD data indicates caution is warranted in using  $H_2$  and  $CH_4$  off-gassing to directly quantify Si-C-C-Si and Si-C-Si crosslink populations. The complete lack of significant correlations between  $C_2H_6$  and Si-Si links further underscores the wide variance in the experimental and predicted concentrations for those two features reflected in Tables 2 and 3.

A pragmatic interpretation of the set of statistically significant correlations indicates that it should be possible to construct a regression model linking off-gassing and crosslinking under certain circumstances. Regression models linking  $H_2$  and Si-C-C-Si links may work well in perfectly desiccated systems. It is less clear whether the same will hold for  $CH_4$  and Si-C-Si links. Importantly, such regression models will need to be trained against data with high chemical specificity, such as that generated from QMD



**Fig. 8** Box and whisker plots of the correlation coefficients  $\rho(A, B)$  for gas evolution and crosslink formation events in PKA simulations with different excitation types and system conditions, including (a) correlation between  $H_2$  and Si-C-C-Si links, (b)  $CH_4$  and Si-C-Si links, and (c)  $C_2H_6$  and Si-Si links. Note that these are somewhat non-standard box and whisker plots with the box corresponding to a 95% confidence interval, the line through the box indicating the median, and either whisker indicating the extremes in a sampling distribution determined via bootstrapping with 10000 resamplings.



**Fig. 9** Ensemble-average population time histories for (a) change in Si-O bonds under dry conditions, (b) change in Si-O bonds under wet conditions, (c) silanol groups under dry conditions, and (d) silanol groups under wet conditions.

simulations. A more sophisticated analysis of the QMD data that considers other trace gases might yield more robust models for quantification of crosslinking through small molecule off-gassing measurements. From a chemical perspective, our results indicate that a qualitative interpretation of Charlesby’s reaction schemes may be most reasonable, as they miss important (if still poorly characterized) branches in a larger reaction network.

## 3.2 Scission Events

### 3.2.1 Time-Dependent Response

Figure 9 shows ensemble-averaged time histories for change in population of Si-O backbone bonds and populations of silanol (Si-OH) groups for the five cases considered in Section 3.1 (varying


wet and dry conditions and the three excitation group types). The change in Si-O bonds relative to time  $t = 0$  ps effectively measures the number of chain scissions. Silanol groups were identified as three-center angles in the all-atom adjacency graphs in a similar way as methyl links (see Figure 3). Here, the angles were required to have the requisite order (Si-O-H), with additional constraints that the O atom had precisely two bonds and the H atom only a single bond.

Inspection of panels (a) and (b) shows that fewer than one Si-O bond is scissioned per PKA event on average. Excitation of Me groups is the most effective route to chain scission among the cases considered. These scission events occur very early in the trajectory following PKA excitation, typically within the first few picoseconds. Chain scissions slowly anneal following Me excitation under dry conditions, whereas the scissions are persistent in the other four cases. Environmental water does not change the initial number of Si-O bonds broken, but it does impede recovery following Me excitation seen in the dry case.

There is a very large difference between wet and dry conditions in terms of silanol formation. Up to four times as many silanols are formed when water is present. The excitation group does not impact silanol production under dry conditions, but has a strong bearing on silanol production in wet conditions. Picosecond-scale silanol formation reactions were predicted to occur in QMD simulations following loss of a phenyl side group in a model siloxane copolymer.<sup>10</sup> In that case it was found that loss of a side group leaves an undercoordinated Si atom, which is highly reactive and readily scavenges OH groups from nearby water. A similar reaction likely occurs here in pure PDMS following loss of a methyl group. Excitation of  $H_2O-H$  is also highly effective at generating silanols. Perhaps surprisingly, while Me-H excitation is the least effective at producing silanols, it is still twice as effective under wet conditions as compared to dry conditions.

### 3.2.2 Conditional Probabilities

Unconditional and conditional probabilities for silanol production and chain scission events are plotted in Figure 10. We denote these events respectively as “Si-OH” and “Si-/O”. In this comparison, it is easier to detect silanol groups in experiments (e.g., through vibrational spectra) as compared to chain scissions. Un-



**Fig. 10** Unconditional and conditional probabilities for the events that at least one silanol (Si-OH) group is formed and at least one Si-O bond is broken.  $P(A)$  is the unconditional probability for event  $A$  and  $P(A|B)$  is the conditional probability for event  $A$  given knowledge that event  $B$  occurred.


like the connections between off-gassing and crosslinking, it is not straightforward to directly measure scission events in experiments, so identifying reasonable proxies for this event are even more important.

As was seen in the time-dependent analysis, unconditional probabilities show silanols are formed about 20% of the time in dry conditions and up to 60% of the time in wet conditions. The conditional probability  $P(\text{Si-OH} | \text{Si-/O})$  is always larger than  $P(\text{Si-OH})$  and it is never smaller than 0.44. In addition, knowledge of Si-O scission reactions increases the probability of silanol formation by a factor of 1.3 to 3.6, as indicated by the ratio of  $P(\text{Si-OH} | \text{Si-/O})$  to  $P(\text{Si-OH})$ .

Unconditional scission probabilities vary most with excitation group and are somewhat larger than 0.5 with Me excitation and closer to 0.3 with H excitation. The conditional probability  $P(\text{Si-/O} | \text{Si-OH})$  is always larger than  $P(\text{Si-/O})$ . Here,  $P(\text{Si-/O} | \text{Si-OH}) = 1.0$  under dry conditions, indicating that every Si-O bond scission is closely connected to silanol formation. These results imply that silanol formation is an excellent proxy for chain scission under dry conditions. Conditional probabilities are somewhat lower under wet conditions ( $0.59 < P(\text{Si-/O} | \text{Si-OH}) < 0.77$ ). Thus, while Si-O bond scission is likely if silanols are detected, there are other chemical events leading to both silanol formation and Si-O bond scission when water is present.

Correlation coefficients for silanol formation and main chain scission were computed using Equation 11 and are plotted in Figure 11. Similar to the analysis of off-gassing and crosslinking in the previous section, confidence intervals for the correlation coefficients were computed via bootstrapping with 10000 resamplings of each 100-simulation ensemble. A statistically significant positive correlation exists with 95% certainty if the entire 95% confidence interval indicated by the box is above zero.

As anticipated from Figure 10, the correlation analysis shows that a positive and statistically significant correlation exists be-



**Fig. 11** Box and whisker plots of the correlation coefficients  $\rho(A,B)$  for chain scission (Si-/O) and silanol (Si-OH) formation events in PKA simulations with different excitation types and system conditions. We follow the same box-and-whisker convention as in Figure 8.

tween chain scissions and silanol formation under all of the conditions studied. The correlation strength here is quite unlike that computed for small molecule off-gassing and crosslinking in Figure 8. Despite this relative increase in strength, the correlation between silanol formation and scission is still much less than unity, indicating that these events are not fully coupled. The strength of the correlation is generally greater for H excitations than for Me excitations and the presence of water systematically lowers the strength relative to dry conditions.

There have been numerous attempts to quantify scissions through experiments, although few can be directly compared to the present work. Comparisons are difficult to make as the experiments either measure “mechanically relevant” crosslinks and scissions or else tie the scission probability to assumed models or complex sets of products. For instance, Squire and Turner<sup>25</sup> estimated ratios of crosslinking and scissioning from sol-dose experiments through an analysis with a probabilistic model that makes a number of assumptions, including that the starting molecular weight distribution is random. Similarly, Tanny and St. Pierre<sup>26</sup> estimated scissioning indirectly through two routes, namely with Tobolsky’s two-network model and as a ratio to crosslinks in sol-dose experiments. The latter makes use of the so-called “Charlesby-Pinner” analysis,<sup>70</sup> which has proven to return similar results as obtained through fitting constitutive models for siloxane elastomer stress-strain responses.<sup>71</sup> These approaches that rely on mechanical data necessarily only account for scissioning and crosslinking that alters mechanical response. Multi-quantum NMR can measure detailed changes in molecular weight distributions, but scissioning and crosslinking are again inferred indirectly through fitting to probabilistic models.<sup>8,9</sup> Hill et al.<sup>23,69</sup> presented an alternative means to measure scissioning through NMR, which can quantify populations for a host of chemical structures that are reasonably interpreted as resulting from chemistry with scissioned chain ends.

Consideration of silanol production as a measure for scissioning dates to early experiments by Miller,<sup>72</sup> who made the (chemically reasonable) assumption that these features were directly related in the analysis of IR spectra for irradiated PDMS loaded with hydrogen donors. More recent experiments by Alam<sup>37</sup> and Patel et

al.<sup>38</sup> used <sup>17</sup>O-labeled water to identify the formation of silanols and incorporation of water oxygen atoms into the main chain during radiolysis. A new approach to detect silanols through NMR via tagging with <sup>19</sup>F-labeled groups that react with silanols offers what is perhaps the cleanest spectroscopic measure for these features.<sup>28</sup> In this context, the present QMD simulations with water suggest that many (but not all) silanols can be traced to chain scissions while the discrepancy in unconditional probabilities for scissioning and silanol formation in dry conditions indicates there are more scissions than silanols. Thus, a population count for silanols in experiments might underrepresent the true number of chain scissions. Calibrated regression models based on QMD data that link scissioning and silanol formation hold promise as a means to systematically correct these underestimates.

## 4 Conclusions

We develop here a general *in silico* analysis framework to test proposed reaction schemes for polymer degradation processes and apply this to characterize the radiolytic chemistry of polydimethylsiloxane (PDMS), the primary constituent of silicones. Here, we use a model system of dodecamethylpentasiloxane (DMPS) in order make simulation of the amorphous polymer more tractable with our quantum calculations. In addition, we model all types of atomic excitations relevant to siloxane systems in the context of long-standing reaction schemes for irradiation of PDMS. In doing so, we can place reasonable bounds on the types of chemical events that can occur as well as their intercorrelations. Our approach combines ensembles of quantum-based molecular dynamics (QMD) simulations to generate statistics for radiation-induced reaction cascades with an event-based conditional probability and correlation analysis to uncover causal connections between experimental observables. In this context, we test a long-standing set of reaction schemes for crosslinking in irradiated PDMS that link small molecule off-gassing products with formation of specific crosslinking motifs. The effects of water as a commonly unavoidable experimental contaminant are also assessed.

The established reaction schemes for crosslinking and off-gassing chemistry in irradiated PDMS date to Charlesby's experiments from the 1950's and are based on highly integrated data. These schemes respectively connect the evolution of hydrogen (H<sub>2</sub>), methane (CH<sub>4</sub>), and ethane (C<sub>2</sub>H<sub>6</sub>) with the formation of silethylene (Si-C-C-Si), silmethylene (Si-C-Si), and silicon-silicon (Si-Si) crosslinks. Our independent analysis of this chemistry through QMD simulations suggests that these reaction schemes are qualitatively reasonable, but lack strong statistically significant connections under a broad set of conditions that would enable making quantitative connections between off-gassing and crosslinking without careful consideration. Conditional probability analysis shows that many Si-C-C-Si and Si-C-Si crosslinks are connected to formation of H<sub>2</sub> and CH<sub>4</sub>, but the reverse is not necessarily true. Large quantities of these gases are produced without any direct connection to these specific crosslinks. The relationship between Si-Si linking and C<sub>2</sub>H<sub>6</sub> production is found to be statistically insignificant under all conditions considered and yields much smaller populations compared to the other crosslink

and gas types. Water is shown to alter relative and absolute product yields, with the results being consistent with the spread in available experiments.

Application of our analysis framework to our QMD data uncovers a strong (but nonideal) quantitative connection between exceptionally hard-to-measure scission events and the formation of silanol (Si-OH) groups. These connections have long been assumed and even exploited as an indirect measure for chain scissioning in experimental diagnostics. We find that under perfectly desiccated conditions, every silanol formed is connected to scission of the main polysiloxane chain. Water has a noticeable effect in opening alternative reaction pathways to silanol formation that are not causally linked to scission. Even under perfectly desiccated conditions, more scissions occur than are accounted for in the silanol populations. These results imply that one cannot count silanols as a means to directly count the number chain scission events, but the statistically significant correlations identified here indicate that a regression model trained on QMD data could offer a route to systematically correct these underestimates.

Implications of our efforts inform confidence in the underlying assumptions used to interpret PDMS radiolysis experiments. In particular, skewness in conditional probability measures cast doubt on using comparatively easy-to-measure small molecule off-gassing products as a quantitatively accurate proxy for hard-to-measure crosslink populations. It also suggests that significant branches are missing in the proposed reaction schemes that would provide other routes to small molecule gases.

The main practical benefit of this analysis approach is that one can independently inform confidence in connections between experimental observables without the burden of fully elucidating entire reaction networks. While the present example considers well-studied PDMS chemistry, our approach is general. Given a suitable initial-boundary value problem for QMD simulations, it can be applied to test any proposed reaction scheme. Our analysis method could thus be applied to any number of reactive degradation processes, including other radiation damage studies where the connection between easy- and hard-to-quantify observables is difficult to determine from experiments alone.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract DE-AC52-07NA27344. Released under document number LLNL-JRNL-829305-DRAFT.

## Notes and references

- 1 I. R. Williams, M. B. Mayor and J. P. Collier, *Clin. Orthop. Relat. Res.*, 1998, **356**, 170–180.
- 2 A. S. Palsule, S. J. Clarson and C. W. Widenhouse, *J. Inorg. Organomet. P.*, 2008, **18**, 207–221.
- 3 B. Arkles, 1983, **13**, 542–555.
- 4 S. J. Harley, E. A. Glascoe and R. S. Maxwell, *J. Phys. Chem. B*, 2012, **116**, 14183–14190.



- 5 Y. Sun, S. J. Harley and E. A. Glascoe, *ChemPhysChem*, 2015, **16**, 3072–3083.
- 6 H. N. Sharma, L. N. Dinh, J. H. Leckey, R. S. Maxwell and W. McLean, *Ind. Eng. Chem. Res.*, 2020, **59**, 19510–19521.
- 7 P.-C. Wang, N. Yang, D. Liu, Z.-M. Qin, Y. An and H.-B. Chen, *Mater. Des.*, 2020, **195**, 108998.
- 8 L. N. Dinh, B. P. Mayer, A. Maiti, S. C. Chinn and R. S. Maxwell, *J. Appl. Phys.*, 2011, **109**, 094905.
- 9 A. Maiti, T. Weisgraber, L. N. Dinh, R. H. Gee, T. Wilson, S. Chinn and R. S. Maxwell, *Phys. Rev. E: Stat., Nonlin., Soft Matter Phys.*, 2011, **83**, 031802.
- 10 M. P. Kroonblawd, N. Goldman and J. P. Lewicki, *J. Phys. Chem. B*, 2018, **122**, 12201–12210.
- 11 M. P. Kroonblawd, N. Goldman, A. Maiti and J. P. Lewicki, *J. Chem. Theory Comput.*, 2021, **17**, 463–473.
- 12 Q. Liu, W. Huang, B. Liu, P.-C. Wang and H.-B. Chen, *ACS Appl. Mater. Interfaces*, 2021, **13**, 41287–41302.
- 13 E. F. Griessbach and R. Lehmann, *Chemosphere*, 1999, **38**, 1461–1468.
- 14 D. Graiver, K. W. Farminer and R. Narayan, *J. Polym. Environ.*, 2003, **11**, 129–136.
- 15 C. Rücker and K. Kümmerer, *Chem. Rev.*, 2015, **115**, 466–524.
- 16 A. Labouriau, C. Cady, J. Gill, D. Taylor, A. Zocco, J. Stull, K. Henderson and D. Wroblewski, *Polym. Degrad. Stab.*, 2015, **117**, 75 – 83.
- 17 M. P. Kroonblawd, N. Goldman and J. P. Lewicki, *J. Phys. Chem. B*, 2019, **123**, 7926–7935.
- 18 S. D. Bruck and E. P. Mueller, *J. Biomed. Mater. Res. Appl. Biomater.*, 1988, **22**, 133–144.
- 19 J. C. Almeida, J. Lancastre, M. H. V. Fernandes, F. M. A. Mar-gaça, L. Ferreira and I. M. M. Salvado, *Mater. Sci. Eng. C*, 2015, **48**, 354 – 358.
- 20 A. Charlesby and F. A. Freeth, *Proc. R. Soc. Lond. A*, 1955, **230**, 120–135.
- 21 A. A. Miller, *J. Am. Chem. Soc.*, 1960, **82**, 3519–3523.
- 22 H. A. Dewhurst and L. E. S. Pierre, *J. Phys. Chem.*, 1960, **64**, 1063–1065.
- 23 D. J. Hill, C. M. Preston and A. K. Whittaker, *Polymer*, 2002, **43**, 1051–1059.
- 24 A. M. Bueche, *J. Polym. Sci.*, 1956, **19**, 297–306.
- 25 D. R. Squire and D. T. Turner, *Macromol.*, 1972, **5**, 401–404.
- 26 G. B. Tanny and L. E. S. Pierre, *Int. J. Polym. Mater.*, 1972, **1**, 279–293.
- 27 A. V. Tobolsky, *Silicon in organic, organometallic, and polymer chemistry*, Wiley, New York, USA, 1960.
- 28 J. N. Rodriguez, C. T. Alviso, C. A. Fox, R. S. Maxwell and J. P. Lewicki, *Macromol.*, 2018, **51**, 1992–2001.
- 29 E. A. Nikitina, V. D. Khavryutchenko, E. F. Sheka, H. Barthel and J. Weis, *J. Phys. Chem. A*, 1999, **103**, 11355–11365.
- 30 G. V. Gibbs, D. Jayatilaka, M. A. Spackman, D. F. Cox and K. M. Rosso, *J. Phys. Chem. A*, 2006, **110**, 12678–12683.
- 31 E. M. Lupton, F. Achenbach, J. Weis, C. Bräuchle and I. Frank, *J. Phys. Chem. B*, 2006, **110**, 14557–14563.
- 32 E. M. Lupton, F. Achenbach, J. Weis, C. Bräuchle and I. Frank, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2007, **76**, 125420.
- 33 S. Nangia and B. J. Garrison, *J. Phys. Chem. A*, 2008, **112**, 2027–2033.
- 34 E. M. Lupton, F. Achenbach, J. Weis, C. Bräuchle and I. Frank, *ChemPhysChem*, **10**, 119–123.
- 35 J. M. Rimsza, J. Yeon, A. C. T. van Duin and J. Du, *J. Phys. Chem. C*, 2016, **120**, 24803–24816.
- 36 K. Nordlund, S. J. Zinkle, A. E. Sand, F. Granberg, R. S. Aver-back, R. E. Stoller, T. Suzudo, L. Malerba, F. Banhart, W. J. Weber, F. Willaime, S. L. Dudarev and D. Simeone, *J. Nucl. Mater.*, 2018, **512**, 450 – 479.
- 37 T. M. Alam, *Radiat. Phys. Chem.*, 2001, **62**, 145–152.
- 38 M. Patel, P. Morrell, J. Cunningham, N. Khan, R. S. Maxwell and S. C. Chinn, *Polym. Degrad. Stab.*, 2008, **93**, 513 – 519.
- 39 M. P. Kroonblawd, F. Pietrucci, A. M. Saitta and N. Goldman, *J. Chem. Theory Comput.*, 2018, **14**, 2207–2218.
- 40 M. Elstner, D. Porezag, G. Jungnickel, J. Elsner, M. Haugk, T. Frauenheim, S. Suhai and G. Seifert, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1998, **58**, 7260 – 7268.
- 41 P. Koskinen and V. Mäkinen, *Comput. Mater. Sci.*, 2009, **47**, 237 – 253.
- 42 B. Aradi, B. Hourahine and T. Frauenheim, *J. Phys. Chem. A*, 2007, **111**, 5678 – 5684.
- 43 W. Kohn and L. J. Sham, *Phys. Rev.*, 1965, **140**, A1133 – A1138.
- 44 J. C. Slater and G. F. Koster, *Phys. Rev.*, 1954, **94**, 1498 – 1524.
- 45 A. K. Rappe, C. J. Casewit, K. S. Colwell, W. A. Goddard III and W. M. Skiff, *J. Am. Chem. Soc.*, 1992, **114**, 10024–10035.
- 46 N. D. Mermin, *Phys. Rev.*, 1965, **137**, A1441 – A1443.
- 47 A. M. N. Niklasson, C. J. Tymczak and M. Challacombe, *Phys. Rev. Lett.*, 2006, **97**, 123001.
- 48 A. M. N. Niklasson, *Phys. Rev. Lett.*, 2008, **100**, 123004.
- 49 A. M. N. Niklasson, P. Steneteg, A. Odell, N. Bock, M. Challa-combe, C. J. Tymczak, E. Holmström, G. Zheng and V. Weber, *J. Chem. Phys.*, 2009, **130**, 214109.
- 50 G. Zheng, A. M. N. Niklasson and M. Karplus, *J. Chem. Phys.*, 2011, **135**, 044122.
- 51 S. Plimpton, *J. Comput. Phys.*, 1995, **117**, 1 – 19.
- 52 S. Nosé, *J. Chem. Phys.*, 1984, **81**, 511 – 519.
- 53 W. G. Hoover, *Phys. Rev. A: At., Mol., Opt. Phys.*, 1985, **31**, 1695 – 1697.
- 54 J. Lehtola, M. Hakala, J. Vaara and K. Hämäläinen, *Phys. Chem. Chem. Phys.*, 2011, **13**, 5630–5641.
- 55 M. P. Kroonblawd and T. D. Sewell, *J. Phys. Chem. C*, 2016, **120**, 17214–17223.
- 56 M. P. Kroonblawd, B. W. Hamilton and A. Strachan, *J. Phys. Chem. C*, 2021, **125**, 20570–20582.
- 57 E. Chen, Q. Yang, V. Dufour-Décieux, C. A. Sing-Long, R. Fre-itas and E. J. Reed, *J. Phys. Chem. A*, 2019, **123**, 1874–1881.
- 58 B. M. Rice, W. D. Mattson, J. P. Larentzos and E. F. C. Byrd, *J. Chem. Phys.*, 2020, **153**, 064102.
- 59 M. Hutchings, J. Liu, Y. Qiu, C. Song and L.-P. Wang, *J. Chem. Theory Comput.*, 2020, **16**, 1606–1617.

- 60 M. N. Sakano, A. Hamed, E. M. Kober, N. Grilli, B. W. Hamilton, M. M. Islam, M. Koslowski and A. Strachan, *J. Phys. Chem. A*, 2020, **124**, 9141–9155.
- 61 F. Pietrucci and W. Andreoni, *Phys. Rev. Lett.*, 2011, **107**, 085504.
- 62 A. Stukowski, *Model. Simul. Mater. Sci. Eng.*, 2010, **18**, 015012.
- 63 L. N. Pankratova, E. V. Saenko, V. L. Bugaenko and V. V. Makhlyarchuk, *Mendeleev Commun.*, 2011, **21**, 157 – 159.
- 64 M. Ormerod and A. Charlesby, *Polymer*, 1963, **4**, 459–470.
- 65 H. Menhofer and H. Heusinger, *Int. J. Radiat. Appl. Instrum. C*, 1987, **29**, 243–251.
- 66 J. F. Zack, E. L. Warrick and G. Knoll, *J. Chem. Eng. Data*, 1961, **6**, 279–281.
- 67 L. E. St. Pierre, H. A. Dewhurst and A. M. Bueche, *J. Polym. Sci.*, 1959, **36**, 105–111.
- 68 E. L. Warrick, *Ind. Eng. Chem.*, 1955, **47**, 2388–2393.
- 69 D. J. Hill, C. M. Preston, D. J. Salisbury and A. K. Whittaker, *Radiat. Phys. Chem.*, 2001, **62**, 11 – 17.
- 70 A. Charlesby, S. H. Pinner and F. P. Bowden, *Proc. R. Soc. Lond. A*, 1959, **249**, 367–386.
- 71 A. Maiti, W. Small, M. P. Kroonblawd, J. P. Lewicki, N. Goldman, T. S. Wilson and A. P. Saab, *J. Phys. Chem. B*, 2021, **125**, 10047–10057.
- 72 A. A. Miller, *J. Am. Chem. Soc.*, 1961, **83**, 31–36.