Order-Disorder Transition driven Superionic Conduction in the New Plastic Polymorph of $\text{Na}_4\text{P}_2\text{S}_6$

Tanja Scholz,^{†,||} Christian Schneider,^{†,||} Maxwell W. Terban,[†] Zeyu Deng,[‡]
Roland Eger,[†] Martin Etter,[¶] Robert E. Dinnebier,[†] Pieremanuele Canepa,^{*,‡,⊥}
and Bettina V. Lotsch^{*,§,†}

[†]*Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart,
Germany*

[‡]*Department of Materials Science and Engineering, National University of Singapore, 9
Engineering Drive 1, 117575, Singapore*

[¶]*German electron synchrotron (DESY), Notkestraße 85, Hamburg, 22607, Germany*

[§]*LMU Munich, Butenandstraße 5-13, 81377 Munich, Germany*

^{||}*Contributed equally to this work.*

[⊥]*Department of Chemical and Biomolecular Engineering, National University of
Singapore, Engineering Drive 4, 117585, Singapore*

E-mail: pcanepa@nus.edu.sg; b.lotsch@fkf.mpg.de

Abstract

Sodium thiophosphates are promising materials for large-scale energy storage applications benefiting from high ionic conductivities and the geo-political abundance of the elements. A representative of this class is $\text{Na}_4\text{P}_2\text{S}_6$, which currently shows two known polymorphs – α and β . This work describes a third polymorph of $\text{Na}_4\text{P}_2\text{S}_6$, γ , that forms above 580°C , exhibits fast-ion conduction with low activation energy, and is mechanically soft. Based on high-temperature diffraction, pair distribution function analysis, thermal analysis, impedance spectroscopy, and *ab initio* molecular dynamic calculations, the γ - $\text{Na}_4\text{P}_2\text{S}_6$ phase is identified to be a plastic crystal, characterized by dynamic orientational disorder of the $\text{P}_2\text{S}_6^{4-}$ anions on a translationally fixed body-centered cubic lattice. The prospect of stabilizing plastic crystals at operating temperatures of solid-state batteries and benefiting from their high ionic conductivities as well as mechanical properties could have a strong impact in the field of solid-state battery research.

The rich chemistry of thiophosphates is an excellent platform for solid-state chemistry to explore compounds with interesting and functional properties. The plethora of possible thiophosphate anions ranges from the tetrahedral ortho-thiophosphate PS_4^{3-} to larger units, such as, corner-sharing $\text{P}_2\text{S}_7^{4-}$ or $\text{P}_2\text{S}_6^{4-}$ having a P–P central bond. The ability of sulfur to form disulfur –S–S– bridges and the broad range of oxidation states of phosphorus allow for even larger, ring-like or square-shaped anions.^{1,2}

Many thiophosphate compounds containing alkaline metals are ion conductors. However, the number of highly conducting phases is still limited to a few well-known representatives, *e.g.* Na_3PS_4 . The as-prepared tetragonal (low temperature) structure of Na_3PS_4 shows a low ionic conductivity of around $4.2 \cdot 10^{-6} \text{ S cm}^{-1}$ (50 °C), but it can be improved up to $\sim 4.6 \cdot 10^{-4} \text{ S cm}^{-1}$ (room temperature) by stabilizing the high temperature cubic phase as a glass–ceramic.^{3–5} This was achieved by ball-milling the starting materials and subsequently annealing the glass at a low temperature of 270 °C to precipitate the cubic phase. Recently, Krauskopf *et al.* have suggested that the room-temperature stabilized cubic phase comprises tetragonal-like local-structure motifs.⁶

Another example of the phase-space flexibility of thiophosphates is $\text{Na}_4\text{P}_2\text{S}_6$.^{7,8} This material can be synthesized *via* a precipitation route, as well as by high-temperature solid-state synthesis.^{9,10} Depending on the preparation method, $\text{Na}_4\text{P}_2\text{S}_6$ crystallizes in the monoclinic polymorphs α - and β - $\text{Na}_4\text{P}_2\text{S}_6$.^{10,11} The polymorphs of $\text{Na}_4\text{P}_2\text{S}_6$, α and β , can also be transformed into each other by heating or annealing the sample. In this study, we identify a new high-temperature polymorph of $\text{Na}_4\text{P}_2\text{S}_6$, γ , which displays plastic crystal characteristics.

Plastic crystals are characterized by a high degree of reorientational freedom, often found for spherical molecules, or conformational freedom, often found for polymers, of a cationic, anionic, or neutral sub-lattice of a solid.^{12–14} The disordered species are translationally fixed, therefore maintaining the lattice. This renders the material a solid with weak interactions in the partly "molten" anion sub-lattice. A number of inorganic ion conductors show these characteristics, including ABH_4 ($\text{A} = \text{Li, Na, K, Rb, Cs}$)^{15–17} Li_2SO_4 ,^{18,19} LiAgSO_4 ,²⁰ LiNaSO_4 ,²¹

Li₄Zn(SO₄)₃,²¹ Na₃PO₄,^{22,23} Na₂AC₆₀ (A = K, Rb, Cs),^{24–26} Na₂B₁₂H₁₂,^{27–29} Na₂B₁₀H₁₀,³⁰ ACB₁₁H₁₂ (A = Li, Na),³¹ Li₂B₁₂H₁₂,²⁹ Rb₂B₁₀H₁₀,³² Na₃PS₄,³³ and Na₄Zn(PO₄)₂,³⁴ (sorted by publication year). All these examples contain rather globular-shaped anions with high point-group symmetries, such as I_h (*e.g.* B₁₂H₁₂²⁻ and C₆₀³⁻), D_{4d} (*e.g.* B₁₀H₁₀²⁻), or T_d (*e.g.* SO₄²⁻). This high intrinsic symmetry of the anion species lowers the sterical hindrance for fast reorientational motion.³⁵

Solid-state batteries require amongst other properties high intrinsic ion conductivity and a robust mechanical interface between the ion conductor and the electrodes. Plastic ion conductor materials can beneficially provide weaker cation–anion interactions and increased volumes that allow for easier ion transport. Furthermore, the ductility of the plastic phase can help to maintain better contact with the electrode and reduce physical degradation of the interface during cycling. A major caveat is that plastic phase transitions in ion conductors are often observed at high temperatures, which impedes their application in real devices. Thus, it is vital to better understand the nature and formation behavior of plastic crystals, to inform strategies for rationally lowering the transition temperature toward ambient conditions. Here, we discover the new γ polymorph of Na₄P₂S₆ which exhibits fast Na⁺ conduction with a low activation energy, a cubic crystal structure, and plastic crystal characteristics. The plastic phase transition is driven by the reorientational freedom of the elongated thiophosphate anion P₂S₆⁴⁻, rendering Na₄P₂S₆ the first example of a salt based on a prolate complex anion showing plastic crystal behavior.

Variable-temperature powder X-ray diffraction (PXRD) experiments were performed on Na₄P₂S₆ well above the α – β phase transition at 160 °C.¹¹ A new set of Bragg peaks is observed to emerge at 580 °C, as shown in Figure 1. The diffraction peaks of β -Na₄P₂S₆ and the new crystalline phase coexist up to 585 °C (measured every 5 K), at which point the β phase disappears. This suggests the existence of a third polymorph of Na₄P₂S₆, which we refer to as γ -Na₄P₂S₆. Upon cooling, the transition is reversible with the reformation of β -

and α - $\text{Na}_4\text{P}_2\text{S}_6$.

Figure 1: Variable temperature PXRD of $\text{Na}_4\text{P}_2\text{S}_6$ upon heating (bottom) and cooling (top) across the β – γ phase transition: contour plot of diffractograms (the color code, red to purple/blue, indicates the ranges from low to high diffraction intensities, respectively) and exemplary diffractograms (black) at 520 °C (β), 620 °C (γ), and 520 °C (β after heating above the phase transition). The selected diffractograms are additionally depicted in Figure S1.

Several remarkable features of the PXRD patterns of γ - $\text{Na}_4\text{P}_2\text{S}_6$ are discussed in the following (labelled (i)–(v)). These points lead us to conclude that γ is a newly observed member of the plastic crystal family.

- (i) The Bragg peaks of γ - $\text{Na}_4\text{P}_2\text{S}_6$ can be indexed to the cubic space group $Im\bar{3}m$ (no. 229) with a lattice parameter of 8.4509(3) Å at 580 °C. However, this high symmetry is not compatible with the ethane-like D_{3d} configuration of the $\text{P}_2\text{S}_6^{4-}$ anions, suggesting that the anions cannot be crystallographically oriented in the structure. This observation suggests that some kind of static or dynamic disorder is present in the anion orientations.
- (ii) The β – γ phase transition is accompanied by a large increase in diffuse scattering inten-

sities, and the observed Bragg peak intensities rapidly decrease and disappear at higher angles. The diffuse scattering can be due to significant disorder, which could result for instance from different anion orientations, and lead to the destructive interference of higher order diffraction components. These are common features observable in the plastic crystal materials mentioned above.

- (iii) The β to γ phase transition is accompanied by an unusually high increase in the volume of the unit cell, from $575.4 \text{ \AA}^3$ to $603.8 \text{ \AA}^3/\text{f.u.}$ (assuming $Z = 2$ for γ). This gives an increase of $\sim 4.9\%$ (see Figure 2a), which compares well to *e.g.* $\sim 3.2\%$ for the monoclinic to cubic transition in Li_2SO_4 and $\sim 10\%$ for the cubic to orthorhombic transition in Na_3PS_4 .
- (iv) A considerable hysteresis of $\sim 30 \text{ K}$ in the β - γ transformation is observed from the diffraction data between heating and cooling, comparable to 40 K in Li_2SO_4 and 40 K in Na_3PS_4 .
- (v) After cooling γ - $\text{Na}_4\text{P}_2\text{S}_6$, preferred orientation, manifested in relative intensity changes, is observed for the subsequent β and α phases (see Figure 1 and EIS). Similar behavior is also observed for Li_2SO_4 and γ - Na_3PS_4 .

The phase transitions in $\text{Na}_4\text{P}_2\text{S}_6$ were additionally studied with differential scanning calorimetry (DSC) as shown in Figure 2b, using a much faster heating rate (20 K min^{-1}) than in the diffraction experiments. Overall, the DSC data confirm all three transitions $\alpha \rightarrow \beta$ (160°C), $\beta \rightarrow \gamma$ (580°C), and γ to the melt ($\sim 800^\circ\text{C}$), and back. Additional PXRD patterns of α -, β -, γ - and molten $\text{Na}_4\text{P}_2\text{S}_6$ are displayed in Figure S2. The $\alpha \rightarrow \beta$ phase transition involves very small atomic rearrangements and shows a correspondingly small latent heat of $\sim 8.7 \text{ J/g}$.¹¹ In contrast, the $\beta \rightarrow \gamma$ transition has a latent heat corresponding to about half that of the melting transition ($\sim 60 \text{ J/g}$ vs. $\sim 90\text{--}120 \text{ J/g}$). This implies that substantial structural rearrangements are now required to form the γ phase. Other known plastic phase transitions also exhibit latent heats of this magnitude, for example, 214 J/g

Figure 2: **a** Temperature-dependent volume expansion and contraction across the $\beta \rightarrow \gamma$ phase transition relative to the room temperature unit cell volume V_{rt} of $\text{Na}_4\text{P}_2\text{S}_6$. **b** Differential scanning calorimetry (DSC) curve.

in Li_2SO_4 or 150 J/g in Na_3PS_4 . While the $\beta \rightarrow \gamma$ phase transition is observed at the same temperature as in the diffraction experiments (580 $^{\circ}\text{C}$), the hysteresis on cooling appears much larger, ~ 60 K. This could suggest kinetic limitations for the transformation back to the β phase.

To check if the $\text{P}_2\text{S}_6^{4-}$ anion undergoes any structural change during the $\beta \rightarrow \gamma$ transition, we measured high-temperature Raman spectra. The spectra of Figure S3 display no change in the local D_{3h} anion symmetry from $\beta \rightarrow \gamma$ - $\text{Na}_4\text{P}_2\text{S}_6$, supporting the assumption of an intact

$\text{P}_2\text{S}_6^{4-}$ unit at high temperature.

A direct structural solution of the γ -phase from the PXRD pattern is complicated by the incompatibility between the observed space group symmetry and the lower symmetry of the $\text{P}_2\text{S}_6^{4-}$ anions. Therefore, we turned to the pair distribution function (PDF) analysis^{36,37} of synchrotron diffraction data to determine possible configurations to describe the local structure. Figure 3a shows the experimental PDF of $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ at $\sim 600^\circ\text{C}$. Sharp peaks observed at 2.048 and 3.392 Å can be indexed to P–P/P–S and S–(P–)S/S–(P–)P atom-pair distances within the $\text{P}_2\text{S}_6^{4-}$ anion. Another sharp peak at 2.801 Å can be assigned to the nearest-neighbor Na–S atom pairs. Interestingly, the peaks expected to correspond to pairs of S atoms located at opposite ends of the anion are not distinctly observed, which may suggest disorder of the anion dihedral angle.

Above 6 Å, the features in the PDF are broad and low-intensity, in contrast to the PDFs measured for the α and β phases (see ESI Figure S4a,b,d vs. S4c for comparison). In line with the body centered cubic (BCC) space group from indexing, a pseudo-cubic model was constructed, with $P1$ space group symmetry, in which the $\text{P}_2\text{S}_6^{4-}$ anion barycenters are translationally fixed on the lattice points. The rotational orientations about the lattice points were allowed to refine freely against the experimental PDF data. A single cell model ($Z' = 2$) gives good agreement to short-range distances and indicates that neighboring anions prefer not to align in the same orientation. However, the model fails when r is greater than the lattice parameter due to the fixed geometry of the second nearest neighbor anions. A $2 \times 2 \times 2$ supercell ($Z' = 16$) was further constructed to test against the data at longer distances. This model allows for a much larger distribution of relative anion orientations sampled at any given distance and also showed good agreement to the data up to approximately 16 Å. Overall, the data at higher distances prefer models with more orientational disorder. This suggests weak or no correlation between relative anion orientations at long distances (see ESI Figure S5).

In order to generate a complete model that is compatible with the data, 8 Na sites were

Figure 3: **a** Experimental synchrotron PDF with PDFs simulated from the fitted structure model and $\text{P}_2\text{S}_6^{4-}$ anion only and **b** Rietveld fit of the PXRD pattern for $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ at 600°C . **c** Illustration of the PDF-refined γ -structure with a static approximation of the $\text{P}_2\text{S}_6^{4-}$ anions in a $2\times 2\times 2$ cell, and **d** in a single unit cell. **e** Overlay of bond valence energy landscape (red surface) and the crystal structure visualising the 3-dimensional Na^+ conducting pathways.

introduced to the single cell model (64 Na sites to the supercell model), and allowed to refine with restraints set for the distances of closest approach: $2.5\text{ \AA}$ (Na-S), $3.4\text{ \AA}$ (Na-P), and $3.5\text{ \AA}$ (Na-Na). A unique set of positions could not be determined, but the refinements preferred the Na atoms to distribute throughout the “interstitial” space around the structure-forming anions, optimizing to give the best agreement to the preferred Na-S neighbor distance. The good agreement between simulated and experimental PDFs and resulting structure are shown in Figures 3(a,c,d).

Inspired by the real-space model, Rietveld refinements were performed using the space group $Im\bar{3}m$ with a single anion fixed at the origin, giving 48 anions each at the corner and

body center position (mirroring free rotation of the anions averaged over all unit cells). The occupancy was fixed to $\frac{1}{48}$. Then Na atom sites were sequentially added and refined until the Bragg peaks could be reproduced. This resulted in 2 symmetry independent sites giving 96 positions each, with the occupancies constrained to give the expected stoichiometry (details in the Experimental Section). Similar to the model from PDF refinement, the Na atoms again distribute to fill the “interstitial” space around the structure-forming anions. The Rietveld fit is shown in Figure 3b. By comparison of the $Im\bar{3}m$ model to higher distances in real-space (see ESI figure S5), it is found to accurately reproduce the on-average pair-density fluctuations beyond $\sim 8 \text{ \AA}$.

For the real-space refinements, it was necessary to set up the models with separate intra- and intermolecular atomic displacement parameters to properly describe the correlated motion.³⁸ To test for disorder within the anions, separate parameters were defined to describe the peak widths of different atom-pair types.³⁹ We found that correlations between opposing S–S pairs were broader than other atom-pair contributions by a factor of more than 2, which further supports the hypothesis of torsional distortions (along the P–P bond) of the anions.

In a complementary approach to locate and count low-energy sites and possible migration pathways for Na^+ , softBV (bond valence) analysis^{40,41} was conducted for the PDF-derived static approximation in a $2 \times 2 \times 2$ cell. Figure 3e illustrates the BV landscape and reveals many of the possible interstitials that exceed the number of Na^+ by far. Therefore, the crystal structure offers a high number of vacancies, which are beneficial for fast ion conduction. A large number of alternative pathways can be found in this structure with energy barriers of comparable barrier heights of $\sim 230 \text{ meV}$.

After obtaining insights into the ion transport pathways of $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ *via* BV modelling, an experimental characterization was attempted. Therefore, high-temperature electrochemical impedance spectroscopy (EIS) measurements were performed on pellets of $\text{Na}_4\text{P}_2\text{S}_6$. The malleability of $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ resulted in pellets being deformed under the slightest contact pressure, changing their thickness as a result, and even leaking out of the set-up. Addition-

Figure 4: **a** Arrhenius plot of ionic conductivity and activation energies derived from impedance spectroscopy. The heating and cooling segments are indicated by orange and blue circles. The error bars arise from the standard deviation of ionic conductivity measured on three distinct pellets. **b** Mean-squared displacements (MSD) of Na, P, and S at 1000 K from AIMD simulations. **c** Arrhenius plot of the ionic conductivity and activation energy from AIMD simulations.

ally, the chemically aggressive nature of $\text{Na}_4\text{P}_2\text{S}_6$ had major implications on the corrosion of electrodes and contacts within shortest amounts of time. Contrary to good EIS measuring practice, the data shown here were obtained with low contact pressures on the pellets, short equilibration time and low temperature-step density, but, nevertheless, highlight the characteristics of the phase transition. The results of the measurement are presented in the Arrhenius plot of Figure 4a (see ESI figure S8 for exemplary spectra). For $\beta\text{-Na}_4\text{P}_2\text{S}_6$ (520 $^{\circ}\text{C}$ to 578 $^{\circ}\text{C}$), an activation energy of 562(48) meV was found, which is slightly higher than the previously reported value obtained in measurements at lower temperature.¹¹ The $\beta \rightarrow \gamma$ transition at around 580 $^{\circ}\text{C}$ causes an abrupt increase in the ionic conductivity from 92(11) mS cm^{-1} to 140(12) mS cm^{-1} . The order of magnitude in ionic conductivities for β - and $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ is comparable to Na_3PS_4 , where the $\beta \rightarrow \gamma$ transition at 500 $^{\circ}\text{C}$ is accompanied with a jump from $\sim 40 \text{ mS cm}^{-1}$ to $\sim 400 \text{ mS cm}^{-1}$.³³ $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ exhibits a lower activation energy of about 89(18) meV, much lower than the BV calculated value on a rigid model, but comparable to $\gamma\text{-Na}_3\text{PS}_4$ (110(10) meV).³³ The behavior of ionic conduction is reversible on cooling, with a similar hysteresis of $\sim 40 \text{ K}$ as found in the diffraction experiments. The ex-

tracted ionic conductivities upon cooling the pellet are higher than for heating. This unusual behavior can be explained by accelerated decomposition of $\text{Na}_4\text{P}_2\text{S}_6$ at elevated temperatures. The visual appearance of the pellet changed from initially white (Image S7a) to dark gray (Image S7b) after cooling down. A microscopy image of the corroded platinum electrode after the EIS measurement is depicted in Figure S7c, showing the aggressive nature of the γ phase. Presumably, $\text{Na}_4\text{P}_2\text{S}_6$ reacts with the Pt electrodes and forms some electronically conducting phases that increase the conductivity, leading to apparent lower activation energies compared to the heating cycle. Hence, the extraction of a true activation energy for ionic motion is vitiated for the cooling cycle. Extrapolating the linear Arrhenius behavior of $\gamma\text{-Na}_4\text{P}_2\text{S}_6$ to 25 °C results in a room-temperature ionic conductivity of 50(24) mS cm^{-1} , similar to the findings of Famprakis *et. al.* for Na_3PS_4 .³³ Despite our efforts to rapidly quench $\text{Na}_4\text{P}_2\text{S}_6$ from high temperature, we were not successful in stabilizing the cubic γ phase at room temperature.

So far, the experimental results strongly suggest plastic behavior of $\gamma\text{-Na}_4\text{P}_2\text{S}_6$, but do not yet distinguish a dynamic versus static nature of the rotational disorder of the $\text{P}_2\text{S}_6^{4-}$ anions. Therefore, the atomic motions of Na^+ and $\text{P}_2\text{S}_6^{4-}$ were tested using *ab initio* molecular dynamics (AIMD) simulations in the temperature range of 600–1200 K, using the PDF-derived $2\times 2\times 2$ model as a starting point for optimization and subsequent MD calculations. The average mean-squared displacement of the atoms of Figure 4b supports the significant mobility of all Na^+ , while P and S atoms do not undergo long-range motion. The calculated activation energy for Na^+ migration above 800 K is 223 meV, though is again much higher than the experimentally obtained activation barrier (89(18) meV). At 600 K, much below the experimental phase transition (~ 850 K), the Na^+ diffusivity is many orders of magnitude smaller.

To determine the possibility for dynamic rotational motion of $\text{P}_2\text{S}_6^{4-}$ anions, the P–P bond orientations were tracked during the AIMD simulations. The individual anions were placed into a reference frame with one P atom fixed to the origin of a Cartesian coordinate

Figure 5: **a** Scheme of the definition of the azimuthal angle (ϕ) and polar angle (θ) with respect to the P–P handle, and scheme of the P–P orientation in Cartesian octants. **b** Orientation heatmap of all $\text{P}_2\text{S}_6^{4-}$ in a $2 \times 2 \times 2$ cell at 1000 K in a 300 ps simulation. **c** Azimuthal angle (ϕ) and **d** polar angle (θ) as a function of time of an exemplary $\text{P}_2\text{S}_6^{4-}$ at 1000 K.

system that aligns with the unit cell axes (see Figure 5a, top left). Then, the orientations were expressed in terms of polar coordinates as a function of azimuthal (ϕ) and polar (θ) angles. Visually, the chosen origin divides the possible orientations into eight octants as depicted in Figure 5a. The initial orientations, defined to have $\theta < 90^\circ$, are marked as orange dots in Figure 5b, and the final distribution is plotted as a 2D histogram (see Figure S10 for other simulation temperatures). Because the anions rotate about their center of mass, rather than the P atom fixed at the origin of the reference frame, octants related by inversion signify the same orientation of the P–P handle with respect to the crystal lattice (but with inverted P atoms). Note that with each simulation frame (*i.e.* reorientational motion of the $\text{P}_2\text{S}_6^{4-}$ anion), the reference frame origin changes with respect to the crystal lattice, such that the center of mass of the P–P handle remains translationally fixed. Thus, the ensuing population of these initially empty octants indicates that significant reorientation of individual anions occurs. Figure 5c and d illustrate the polar coordinates of an exemplary anion from the AIMD simulations at 1000 K and enable the derivation of reorientation times of ~ 20 – 100 ps. Here, a direct comparison to plastic phases of sodium *closo*-borane $\text{Na}_2\text{B}_{12}\text{H}_{12}$ can be made: Just above the first-order transition from the low- T monoclinic to the high- T cubic phase near 520 K, the reorientational jump rate τ^{-1} , derived from NMR experiments, is 10^{11} Hz (equal to 10 ps),²⁷ a comparable value to the $\text{P}_2\text{S}_6^{4-}$ reorientations, although the different

shape and size of the anions should be taken into account. Meanwhile, the Na^+ short-ranged hopping (not necessarily long-ranged diffusion) was calculated to be ~ 0.6 ps at 1000 K (see ESI, Figure S13), two orders of magnitude faster than the anion motion.

The orientation distribution suggests that the anions prefer to point roughly along the four body diagonals of their respective unit cells. This is in agreement with the on-average ($Im\bar{3}m$) structure obtained from Rietveld refinement, where the P–P bonds of all orientations on the lattice point overlap to form a roughly cubic distribution that is co-oriented with the crystallographic cell (see ESI). The results suggest that dynamic reorientation of the $\text{P}_2\text{S}_6^{4-}$ units occurs, consisting primarily of hops between the four body diagonal orientations of the cubic lattice. Unsurprisingly, the frequency of the $\text{P}_2\text{S}_6^{4-}$ reorientation increases with the simulation temperature. Further analysis of this behavior suggests that reorientation of one anion does not necessarily induce a change in its neighbors’ orientations.

The conformational freedom of the $\text{P}_2\text{S}_6^{4-}$ anions was also investigated. Rotation around the PS_3 – PS_3 bond is possible (see figure S11), similar to ethane and its derivatives. The initial anions had a *gauche* conformation ($(|\angle| = 60^\circ)$ as observed in the α and β crystal structures. To capture the evolution of the $\text{P}_2\text{S}_6^{4-}$ dihedral angle for the ensemble of anions, we counted the number of dihedral angles for different time scales. The histogram plots depicted in Figure S11b,b,e and f show an increase in the *anti* ($|\angle| = 180^\circ$), and Figure S12 show the time evolution of the dihedral angle of three randomly chosen S–P–P–S units. Although rotations around the P–P axis are observed, some anions showed no conformational reorientation on the 300 ps time scale. The likelihood for rotation around the P–P bond of the anions is supported by the lack of sharp correlations between the S–P–P–S atom-pairs in the experimental PDF and the corresponding need for significantly broadening these contributions in fitting the model.

In this work we have identified a new high-temperature phase transition at 580 °C in the thiophosphate Na ion conductor $\text{Na}_4\text{P}_2\text{S}_6$. The phase transition is accompanied by a large

latent heat, a change in crystal structure (from monoclinic $C2/m$ to cubic $Im\bar{3}m$), as well as a jump in sodium ion transport properties. A structure model with $P_2S_6^{4-}$ anions occupying the BCC lattice points was derived from pair distribution function analysis. The PDF structure model was used to simulate cation and anion dynamics with *ab initio* molecular dynamics. We demonstrate that while sodium shows a high diffusion coefficient in the AIMD simulation, the $P_2S_6^{4-}$ anions form a translationally fixed sub-lattice characterized by orientational disorder and the ability to dynamically reorient, primarily between the four body diagonal directions. $Na_4P_2S_6$ is malleable at high temperature and mechanically deforms under even slight compressive stress: a property in solid ion conductors that is unique to plastic phases. Altogether, the evidence suggests that γ - $Na_4P_2S_6$ is a new member of the plastic ionic conductors.

Despite the advantageous mechanical and conduction properties of plastic ion conductors, the temperatures needed to stabilize these phases are still far too high for operation in solid-state batteries. A key goal in solid-state battery chemistry is thus to stabilize such plastic phases at close to ambient temperature. Thus, further search and a detailed understanding of the underlying structure–property relationships of such phases will be necessary to identify plastic phases with lower transition temperatures.

$\text{Na}_4\text{P}_2\text{S}_6$ can be prepared using two different synthesis routes. A solid-state reaction as described in Ref.¹⁰ yields a very crystalline powder from which also single crystals can be extracted. Further, the solution synthesis *via* the hydrated compound $\text{Na}_4\text{P}_2\text{S}_6 \cdot 6\text{H}_2\text{O}$ as in Ref.⁹ gives a powder product with stacking faults. The latter anneals above 500 °C to a product very similar to the solid-state material. The structural differences are discussed in detail in Ref.¹¹ The $\beta \rightarrow \gamma$ phase transition is not affected by the $\text{Na}_4\text{P}_2\text{S}_6$ synthesis.

Variable temperature powder X-Ray diffraction (PXRD) patterns were measured using a STOE StadiP diffractometer (Mo- $K\alpha_1$ radiation ($\lambda = 0.7093 \text{ \AA}$), curved germanium (111) monochromator, DECTRIS Mythen2R 1K detector) with a STOE capillary furnace in Debye-Scherrer geometry. Fine powdered samples were filled in quartz glass capillaries of 0.5 mm diameter by HILGENBERG and sealed under argon. Data collection was done in the range from 2° to 62° 2θ with a step size of 0.015° in the temperature range of 510, 650, and 440 °C in steps of 5 K around the immediate $\beta \rightarrow \gamma$ phase transition and 10 K for more distant temperatures. The indexing of the powder patterns was performed with JANA2006⁴² in space groups $C/2m$ and $Im\bar{3}m$ for β - and γ - $\text{Na}_4\text{P}_2\text{S}_6$, respectively. Errors of the results of the Rietveld refinements are specified as 3σ .

Total scattering measurements were carried out using beamline P02.1 at PETRA III of the Deutsches Elektronen-Synchrotron (DESY). Data were collected in rapid acquisition mode⁴³ with a large-area 2D PerkinElmer detector (2048×2048 pixels, 200×200 μm^2 each) and sample-to-detector distance of 311.36 mm. The incident energy of the X-rays was 59.772 keV ($\lambda = 0.20743 \text{ \AA}$). Samples were loaded into 0.7 mm diameter quartz glass capillaries and measured at roughly 30 and 100–650 °C in increments of 50 °C. An empty capillary was measured to account for the background, and a LaB_6 standard was measured at room temperature for calibration of the setup. Sample temperature was controlled using a custom ceramic heater operated using a Eurotherm 2408 temperature-controller. Calibration, polarization correction, and azimuthal integration to 1D diffraction patterns were performed using the software pyFAI.⁴⁴ Further correction, background subtraction, and normalization of the

1D diffraction intensities were carried out to obtain the total scattering structure function, $F(Q)$, which was Fourier transformed to the PDF, $G(r)$, using PDFgetX3 within xPDF-suite.^{45,46} The maximum value of the momentum transfer Q used in the Fourier transform was $19.5 \text{ \AA}^{-1}$.

Additional total scattering measurements were performed using a Stoe Stadi-P diffractometer with $\text{Ag-}K\alpha_1$ radiation ($\lambda = 0.55941 \text{ \AA}$), a Ge(111) Johann monochromator, and an array of three DECTRIS Mythen 1K detectors in Debye-Scherrer geometry. Data were directly corrected for the 2θ offset of the instrument, polarization, and background scattering.

Pair distribution function (PDF) refinements were carried out using TOPAS Academic v6.^{47,48} In all refinements, the $\text{P}_2\text{S}_6^{4-}$ anions were set up as rigid bodies defined by the P–P and P–S bond lengths and P–P–S bond angle and fixed at the lattice points, and allowed to rotate freely about their center of mass. When added, Na atom positions were allowed to refined with anti-bump constraints set to prevent unrealistic distances. PDF refinements were performed in $P1$ symmetry with either two separate anions (single cell model) refined up to $1.5\text{--}7 \text{ \AA}$, or sixteen separate anions (supercell model) refined $1.5\text{--}16 \text{ \AA}$. The damping of the experimental signal due to instrumental resolution and effects of data truncation were accounted for and fixed, and the lattice parameter and scale factor were refined. B_{iso} was fixed to $2.0 \text{ \AA}^2$ for S and P atoms, and separate intramolecular pair linewidths were described with five parameters corresponding to P–P, bonding P–S, adjacent S–S, non-bonding P–S, and opposing S–S, to account for intra-anion disorder.³⁹ Since Na atoms only show correlation at short distances, the partial pair widths were described using an empirical function ($x_1 + x_2r + x_3r^2$) that allows for high correlation with neighbor atoms at short distances and progression to low structural correlation at higher distances.

Rietveld refinements^{49,50} were performed with the $Im\bar{3}m$ model refined over a range of $4 - 28^\circ 2\theta$. The background was described using Chebychev polynomials of 19th order. The Lorentz-Polarization factor was set to 9.825. A zero-error correction was refined to correct for detector offset, and a simple axial model was used to describe the instrumental

peak shape along with Gaussian and Lorentzian components for crystallite size and strain broadening. The lattice parameter, global scaling factor, and two separate isotropic displacement parameters for Na and S/P were additionally refined. Convergence of the reciprocal- and real-space refinements was achieved using the global optimization method of simulated annealing in real space.⁵¹

For Differential Scanning Calorimetry (DSC) measurements 50 mg of fine powdered sample were sealed in quartz ampules (6 mm diameter, 10 to 15 mm in height) under vacuum. For improved heat flow ampules with a flat bottom were used. DSC measurements were performed on a NETZSCH STA 449 F5 Jupiter in a temperature range of 30 °C to 850 °C. The heating rate for all segments was set to 20 K min⁻¹. Data evaluation was performed using the NETZSCH software package PROTEUS.

Electrochemical impedance spectroscopy (EIS) measurements were performed using a NOVOCONTROL TECHNOLOGIES Alpha-A analyzer. For sample preparation fine powder of Na₄P₂S₆ (ca. 70 mg) was pressed uniaxially at 1 GPa into pellets of 6 mm diameter. Both sides of the pellets were sputtered with Platinum to ensure electrical contact during the high-temperature impedance measurement. Pellets were placed between two Lithium ion blocking Platinum electrodes and loaded onto an in-house built cell. To prevent the deformation of the pellet due to mechanical softening in the γ phase, the pellet was placed in a hole in a ceramic spacer of 1 mm height. This has proven to give reproducible results that are only affected by sample decomposition and corrosion of the electrode by sulfur at high temperature. The equilibration time prior to each impedance measurement at the programmed temperature steps was set to 15 m. A short equilibration time translates into a shorter time the sample is exposed to high temperatures. This was necessary as the sample decomposes within in day at 600 °C or above. On the other hand, short equilibration times bear the difficulty of measuring in a non-equilibrium state, that can result in visible drifts in long impedance measurements. Hence, the spectra were recorded in a frequency range of 1 MHz to 10 Hz and with an applied voltage of $V_{RMS} = 100$ mV. The spectra were

recorded between 500 °C and 640 C. Data treatment and evaluation was performed using the RHD INSTRUMENTS software package RelaxIS 3. To check data reliability Kramers-Kronig relation tests were performed prior to fitting. Fitting the impedance spectra to equivalent circuits was done by weighting the data points proportionally. Given error bars stem from error propagation of uncertainties in pellet geometric area, pellet thickness, and applied temperature as well as errors in resistance obtained by equivalent circuit fitting.

Temperature dependent Raman spectra were recorded using a Jobin Yvon Type 010 labram single grating spectrometer equipped with a double super razor edge filter. Data collection was performed with a peltier cooled CCD camera (spectral resolution: 1 cm⁻¹).

DFT simulations were performed using the Vienna *ab initio* Simulation Package.^{52,53} The unknown exchange correlation energy in DFT was approximated by the generalized gradient approximation,⁵⁴ and van der Waals forces were captured using the Grimme scheme.⁵⁵ Valence electrons were expanded as plane-waves with a maximum kinetic energy of 520 eV, and DFT total energies integrated at the Γ -point. Core electrons were described with projected augmented wave potentials,^{56,57} treating the following electrons explicitly: Na ($2s^1$), S ($3s^23p^4$) and P ($3s^23p^3$).

Starting from the PDF-derived crystal structures of γ -Na₄P₂S₆ ($2 \times 2 \times 2$ cell), all P₂S₆⁴⁻ units were oriented along the $\langle 111 \rangle$ directions and being perpendicular with each other in the (100) and (010) planes. Then a structure optimization was performed until the interatomic forces less than 0.01 eV/Å while keeping the cell volume fixed to that derived from the temperature dependent diffraction experiments.

Using the DFT-optimized γ -Na₄P₂S₆ model, canonical (NVT) ensemble *ab initio* molecular dynamics (AIMD) simulations were performed at selected temperatures of 600, 800, 900, 1000 and 1200 K, respectively. The NVT ensemble was achieved via a Nosé-Hoover thermostat^{58,59} with a 2 fs time step. The simulations were initialized at 100 K, and temperatures were ramped to target values within 2 ps. MD runs were performed with a production time of 600 ps (for 600 and 800 K) and 300 ps (for 1000 and 1200 K). Trajectories were collected

for the data analysis excluding the initial period of 20 ps for equilibration.

The following file is available free of charge.

- **gamma-Na₄P₂S₆-ESI**: Additional details on diffraction experiments, Raman spectroscopy, pair distribution function analysis, impedance spectroscopy, photographs of impedance samples, and AIMD simulation results.

Bettina V. Lotsch - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany; LMU Munich, Butenandstraße 5-13, 81377 Munich, Germany.
Email: b.lotsch@fkf.mpg.de

ORCID: <https://orcid.org/0000-0002-3094-303X>

Pieremanuele Canepa - Department of Materials Science and Engineering, National University of Singapore, 9 Engineering Drive 1, 117575, Singapore; Department of Chemical and Biomolecular Engineering, National University of Singapore, Engineering Drive 4, 117585, Singapore.

Email: pcanepa@nus.edu.sg

ORCID: <https://orcid.org/0000-0002-5168-9253>

Tanja Scholz - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany. ORCID: <https://orcid.org/0000-0003-3474-1272>

Christian Schneider - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany. ORCID: <https://orcid.org/0000-0003-4386-9788>

Maxwell W. Terban - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany. ORCID: <https://orcid.org/0000-0002-7094-1266>

Zeyu Deng - Department of Materials Science and Engineering, National University of Singapore, 9 Engineering Drive 1, 117575, Singapore. ORCID: <https://orcid.org/0000-0003-0109-9367>

Roland Eger - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany.

Martin Etter - German electron synchrotron (DESY), Notkestraße 85, Hamburg, 22607, Germany. ORCID: <https://orcid.org/0000-0002-5183-3585>

Robert E. Dinnebier - Max Planck Institute for Solid State Research, Heisenbergstraße 1, 70569 Stuttgart, Germany. ORCID: <https://orcid.org/0000-0003-2778-2113>

The authors acknowledge Armin Schulz and Christine Stefani for measuring Raman and PXRD, respectively. The authors acknowledge financial support by the Max Planck Society, the German Federal Ministry of Research and Education (BMBF), project 03XP0177B (FestBatt), the Center for Nanoscience (CeNS) and the Cluster of Excellence e-conversion. P.C. and Z.D. are grateful to funding from the National Research Foundation (Singapore) under P.C. NRF Fellowship NRFF12-2020-0012. P.C. was also supported by the the ANR-NRF NRF2019-NRF-ANR073 Na-MASTER. We acknowledge DESY (Hamburg, Germany), a member of the Helmholtz Association HGF, for the provision of experimental facilities. Parts of this research were carried out at beamline P02.1.

References

- (1) Wiberg, N. Lehrbuch der Anorganischen Chemie; De Gruyter, 2008.
- (2) Yang, Y.; Song, M.; Wu, X.; Wu, K. A review of the structural diversity of $[P_xS_y]^{n-}$ motifs and their potential application prospects in metal thiophosphates. J. Phys. D **2021**, 54, 463002.
- (3) Jansen, M.; Henseler, U. Synthesis, structure determination, and ionic conductivity of sodium tetrathiophosphate. J. Solid State Chem. **1992**, 99, 110–119.
- (4) Hayashi, A.; Noi, K.; Sakuda, A.; Tatsumisago, M. Superionic glass-ceramic electrolytes for room-temperature rechargeable sodium batteries. Nat. Commun. **2012**, 3, 856.
- (5) Hayashi, A.; Noi, K.; Tanibata, N.; Nagao, M.; Tatsumisago, M. High sodium ion conductivity of glass–ceramic electrolytes with cubic Na_3PS_4 . J. Power Sources **2014**, 258, 420–423.
- (6) Krauskopf, T.; Culver, S. P.; Zeier, W. G. Local Tetragonal Structure of the Cubic Superionic Conductor Na_3PS_4 . Inorg. Chem. **2018**, 57, 4739–4744, PMID: 29613779.
- (7) Rush, L. E.; Holzwarth, N. A. W. First principles investigation of the structural and electrochemical properties of $Na_4P_2S_6$ and $Li_4P_2S_6$. Solid State Ion. **2016**, 286, 45–50.
- (8) RUSH, L. E. J. First-Principles Investigation of Electronic Properties in Sodium-Ion Electrolytes for Solid-State Battery Materials. Thesis, 2017.
- (9) Fincher, T.; LeBret, G.; Cleary, D. A. Single-Crystal Structure Determination of $Na_4P_2S_6 \cdot 6H_2O$. J. Solid State Chem. **1998**, 141, 274–281.
- (10) Kuhn, A.; Eger, R.; Nuss, J.; Lotsch, B. V. Synthesis and Structural Characterization of the Alkali Thiophosphates $Na_2P_2S_6$, $Na_4P_2S_6$, $K_4P_2S_6$, and $Rb_4P_2S_6$. Z. Anorg. Allg. Chem. **2014**, 640, 689–692.

- (11) Scholz, T.; Schneider, C.; Eger, R.; Duppel, V.; Moudrakovski, I.; Schulz, A.; Nuss, J.; Lotsch, B. V. Phase formation through synthetic control: polymorphism in the sodium-ion solid electrolyte $\text{Na}_4\text{P}_2\text{S}_6$. J. Mater. Chem. A **2021**, 9, 8692–8703.
- (12) Timmermans, J. Plastic crystals: A historical review. J Phys Chem Solids **1961**, 18, 1–8.
- (13) Lunkenheimer, P.; Michl, M.; Loidl, A. J. Adv. Dielectr.; Springer International Publishing, 2018; pp 277–300.
- (14) MacFarlane, D. R.; Forsyth, M. Plastic Crystal Electrolyte Materials: New Perspectives on Solid State Ion. **2001**, 13, 957–966.
- (15) Tsang, T.; Farrar, T. C. Nuclear Magnetic Relaxation Studies of Internal Rotations and Phase Transitions in Borohydrides of Lithium, Sodium, and Potassium. J. Chem. Phys. **1969**, 50, 3498–3502.
- (16) Matsuo, M.; Nakamori, Y.; Orimo, S.-I.; Maekawa, H.; Takamura, H. Lithium superionic conduction in lithium borohydride accompanied by structural transition. Appl. Phys. Lett. **2007**, 91, 224103.
- (17) Hagemann, H.; Gomes, S.; Renaudin, G.; Yvon, K. Raman studies of reorientation motions of $[\text{BH}_4]^-$ anions in alkali borohydrides. J. Alloys Compd. **2004**, 363, 129–132.
- (18) Nilsson, L.; Thomas, J. O.; Tofield, B. C. The structure of the high-temperature solid electrolyte lithium sulphate at 908 K. J. phys., C, Solid state phys. **1980**, 13, 6441–6451.
- (19) Aronsson, R.; Jansson, B.; Knape, H. E. G.; Lundén, A.; Nilsson, L.; Sjöblom, C.-A.; Torell, L. M. Fast ion conductors with rotating sulphate ions. J. phys. Colloq. **1980**, 41, C6–35–C6–37.
- (20) Boerjesson, L.; Torell, L. M. Reorientational motion in superionic sulfates: A Raman linewidth study. Phys. Rev. B **1985**, 32, 2471–2477.

- (21) Lundén, A. Enhancement of cation mobility in some sulphate phases due to a paddle-wheel mechanism. Solid State Ion. **1988**, 28-30, 163–167.
- (22) Jansen, M. Volume Effect or Paddle-Wheel Mechanism—Fast Alkali-Metal Ionic Conduction in Solids with Rotationally Disordered Complex Anions. Angew. Chem. Int. Ed. **1991**, 30, 1547–1558.
- (23) Witschas, M.; Eckert, H.; Wilmer, D.; Banhatti, R.; Funke, H.; Fitter, J.; Lechner, R. E.; Korus, G.; Jansen, M. Anion Rotation and Cation Transport in the Rotor Phase α -Sodium Orthophosphate: Paddle-Wheel Mechanism Redefined in View of New Experimental Results. Z Phys Chem **2000**, 214, 643–673.
- (24) Kniaź, K.; Fischer, J. E.; Zhu, Q.; Rosseinsky, M. J.; Zhou, O.; Murphy, D. W. C_{60} orientational ordering in superconducting Na_2RbC_{60} . Solid State Commun. **1993**, 88, 47–50.
- (25) Tanigaki, K.; Hirose, I.; Manako, T.; Tsai, J. S.; Mizuki, J.; Ebbesen, T. W. Phase transitions in Na_2AC_{60} ($A=Cs$, Rb , and K) fullerenes. Physical Review B **1994**, 49, 12307–12310.
- (26) Saito, T.; Maniwa, Y.; Oda, H.; Kume, K.; Kosaka, M.; Hirose, I.; Tanigaki, K. NMR Studies on Orientational Ordering Phase Transition in Na_2CsC_{60} . J. Phys. Soc. Japan **1995**, 64, 4513–4517.
- (27) Skripov, A. V.; Babanova, O. A.; Soloninin, A. V.; Stavila, V.; Verdal, N.; Udovic, T. J.; Rush, J. J. Nuclear Magnetic Resonance Study of Atomic Motion in $A_2B_{12}H_{12}$ ($A = Na, K, Rb, Cs$): Anion Reorientations and Na^+ Mobility. J. Phys. Chem. C. **2013**, 117, 25961–25968.
- (28) Udovic, T. J.; Matsuo, M.; Unemoto, A.; Verdal, N.; Stavila, V.; Skripov, A. V.; Rush, J. J.; Takamura, H.; Orimo, S.-i. Sodium superionic conduction in $Na_2B_{12}H_{12}$. Chem. Commun. **2014**, 50, 3750–3752.

- (29) Kweon, K. E.; Varley, J. B.; Shea, P.; Adelstein, N.; Mehta, P.; Heo, T. W.; Udovic, T. J.; Stavila, V.; Wood, B. C. Structural, Chemical, and Dynamical Frustration: Origins of Superionic Conductivity in closo-Borate Solid Electrolytes. Chem. Mater. **2017**, 29, 9142–9153.
- (30) Udovic, T. J.; Matsuo, M.; Tang, W. S.; Wu, H.; Stavila, V.; Soloninin, A. V.; Skoryunov, R. V.; Babanova, O. A.; Skripov, A. V.; Rush, J. J.; Unemoto, A.; Takamura, H.; Orimo, S.-I. Exceptional Superionic Conductivity in Disordered Sodium Decahydro-closo-decaborate. Adv. Mater. **2014**, 26, 7622–7626.
- (31) Tang, W. S.; Unemoto, A.; Zhou, W.; Stavila, V.; Matsuo, M.; Wu, H.; Orimo, S.-i.; Udovic, T. J. Unparalleled lithium and sodium superionic conduction in solid electrolytes with large monovalent cage-like anions. Energy Environ. Sci. **2015**, 8, 3637–3645.
- (32) Dimitrievska, M.; Stavila, V.; Soloninin, A. V.; Skoryunov, R. V.; Babanova, O. A.; Wu, H.; Zhou, W.; Tang, W. S.; Faraone, A.; Tarver, J. D.; Trump, B. A.; Skripov, A. V.; Udovic, T. J. Nature of Decahydro-closo-decaborate Anion Reorientations in an Ordered Alkali-Metal Salt: $\text{Rb}_2\text{B}_{10}\text{H}_{10}$. J. Phys. Chem **2018**, 122, 15198–15207.
- (33) Famprakis, T.; Dawson, J. A.; Fauth, F.; Clemens, O.; Suard, E.; Fleutot, B.; Courty, M.; Chotard, J.-N.; Islam, M. S.; Masquelier, C. A New Superionic Plastic Polymorph of the Na^+ Conductor Na_3PS_4 . ACS Materials Letters **2019**, 1, 641–646.
- (34) Saha, S.; Rousse, G.; Courty, M.; Shakhova, Y.; Kirsanova, M.; Fauth, F.; Pomjakushin, V.; Abakumov, A. M.; Tarascon, J. M. Structural Polymorphism in $\text{Na}_4\text{Zn}(\text{PO}_4)_2$ Driven by Rotational Order–Disorder Transitions and the Impact of Heterovalent Substitutions on Na-Ion Conductivity. Inorg. Chem. **2020**, 59, 6528–6540.
- (35) Geirhos, K.; Lunkenheimer, P.; Michl, M.; Reuter, D.; Loidl, A. Communication: Con-

- ductivity enhancement in plastic-crystalline solid-state electrolytes. J. Chem. Phys. **2015**, 143, 081101.
- (36) Egami, T.; Billinge, S. J. L. Underneath the Bragg peaks: structural analysis of complex materials, 2nd ed.; Elsevier: Amsterdam, 2012.
- (37) Terban, M. W.; Billinge, S. J. L. Structural analysis of molecular materials using the pair distribution function. Chem. Rev. **2021**, 10.1021/acs.chemrev.1c00237.
- (38) Prill, D.; Juhás, P.; Schmidt, M. U.; Billinge, S. J. L. Modelling pair distribution functions (PDFs) of organic compounds: describing both intra- and intermolecular correlation functions in calculated PDFs. J. Appl. Cryst. **2015**, 48, 171–178.
- (39) Terban, M. W.; Russo, L.; Pham, T. N.; Barich, D. H.; Sun, Y. T.; Burke, M. D.; Brum, J.; Billinge, S. J. L. Local structural effects due to micronization and amorphization on an HIV treatment active pharmaceutical ingredient. Mol. Pharmaceutics **2020**, 17, 2370—2389.
- (40) Adams, S.; Rao, R. P. High power lithium ion battery materials by computational design. Phys. Status Solidi A **2011**, 208, 1746–1753.
- (41) Chen, H.; Wong, L. L.; Adams, S. SoftBV – a software tool for screening the materials genome of inorganic fast ion conductors. Acta Crystallographica Section B **2019**, 75, 18–33.
- (42) Petříček, V.; Dušek, M.; Palatinus, L. Crystallographic Computing System JANA2006: General features. Z. Kristallogr. **2014**, 229, 345–352.
- (43) Chupas, P. J.; Qiu, X.; Hanson, J. C.; Lee, P. L.; Grey, C. P.; Billinge, S. J. L. Rapid acquisition pair distribution function analysis (RA-PDF). J. Appl. Cryst. **2003**, 36, 1342–1347.

- (44) Kieffer, J.; Ashiotis, G.; Deschildre, A.; Nawaz, Z.; Wright, J. P.; Karkoulis, D.; Picca, F. E. The fast azimuthal integration Python library: pyFAI. J. Appl. Cryst. **2015**, 48, 510–519.
- (45) Juhás, P.; Davis, T.; Farrow, C. L.; Billinge, S. J. L. PDFgetX3: A rapid and highly automatable program for processing powder diffraction data into total scattering pair distribution functions. J. Appl. Cryst. **2013**, 46, 560–566.
- (46) Yang, X.; Juhás, P.; Farrow, C.; Billinge, S. J. L. xPDFsuite: an end-to-end software solution for high throughput pair distribution function transformation, visualization and analysis. **2015**, arXiv:1402.3163.
- (47) Coelho, A. A.; Chater, P. A.; Kern, A. Fast synthesis and refinement of the atomic pair distribution function. J. Appl. Cryst. **2015**, 48, 869–875.
- (48) Coelho, A. A. TOPAS and TOPAS-Academic: an optimization program integrating computer algebra and crystallographic objects written in C++. J. Appl. Cryst. **2018**, 51, 210–218.
- (49) Rietveld, H. M. A Profile Refinement Method for Nuclear and Magnetic Structures. J. Appl. Cryst. **1969**, 2, 65–71.
- (50) Dinnebier, R. E.; Leineweber, A.; Evans, J. S. O. Rietveld Refinement: Practical Powder Diffraction Pattern Analysis Using TOPAS, 1st ed.; De Gruyter STEM: Berlin, 2019.
- (51) Coelho, A. A. Whole-profile structure solution from powder diffraction data using simulated annealing. J. Appl. Cryst. **2000**, 33, 899–908.
- (52) Kresse, G.; Furthmüller, J. Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. Phys. Rev. B **1996**, 54, 11169–11186.

- (53) Kresse, G.; Furthmüller, J. Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set. Comput. Mater. Sci. **1996**, 6, 15–50.
- (54) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple. Phys. Rev. Lett. **1996**, 77, 3865–3868.
- (55) Grimme, S.; Antony, J.; Ehrlich, S.; Krieg, H. A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H-Pu. J. Chem. Phys. **2010**, 132, 154104.
- (56) Blöchl, P. E. Projector augmented-wave method. Phys. Rev. B **1994**, 50, 17953–17979.
- (57) Kresse, G.; Joubert, D. From ultrasoft pseudopotentials to the projector augmented-wave method. Phys. Rev. B **1999**, 59, 1758–1775.
- (58) Nosé, S. A unified formulation of the constant temperature molecular dynamics methods. J. Chem. Phys. **1984**, 81, 511–519.
- (59) Hoover, W. G. Canonical dynamics: Equilibrium phase-space distributions. Phys. Rev. A **1985**, 31, 1695–1697.