# Construction of Cascade Nanozymatic Networks for Cell Mimic with Highly Selective Recognition and Linear Perception to H<sub>2</sub>O<sub>2</sub>

Caixia Zhu,<sup>a</sup> Zhixin Zhou,<sup>a</sup> Xuejiao J. Gao,<sup>b</sup> Yanhong Tao,<sup>b</sup> Xuwen Cao,<sup>a</sup> Yuan Xu,<sup>a</sup> Yanfei Shen,<sup>a</sup> Songqin Liu,<sup>a</sup> Yuanjian Zhang<sup>a</sup>\*

<sup>a</sup>Jiangsu Engineering Laboratory of Smart Carbon-Rich Materials and Devices, Jiangsu Province Hi-Tech Key Laboratory for Bio-Medical Research, State Key Laboratory of Bioelectronics, School of Chemistry and Chemical Engineering, Medical School, Southeast University, Nanjing 21189, China. Email: <u>Yuanjian.Zhang@seu.edu.cn</u> <sup>b</sup>College of Chemistry and Chemical Engineering, Jiangxi Normal University, Nanchang, 330022, China

#### Abstract

A single stimulus leading to multiple responses is an essential function of many biological enzymatic reaction networks, which enable complex life activities. Owing to the lack of allosteric regulation of natural enzymes, it is challenging to duplicate a similar network using non-living chemicals. Herein, we report a nanozymatic cascade reaction network that demonstrates multiple responses of different modes and intensities upon a single H<sub>2</sub>O<sub>2</sub> stimulus based on a single-atom nanozyme (Co-N-CNTs). Taking the two-electron cascade oxidation of 3,3',5,5'-tetramethylbenzidine (TMB) as an example, the endogenous product H<sub>2</sub>O<sub>2</sub> competitively inhibited substrates in the first one-electron oxidation at the Co-N<sub>4</sub> active site on Co-N-CNTs, while accelerated the second one-electron oxidation under a micellar nanozyme. Using such a nanozymatic network, the feedback and feedforward regulation of product transformation were further applied to microfluidic flow reactors as a cell mimic. Owing to the unique varieties of response in intensities and modes, the proposed cell mimic demonstrated highly selective recognition and linear perception of H<sub>2</sub>O<sub>2</sub> against over 20 interferences in a wide range of concentrations (0.01-100 mM), reminiscent of a primordial life-like process in mutable and harsh conditions.

**Keywords:** Chemical reaction networks, Nanozyme, Competition inhibition, Cascade reaction, Selectivity

### Introduction

The creation and evolution of life are one of the most important scientific questions. Simulating a true evolutionary process as well as a primordial life-like process, and then answering one of the most intriguing and fascinating questions of humankind, has been the research topic of scientists' passion. As Lehn envisioned more than a decade ago,<sup>1</sup> possible answers to these challenging questions come from chemistry, in particular "systems chemistry", a field that aims to mimic the functional behavior of living systems using reaction networks. Considerable effort has already been made in this direction. Purified biochemical components are used as building blocks to form chemical reaction networks triggered by auxiliary chemical or physical stimuli, leading to complex and programmed reaction pathways. These chemical reaction networks reveal dissipative network,<sup>2-3</sup> adaptation,<sup>4-5</sup> signaling network,<sup>6</sup> switching,<sup>7-8</sup> feedback,<sup>9-11</sup> communication,<sup>12-13</sup> and oscillators.<sup>14</sup> The further development of chemical reaction networks suffers, however, from fundamental limitations of natural matter such as nucleic acids and enzymes in the scalability for implementing batch experiments or large-scale production, which impedes their broad applications. Moreover, according to the theory of chemical evolution, under the conditions of the primitive earth, inorganics are the origin of evolution.<sup>15-16</sup> Therefore, there is an urgent need to fill the gap in the field of reaction networks based on nonbiological matters.

As the basis of enzymatic reaction networks, cascade reaction systems play a crucial role in mediating biological processes such as signal transduction and amplification, and metabolic and catabolic reactions. Owing to their low cost, ease of obtaining, and high stability against biodegradation and denaturation,<sup>17-19</sup> nanomaterials with enzyme-like activity (termed nanozymes) have drawn increasing attention in various fields, such as biosensors, immunoassays, and cancer therapeutics.<sup>20-24</sup> Along this line, nanozyme-based cascade systems have already been reported for signal amplification and selective biosensing.<sup>25-26</sup> However, to engineer more advanced behaviors, such as metabolic regulation and signal transduction, it is necessary to use a single stimulus to trigger diverse responses for a cascade system. For example, in the muscle, glycogen phosphorylase is inhibited by the metabolites glucose and G6P. Similarly, insulin acts on glucose metabolism through activation of glycogen synthase and inhibition of phosphorylase kinase and phosphorylase a.<sup>27</sup> The reaction characteristics are finally

manifested as the flexibility and tunability of the reaction network. Nonetheless, it is challenging to achieve such a metabolic response using nanozymes because of the lack of allosteric regulatory functions as enzymes. Interestingly, considering the intrinsic characteristics of nanozymes, their regulatory ability may be alternatively obtained in kinetics by the competition of different substrates at the same active site. Despite numerous unprecedented successes of nanozymes in biological catalysis and medical applications,<sup>28-33</sup> nanozyme-based reaction networks have not yet been explored.

Here, we report a cascade nanozymatic network based on Co-N-doped carbon nanotubes (Co-N-CNTs) with active sites competing with different substrates.  $H_2O_2$ , an important short-lived product in biochemical processes, was devised as the endogenous product of a 3, 3', 5, 5'-tetramethylbenzidine (TMB) oxidation cascade via two-electron transfer. It was found that  $H_2O_2$  competitively inhibited the first one-electron oxidation of TMB at the active site Co-N<sub>4</sub> of Co-N-CNTs nanozymes but accelerated the second one-electron oxidation driven by a micellar nanozyme. The cascade reaction network with diverse responses to a single stimulus was further incorporated into a microfluidic flow reactor as a simplified artificial cell. Interestingly, highly selective recognition and linear perception to  $H_2O_2$  over a wide range of concentrations were successfully achieved using the proposed cell mimic.

#### **Results and discussion**

#### Synthesis and Characterization of Co-N-CNTs.

The atomically dispersed metal centers of single-atom nanozymes made it easy to distinguish the actual active sites and search for the source of enzyme-like activity.<sup>32, 34-39</sup> Given the interaction of a single atom with a ligand, single-atom Co-N-CNTs were prepared by two-step pyrolysis, in which the product of the first reaction was used as the catalyst for the second chemical vapor deposition (Figure S1).<sup>40-43</sup> As shown in Figure 1a and S1 (inset), scanning electron microscopy (SEM) and transmission electron microscopy (TEM) images indicated that Co-N-CNTs consisted of nanotubes with multiple interlaced walls. High-resolution TEM images were obtained to ascertain the detailed texture of the Co-N-CNTs (Figure 1b), depicting the (002) graphitic striations. Consistently, the (002) peak at  $2\theta = 25.9^{\circ}$  was observed in the XRD pattern (Figure S2). High-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) revealed the state of the metal center in the Co-N-CNTs. As shown

in Figure 1c, single Co atoms, highlighted by yellow circles were dispersed across the entire nanotube. Meanwhile, the fact that the single Co atom surrounded by the N atoms was observed using the electron energy loss spectrum (Figure 1c, inset).<sup>44</sup> X-ray photoelectron spectroscopy (XPS) analysis of Co-N-CNTs suggested that the valence state of Co was between +2 and +3 (see Figure S3 and Supporting Information for more details). The content of Co ions in Co-N-CNTs measured by inductively coupled plasma-mass spectrometry (ICP-MS) was approximately 2.5 wt%. These results suggest that co-N-CNTs with a single-atom cobalt dispersion were successfully synthesized by secondary pyrolytic chemical vapor deposition.



**Figure 1. Structural characterization of the Co-N-CNTs nanozyme.** (a) TEM and (b) high-resolution TEM images of Co-N-CNTs. (c) Aberration-corrected HAADF-STEM image. Inset: EEL spectrum. (d) XANES spectra at the Co K-edge of Co-N-CNTs and reference samples. Inset: first-order derivative of the normalized XANES spectra. (e) FT k<sup>3</sup>-weighted EXAFS spectra of Co-N-CNTs and the reference samples of Co foil, CoO, Co<sub>2</sub>O<sub>3</sub>, Co<sub>3</sub>O<sub>4</sub>, and CoPc. (f) Experimental FT-EXAFS spectrum and the fitting curve of Co-N-CNTs.

To further confirm the electronic structure and coordination environment of Co-N-CNTs at the atomic level, X-ray absorption near-edge structure (XANES) and extended X-ray absorption fine structure (EXAFS) analysis were performed. The absorption edge position of Co-N-CNTs was located between that of CoO and Co<sub>3</sub>O<sub>4</sub> (Figure 1d), suggesting that a single Co atom carries a positive charge, and the valence state of Co was between +2 and +3. The Fourier transform (FT) k<sup>3</sup>-weighted EXAFS spectra in Figure 1e illustrated that, compared with the reference CoPc, Co-N-CNTs exhibited only a prominent peak located at  $\approx$ 1.4 Å, which was mainly attributed to the Co–N first coordination shell rather than the Co-Co bond (2.2 Å). This result was complementary to the HAADF-STEM images, confirming that the Co species in the Co-N-CNTs were atomically dispersed. The quantitative coordination configuration of the Co atom was obtained by EXAFS fitting (Figure 1f, Table S1). The bond length was 1.86 Å and the coordination number of Co atoms were atomically dispersed in a carbon matrix and coordinated by four N atoms.

#### Competitive inhibition at the active site Co-N4 of Co-N-CNTs.

In kinetics, the activation energy of the intermediates formed on the active site of the catalyst determines the preferred reaction pathway on the catalyst. In the field of nanozyme research, oxidoreductase reactions are widely studied as the most common type of enzymatic reactions.  $H_2O_2$  plays an important role as a substrate for oxidation reactions and sometimes as an intermediate product of redox reactions.  $H_2O_2$  is an important short-lived product of biochemical processes that is essential for the normal activities of living organisms. Therefore, to regulate the reaction kinetics, in addition to  $O_2$ , the basic substrate of oxidoreductase,  $H_2O_2$  was selected as an important competitive substrate to investigate the enzyme-like activity of Co-N-CNTs.

The oxidase-like catalytic activity of Co-N-CNTs was first investigated using molecular  $O_2$  and standard 3,3',5,5'-tetramethylbenzidine (TMB) as substrates. As shown in Figure 2a, a typical one-electron oxidized product of TMB (i.e., TMB<sub>ox1</sub>) was observed (see the detailed reaction equation in Figure S4a). At the same time, the control experiments verified that  $O_2$  participated in the oxidation of TMB (Figure S5). In addition to the oxidase-like catalytic activity, the catalase-like catalytic activity of Co-N-CNTs was experimentally confirmed by comparative experiments. As shown in Figure 2c, the addition of Co-N-CNTs significantly increased the  $O_2$  production rate (red line) compared to that of the blank sample without catalysis (black line). Detailed kinetic studies demonstrated that the oxidase (Table S2) and catalase-like (Table S3)

activities of Co-N-CNTs were comparable to those of previous nanozymes, indicating the outstanding enzyme-mimicking activity of Co-N-CNTs (Figure 2b, d). Notably, for catalase-like activity, Co-N-CNTs showed a lower  $K_M$  and a higher  $V_{max}$  than other reported catalase-like nanozymes, indicative of an excellent affinity and catalytic activity for H<sub>2</sub>O<sub>2</sub> (Table S3). In addition, Co-N-CNTs also demonstrated high stability in cycling tests and long-term storage (see further discussion in Figure S6).



Figure 2. Competitive inhibition at the active site Co-N<sub>4</sub> of Co-N-CNTs. (a) UV-vis absorption spectra of TMB (0.05 mM) after catalyzed by Co-N-CNTs (0.05 mg mL<sup>-1</sup>) in O<sub>2</sub>-saturated 0.1 M HAc-NaAc buffer solution. (b) Michaelis-Menten curves for the oxidase-like activity of Co-N-CNTs (50 µg/mL) with different concentrations of TMB in air-saturated HAc-NaAc (0.1 M, pH 3.5) solution. (c) Catalytic O<sub>2</sub> generation by Co-N-CNTs (0.05 mg mL<sup>-1</sup>) in H<sub>2</sub>O<sub>2</sub> (100 mM). (d) Michaelis-Menten curves for the catalase-like activity of Co-N-CNTs (50 µg/mL) with different concentrations of H<sub>2</sub>O<sub>2</sub> in HAc-NaAc (0.1 M, pH 3.5). (e) UV-vis absorption spectra of the oxidized product of TMB catalyzed by Co-N-CNTs before and after SCN<sup>-</sup> poisoning. (f) O<sub>2</sub> yield by decomposition of H<sub>2</sub>O<sub>2</sub> catalyzed by Co-N-CNTs before and after SCN<sup>-</sup> poisoning. (g) Influence of TMB on the decomposition of H<sub>2</sub>O<sub>2</sub> (100 mM) catalyzed by Co-N-CNTs. (i) Scheme of active sites Co-N<sub>4</sub> competed by different substrates.

More interestingly, it was found that Co-N-CNTs could not oxidize TMB using H<sub>2</sub>O<sub>2</sub>; instead, the oxidation of TMB was inhibited by H<sub>2</sub>O<sub>2</sub> (Figure S4b). This is distinctive from the well-known Fe-N-C single-atom nanozyme that has both peroxidase and oxidase-like activities.<sup>21, 45-47</sup> In essence, this competition phenomenon was supposed to be closely related to the catalytic active site. To further understand the origin of the catalytic activity of Co-N-CNTs, the thiocyanate ion (SCN<sup>-</sup>) was used as a poison probe to investigate the active sites of single-atom Co-N-CNTs.<sup>48-50</sup> It was found that both oxidase and catalase-like activities of Co-N-CNTs were irreversibly inhibited by 59% and 47%, respectively, after SCN<sup>-</sup> poisoning (Figure 2e, f), indicating that the single-atom Co sites (Co-N<sub>4</sub>) of Co-N-CNTs served as both oxidase- and catalase-like active sites. Therefore, a competitive reaction between H<sub>2</sub>O<sub>2</sub> and O<sub>2</sub> (TMB) occurred at the Co-N<sub>4</sub> active site. In addition, the O<sub>2</sub> formation rate remained almost the same with and without TMB, whereas the catalytic oxidation rate of TMB by Co-N-CNTs decreased upon the addition of H<sub>2</sub>O<sub>2</sub> (Figure 2g and h). In biology, this phenomenon is known as competitive inhibition.  $H_2O_2$  and  $O_2$  (TMB) competed for the same binding site-the active site (Co-N<sub>4</sub>)-of the nanozyme (Figure 2i), which hindered the combination of O<sub>2</sub> (TMB) and the nanozyme, resulting in the reduction of the oxidaselike catalytic reaction rate of the nanozyme. In addition, H<sub>2</sub>O<sub>2</sub> was detected during the oxidation of TMB by Co-N-CNTs (Figure S4c), which indicated that the reduction product of O<sub>2</sub> also included H<sub>2</sub>O<sub>2</sub>. As an intrinsic factor, the intermediate product H<sub>2</sub>O<sub>2</sub> would, in turn, compete with TMB and reduce the velocity of the oxidase-like reaction, thus becoming a foundation for constructing the nanozyme network with an intrinsic feedback feature (vide infra).

To explore the kinetics of the TMB oxidation reaction catalyzed by Co-N-CNTs, Lineweaver-Burk plots were constructed (Figure S7a, b). The two groups of lines displayed characteristic intersecting lines, suggesting that the catalytic reaction underwent a symbolic sequence Bi-Bi mechanism.<sup>51-53</sup> It was supposed that both O<sub>2</sub> and TMB were bound to Co-N-CNTs to form a ternary intermediate complex. To identify the above kinetic mechanism, electron spin resonance (ESR) spectra were obtained to monitor the possible intermediate reactive oxygen species (ROS) in TMB-involved redox reactions (Figure S7c). No signal was observed for any ROS-trapping agent adduct during the expression of oxidase-like activity by the Co-N-CNTs nanozyme. Furthermore, SOD and isopropyl alcohol (IPA) were selected as scavengers

for monitoring superoxide and hydroxyl radicals. As shown in Figure S7d, the addition of a trapping agent also had no significant effect on the oxidation of TMB by Co-N-CNTs. This indicated that the oxidase-like activity of Co-N-CNTs was not derived from the generation of free radicals, which conformed to the sequence Bi-Bi mechanism. To gain insights into the catalase-mimicking activities of Co-N-CNTs, electron spin resonance (ESR) and optical trapping experiments were performed to detect possible intermediate ROS (see more discussion in Figure S7e, f). It was found that there was no detectable free radical generation during the catalase-like reaction by the Co-N-CNTs nanozyme.

#### Density functional theory studies of competitive inhibition at the active site Co-N<sub>4</sub>.

DFT calculations were conducted to gain further insight into the underlying mechanisms of the oxidase- and catalase-mimicking activities of Co-N-CNTs, in which the Co-N<sub>4</sub> patches were considered as the active centers. We aimed to solve two problems using DFT calculations: one was the chemical change process behind enzyme-mimicking activity, and the other was the competitive mechanism of oxidase- and catalase-mimicking catalytic processes. The proposed mechanisms and calculated energy profiles are shown in Fig. 3.

For the oxidase-mimicking activity, two possible mechanisms for the four- and twoelectron O<sub>2</sub> reductions were investigated, and the results are shown in Figure 3a and 3b, respectively. From the calculated potential energy surface, it can be seen that whether in the 4-electron or the 2-electron process, the oxidation of the first TMB by OO\* was easy, accompanied by significant energy release of -2.05 eV (2 to 3 in Figure 3a and 8 to 9 in Figure 3b). And then, the O on the outside of the OOH\*, rather than the O on the adsorption end, preferred to capture reductive H form TMB, because there was only an energy increase of 0.04 eV from int12 to int13, while it was necessary to overcome 2.79 eV from int22 to int23. The energy raises of the oxidation of TMB by O\* and OH\* were 1.51 and 0.04 eV, respectively. The above results indicated that the four-electron catalytic cycle was more thermodynamically favorable than the two-electron process at room temperature because its maximum energy rise (1.51 eV) was less than that of the two-electron process (2.79 eV). Nonetheless, considering the observation of H<sub>2</sub>O<sub>2</sub> in experiments with a molar ratio of 1:1 to the TMB<sub>ox1</sub> product (see Figure S4 and more discussion in SI), the oxidation of TMB by O<sub>2</sub> via the 2-electron pathway also occurred significantly, presumably owing to favorable kinetics.





For catalase-mimicking activity, two possible mechanisms regarding the heterolytic and homolytic cleavage of H<sub>2</sub>O<sub>2</sub> were investigated, and the results are shown in Figure 3c and 3d, respectively. The difference between these two mechanisms lies in the decomposition mode of H<sub>2</sub>O<sub>2</sub>. The step from int31 to int32 was the heterolytic cleavage of the O-O bond, while that from int41 to int42 was the homogeneous cleavage of the O-O bond. From the energy point of view, heterolytic cleavage was more advantageous with an energy decrease of -0.66 eV, while the homogeneous cleavage was accompanied with an energy increase of 0.41 eV energy. Moreover, for these two mechanisms, the highest energy-rising step was the desorption of O<sub>2</sub>, and the energy increase was only 0.55 eV. This indicated that the Co-N-CNTs had superior catalasemimicking activity compared to the oxidase-mimicking activity, as the highest energy increase for the latter was 1.51 or 2.79 eV. In this regard, DFT calculations indicated that Co-N-CNTs had both oxidase- and catalase-mimicking activities. For oxidasemimicking activity, the 4-electron reduction of O<sub>2</sub> was thermodynamically more favorable than the 2-electron reduction pathway. However, considering the results of the experiment, both pathways were equally likely to occur (see Figure S4 and further discussion in the SI). Reminiscent of the oxygen reduction reaction at electrocatalysts, the kinetics of a combination of 4- and 2-electron pathways is common.<sup>50</sup> For catalasemimicking activity, both heterolytic and homolytic cleavage of the O-O bond of H<sub>2</sub>O<sub>2</sub> might occur, and the former was more advantageous.

More importantly, the selectivity of catalase-mimicking activity was higher than that of oxidase-mimicking activity. In other words, when  $H_2O_2$  and  $O_2$  were present simultaneously, the Co-N-CNTs were preferentially catalyzed by  $H_2O_2$  instead of  $O_2$ . These results agreed well with the experimental observations. Therefore, a unique competition for the same active site was created between different substrates, catalyzed by the different enzyme-like activities of Co-N-CNTs. At Co-N<sub>4</sub>, the reaction of  $O_2$ (TMB) was competed not only by exogenous  $H_2O_2$  but also by endogenous  $H_2O_2$ , which provided an opportunity to construct a nanozyme reaction network with intrinsic feedback properties.

#### Nanozymatic reaction networks using Co-N-CNTs.

The metabolic regulation evolved by organisms to adapt to environmental changes mainly depends on the regulation of enzyme activity. As discussed above, the welldefined structure and excellent enzyme-like activity of the single-atom Co-N-CNTs nanozyme provided a good basis for the realization of a biomimetic metabolism network. Although the activity cannot be modulated allosterically like the enzyme, Co-N-CNTs with competitive inhibition at the active site Co-N<sub>4</sub> would alternatively provide flexible solutions to build complicated chemical reaction networks, meanwhile overcome the fundamental limitations of natural matter in terms of scalability for implementing batch experiments or large-scale production. Thus, a metabolic reaction network based on Co-N-CNTs was proposed.

As the basis of chemical reaction networks, enzyme cascade reactions play an important role in signal transduction and amplification, as well as in metabolic and catalytic pathways. In contrast to other enzymatic substrates, such as ophenylenediamine (OPD) and 2, 2'-azino-bis(3-ethylbenzothiazoline-6-sulfonic acid) (ABTs), the oxidation of TMB is not a one-step reaction but a two-step cascade.<sup>54</sup> Therefore, the stepwise oxidation of TMB was chosen as the model for the cascade reaction network. As mentioned above, the oxidation of TMB by the Co-N-CNT nanozyme resulted in a one-electron oxidation product, TMB<sub>ox1</sub>. It is well known that this cascade requires the synergistic action of multiple catalysts. Therefore, to achieve a cascade of reactions, it is necessary to search for catalysts capable of oxidizing TMB<sub>ox1</sub> to TMB<sub>ox2</sub> (Figure 4a).

Indeed, because of the reducing nature of TMB, it is challenging to achieve TMB<sub>ox1</sub> reoxidation in the presence of TMB (the substrate of the first-step reaction). However, micellar nanozymes have catalytic mechanisms that are different from those of previous oxidoreductases, providing an interesting candidate to construct a cascade reaction of TMB oxidation.<sup>55</sup> In brief, similar to enzymes and cell membranes, micelles also consist of hydrophilic and hydrophobic portions, and thus could self-assemble into nanoreactors in water to accelerate reactions.<sup>56-57</sup> Among them, anionic micellar nanozymes prefer to generate positively charged products due to electrostatic interactions. Therefore, based on the positive electrical properties of TMB<sub>ox2</sub>,<sup>58</sup>, an SDS micelle nanozyme consisting of a common anionic surfactant was chosen to construct the cascade reaction (Figure 4a and Figure S8a). To monitor the transition of the reaction product, the time-dependent absorbances at 652 nm (TMB<sub>ox1</sub>) and 450 nm (TMB<sub>ox2</sub>) were collected. As shown in Figure 4b, TMB (0.5 mM) was oxidized by Co-N-CNTs (0.05 mg/mL) to lose an electron and obtain TMB<sub>ox1</sub>, which was accompanied

by an increase in absorbance at 652 nm. Upon reaching a reaction time of 300 s, the second step of cascade transformation was induced by the addition of SDS micellar nanozymes (10 mM). The absorbance of  $TMB_{ox2}$  (450 nm) increased sharply, whereas the absorbance of  $TMB_{ox1}$  (652 nm) decreased (Figure 4b). Therefore, the SDS micellar nanozyme catalyzed the oxidation of  $TMB_{ox1}$  into  $TMB_{ox2}$  (see further discussion in Figure S8b, c). Notably, the hydrophobic TMB was supposed to be encapsulated in the hydrophobic chamber of the micelle nanozyme, which eliminates the potential interference to  $TMB_{ox2}$  generation.<sup>59</sup> In this sense, the cascade reaction could be constructed by using Co-N-CNTs nanozyme (E<sub>1</sub>) and SDS micelle nanozyme (E<sub>2</sub>), as summarized in Figure 4a.



Figure 4. Cascade nanozymatic network and distinctive stimulus responses. (a) Scheme of nanozyme-based network. (b) Time-dependent UV-vis absorption spectra of TMB<sub>ox1</sub> and TMB<sub>ox2</sub> at 652 and 450 nm, respectively. SDS micellar nanozyme was applied to the catalytic TMB oxidation reaction at 300 s. (c) Diverse response in mode and intensity of the chemical reaction network caused by a single H<sub>2</sub>O<sub>2</sub> stimulation: the yield of the TMB<sub>ox1</sub> reaction decreased in the first step (left) and the TMB<sub>ox2</sub> reaction increased in the second step (right) of the cascade reactions.

Cascade reactions form the basis of sophisticated metabolic reactions in organisms. Among them, the diverse responses of individual enzymes in the cascade to stimuli ensure the flexibility of cellular metabolic activities. In the cascade reaction involving a series of signal transmissions in the cell, there must be two positive and negative complementary feedback mechanisms for precise control. For example, gluco-6phosphate has a positive feedforward effect on glycogen synthesis and a negative feedback effect on hexokinase.<sup>27</sup> As aforementioned, both theoretical calculations and experiments show that a competitive reaction occurs between the substrate H<sub>2</sub>O<sub>2</sub> and O<sub>2</sub> (TMB), which was the basis for achieving more advanced nanozyme reaction network. Notably, H<sub>2</sub>O<sub>2</sub> (an important short-lived product in biochemical processes) was detected as an intermediate metabolite in the catalytic oxidation of TMB by Co-N-CNTs (Figure S6b), which made  $H_2O_2$  an intrinsic regulator of the nanozyme reaction network (Figure 4a). In addition, Co-N-CNTs exhibited a more catalase-like reaction in the presence of both H<sub>2</sub>O<sub>2</sub> and O<sub>2</sub> (TMB), whereas the performance of the oxide-like reaction was inhibited (Figure 3g, h). This suggested that H<sub>2</sub>O<sub>2</sub> had a competitive inhibitory effect on the O<sub>2</sub> (TMB) reaction at the Co-N<sub>4</sub> active site, which was the key to realizing feedback in the nanozyme reaction network. Therefore, as shown in Figure 4c (left) and Figure S9a, the addition of H<sub>2</sub>O<sub>2</sub> significantly reduced the catalytic oxidation of TMB to TMB<sub>ox1</sub> by Co-N-CNTs.

In fact, the intermediate metabolite  $H_2O_2$ , a common oxidant, also has an accelerating effect on the re-oxidation reaction of  $TMB_{ox1}$ , which provides the possibility of feedforward regulation. As shown in Figure 4c (right) and Figure S9b, the yield and generation rate of  $TMB_{ox2}$  increased with the increase in  $H_2O_2$  concentration (see mechanism in another work<sup>55</sup>). The results showed that  $H_2O_2$  promoted the rate and efficiency of the second re-oxidation step. In contrast to the inhibition of  $TMB_{ox1}$  production,  $H_2O_2$ , as an oxidation species, showed a positive feedforward effect on  $TMB_{ox2}$  production, promoting cascaded reaction catalysis. All these results collaboratively showed that the intermediate metabolite  $H_2O_2$  had a feedback inhibition effect in the first step of the reaction and a distinct feedforward activation effect in the second step of the reaction of the proposed nanozymatic reaction network (Figure 4a). Moreover, the degrees of feedback inhibition and feedforward activation at the same concentration of  $H_2O_2$  were also different. This interesting single stimulus enabled

different metabolic pathways to communicate and was a prerequisite for a metabolic response network to have a self-regulation function. This demonstrated the feasibility of using nanozymes as basic units to replace natural matter in the design of chemical reaction networks. This finding greatly expands the potential applications of lifelike materials and provides new options and possibilities for designing complicated living systems.

# Nanozymatic network-based cell mimics enabling highly selective and linear response to H<sub>2</sub>O<sub>2</sub>

Based on the above analysis, a cascade nanozymatic network with diverse responses to a single stimulus was successfully constructed. A further important step toward engineering biomimetic systems is to confine the reactions in an "artificial cell".<sup>60</sup> In general, enzymes are separated in the cell by endomembrane systems to prevent unwanted interference between enzymatic reactions. There is also a flow of substances between different organelles for metabolism and signaling. Therefore, separation of enzyme-like reactions in a single device is of great significance for constructing practical chemical reaction networks. Microfluidic chip technology provides an opportunity to achieve in vitro separation and assembly of enzyme-like reactions (Figure 5a).<sup>25</sup> The control sample, Co and N-doped carbon nanoparticles (Co-N-CNPs) were synthesized according to a previous reference.<sup>61</sup> An interesting geometric effect on the stability and activity of Co and N-doped carbon was observed when deposited in microfluidic chips, that is, nanotubular ones were superior to nanoparticular ones. It was supposed that for effective immobilization, each nanoparticle should contact the channels of microfluidic chips; in contrast, the crosslinked nanotube networks would inherently work better, even with fewer contact points. Accordingly, the active sites on the nanotubes would be more exposed, leading to higher activity. As shown in Figure 5b, the tubular characteristics of Co-N-CNTs favored the assembly and fixation in the chamber of the microfluidic chips compared to their particulate counterparts. Such advantages of Co-N-CNTs are crucial for the successful development of artificial organelles using microfluidic chips as a simplified model for long-term operation. The composition of the product was determined by sampling the outflow at regular intervals using an online UV-vis spectrometer. Precise control of the cascade reaction was achieved by altering the injected factors at entrances 2 and 3 in the microfluidic chip

(Figure 5c and S10). As mentioned earlier, evolution supposes that life may somehow come from some type of non-living matter millions of years ago. The successful implementation of the proposed cell mimics demonstrated the possibility of a flexible response process for the initial life evolution.



Figure 5. Co-N-CNTs based network in microfluidics as cell mimics and diverse response to H<sub>2</sub>O<sub>2</sub>. (a) Scheme of the microfluidic device. (b) Stability evaluation of Co-N-CNTs and Co-N-CNPs for catalytic oxidation in the microfluidic chip.

Conditions of injection: Entrance 1: TMB (0.5 mM); Entrance 2: closed; Entrance 3: closed. (c) Cascade-reaction module cycles in microfluidics. Conditions of injection: Entrance 1: TMB (0.5 mM); Entrance 2: closed; Entrance 3: buffer and micellar nanozyme were injected alternately. (d) Calibration curves of  $H_2O_2$  in the (left) feedback and (right) feedforward response. (e) Selective response to  $H_2O_2$ . Other interferents were g adrenaline, ascorbic acid, dopamine, glutathione, citric acid, uric acid, cysteine, histidine, leucine, alanine, valine, serine, glycine, proline, glucose, cytochrome C,  $Zn^{2+}$ ,  $Mn^{2+}$ ,  $Cu^{2+}$ ,  $Mg^{2+}$ ,  $Fe^{3+}$ , and  $NO_2^-$ .  $\Delta Y_1$  ( $\Delta Y_2$ ) is the change in the TMB<sub>ox1</sub> (TMB<sub>ox2</sub>) yield with and without external stimuli.

Notably, although more and more advanced, yet functional chemical reaction networks are being constructed, the question of practicality, and the suggestion of feasible uses of such systems beyond basic science, are still open. The concentration of  $H_2O_2$  in different environments varies greatly, typically ranging from micromolar (in vivo conditions, foodstuff, and drinking water) to tens of millimolar (hazardous wastes and bleaching environment).<sup>62-63</sup> Therefore, the selective and rapid response of H<sub>2</sub>O<sub>2</sub> over a wide range is an essential feature for cell mimics. By the feedback and feedforward response of Co-N-CNTs-derived network, a highly selective colorimetric response to H<sub>2</sub>O<sub>2</sub> with a wide range, particularly at high concentration, was developed. Owing to the stimulus response of different intensities, the linear response to  $H_2O_2$  at various concentrations was realized under the feedback (0.01 mM-1.6 mM) and feedforward (1 mM-100 mM) responses (Figure 5d, see Figure S11 and more details in SI). Compared with previous studies quantitatively responsive to H<sub>2</sub>O<sub>2</sub> (Table S4), the proposed cell mimics demonstrated a wider linear response range, which was particularly important for a primordial life-like process in mutable and harsh conditions. Owing to the multiple responses of variable intensities for the network to stimulus, the colorimetric response to H<sub>2</sub>O<sub>2</sub> in concentrations from micromoles to tens of millimoles per liter was realized.

Notably, living systems and conventional sensing methods often require receptors that are highly specific to the target (such as a lock and key) for recognition. Interestingly, the unique response characteristics of each step in the reaction network to  $H_2O_2$  enable a highly selective response from other interfering molecules without any

natural biological recognition units (e.g., nucleic acids, enzymes, and antibody/antigen). As shown in Figure 5e, the decrease in TMB<sub>ox1</sub> production and the increase in TMB<sub>ox2</sub> production were due to the addition of  $H_2O_2$ , making  $H_2O_2$  (the second quadrant) clearly different from other interferents, including biological reducing small molecules, amino acids, and metal ions. Therefore, without biological components, a cascade nanozymatic reaction network with diverse responses provides an effective way to specifically recognize small molecules. Such a mode that merely uses nonbiological chemicals to achieve substance-specific responses would be one possibility for initial life evolution. Moreover, beyond basic science, nanozymatic reaction networks would also be attractive for building highly selective biosensors with high stability and low cost for practical applications.

## Conclusion

In summary, we report a cascade nanozymatic network based on Co-N-CNTs. Under a single stimulus, that is, using H<sub>2</sub>O<sub>2</sub> (an important short-lived product in biochemical processes), distinctive feedback and feedforward responses of different intensities were observed for the proposed cascade reactions of two-electron TMB oxidation. The competition between different substrates, that is,  $H_2O_2$  and  $O_2$ , at the same Co-N<sub>4</sub> active site played a crucial role in successful cascade network construction. Co-N-CNTsderived network was further incorporated into a microfluidic flow reactor as a simplified artificial cell. Owing to the unique responses of variable intensities and modes, the proposed cell mimics exhibited highly selective recognition and linear perception to H<sub>2</sub>O<sub>2</sub> over a wide range of concentrations. The proposed nanozymatic network fills a gap in the reaction networks using non-living chemicals. This demonstrates the possibility of initial life evolution and opens a scalable pathway for chemical reaction networks to solve practical application problems beyond basic science. It is worth noting that as a proof of concept, the widely discussed oxidoreductase-like activity was used in the present research, although there is still a long way to synthesize versatile nanozymes in the future for more prominent chemical reaction networks.

#### Acknowledgements

This work was supported by the National Natural Science Foundation of China (21675022 and 21775018).

#### References

1. Lehn, J. M., From supramolecular chemistry towards constitutional dynamic chemistry and adaptive chemistry. *Chem. Soc. Rev.* 2007, *36*, 151-160.

2. Rizzuto, F. J.; Platnich, C. M.; Luo, X.; Shen, Y.; Dore, M. D.; Lachance-Brais, C.; Guarné, A.; Cosa, G.; Sleiman, H. F., A dissipative pathway for the structural evolution of DNA fibres. *Nat. Chem.* **2021**, *13*, 843-849.

3. Zhou, Z.; Ouyang, Y.; Wang, J.; Willner, I., Dissipative Gated and Cascaded DNA Networks. *J. Am. Chem. Soc.* **2021**, *143*, 5071-5079.

4. Helwig, B.; van Sluijs, B.; Pogodaev, A. A.; Postma, S. G. J.; Huck, W. T. S., Bottom-Up Construction of an Adaptive Enzymatic Reaction Network. *Angew. Chem., Int. Ed.* **2018**, *57*, 14065-14069.

5. Yue, L.; Wang, S.; Zhou, Z.; Willner, I., Nucleic Acid Based Constitutional Dynamic Networks: From Basic Principles to Applications. *J. Am. Chem. Soc.* 2020, *142*, 21577-21594.

6. Peng, R.; Xu, L.; Wang, H.; Lyu, Y.; Wang, D.; Bi, C.; Cui, C.; Fan, C.; Liu, Q.; Zhang, X.; Tan, W., DNA-based artificial molecular signaling system that mimics basic elements of reception and response. *Nat. Commun.* **2020**, *11*, 978.

7. Wang, S.; Yue, L.; Li, Z. Y.; Zhang, J.; Tian, H.; Willner, I., Light-Induced Reversible Reconfiguration of DNA-Based Constitutional Dynamic Networks: Application to Switchable Catalysis. *Angew. Chem., Int. Ed.* **2018,** *57*, 8105-8109.

8. Teders, M.; Pogodaev, A. A.; Bojanov, G.; Huck, W. T. S., Reversible Photoswitchable Inhibitors Generate Ultrasensitivity in Out-of-Equilibrium Enzymatic Reactions. *J. Am. Chem. Soc.* **2021**, *143*, 5709-5716.

9. Semenov, S. N.; Wong, A. S.; van der Made, R. M.; Postma, S. G.; Groen, J.; van Roekel, H. W.; de Greef, T. F.; Huck, W. T., Rational design of functional and tunable oscillating enzymatic networks. *Nat. Chem.* **2015**, *7*, 160-165.

10. Pogodaev, A. A.; Wong, A. S. Y.; Huck, W. T. S., Photochemical Control over

Oscillations in Chemical Reaction Networks. J. Am. Chem. Soc. 2017, 139, 15296-15299.

Yue, L.; Wang, S.; Wulf, V.; Lilienthal, S.; Remacle, F.; Levine, R. D.; Willner,
 I., Consecutive feedback-driven constitutional dynamic networks. *Proc. Natl. Acad. Sci.* U. S. A. 2019, *116*, 2843-2848.

12. Han, D.; Wu, C.; You, M.; Zhang, T.; Wan, S.; Chen, T.; Qiu, L.; Zheng, Z.; Liang, H.; Tan, W., A cascade reaction network mimicking the basic functional steps of adaptive immune response. *Nat. Chem.* **2015**, *7*, 835-841.

13. Wang, C.; Yue, L.; Willner, I., Controlling biocatalytic cascades with enzyme-DNA dynamic networks. *Nat. Catal.* **2020**, *3*, 941-950.

14. Srinivas, N.; Parkin, J.; Seelig, G.; Winfree, E.; Soloveichik, D., Enzyme-free nucleic acid dynamical systems. *Science* **2017**, *358*, eaal2052.

15. Oparin, A., Proikhozndenie Zhizni. Izd, Moskovskij Rabochij, Moscow, 1924.

16. Haldane, J. B. S., The origin of life. *Rationalist Annual* **1929**, *148*, 3-10.

17. Gao, L.; Zhuang, J.; Nie, L.; Zhang, J.; Zhang, Y.; Gu, N.; Wang, T.; Feng, J.; Yang, D.; Perrett, S.; Yan, X., Intrinsic peroxidase-like activity of ferromagnetic nanoparticles. *Nat. Nanotechnol.* **2007**, *2*, 577-583.

18. Wu, J.; Wang, X.; Wang, Q.; Lou, Z.; Li, S.; Zhu, Y.; Qin, L.; Wei, H., Nanomaterials with enzyme-like characteristics (nanozymes): next-generation artificial enzymes (II). *Chem. Soc. Rev.* **2019**, *48*, 1004-1076.

19. Huang, Y.; Ren, J.; Qu, X., Nanozymes: Classification, Catalytic Mechanisms, Activity Regulation, and Applications. *Chem. Rev.* **2019**, *119*, 4357-4412.

20. Jiao, L.; Xu, W.; Yan, H.; Wu, Y.; Liu, C.; Du, D.; Lin, Y.; Zhu, C., Fe-N-C Single-Atom Nanozymes for the Intracellular Hydrogen Peroxide Detection. *Anal. Chem.* **2019**, *91*, 11994-11999.

21. Zhen, W.; Liu, Y.; Wang, W.; Zhang, M.; Hu, W.; Jia, X.; Wang, C.; Jiang, X., Specific "Unlocking" of a Nanozyme-Based Butterfly Effect To Break the Evolutionary Fitness of Chaotic Tumors. *Angew. Chem., Int. Ed.* **2020**, *59*, 9491-9497.

22. Zhou, Y.; Liu, C.; Yu, Y.; Yin, M.; Sun, J.; Huang, J.; Chen, N.; Wang, H.; Fan,

C.; Song, H., An Organelle-Specific Nanozyme for Diabetes Care in Genetically or Diet-Induced Models. *Adv. Mater.* **2020**, *32*, 2003708.

23. Zhen, W.; An, S.; Wang, S.; Hu, W.; Li, Y.; Jiang, X.; Li, J., Precise Subcellular Organelle Targeting for Boosting Endogenous-Stimuli-Mediated Tumor Therapy. *Adv. Mater.* **2021**, *33*, 2101572.

24. Zhang, X.; Lin, S.; Huang, R.; Gupta, A.; Fedeli, S.; Cao-Milán, R.; Luther, D. C.; Liu, Y.; Jiang, M.; Li, G., Degradable ZnS-Supported Bioorthogonal Nanozymes with Enhanced Catalytic Activity for Intracellular Activation of Therapeutics. *J. Am. Chem. Soc.* **2022**, *144*, 12893-12900.

25. Zhou, Q.; Yang, H.; Chen, X.; Xu, Y.; Han, D.; Zhou, S.; Liu, S.; Shen, Y.; Zhang, Y., Cascaded Nanozyme System with High Reaction Selectivity by Substrate Screening and Channeling in a Microfluidic Device. *Angew. Chem., Int. Ed.* **2022**, *61*, e202112453.

26. Xu, W.; Jiao, L.; Wu, Y.; Hu, L.; Gu, W.; Zhu, C., Metal–Organic Frameworks Enhance Biomimetic Cascade Catalysis for Biosensing. *Adv. Mater.* **2021**, *33*, 2005172.

27. Voet, Principles of Biochemistry, 4th Edition International Student Version.2015.

28. Shen, X.; Liu, W.; Gao, X.; Lu, Z.; Wu, X.; Gao, X., Mechanisms of Oxidase and Superoxide Dismutation-like Activities of Gold, Silver, Platinum, and Palladium, and Their Alloys: A General Way to the Activation of Molecular Oxygen. *J. Am. Chem. Soc.* **2015**, *137*, 15882-15891.

29. Zhang, Z.; Zhang, X.; Liu, B.; Liu, J., Molecular Imprinting on Inorganic Nanozymes for Hundred-fold Enzyme Specificity. *J. Am. Chem. Soc.* **2017**, *139*, 5412-5419.

30. Zhang, P.; Sun, D.; Cho, A.; Weon, S.; Lee, S.; Lee, J.; Han, J. W.; Kim, D. P.; Choi, W., Modified carbon nitride nanozyme as bifunctional glucose oxidaseperoxidase for metal-free bioinspired cascade photocatalysis. *Nat. Commun.* **2019**, *10*, 940.

31. Li, M.; Chen, J.; Wu, W.; Fang, Y.; Dong, S., Oxidase-like MOF-818

Nanozyme with High Specificity for Catalysis of Catechol Oxidation. J. Am. Chem. Soc. 2020, 142, 15569-15574.

32. Wang, Y.; Jia, G.; Cui, X.; Zhao, X.; Zhang, Q.; Gu, L.; Zheng, L.; Li, L. H.; Wu, Q.; Singh, D. J.; Matsumura, D.; Tsuji, T.; Cui, Y.-T.; Zhao, J.; Zheng, W., Coordination Number Regulation of Molybdenum Single-Atom Nanozyme Peroxidase-like Specificity. *Chem.* **2021**, *7*, 436-449.

33. Chen, X.; Wang, Y.; Dai, X.; Ding, L.; Chen, J.; Yao, G.; Liu, X.; Luo, S.; Shi, J.; Wang, L.; Nechushtai, R.; Pikarsky, E.; Willner, I.; Fan, C.; Li, J., Single-Stranded DNA-Encoded Gold Nanoparticle Clusters as Programmable Enzyme Equivalents. *J. Am. Chem. Soc.* **2022**, *144*, 6311-6320.

34. He, F.; Mi, L.; Shen, Y.; Mori, T.; Liu, S.; Zhang, Y., Fe-N-C Artificial Enzyme: Activation of Oxygen for Dehydrogenation and Monoxygenation of Organic Substrates under Mild Condition and Cancer Therapeutic Application. *ACS Appl. Mater. Interfaces* **2018**, *10*, 35327-35333.

35. Xu, B.; Wang, H.; Wang, W.; Gao, L.; Li, S.; Pan, X.; Wang, H.; Yang, H.; Meng, X.; Wu, Q.; Zheng, L.; Chen, S.; Shi, X.; Fan, K.; Yan, X.; Liu, H., A Single-Atom Nanozyme for Wound Disinfection Applications. *Angew. Chem., Int. Ed.* **2019**, *58*, 4911-4916.

36. Huang, L.; Chen, J.; Gan, L.; Wang, J.; Dong, S., Single-atom nanozymes. *Sci. Adv.* **2019**, *5*, eaav5490.

37. Jiao, L.; Yan, H.; Wu, Y.; Gu, W.; Zhu, C.; Du, D.; Lin, Y., When Nanozymes Meet Single-Atom Catalysis. *Angew. Chem., Int. Ed.* **2020**, *59*, 2565-2576.

38. Cao, F.; Zhang, L.; You, Y.; Zheng, L.; Ren, J.; Qu, X., An Enzyme-Mimicking Single-Atom Catalyst as an Efficient Multiple Reactive Oxygen and Nitrogen Species Scavenger for Sepsis Management. *Angew. Chem., Int. Ed.* **2020**, *59*, 5108-5115.

 Ji, S.; Jiang, B.; Hao, H.; Chen, Y.; Dong, J.; Mao, Y.; Zhang, Z.; Gao, R.; Chen,
 W.; Zhang, R.; Liang, Q.; Li, H.; Liu, S.; Wang, Y.; Zhang, Q.; Gu, L.; Duan, D.; Liang,
 M.; Wang, D.; Yan, X.; Li, Y., Matching the kinetics of natural enzymes with a singleatom iron nanozyme. *Nat. Catal.* 2021, *4*, 407-417. 40. Wang, X.; Song, J.; Zhang, F.; He, C.; Hu, Z.; Wang, Z., Electricity Generation based on One-Dimensional Group-III Nitride Nanomaterials. *Adv. Mater.* **2010**, *22*, 2155-2158.

41. Yan, Y.; Miao, J.; Yang, Z.; Xiao, F.; Yang, H.; Liu, B.; Yang, Y., Carbon nanotube catalysts: recent advances in synthesis, characterization and applications. *Chem. Soc. Rev.* **2015**, *44*, 3295-3346.

42. Cheng, Y.; Zhao, S.; Johannessen, B.; Veder, J. P.; Saunders, M.; Rowles, M. R.; Cheng, M.; Liu, C.; Chisholm, M. F.; De Marco, R.; Cheng, H.; Yang, S.; Jiang, S., Atomically Dispersed Transition Metals on Carbon Nanotubes with Ultrahigh Loading for Selective Electrochemical Carbon Dioxide Reduction. *Adv. Mater.* **2018**, *30*, e1706287.

43. Xia, D.; Yang, X.; Xie, L.; Wei, Y.; Jiang, W.; Dou, M.; Li, X.; Li, J.; Gan, L.; Kang, F., Direct Growth of Carbon Nanotubes Doped with Single Atomic Fe-N<sub>4</sub> Active Sites and Neighboring Graphitic Nitrogen for Efficient and Stable Oxygen Reduction Electrocatalysis. *Adv. Funct. Mater.* **2019**, *29*, 1906174.

Pan, Y.; Lin, R.; Chen, Y.; Liu, S.; Zhu, W.; Cao, X.; Chen, W.; Wu, K.; Cheong,
W. C.; Wang, Y.; Zheng, L.; Luo, J.; Lin, Y.; Liu, Y.; Liu, C.; Li, J.; Lu, Q.; Chen, X.;
Wang, D.; Peng, Q.; Chen, C.; Li, Y., Design of Single-Atom Co-N<sub>5</sub> Catalytic Site: A
Robust Electrocatalyst for CO<sub>2</sub> Reduction with Nearly 100% CO Selectivity and
Remarkable Stability. *J. Am. Chem. Soc.* 2018, *140*, 4218-4221.

45. Fan, K.; Xi, J.; Fan, L.; Wang, P.; Zhu, C.; Tang, Y.; Xu, X.; Liang, M.; Jiang, B.; Yan, X., In vivo guiding nitrogen-doped carbon nanozyme for tumor catalytic therapy. *Nat. Commun.* **2018**, *9*, 1440.

46. Xi, J.; Zhang, R.; Wang, L.; Xu, W.; Liang, Q.; Li, J.; Jiang, J.; Yang, Y.; Yan, X.; Fan, K.; Gao, L., A Nanozyme-Based Artificial Peroxisome Ameliorates Hyperuricemia and Ischemic Stroke. *Adv. Funct. Mater.* **2020**, *31*.

47. Niu, R.; Liu, Y.; Wang, Y.; Zhang, H., An Fe-based single-atom nanozyme with multi-enzyme activity for parallel catalytic therapy via a cascade reaction. *Chem. Commun.* **2022**, *58*, 7924-7927.

48. Wang, Q.; Zhou, Z.; Lai, Y.; You, Y.; Liu, J. G.; Wu, X.; Terefe, E.; Chen, C.; Song, L.; Rauf, M.; Tian, N.; Sun, S., Phenylenediamine-based FeN(x)/C catalyst with high activity for oxygen reduction in acid medium and its active-site probing. *J. Am. Chem. Soc.* **2014**, *136*, 10882-10885.

49. Liang, H.; Bruller, S.; Dong, R.; Zhang, J.; Feng, X.; Mullen, K., Molecular metal-N<sub>x</sub> centres in porous carbon for electrocatalytic hydrogen evolution. *Nat. Commun.* **2015**, *6*, 7992.

50. Xu, Y.; Xue, J.; Zhou, Q.; Zheng, Y.; Chen, X.; Liu, S.; Shen, Y.; Zhang, Y., The Fe-N-C Nanozyme with Both Accelerated and Inhibited Biocatalytic Activities Capable of Accessing Drug-Drug Interactions. *Angew. Chem., Int. Ed.* **2020**, *59*, 14498-14503.

Pérez Galende, P.; Hidalgo Cuadrado, N.; Kostetsky, E. Y.; Roig, M. G.; Villar,
 E.; Shnyrov, V. L.; Kennedy, J. F., Kinetics of Spanish broom peroxidase obeys a Ping-Pong Bi-Bi mechanism with competitive inhibition by substrates. *Int. J. Biol. Macromol.* 2015, *81*, 1005-1011.

52. Liang, X.; Han, L., White Peroxidase-Mimicking Nanozymes: Colorimetric Pesticide Assay without Interferences of O<sub>2</sub> and Color. *Adv. Funct. Mater.* **2020**, *30*, 2001933.

53. Zhang, C.; Chen, L.; Bai, Q.; Wang, L.; Li, S.; Sui, N.; Yang, D.; Zhu, Z., Nonmetal Graphdiyne Nanozyme-Based Ferroptosis-Apoptosis Strategy for Colon Cancer Therapy. *ACS Appl. Mater. Interfaces* **2022**, *14*, 27720-27732.

54. Josephy, P. D.; Eling, T.; Mason, R. P., The horseradish peroxidase-catalyzed oxidation of 3,5,3',5'-tetramethylbenzidine. Free radical and charge-transfer complex intermediates. *J. Biol. Chem.* **1982**, *257*, 3669-3675.

55. Zhu, C.; Xu, Y.; Hong, Q.; Cao, X.; Wang, K.; Shen, Y.; Liu, S.; Zhang, Y., Enhancing Reliability of Chromogenic Bioassay with Two-Electron TMB Oxidation Enabled by Self-assembled Surfactants Nanozyme. *ChemRxiv.* **2022**, *10.26434/chemrxiv-2022-cw9v0*.

56. Piszkiewicz, D., Micelle Catalyzed Reactions Are Models of Enzyme

Catalyzed Reactions Which Show Positive Homotropic Interactions. J. Am. Chem. Soc. **1976**, *98*, 3053-3055.

57. Serrano-Luginbühl, S.; Ruiz-Mirazo, K.; Ostaszewski, R.; Gallou, F.; Walde, P., Soft and dispersed interface-rich aqueous systems that promote and guide chemical reactions. *Nat. Rev. Chem.* **2018**, *2*, 306-327.

58. Misono, Y.; Ohkata, Y.; Morikawa, T.; Itoh, K., Resonance Raman and absorption spectroscopic studies on the electrochemical oxidation processes of 3, 3', 5, 5'-tetramethylbenzidine. *J. Electroanal. Chem.* **1997**, *436*, 203-212.

59. Kumar, A.; Gupta, M. K.; Kumar, M., Non-ionic surfactant catalyzed synthesis of Betti base in water. *Tetrahedron Lett.* **2010**, *51*, 1582-1584.

60. Gaitzsch, J.; Huang, X.; Voit, B., Engineering Functional Polymer Capsules toward Smart Nanoreactors. *Chem. Rev.* **2016**, *116*, 1053-1093.

61. Chen, X.; Zhao, L.; Wu, K.; Yang, H.; Zhou, Q.; Xu, Y.; Zheng, Y.; Shen, Y.; Liu, S.; Zhang, Y., Bound oxygen-atom transfer endows peroxidase-mimic M-N-C with high substrate selectivity. *Chem. Sci.* **2021**, *12*, 8865-8871.

62. Chidambara Raj, C. B.; Li Quen, H., Advanced oxidation processes for wastewater treatment: Optimization of UV/H<sub>2</sub>O<sub>2</sub> process through a statistical technique. *Chem. Eng. Sci.* **2005**, *60*, 5305-5311.

63. Soares, D. G.; Basso, F. G.; Pontes, E. C. V.; Garcia, L. d. F. R.; Hebling, J.; de Souza Costa, C. A., Effective tooth-bleaching protocols capable of reducing H<sub>2</sub>O<sub>2</sub> diffusion through enamel and dentine. *Journal of Dentistry* **2014**, *42*, 351-358.