# Mapping Structure-Property Relationships in Fullerene Systems: A Computational Study from $C_{20}$ to $C_{60}$

Bin Liu<sup>1</sup>, Jirui Jin<sup>1</sup>, and Mingjie Liu<sup>1\*</sup>

<sup>1</sup>Department of Chemistry, University of Florida, Gainesville, FL 32611, United States. \*mingjieliu@ufl.edu

March 11, 2024

#### Abstract

Fullerenes, as characteristic carbon nanomaterials, offer significant potential for diverse applications due to their structural diversity and tunable properties. Numerous isomers can exist for a specific fullerene size, yet a comprehensive understanding of their fundamental properties remains elusive. In this study, we construct an up-to-date computational database for  $C_{20}$ - $C_{60}$ fullerenes, consisting of 5770 structures, and calculate 12 fundamental properties using DFT, including stability (binding energy), electronic properties (HOMO-LUMO gap), and solubility (partition coefficient logP). Our findings reveal that the HOMO-LUMO gap weakly correlates with both binding energy and logP, indicating that electronic properties can be tailored for specific uses without affecting stability or solubility. In addition, we introduce a set of novel topological features and geometric measures to investigate structure-property relationships. For the first time, we apply atom, bond, and hexagon features to effectively predict the stability of  $C_{20}$ - $C_{60}$  full erenes, surpassing the conventional qualitative isolated pentagon rule, and demonstrating their robust transferability to larger-size fullerenes beyond  $C_{60}$ . Our work offers guidance for optimizing fullerenes as electron acceptors in organic solar cells and lays a foundational understanding of their functionalization and applications in energy conversion and nanomaterial sciences.

# 1 Introduction

Carbon-based nanomaterials, including fullerenes, nanotubes, and graphene, are widely utilized in various fields for their unique properties that arise from their aromatic carbon frameworks.[1–5] Among them, fullerenes are polyhedral cage molecules with the general molecular formula  $C_{20+2n}$  ( $n \ge 0$ ,  $n \ne 1$ ) composed of sp<sup>2</sup> hybridized carbons arranged in pentagon and hexagon rings. The variation in the arrangement of these rings across the fullerene cages leads to numerous isomeric structures for each fullerene size. For example,  $C_{60}$  fullerene adopts 1812 non-isomorphic structures with different distributions of the 12 pentagon and 20 hexagon rings on a spherical surface. The number of possible isomers for fullerene cages with N = 20 + 2n carbon atoms increases at a rate of  $O(N^9)$ [6], creating an extensive family of fullerenes with a vast array of isomers. The unique zero-dimensional spherical cage structures of fullerenes contribute to their remarkable physical and chemical characteristics, such as high thermal and electrical conductivity, extraordinary tensile strength, and efficient electron donation and acceptance abilities.[7] Owing to their structural diversity that offers tunable electronic properties and reactivities, fullerenes have been extensively investigated as components in optoelectronics[8–11], solar cells[12–14], gas storage and separation[15, 16], biology and medicine[17– 19]. Although fullerenes have significant untapped potential in various applications, fully harnessing their capabilities – especially in customizing electronic properties and functionalization for practical uses – requires a thorough understanding of the structure-property relationships across the entire spectrum of fullerene varieties.

The investigation of fundamental properties across different fullerene isomers has been the focus of numerous earlier studies. [20–28] For example, Rebecca et al. investigated the relative energy distribution among the 1812 isomers of  $C_{60}$  fullerene with DFT method and correlated the isomeric stability with a variety of topological indices, electronic, and geometric properties. Aside from the common isolated pentagon rule (IPR), they proposed that a small pentagon signature  $P_1$ , a large volume, and a more spherical cage can lead to a relatively stable isomer. [23] Zhao et al. explored the origin and characteristics of isomeric stability in four fullerene systems,  $C_{44}$ ,  $C_{48}$ ,  $C_{52}$ , and  $C_{60}$ , using DFT simulations. Through energy decomposition analysis, they found that electrostatic potential is the primary determinant of isomeric stability, surpassing other factors such as steric and quantum effects. They further highlighted the importance of spatial delocalization of the electron density on the stabilization of fullerene isomers. [29] Chan and Karton studied the size dependence of a variety of electronic properties in small fullerenes from  $C_{20}$  to  $C_{50}$  with 812 isomeric structures, including the energy difference between the lowest-energy singlet and triplet states (i.e.,  $S_0$  and  $T_1$ , or  $T_0$  and  $S_1$ ), and the related quantities of ionization potential (IP) and electron affinity (EA). They found a linear correlation between triplet-singlet energy difference and IP-EA difference, and further surveyed larger fullerenes in search of candidates with superior charge-transfer properties. [30] Based on our comprehensive literature review, we observed that the previous research into the structure-property relationships of fullerenes has been grounded in selected datasets that represent an incomplete array of fullerene isomers, with the bulk of these studies primarily focusing on stability analysis. To the best of our knowledge, there remains a gap in literature for a comprehensive and accurate examination of the fundamental properties of all fullerene isomers from  $C_{20}$  to  $C_{60}$ .

In this study, we have compiled the most extensive computational dataset of  $C_{20}$ - $C_{60}$  fullerenes to date, incorporating a total of 5770 structures. Following our benchmark study, we calculated 12 fundamental properties with DFT-level accuracy, e.g., fullerene binding energy  $(E_b)$ , HOMO-LUMO gap  $(E_g)$ , and partition coefficient of solvation free energies in 1,2-dichlorobenzene (ODCB) and water phases as listed in Table 1, and evaluated their Pearson correlation coefficients. The weak correlations between  $E_g$  and both  $E_b$  and logP suggest that favorable electronic properties can be independently adjusted for particular applications without compromising the stability and solubility. To delve deeper into the structural features influencing these properties, we introduced various topological indices and geometric measures, going beyond the IPR. For the first time, we reveal that compared to pentagon-related features, atom, bond, and hexagon features demonstrate significantly superior effectiveness in capturing the intricate local structural environments of the carbon atoms on the spherical cage. The linear models fitted by those features enable precise predictions of the fullerene stability across various sizes and show robust transferability to larger-size fullerenes beyond  $C_{60}$ . We further offer a practical guide for researchers interested in screening fullerenes for optimal electron acceptor candidates in organic solar cells. Our study provides a deep understanding of the structure-property relationships across fullerene isomers, setting a foundation for future advancements in fullerene functionalization and applications in energy conversion and nanosciences.

# 2 Computational details

#### 2.1 Dataset construction

Here we constructed the fullerene dataset from  $C_{20}$  to  $C_{60}$  with a total of 5770 structures. Table S1 lists the number of possible isomers, hexagon rings, C-C bonds, and IPR isomers for each fullerene cage size. The initial structures of fullerenes from  $C_{20}$  to  $C_{52}$  with 1249 structures were obtained from the online fullerene database[31], and 1812 isomer structures of  $C_{60}$  were adopted from the published paper.[23] For the remaining 2709 fullerene structures from  $C_{54}$  to  $C_{58}$ , we utilized the program FULLERENE (version 4.5) to generate the initial xyz coordinates and applied a force field specifically designed for fullerenes to optimize them.[32] All the optimized structures from our study can be found in the Supporting Information.

#### 2.2 DFT calculations

All the DFT calculations were performed with Gaussian 16 package.[33] The B3LYP hybrid functional[34–36] together with D3 dispersion correction[37] and 6-31G\* basis set were employed for geometry optimization of all 5770 fullerene isomers. The maximum force tolerance was set to 0.02 eV/Å. Subsequently, single-point calculations at singlet state were carried out with B3LYP functional and 6-311G\* basis set to determine the energies and electronic properties. The continuum solvation model based on density (SMD) was used to obtain the solvation energy.[38] The dielectric constants of water and ODCB solvents are set as 78 and 10, respectively.

#### 2.3 Topological features and indices

We introduced 4 types of topological features, namely, atom, bond, pentagon, and hexagon features to characterize the structure of fullerenes. Each carbon atom in the fullerene cage can form three C-C bonds, and each bond is surrounded by four polygonal rings which belong to either pentagon or hexagon. The atom features categorize carbon atoms into 4 types, denoted as  $\{n_i | i = 0, 1, 2, 3\}$ , representing the count of carbon atoms fused to *i* adjacent pentagons (Figure S1). Similarly, the bond features define 9 types of C-C bonds  $\{e_i | i = 0, ..., 8\}$  according to the number and arrangements of the 4 surrounding polygonal rings (Figure S2). The pentagon features define 8 types of pentagons  $\{p_i | i = 0, ..., 7\}$  depending on the number of arrangements of the 5 abutting polygons (Figure S3). The hexagon features define 13 types of hexagons  $\{h_i | i = 0, ..., 12\}$  which rely on the number and arrangements of the 6 neighboring polygons (Figure S4). Table S2 lists the values of these 4 topological features for  $C_{20}$ -#1,  $C_{60}$ -#1, and  $C_{60}$ -#1812. It is important to note that Fowler and Manolopoulos also designed pentagon  $\{p'_i | i = 0, ..., 5\}$  and hexagon  $\{h'_i | i = 0, ..., 6\}$  indices; however, they only considered the number of pentagons (hexagons) attached to *i* other pentagons (hexagons) but ignored different arrangements of the pentagons (hexagons).[39, 40] For instance,  $p'_2$ equals the sum of  $p_2$  and  $p_3$ , whereas  $p'_3$  equals the sum of  $p_4$  and  $p_5$  (see Figure S3). They further consolidated the pentagon and hexagon indices into a more practical set of topological indices, namely, the pentagon signature  $P_1$ , and the n-th moment hexagon signature  $H_n$  using the formulas below:

$$P_1 = \frac{1}{2} \sum_{i=0}^{5} i p'_i \tag{1}$$

$$H_n = \sum_{i=0}^{6} i^n h'_i$$
 (2)

For example, the IPR-conforming C<sub>60</sub>–Ih buckminsterfullerene (C<sub>60</sub>–#1), where all the pentagons are isolated by the hexagons yields  $p'_0=12$  and  $h'_3=20$  with all other terms equating to zero, resulting in  $P_1=0$ ,  $H_1=60$ , and  $H_2=180$ .

#### 2.4 Geometric measures

We computed 7 geometric measures based on the optimized fullerene structures: average bond length  $(\bar{d})$ , volume (V), surface area (A), ratio of surface area and volume (A/V), Fowler asymmetry parameter  $(F_{asym})[41]$ , deviation from isoperimetric quotient  $(D_{IPQ})[42]$ , and the average curvature  $(\bar{\kappa})$  of the fullerene cage.

 $\overline{d}$  is the mean of all C-C bond lengths within the structure. V of a fullerene is determined by treating the cage as a polyhedron, composed entirely of pentagons and hexagons as its facets. Analogous to a polygon being segmented into triangles, the polyhedron fullerene cage can similarly be deconstructed into a collection of tetrahedra, with its volume being the sum of these tetrahedra. Similarly, A of a fullerene cage is the sum of the areas of the pentagons and hexagons constituting the fullerene cage, each of which can be further divided into triangles.

 $F_{asym}$  is calculated as follows:

$$F_{asym} = \sum_{i}^{N} \frac{(R_i - R_{av})^2}{R_{av}^2}$$
(3)

in which  $R_i$  is the radial distance of each carbon atom *i* from the center of mass of the fullerene,  $R_{av}$  is the average radial distance, and N represents the number of carbon atoms in the fullerene.  $F_{asym}$  equals 0 when all atoms lie on an ideal spherical fullerene cage, such as C<sub>60</sub>–Ih (C<sub>60</sub>–#1).  $D_{IPQ}$  is calculated from the volume and surface area as follows:[23]

$$D_{IPD} = 1 - \frac{36\pi V^2}{A^3} \tag{4}$$

 $D_{IPD}$  is dimensionless and equals 0 for a perfect sphere.

The curvature at each carbon atom is defined as follows: in a given fullerene molecule, a carbon atom, designated as the central carbon, forms a tetrahedron with its three neighboring atoms. This tetrahedron uniquely dictates a circumsphere where all four carbon atoms reside. The radius of the circumsphere represents the curvature radius (R) at the central carbon atom's position. Consequently, the curvature ( $\kappa$ ) is the reciprocal of R:

$$\kappa = \frac{1}{R} \tag{5}$$

Thus,  $\bar{\kappa}$  of the fullerene cage can be obtained by calculating the radius of curvature at each carbon atom of the fullerene cage.

## **3** Results and Discussion

#### 3.1 Fundamental properties analysis

#### 3.1.1 Stability

First, we evaluated the thermodynamic stability of 5770 fullerene structures by calculating the binding energy per carbon atom with the atomic carbon at triplet state as the reference.[43]

$$E_b(C_n) = \frac{1}{n}(E_{C_n} - nE_C)$$
(6)

 $E_{C_n}$  is the total energy of fullerene  $C_n$  with n carbon atoms, whereas  $E_C$  is the energy of an isolated carbon atom at triplet state. The binding energy distribution indicates a trend of decreasing binding energies as the fullerene cage size increases, as depicted in Figure 1(a). Within the dataset, the renowned C<sub>60</sub>–Ih buckminsterfullerene (C<sub>60</sub>–#1), which possesses icosahedral symmetry and is the sole isomer conforming to the IPR, exhibits the lowest  $E_b$  of -6.96 eV/atom, comparable to the experimental value of -7.04 eV/atom.[44] Conversely, the C<sub>20</sub>–#1 fullerene, comprised solely of 12 pentagons devoid of hexagons, exhibits the highest  $E_b$  of -6.12 eV/atom. The statistical analysis of the  $E_b$  values is detailed in Table S3, together with the molecular geometries of fullerene isomers shown in Figure S5.

To assess the accuracy of the DFT calculated energies, we benchmarked the relative energies of ten  $C_{60}$  isomers compared to  $C_{60}$ -#1 with the relative energies from DLPNO-CCSD(T)/CBS\* reference results adopted from Rebecca et al's work.[23] The geometries of these ten isomers are shown in Figure S6. The DLPNO-CCSD(T)/CBS\* relative energies are expected to have an error of  $\pm 0.5$  kcal/mol which can be used for benchmark.[45, 46] The comparison reveals that the outcomes obtained using B3LYP-D3/6-311G\* exhibit a consistent ranking of relative energies for the ten

fullerene isomers with small deviations when benchmarked against the DLPNO-CCSD(T)/CBS\* results (Table S4).

The histogram illustrating the binding energy distribution among the 5770 fullerene structures reveals that 80% are within the energy range of -6.85~-6.72 eV/atom, with an average binding energy of -6.79±0.06 eV/atom (Figure 2(a)). This indicates that most of the fullerene structures are much more stable than C<sub>20</sub>. Prior research has shown that C<sub>20</sub> can be synthesized in the gas-phase[47], indicating the possibility of synthesizing other more stable fullerene structures. In addition, other smaller fullerene like C<sub>36</sub> have been synthesized experimentally using the arc-discharge method.[48] Functionalization, both endohedral and exohedral, has been shown to enhance the stability of non-IPR fullerene isomers, exemplified by compound such as  $C_{50}Cl_{10}[49]$ ,  $C_{60}Cl_{12}$ , and  $C_{60}Cl_8[50]$ . We anticipate that our comprehensive computed binding energy will provide a reliable benchmark for future theoretical and experimental research into fullerene synthesis and functionalization.

#### 3.1.2 Electronic properties

Frontier molecular orbitals, i.e., HOMO and LUMO levels, along with HOMO-LUMO gap  $(E_g)$ , are critical properties in evaluating the electronic and optical properties, electric conductivity, charge transport, and chemical reactivity of materials. Specifically, understanding the distribution of these fundamental properties across various sizes of fullerenes is essential for designing and optimizing fullerenes and their derivatives with specific requirements, such as improved conductivity, enhanced light absorption, or more favourable reactivity. In contrast to the distribution of  $E_b$  values, the distribution of  $E_g$  exhibits a lower dependence on the size of the fullerene cage, as showed in Figure 1(b). The histogram plot in Figure 2(b) reveals that approximately 80% of  $E_g$  values are within the range of 0.97~1.54 eV, with the maximum gap being 2.72 eV (C<sub>60</sub>-#1) and minimum at 0.41 eV (C<sub>60</sub>-#1748), calculated at the B3LYP level (also see Table S3 and Figure S5). The distributions of HOMO and LUMO also exhibit weak dependence on the fullerene size, and the details can be found in Figure S7.

Currently, fullerene  $C_{60}$ ,  $C_{70}$ ,  $C_{84}$  and their derivatives have been widely explored as the acceptor to pair with conjugated polymer donors in organic solar cells (OSCs).[12, 51–53] To offer a practical guide for researchers in the field of OSCs, we applied Scharber's model[54–56] to assess the photovoltaic performance of the fullerenes. The power conversion efficiency (PCE) of an OSC device under sunlight irradiation is determined by open-circuit voltage ( $V_{OC}$ ), short-circuit current density ( $J_{SC}$ ), fill factor (FF), and the power of incident light  $P_{in}$  with:

$$PCE = \frac{P_{out}}{P_{in}} = \frac{V_{OC}J_{SC}FF}{P_{in}} \times 100\%$$
<sup>(7)</sup>

 $P_{in}$  is calculated by integrating the AM1.5 spectra[57] across the wavelength, resulting in an approximate value of 1000  $W/m^2$ .  $V_{OC}$  can be determined by the HOMO level of polymer donor  $(E^D_{HOMO})$ and the LUMO level of fullerene acceptor  $(E^A_{LUMO})$  as follows:

$$V_{OC} = \frac{1}{e} |E_{HOMO}^D - E_{LUMO}^A| - 0.3$$
(8)

 $J_{SC}$  is assumed to be the current from absorbing all the incident photons above the  $E_g$  of the conjugated polymer donor as follows:

$$J_{SC} = EQE \int_{E_g}^{\infty} e\Phi_{ph}(E)dE \tag{9}$$

in which the external quantum efficiency EQE is set to 0.65, and  $\Phi_{ph}$  represents the incident solar photon flux density as a function of energy E. In addition, FF in eq(7) is set to 0.65. Furthermore, in fullerene-based OSCs, energy offsets exceeding 0.3 eV between the HOMO levels of the polymer donor and fullerene ( $\Delta E_{HOMO}$ ); as well as between the LUMO levels of the polymer donor and fullerene ( $\Delta E_{LUMO}$ ), are essntial to provide the necessary driving force for efficient exciton dissociation.[52] The Scharber's model has been extensively applied in high-throughput screening and the design of OSC device[58], such as the Harvard Clean Energy Porject database introduced by Hachmann et al.[56]

Here we employ the widely used polymer P3HT as an example of donor material. We utilized an oligomer comprising 8 thiophene rings to depict the polymer, while also substituting all alkyl side chains with hydrogen atoms as shown in Figure 3(b), which exhibits a HOMO level of -4.85 eV and a LUMO level of -2.48 eV at B3LYP level from our calculations. Accordingly, the ideal fullerene acceptor should possess a HOMO level of approximately -5.15 eV and a LUMO level of -2.78 eV (inset of Figure 3(a)). The estimated PCE of C<sub>60</sub>–Ih (C<sub>60</sub>–#1) based OSC is about 8.1%, which is consistent to the experimental value of ~5%.[59, 60] By applying the aforementioned requirements as screening conditions to the fullerene database, 2771 out of 5770 fullerene isomers could be potential candidates to pair with P3HT in OSC devices (see Figure 3(a)). The highest PCE values can reach 9.6%, achieved by C<sub>20</sub>–#1, as well as the next three top-performing fullerene structures showed in Figure 3(b).

Dipole moment stands as another critical property for OSC materials, which affects intermolecular interactions and the morphology of the organic material film. Previous studies have highlighted the effectiveness of strategically selecting and designing materials with appropriate dipole moments to enhance charge separation, promote efficient exciton dissociation, optimize energy level alignment at interfaces, and consequently improve the overall efficiency and stability of OSCs.[61–64] The dipole moment distribution of fullerenes from  $C_{20}$  to  $C_{60}$  also shows weak dependence on the size of the fullerene cage (Figure 1(c)). The majority of fullerenes display a permanent dipole moment that is non-negligible. For example, among 5770 fullerene structures, only around 200 exhibit a zero dipole moment as shown in Figure 2(c). Notably, fullerene  $C_{60}$ –#1646 exhibits the largest dipole moment of 3.98 D among all the fullerenes (see Table S3).

In addition to  $E_g$ , other fundamental quantities related to electronic properties have also been computed, such as the fundamental gap  $E_{fund}$  between IP and EA, and the energy difference between triplet and singlet states  $\Delta E_{T-S}$ , which are also crucial for the stability and catalytic activity of materials. As shown in Figure S8,  $E_g$  values show strong correlations with both  $E_{fund}$  and  $\Delta E_{T-S}$ across the C<sub>20</sub>-C<sub>60</sub> database, with  $R^2$  values exceeding 0.9, whereas the linear correlation between fundamental gap and triplet-singlet energy difference exhibits cage size dependence with a lower  $R^2$ of 0.774. Indeed, Table S5 reveals that, for fullerene cages of the same size,  $R^2$  values for the  $E_q$ ,  $E_{fund}$ , and  $\Delta E_{T-S}$  all exceed 0.94, with the exception of C<sub>36</sub>, which are consistent with the previous studies.[30]

Besides its significance in photovoltaic applications,  $E_g$  is also connected to other essential properties in electrochemistry. For instance,  $E_g$  is linked to the redox potential, a key factor in processes such as cyclic voltammetry (CV), energy storage in batteries and fuel cells, and electrocatalysis. Previous studies have demonstrated that, across a series of five fullerenes, the experimentally determined redox potential strongly correlate with the calculated  $E_g$ .[65] We are confident that our extensive dataset of fullerenes, with computed HOMO, LUMO, and  $E_g$ , can assist in the selection of potential fullerene candidates for solar cells and electrochemical applications.

#### 3.1.3 Solubility and ODCB–water partition coefficient

Solubility is an essential factor for the practical utilization of fullerenes. It is widely recognized that fullerenes are insoluble in water but exhibit high solubility in organic solvents.[66, 67] For example, the solubility of  $C_{60}$  is 24 g/L in 1,2-dichlorobenzene (ODCB) solution, compared to  $1.3 \times 10^{-11} g/L$ in water.[67] In this work, we calculated the Gibbs free energy of solvation ( $\Delta G_{sol}$ ) in ODCB and water for our fullerene dataset. The  $\Delta G_{sol}$  is computed as the electronic energy difference between the fullerene molecule in solvent phase E(solvent) and gas phase E(gas) as given in the equation with other terms in free energies ignored:[68]

$$\Delta G_{sol} = E(solvent) - E(gas) \tag{10}$$

We observed linear correlation between both  $\Delta G_{sol}(ODCB)$  and  $\Delta G_{sol}(water)$  with the size of fullerene cage; larger sizes correspond to lower solvation energies (Figure 1(d,e)). Previous studies have also found that the solvation free energies of carbon allotropes, including C<sub>60</sub> and carbon nanotubes, exhibit a negative linear correlation with their surface area.[69] The correlation between solvation free energy and geometric measures will be addressed in section 3.2.2.

The histogram depicting the distribution of  $\Delta G_{sol}(water)$  in Figure 2(d) indicates that around 80% of  $\Delta G_{sol}(water)$  values are within the range of -48.81~-42.10 kJ/mol with an average value of -45.74±2.88 kJ/mol (also see Table S3). The maximum  $\Delta G_{sol}(water)$ , observed for C<sub>20</sub>-#1 is -21.32 kJ/mol, while C<sub>56</sub>-#3 exhibits the minimum at -67.74 kJ/mol. Notably, the  $\Delta G_{sol}(water)$ value of -43.85 kJ/mol measured for C<sub>60</sub>-#1 molecule agrees with previous studies by Varanasi et al. (-55.27 kJ/mol),[70] Garde et al. (-54.1 kJ/mol),[71] and Kevin et al. (-50.9 kJ/mol).[69] Similar low solvation behavior of C<sub>60</sub>-#1 in water has also been reported by Muthukrishnan et al. (-36.10 kJ/mol)[72] and Graziano (-18.4 kJ/mol).[73] In contrast, the histogram illustrating the distribution of  $\Delta G_{sol}(ODCB)$  in Figure 2(e) shows a skewed pattern, suggesting a pronounced preference of fullerene molecules for organic solvents. Approximately 80% of the value falls within the range of -162.08~-139.90 kJ/mol (Figure 2(e)). Similar to  $\Delta G_{sol}(water)$ , C<sub>20</sub>-#1 and C<sub>56</sub>-#3 exhibit the highest and lowest  $\Delta G_{sol}(ODCB)$  values of -76.21 and -168.41 kJ/mol, respectively (see Table S3). Meanwhile, C<sub>60</sub>-#1 shows a relatively low  $\Delta G_{sol}(ODCB)$  value of -158.58 kJ/mol.

To indicate the partitioning of fullerenes between ODCB and water phases, we calculated the

ODCB-water partition coefficient logP as given in equation: [74, 75]

$$logP = -\frac{\Delta G_{sol}(ODCB) - \Delta G_{sol}(water)}{2.303RT}$$
(11)

in which R is the gas constant (8.314  $J/(mol \cdot K)$ ) and T the room temperature (298.15 K). The partition coefficient serves as an indicator for predicting the lipophilicity of molecules. A higher logP value suggests a stronger propensity for dissolution in non-polar organic solvents as opposed to the polar aqueous phase. For fullerenes, logP demonstrates a significant correlation with cage size, as illustrated in Figure 1(f). Fullerene molecule with favorable solubility in ODCB typically exhibit logP values significantly greater than 0. Among the 5770 fullerene isomers, 80% of logP values fall in the range of 17.1~19.99 with the average value of  $18.8\pm1.32$  (Figure 2(f)). The maximum and minimum logP values are 20.22 for C<sub>60</sub>-#1790 and 9.61 for C<sub>20</sub>-#1, respectively (see Table S3). The logP value for C<sub>60</sub>-#1 stands at 20.09, signifying a pronounced preference of C<sub>60</sub>-#1 molecule for the ODCB solvent over water. This finding is consistent with the previous studies. For example, Evgeny et al. reported the  $\Delta G_{sol}(water)$  and  $\Delta G_{sol}(ODCB)$  as -2.9 and -123.9 kJ/mol respectively calculated by effective Hamiltonian methods, which gives the logP value of 21.19. They also obtained the experimental solvation free energies of -17.4 and -127.6 kJ/mol for C<sub>60</sub>-#1 in ODCB and water, which results in a logP value of 19.29.[76].

For the practical application of fullerenes in energy conversion, storage, electrochemistry and nanoelectronics, it is essential to concurrently evaluate multiple key properties. Here we examine the Pearson correlation coefficients (r) among 12 fundamental properties for  $C_{20}$ – $C_{60}$  fullerenes (see Figure S9). Particularly, the correlations among stability, electronic properties, and solubility were assessed by calculating the r values among  $E_b$ ,  $E_g$ , and logP. As shown in Figure 4(a),  $E_b$  is inversely related to logP with r = -0.79. This suggests that the greater stability, indicated by a lower binding energy, is associated with enhanced solubility in the ODCB phase. In comparison, the  $E_g$  value exhibits a weak correlation with both binding energy and logP, with r = 0.13 and -0.24, respectively. These findings imply that it is possible to attain high stability, desirable solubility, and an optimal  $E_g$  concurrently for targeted applications. The density plot in Figure 4(b) encapsulates the correlation between these properties and facilitates the identification of potential candidates for customizing properties to suit specific applications. For instance, when considering four fullerenes with the highest PCE values predicted by Scharber's model (see Figure 3(b)),  $C_{52}$ –#333 and  $C_{60}$ -#60 emerge as more suitable fullerene acceptors compared to  $C_{20}$ –#1 and  $C_{32}$ –#5 owing to their superior stability and solubility.

# 3.2 Correlations of topological indices and geometric measures with fundamental properties

So far, we have constructed a comprehensive dataset of  $C_{20}$ - $C_{60}$  fullerenes with 5770 structures and provided 12 DFT-level accurate fundamental properties, including  $E_b$ ,  $E_g$ , and logP. Previous studies have shown that the IPR can be employed to identify a set of stable isomers among all possible isomers for a given fullerene size.[77] Additionally, topological indices such as the first moment pentagon signature  $P_1$  and the second moment hexagon signature  $H_2$  have also been used to pinpoint the most stable isomers from a set of IPR-compliant isomers for a given fullerene size.[23, 39] However, to the best of our knowledge, a generalized rule for estimating the stability, electronic properties, and solubility across the entire spectrum of potential fullerene isomers of varying sizes has not yet been established. Leveraging the comprehensive dataset computed in our study, we will examine the  $E_b$ ,  $E_g$ , and logP values with various topological features, indices, and geometric measures.

#### 3.2.1 Topological features and indices

To characterize the chemical environment of carbon atoms, C-C bonds, pentagons, and hexagons distributed across the fullerene cage, we introduced 4 types of topological features, as described in section 2.3. Linear regression has been used to fit  $E_b$ ,  $E_g$ , and logP using these topological features (Figure 5 and Table 2). We observed that the atom, bond, and hexagon features exhibit substantial linear correlations with  $E_b$ , resulting in  $R^2$  values exceeding 0.96 (Figure 5(a,b,d)). For example, the linear fitting between  $E_b$  and atom features, i.e.,  $n_0$ ,  $n_1$ ,  $n_2$ , and  $n_3$ , can be expressed as follows:

$$E_b \left( eV/atom \right) = c_0 n_0 + c_1 n_1 + c_2 n_2 + c_3 n_3 + b \tag{12}$$

We found that  $c_0$  equals -4.9 meV/atom, indicating that the incorporation of an additional carbon atom fused by three hexagons (thereby increasing  $n_0$  by 1) into fullerene cage will negligibly decrease  $E_b$  by 4.9 meV/atom. This result aligns with the fact that the growth of sp<sup>2</sup> carbons in a honeycomb lattice is thermodynamically favorable.[78–80] We have also noted that the coefficients  $c_1$ ,  $c_2$ , and  $c_3$  are positive and proportional to each other, with a correlation of  $c_1 = \frac{1}{2}c_2 = \frac{1}{3}c_3$ . Additionally,  $c_1$  is approximately 13 orders of magnitude larger than the absolute value of  $c_0$ . Consequently, the linear fitting formula can be adjusted as follows:

$$E_b \left( eV/atom \right) = c_1 \left( \frac{c_0}{c_1} n_0 + n_1 + 2n_2 + 3n_3 \right) + b \tag{13}$$

Given that  $n_1$ ,  $n_2$ , and  $n_3$  denote the count of carbon atoms fused to 1, 2, and 3 adjacent pentagons respectively,  $E_b$  will increase proportionally with the number of carbon atoms fused in pentagons, suggesting that the substitution of a hexagon with a pentagon will significantly diminish the thermodynamic stability of fullerene structures. Furthermore, the relationship of  $c_1 = \frac{1}{2}c_2 = \frac{1}{3}c_3$  implies that as multiple pentagons fuse together (denoted by  $n_2$  and  $n_3$ ),  $E_b$  will increase dramatically, with the slope doubling or tripling. These findings are consistent with the IPR concept that fullerene isomers with isolated pentagons tend to be more stable. Our interpretations of the values of  $c_0$ ,  $c_1$ ,  $c_2$ , and  $c_3$  contribute to a deeper comprehension of the relationship between structure and stability in fullerene molecules ranging from  $C_{20}$  to  $C_{60}$ . In contrast, the pentagon features display a lower  $R^2$ of 0.85 (Figure 5(c)). The slightly inferior fit from pentagon features stems from their dependence on cage size. This is evidenced by the results obtained from analyzing only 1812  $C_{60}$  isomers, where the  $R^2$  value improved to 0.92 with pentagon features (Figure S10 and Table S6).

To evaluate the transferability of the linear fitting model-defined as its capacity to learn and

apply the correlations between topological features and binding energy in the dataset of  $C_{20}-C_{60}$ fullerenes to larger ones-we utilized the linear fitting equations derived from the  $C_{20}-C_{60}$  dataset to predict the  $E_b$  values of four IPR-conforming fullerenes, namely,  $C_{70}$ ,  $C_{80}$ ,  $C_{90}$ , and  $C_{100}$  (see Figure S11). The predictions obtained from atom, bond, and hexagon features demonstrate a consistent trend of decreasing  $E_b$  values with the increase in fullerene cage size, with  $E_b$  values closely matching the results from B3LYP-D3/6-311G\* calculations (Table 3). This consistency underscores the robust transferability of the linear model fitted by the  $C_{20}-C_{60}$  dataset. When applying the linear model based on pentagon features, we observed that it assigned identical  $E_b$  values to  $C_{70}$ ,  $C_{80}$ ,  $C_{90}$ , and  $C_{100}$  IPR-conforming fullerenes. In essence, pentagon features fail to distinguish the stability of IPR-conforming fullerene molecules, as they all share the same  $p_0$  value of 12 with other pentagonrelated features ( $p_1$  to  $p_7$ ) set to 0 (Table S7). Such findings highlight the limitations of relying solely on pentagon features, as well as the IPR, for capturing the nuanced chemical environments of fullerenes across a range of sizes and topologies.

According to the previous study, the first-moment pentagon signature  $P_1$ , the first and secondmoment hexagon signatures  $H_1$  and  $H_2$  were highly correlated with the stability of  $C_{60}$  fullerenes.[23] We further examined these three signatures for the extended dataset from  $C_{20}$  to  $C_{60}$ , and broadening the properties from binding energy to include  $E_g$  and logP (Table S8 and Figure S12). Notably, within the group of fullerenes with identical size, a robust linear correlation emerges between topological signatures and the binding energies of fullerenes (Figure S13), aligning with findings from previous reports[23]. For example, the linear relationship between  $E_b$  and  $P_1$  in 1812  $C_{60}$  database is described as:

$$E_b \left( eV/atom \right) = -6.9583 + 0.0167 P_1 \tag{14}$$

The  $E_b$  value of  $C_{60}$ -#1 predicted by linear fitting is -6.9583 eV/atom as  $P_1$  equals 0, closely matching the DFT-calculated value of -6.96 eV/atom. Introducing each pentagon-pentagon fusion (thereby incrementing  $P_1$  by 1) results in an energy penalty of 0.0167 eV/atom (0.385 kcal/(mol·atom)) to  $E_b$ , equivalent to approximately 23.1 kcal/mol for C<sub>60</sub> fullerenes. Our results are in good agreement with the value of 20-25 kcal/mol reported by Sure et al.[23] However, it is essential to note that this linear correlation does not extend consistently across fullerenes with differing sizes (Figure S12(a-c)).

Unlike  $E_b$ ,  $E_g$  shows no linear relationship with both topological features (Figure 5(e-h) and Table 2) and topological signatures (Figure S12(d-f) and Table S8). The  $R^2$  values for the correlation between the  $E_g$  and topological features fall below 0.2. This weak correlation still persists when only  $C_{60}$  isomers are considered (Table S6 and Figure S10(e-h)), suggesting that linear models based on topological indices cannot effectively predict the electronic properties of fullerenes.

Implied by the correlation between  $E_b$  and logP, the solubility of fullerenes also exhibits a strong linear relationship with the atom, bond, and hexagon features, sharing an identical  $R^2$  value of 0.996 (Table 2 and Figure 5(i,j,l)). However, when exclusively considering C<sub>60</sub> isomers, the respective  $R^2$ values drop to 0.297, 0.353, and 0.448 (Table S6 and Figure S10(i,j,l). These findings underscore the notable relationship between logP values and fullerene cage size, which is well captured by topological features. Yet, within fullerene of the same size, logP values do not show a linear correlation with these topological features. Regarding pentagon features, the low  $R^2$  value of 0.324 for logP in  $C_{20}-C_{60}$  dataset (Figure 5(k)) indicates a limited ability of pentagon features to correlate with the fullerene cage size. This is consistent with the fact that the number of pentagons in a fullerene molecule remains fixed at 12, regardless of cage size, while the counts of carbon atoms, C-C bonds, and hexagons increases with cage size. This weak correlation with logP persists when focusing exclusively on  $C_{60}$  (Figure S10(k)).

We further evaluated the relationships between logP and topological signatures. As illustrated in Figure S12(g-i), the hexagon-derived signatures,  $H_1$  and  $H_2$  display a stronger correlation with logP compared to the pentagon-based signature  $P_1$  across the C<sub>20</sub>–C<sub>60</sub> dataset, demonstrating that hexagon features are more adept at capturing the properties of fullerenes across different sizes than pentagon features. Nevertheless, among fullerenes of the same size, logP values do not exhibit a linear correlation with any of the topological signatures (see Figure S13(g-i)).

#### 3.2.2 Geometric measures

We also investigated a series of geometric measures, as described in section 2.4, and their correlations with fundamental properties. The coefficient of determination  $R^2$  from linear fitting between geometric measures and fundamental properties can be found in Table 2. Across the entire fullerene dataset,  $\bar{d}$ ,  $\bar{\kappa}$ , and A/V ratio exhibit strong linear correlations with fullerene binding energy  $E_b$ , with  $R^2$  values of 0.946, 0.839, and 0.878, respectively (Figure S14(a,c,f)). Other geometric measures, including  $F_{asym}$ , V, A, and  $D_{IPQ}$ , which assess the sphericity of the cage, exhibit a dependence on the fullerene size, as evident from the clustering of  $E_b$  values across various fullerene sizes (Figure S14(b,d,e,g)). For example, when considering only the 1812 C<sub>60</sub> isomers, the  $R^2$  values of  $E_b$  fitted with  $F_{asym}$ , V, A, and  $D_{IPQ}$  are 0.714, 0.85, 0.627, and 0.875, respectively (Table S6 and Figure S15(b,d,e,g)), consistent with previous findings[23]. These findings align with the observation that fullerene cages with larger volumes and more spherical shapes undergo reduced strain, leading to enhanced stability. However, it is crucial to note that this linear relationship does not extend uniformly across groups of fullerenes with differing sizes. When considering the entire fullerene dataset, these  $R^2$  values decrease to 0.092, 0.721, 0.595, and 0.707 (Table 2 and Figure S14(b,d,e,g)).

In contrast to  $E_b$ ,  $E_g$  displays no correlation with all the geometric measures collected in this study, yielding  $R^2$  values below 0.1 (Table 2 and Figure S16). Importantly, this low correlation is independent of the cage size of fullerenes (see Table S6 and Figure S17).

Additionally, we calculated the  $R^2$  values for logP. As shown in Table 2 and Figure S18, across the entire  $C_{20}-C_{60}$  fullerene database, both V and A exhibit strong correlations with logP values of fullerenes, yielding  $R^2$  values of 0.977 and 0.995, respectively. Given that the V and A of a fullerene cage depend on its size, these findings align with our earlier discussion that logP strongly correlates with fullerene cage size. Interestingly, the  $R^2$  values of both V versus logP and A versus logP for 1812  $C_{60}$  isomers significantly decrease to 0.32, and 0.064 as presented in Table S6 and Figure S19, suggesting that V and A are inadequate to differentiate the solubility of fullerenes with identical size.  $\bar{\kappa}$  and A/V ratio also exhibit high correlates with logP values, resulting in  $R^2$  values of 0.919 and 0.85 for  $C_{20}-C_{60}$ , respectively (see Figure S18(c,f)). The observed similarity in the distributions of logP when plotted against  $\bar{\kappa}$  and the A/V ratio suggests a strong correlation between A/V and  $\bar{\kappa}$ . In fact,  $A/V = 3\bar{\kappa}$  for a perfect sphere.

In summary, the stability of fullerenes with different carbon atoms can be inferred from topological attributes such as atom, bond, and hexagon features, alongside geometric measures like  $\bar{d}$ ,  $\bar{\kappa}$ , and A/V ratio. Furthermore, there is a notable correlation between the logP values across ODCB and water phases and the cage sizes of fullerenes. While these topological attributes and geometric measures (i.e., V and A) effectively illustrate trends from C<sub>20</sub> to C<sub>60</sub> fullerenes, they fall short in precisely predicting logP values for fullerenes of identical sizes. Nonetheless, accurately determining the  $E_g$  through these topological features and geometric measures remains a challenge. Future work might benefit from employing more complex models beyond linear regression or incorporating additional properties, to enhance the prediction of  $E_g$  values in fullerenes. This falls beyond the scope of our current paper.

# 4 Conclusion

In this study, we built up a comprehensive computational dataset for  $C_{20}$ - $C_{60}$  fullerenes with 5770 structures and computed 12 fundamental properties at DFT-level. We conducted statistical analysis on stability, electronic properties, and solubility, and assessed the Pearson correlation coefficients among them. The observed weak correlations between  $E_q$  and both  $E_b$  (r = 0.13) and logP (r = -0.24) suggest that favorable electronic properties can be independently adjusted for particular applications without compromising the stability and solubility. To gain a deeper understanding of the structure-property relationships in fullerenes, we introduced various multi-dimensional topological features, as well as geometric measures to further explore the nature and origin of these properties expanding beyond the commonly used IPR. Among them, atom, bond, and hexagon features prove effective in capturing the intricate local structural environments of the carbon atoms on the spherical cage. This capability facilitates precise predictions of fullerene stability across various sizes from  $C_{20}$ to  $C_{60}$ , and ensures robust transferability to larger fullerene sizes beyond  $C_{60}$ . In contrast, pentagon features, along with the IPR, demonstrate inferior capacity due to the fixed number of 12 pentagons in a fullerene molecule, regardless of the cage size. The solubility of fullerenes represented by logP values adopts high correlation with the fullerene cage size, which is well captured by atom, bond, and hexagon features. However, within fullerenes of the same size, logP values do not show a linear correlation with the topological features. Unlike  $E_b$  and logP,  $E_g$  exhibits no linear relationship with either topological features or geometric measures, leaving its correlation with fullerene structures as an open question. Our study lays a fundamental basis for future advancements in the functionalization and practical applications of fullerenes in the fields of energy conversion and nanomaterials sciences.

## 5 Author contributions

B.L. and M.L. initiated this study. B.L. was responsible for conducting the theoretical calculations and analyzing the data. The Python code used to compute the topological features and geometric measures was developed by J.J. The manuscript was written by B.L. and M.L., with all authors contributing through discussions.

# 6 Acknowledgements

This work was financially supported by the University of Florida's new faculty start-up funding. The authors acknowledge University of Florida Research Computing for providing computational resources and support that have contributed to the research results reported in this publication.

### 7 Competing interests

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

### 8 Data availability

The datasets used and/or analysed during the current study available from the corresponding author on reasonable request.

# 9 Supporting Information

The Supporting Information is available free of charge.

• The number of possible isomers, hexagon rings, carbon-carbon bonds, and IPR isomers for each fullerene cage size. Schematic plots of atom, bond, pentagon, and hexagon features. Statistic analysis of fundamental properties. Distributions of HOMO and LUMO levels. Correlations among HOMO-LUMO gap, fundamental gap, and triplet-singlet energy differences. Coefficient of determination  $R^2$  obtained from linear fitting of topological features and geometrical measures with fundamental properties. Binding energies of larger-size fullerenes from  $C_{70}$  and beyond predicted from linear fitting and calculated with B3LYP-D3/6-311G<sup>\*</sup>. The binding energy, HOMO-LUMO gap, and logP values as a function of 4 topological features and 7 geometric measures.

Fundamental properties	Unit
Binding energy $(E_b)$	eV/atom
HOMO level	eV
LUMO level	eV
HOMO-LUMO gap $(E_q)$	eV
Ionization Potential (IP)	eV
Electron affinity (EA)	eV
IP-EA gap $(E_{fund})$	eV
Dipole moment $(\mu)$	D
Triplet-singlet energy difference $(\Delta E_{T-S})$	eV
Solvation free energy in water $(\Delta G_{sol}(water))$	kJ/mol
Solvation free energy in ODCB $(\Delta G_{sol}(ODCB))$	kJ/mol
ODCB-water partition coefficient (logP)	-

Table 1: The summary of 12 fundamental properties for the 5770  $\rm C_{20}\text{-}C_{60}$  database calculated at B3LYP level.

Table 2: Coefficient of determination  $(R^2)$  obtained from linear fitting of topological features and geometric measures with fundamental properties, i.e., binding energy  $(E_b \text{ (eV/atom)})$ , HOMO-LUMO gap  $(E_g \text{ (eV)})$ , and ODCB-water partition coefficient (logP) for the 5770 C<sub>20</sub>-C<sub>60</sub> database.

		$R^2$	
Topological features	$E_b$	$E_g$	$\log P$
Atom features $(\{n_i   i = 0, 1, 2, 3\})$	0.965	0.076	0.996
Bond features $(\{e_i   i = 0, \dots, 8\})$	0.968	0.107	0.996
Pentagon features $(\{p_i   i = 0, \dots, 7\})$	0.85	0.023	0.324
Hexagon features $(\{h_i   i = 0, \dots, 12\})$	0.972	0.171	0.996
Geometric measures			
Average bond length $(\bar{d})$	0.946	0.036	0.545
Fowler asymmetry parameter $(F_{asym})$	0.092	0.006	0.042
Average Curvature $(\bar{\kappa})$	0.839	0.061	0.919
Volume (V)	0.721	0.062	0.977
Surface area (A)	0.595	0.067	0.995
Ratio $A/V$	0.878	0.054	0.85
Deviation from isoperimetric quotient $(D_{IPQ})$	0.707	0.006	0.194



Figure 1: Violin plots for the distributions of (a) binding energy  $E_b$  (eV/atom) (b) HOMO-LUMO gap  $E_g$  (eV) (c) dipole moment  $\mu$  (D) (d,e) solvation free energy in water  $\Delta G_{sol}(water)$  and 1,2dichlorobenzene (ODCB)  $\Delta G_{sol}(ODCB)$  (kJ/mol) (f) ODCB-water partition coefficient logP from fullerene C<sub>20</sub> to C<sub>60</sub>.



Figure 2: Histogram plots for the distributions of (a) binding energy  $E_b$  (eV/atom) (b) HOMO-LUMO gap  $E_g$  (eV) (c) dipole moment  $\mu$  (D) (d,e) solvation free energy in water  $\Delta G_{sol}(water)$  and 1,2-dichlorobenzene (ODCB)  $\Delta G_{sol}(ODCB)$  (kJ/mol) (f) ODCB-water partition coefficient logP from fullerene C<sub>20</sub> to C<sub>60</sub>. The star marks highlight the values of C<sub>60</sub>-#1.



Figure 3: (a) The power conversion efficiency (PCE) of fullerene-based OSCs with P3HT as donor estimated by Scharber's model. (inset: Energy level diagram for ideal fullerene acceptors aligned with P3HT polymer donor in OSC devices. The HOMO level offsets ( $\Delta E_{HOMO}$ ) and LUMO level offsets ( $\Delta E_{LUMO}$ ) between P3HT and fullerenes are  $\geq 0.3 \text{ eV.}$ )(b) Chemical structures of P3HT oligomer and four fullerenes with the highest PCE values predicted by Scharber's model (plotted with Jmol).



Figure 4: (a) Pearson correlation coefficients and (b) contour plot of binding energy  $E_b$  (eV/atom), HOMO-LUMO gap  $E_g$  (eV), and logP. The yellow dots highlight the values of four fullerenes with the highest power conversion efficiency (PCE) values predicted by Scharber's model. (The chemical structures are depicted in Figure 3(b)).

Table 3: The binding energies  $(E_b)$  of four large-size fullerenes (Cn) calculated with B3LYP-D3/6-311G<sup>\*</sup> compared to the values predicted by linear fitting models with atom, bond, pentagon, and hexagon features respectively across  $C_{20}$ - $C_{60}$  fullerenes, together with various statistical measures, i.e., the mean deviation (MD), the overall mean absolute deviation (MAD), the standard deviation (SD), and the maximal absolute error (MAX). The units for all the values are given in eV/atom. The molecular structures of these large-size fullerenes are shown in Figure S11.

Cn	$E_b^{DFT}$	$E_b^{atom}$	$E_b^{bond}$	$E_b^{pentagon}$	$E_b^{hexagon}$
$C_{70}$	-6.997	-7.027	-7.016	-6.988	-7.03
$C_{80}$	-7.011	-7.076	-7.062	-6.988	-7.077
$C_{90}$	-7.036	-7.125	-7.109	-6.988	-7.099
$C_{100}$	-7.05	-7.174	-7.156	-6.988	-7.121
	MD	-0.077	-0.062	0.035	-0.058
	MAD	0.077	0.062	0.035	0.058
	SD	0.034	0.032	0.021	0.015
	MAX	0.124	0.106	0.062	0.071



Figure 5: The parity plot of DFT calculated binding energy  $(E_b \text{ (eV/atom)})$  (left panel), HOMO-LUMO gap  $(E_g \text{ (eV)})$  (middle panel), and ODCB-water partition coefficient (logP) (right panel) of all 5770 C<sub>20</sub>-C<sub>60</sub> fullerenes versus predicted values of linear regression based on (a,b,c) atom features, (d,e,f) bond features, (g,h,i) pentagon features, and (j,k,l) hexagon features. The color bar indicates varying fullerene sizes



Figure 6: Table of contents.

# References

- Ramar V and Balraj A. Critical review on carbon-based nanomaterial for carbon capture: technical challenges, opportunities, and future perspectives. Energy & Fuels 2022;36:13479– 505.
- 2. Speranza G. Carbon nanomaterials: Synthesis, functionalization and sensing applications. Nanomaterials 2021;11:967.
- 3. Zhang BT, Zheng X, Li HF, and Lin JM. Application of carbon-based nanomaterials in sample preparation: A review. Analytica chimica acta 2013;784:1–17.
- 4. Scida K, Stege PW, Haby G, Messina GA, and García CD. Recent applications of carbon-based nanomaterials in analytical chemistry: critical review. Analytica Chimica Acta 2011;691:6–17.
- 5. Maiti D, Tong X, Mou X, and Yang K. Carbon-based nanomaterials for biomedical applications: a recent study. Frontiers in pharmacology 2019;9:1401.
- Thurston WP. Shapes of polyhedra and triangulations of the sphere. arXiv preprint math/9801088 1998.
- Paukov M, Kramberger C, Begichev I, Kharlamova M, and Burdanova M. Functionalized Fullerenes and Their Applications in Electrochemistry, Solar Cells, and Nanoelectronics. Materials 2023;16:1276.
- Chen JX, Wang H, Zhang X, et al. Using fullerene fragments as acceptors to construct thermally activated delayed fluorescence emitters for high-efficiency organic light-emitting diodes. Chemical Engineering Journal 2022;435:134731.
- 9. Kausar A, Ahmad I, Maaza M, Eisa M, and Bocchetta P. Polymer/Fullerene Nanocomposite for Optoelectronics—Moving toward Green Technology. Journal of Composites Science 2022;6:393.
- Jakšić J, Milinković E, Cvetanović K, et al. Exploring fullerene derivatives for optoelectronic applications: synthesis and characterization study. Physical Chemistry Chemical Physics 2024;26:517– 23.
- 11. Yin H, Lin H, Zong Y, and Wang XD. The recent advances in C60 micro/nanostructures and their optoelectronic applications. Organic Electronics 2021;93:106142.
- Ganesamoorthy R, Sathiyan G, and Sakthivel P. Fullerene based acceptors for efficient bulk heterojunction organic solar cell applications. Solar Energy Materials and Solar Cells 2017;161:102– 48.
- Dennler G, Scharber MC, and Brabec CJ. Polymer-fullerene bulk-heterojunction solar cells. Advanced materials 2009;21:1323–38.
- Brabec CJ, Gowrisanker S, Halls JJ, Laird D, Jia S, and Williams SP. Polymer–fullerene bulkheterojunction solar cells. Advanced Materials 2010;22:3839–56.
- 15. Agrawal PS, Belkhode PN, Brijpuriya DS, Gouda SP, and Rokhum SL. Stimulation in fullerene for adsorbing pollutant gases: a review. Chemical Physics Impact 2023:100156.

- Haghgoo S and Nekoei AR. Metal oxide adsorption on fullerene C60 and its potential for adsorption of pollutant gases; density functional theory studies. RSC advances 2021;11:17377– 90.
- 17. Castro E, Garcia AH, Zavala G, and Echegoyen L. Fullerenes in biology and medicine. Journal of Materials Chemistry B 2017;5:6523–35.
- Yáñez-Sedeño P, Campuzano S, and Pingarrón JM. Fullerenes in electrochemical catalytic and affinity biosensing: a review. C 2017;3:21.
- Pilehvar S and De Wael K. Recent advances in electrochemical biosensors based on fullerene-C60 nano-structured platforms. Nanocarbons for Electroanalysis 2017:173–96.
- 20. Colt JR and Scuseria GE. An ab initio study of the C78 fullerene isomers. Chemical physics letters 1992;199:505–12.
- 21. Wang Y, Díaz-Tendero S, Alcamí M, and Martín F. Cage connectivity and frontier  $\pi$  orbitals govern the relative stability of charged fullerene isomers. Nature chemistry 2015;7:927–34.
- 22. Aghajamali A and Karton A. Can force fields developed for carbon nanomaterials describe the isomerization energies of fullerenes? Chemical Physics Letters 2021;779:138853.
- Sure R, Hansen A, Schwerdtfeger P, and Grimme S. Comprehensive theoretical study of all 1812 C 60 isomers. Physical Chemistry Chemical Physics 2017;19:14296–305.
- Sabirov DS, Ori O, and László I. Isomers of the C84 fullerene: A theoretical consideration within energetic, structural, and topological approaches. Fullerenes, Nanotubes and Carbon Nanostructures 2018;26:100–10.
- Austin S, Fowler P, Orlandi G, Manolopoulos D, and Zerbetto F. Relative stabilities of C76 isomers. A numerical test of the fullerene isolated-pentagon rule. Chemical physics letters 1994;226:219–25.
- 26. Song X, Mao R, Wang Z, and Qi J. Structural and spectral properties of a non-classical C 58 isomer and its fluorinated derivatives in theory. RSC advances 2021;11:1472–81.
- Mao R, Wang Z, Song X, Chen WK, and Qi J. Structural and Spectral Properties of a Nonclassical C66 Isomer with Its Hydrogenated Derivative C66H4 in Theory. ACS omega 2021;6:27101–11.
- Cui YH, Chen DL, Tian WQ, and Feng JK. Structures, stabilities, and electronic and optical properties of C62 fullerene isomers. The Journal of Physical Chemistry A 2007;111:7933–9.
- 29. Zhao D, Liu S, Rong C, Zhong A, and Liu S. Toward understanding the isomeric stability of fullerenes with density functional theory and the information-theoretic approach. ACS omega 2018;3:17986–90.
- 30. Chan B and Karton A. Computational insights into the singlet-triplet energy gaps, ionization energies, and electron affinities for a diverse set of 812 small fullerenes (C 20-C 50). Physical Chemistry Chemical Physics 2023;25:10899–906.
- 31. URL: https://houseofgraphs.org/meta-directory/fullerenes.

- Schwerdtfeger P, Wirz L, and Avery J. Program fullerene: a software package for constructing and analyzing structures of regular fullerenes. Journal of computational chemistry 2013;34:1508– 26.
- Frisch M, Trucks G, Schlegel H, et al. GAUSSIAN16. Revision C. 01. Gaussian Inc., Wallingford, CT, USA. 2016.
- 34. Becke AD. A new mixing of Hartree–Fock and local density-functional theories. The Journal of chemical physics 1993;98:1372–7.
- Stephens PJ, Devlin FJ, Chabalowski CF, and Frisch MJ. Ab initio calculation of vibrational absorption and circular dichroism spectra using density functional force fields. The Journal of physical chemistry 1994;98:11623–7.
- 36. Lee C, Yang W, and Parr RG. Development of the Colle-Salvetti correlation-energy formula into a functional of the electron density. Physical review B 1988;37:785.
- 37. Grimme S, Antony J, Ehrlich S, and Krieg H. A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H-Pu. The Journal of chemical physics 2010;132.
- 38. Marenich AV, Cramer CJ, and Truhlar DG. Universal solvation model based on solute electron density and on a continuum model of the solvent defined by the bulk dielectric constant and atomic surface tensions. The Journal of Physical Chemistry B 2009;113:6378–96.
- Fowler PW, Caporossi G, and Hansen P. Distance matrices, Wiener indices, and related invariants of fullerenes. The Journal of Physical Chemistry A 2001;105:6232–42.
- 40. Fowler PW and Manolopoulos DE. An atlas of fullerenes. Courier Corporation, 2007.
- Fowler PW, Heine T, and Zerbetto F. Competition between even and odd fullerenes: C118, C119, and C120. The Journal of Physical Chemistry A 2000;104:9625–9.
- Pisanski T, Kaufman M, Bokal D, Kirby EC, and Graovac A. Isoperimetric quotient for fullerenes and other polyhedral cages. Journal of chemical information and computer sciences 1997;37:1028–32.
- 43. Shin H, Kang S, Koo J, Lee H, Kim J, and Kwon Y. Cohesion energetics of carbon allotropes: Quantum Monte Carlo study. The Journal of chemical physics 2014;140.
- 44. Dresselhaus MS, Dresselhaus G, and Eklund PC. Science of fullerenes and carbon nanotubes: their properties and applications. Elsevier, 1996.
- 45. Liakos DG, Sparta M, Kesharwani MK, Martin JM, and Neese F. Exploring the accuracy limits of local pair natural orbital coupled-cluster theory. Journal of chemical theory and computation 2015;11:1525–39.
- 46. Minenkov Y, Chermak E, and Cavallo L. Accuracy of DLPNO–CCSD (T) method for noncovalent bond dissociation enthalpies from coinage metal cation complexes. Journal of chemical theory and computation 2015;11:4664–76.
- Prinzbach H, Weiler A, Landenberger P, et al. Gas-phase production and photoelectron spectroscopy of the smallest fullerene, C20. Nature 2000;407:60–3.

- 48. Piskoti C, Yarger J, and Zettl A. C36, a new carbon solid. nature 1998;393:771-4.
- Xie SY, Gao F, Lu X, et al. Capturing the labile fullerene [50] as C50Cl10. Science 2004;304:699– 9.
- 50. Tan YZ, Liao ZJ, Qian ZZ, et al. Two I h-symmetry-breaking C60 isomers stabilized by chlorination. Nature Materials 2008;7:790–4.
- 51. Mumyatov AV and Troshin PA. A Review on Fullerene Derivatives with Reduced Electron Affinity as Acceptor Materials for Organic Solar Cells. Energies 2023;16:1924.
- 52. Thompson BC and Fréchet JM. Polymer–fullerene composite solar cells. Angewandte chemie international edition 2008;47:58–77.
- Kooistra FB, Mihailetchi VD, Popescu LM, Kronholm D, Blom PW, and Hummelen JC. New C84 derivative and its application in a bulk heterojunction solar cell. Chemistry of materials 2006;18:3068–73.
- Scharber MC, Mühlbacher D, Koppe M, et al. Design rules for donors in bulk-heterojunction solar cells—Towards 10% energy-conversion efficiency. Advanced materials 2006;18:789–94.
- 55. Eibeck A, Nurkowski D, Menon A, et al. Predicting power conversion efficiency of organic photovoltaics: models and data analysis. ACS omega 2021;6:23764–75.
- 56. Hachmann J, Olivares-Amaya R, Atahan-Evrenk S, et al. The Harvard clean energy project: large-scale computational screening and design of organic photovoltaics on the world community grid. The Journal of Physical Chemistry Letters 2011;2:2241–51.
- 57. Gueymard CA, Myers D, and Emery K. Proposed reference irradiance spectra for solar energy systems testing. Solar energy 2002;73:443–67.
- Scharber MC and Sariciftci NS. Efficiency of bulk-heterojunction organic solar cells. Progress in polymer science 2013;38:1929–40.
- Grancharov G, Atanasova MD, Kalinova R, et al. Flexible polymer-organic solar cells based on P3HT: PCBM bulk heterojunction active layer constructed under environmental conditions. Molecules 2021;26:6890.
- Krebs FC. Fabrication and processing of polymer solar cells: A review of printing and coating techniques. Solar energy materials and solar cells 2009;93:394–412.
- Arndt AP, Gerhard M, Koch M, Lemmer U, and Howard IA. Identifying charge-transfer states in polymer: fullerene heterojunctions by their emission polarization anisotropy. The Journal of Physical Chemistry C 2017;121:6357–64.
- Arkhipov V, Heremans P, and Bässler H. Why is exciton dissociation so efficient at the interface between a conjugated polymer and an electron acceptor? Applied Physics Letters 2003;82:4605– 7.
- 63. Gier HD de, Jahani F, Broer R, Hummelen JC, and Havenith RW. Promising strategy to improve charge separation in organic photovoltaics: Installing permanent dipoles in PCBM analogues. The Journal of Physical Chemistry A 2016;120:4664–71.

- Carsten B, Szarko JM, Son HJ, et al. Examining the effect of the dipole moment on charge separation in donor-acceptor polymers for organic photovoltaic applications. Journal of the American Chemical Society 2011;133:20468–75.
- Yang Y, Arias F, Echegoyen L, et al. Reversible fullerene electrochemistry: correlation with the HOMO-LUMO energy difference for C60, C70, C76, C78, and C84. Journal of the American Chemical Society 1995;117:7801–4.
- Semenov KN, Charykov NA, Keskinov VA, Piartman AK, Blokhin AA, and Kopyrin AA. Solubility of light fullerenes in organic solvents. Journal of Chemical & Engineering Data 2010;55:13–36.
- Kharissova OV, Oliva González CM, and Kharisov BI. Solubilization and dispersion of carbon allotropes in water and non-aqueous solvents. Industrial & Engineering Chemistry Research 2018;57:12624–45.
- Ferreira RA, Santos JR dos, Falleiros JM, Silva EL da, and Santos JD dos. Functionalization of fullerene isomers [60, 70, 80 and 82] with R-thiazolidinethione: A DFT study. Chemical Physics Letters 2021;769:138421.
- Hinkle KR and Phelan Jr FR. Solvation of carbon nanoparticles in water/alcohol mixtures: using molecular simulation to probe energetics, structure, and dynamics. The Journal of Physical Chemistry C 2017;121:22926–38.
- Varanasi S, Guskova O, John A, and Sommer JU. Water around fullerene shape amphiphiles: A molecular dynamics simulation study of hydrophobic hydration. The Journal of Chemical Physics 2015;142.
- Athawale MV, Jamadagni SN, and Garde S. How hydrophobic hydration responds to solute size and attractions: Theory and simulations. The Journal of chemical physics 2009;131.
- Muthukrishnan A and Sangaranarayanan M. Hydration energies of C60 and C70 fullerenes–A novel Monte Carlo simulation study. Chemical physics 2007;331:200–6.
- Graziano G. On the pairwise hydrophobic interaction of fullerene. Chemical Physics Letters 2010;499:79–82.
- Bannan CC, Calabró G, Kyu DY, and Mobley DL. Calculating partition coefficients of small molecules in octanol/water and cyclohexane/water. Journal of chemical theory and computation 2016;12:4015–24.
- Ben-Naim A and Marcus Y. Solvation thermodynamics of nonionic solutes. The Journal of chemical physics 1984;81:2016–27.
- 76. Stukalin EB, Korobov MV, and Avramenko NV. Solvation free energies of the fullerenes C60 and C70 in the framework of polarizable continuum model. The Journal of Physical Chemistry B 2003;107:9692–700.
- 77. Kroto H. The stability of the fullerenes C n, with n=24, 28, 32, 36, 50, 60 and 70. Nature 1987;329:529–31.

- 78. Karfunkel HR and Dressler T. New hypothetical carbon allotropes of remarkable stability estimated by MNDO solid-state SCF computations. Journal of the American Chemical Society 1992;114:2285–8.
- 79. Balaban A, Klein D, and Folden C. Diamond-graphite hybrids. Chemical Physics Letters 1994;217:266–70.
- 80. Park N and Ihm J. Electronic structure and mechanical stability of the graphitic honeycomb lattice. Physical Review B 2000;62:7614.