# Tuning the band gap and structure from wide gap SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> to narrow gap Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> by aliovalent anion substitution

T. Robinson<sup>1</sup>, A. Safdar<sup>1</sup> J.W. Still<sup>2</sup>, I. D. Seymour<sup>1</sup>, Q.D. Gibson<sup>1\*</sup>

<sup>1</sup>University of Aberdeen, Department of Chemistry, Advanced Centre for Energy and Sustainability (ACES)

<sup>2</sup>University of Aberdeen, School of Geosciences

\*corresponding author: quinn.gibson@abdn.ac.uk

## Abstract

Modifying the atomic and electronic structure of materials by chemical substitution is a common method of achieving properties by design. Cations and metal atoms are the most frequent choices for chemical substitution; replacing anions with ones from a different chemical group is unusual due to the very different orbital energies and electronegativities involved. Here we demonstrate full substitution of Se by Cl in the visible band gap material Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> charge balanced y simultaneous replacement of Bi with Sr, all the way to the wide gap photocatalyst material SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>. This compositional flexibility is associated with the layer-segregation of Sr and Se atoms. The crystal structure and electronic structure change non-linearly, with a compositional regime of two band gap transitions observed, due to the introduction of in-gap Se states to the electronic structure. The material CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> is also synthesized, revealing the separate effects on the crystal structure of the anion and cation composition. This work presents aliovalent anion substitution in multiple anion materials as a strategy for tuning between narrow and wide gap materials, with properties showing more than one optical transition achievable at intermediate compositions.

# Introduction

Multiple anion, or heteroanionic, materials are a class of compounds that have two or more anion species. This chemistry allows for complex packings of the anion sublattices as well as diversity of the chemical bond types compared to single anion materials, facilitating properties such as superconductivity<sup>1</sup>, superionic transport<sup>2</sup>, low thermal conductivity<sup>3-5</sup>, catalysis<sup>6</sup> and quantum magnetism<sup>7</sup>. Properties design via chemical tuning of single anion materials often involves either the isovalent or aliovalent substitution of the cation or metal sites, for example tuning the A and B composition in the perovskite structure ABX<sub>3</sub>. Isovalent substitution of the anion sites in multiple anion materials can also be utilised, such as band gap tuning in the BiOCl type family for photocatalytic applications<sup>8</sup> or in halide perovskites with photovoltaic applications<sup>9,10</sup>. Aliovalent anion substitution, where an anion is replaced by another anion of a different group, can also be used to tune properties. There are cases in which some  $O^{2-}$  replaced by some amount of H<sup>-</sup>, F<sup>-</sup> or N<sup>3-</sup>, often charge balanced by a redox active cation becoming reduced or oxidized<sup>11,12</sup>. Another technique is to charge balance aliovalent substitution on the anion sublattice by simultaneous aliovalent substitution on the cation sublattice or of a different anion. For example, Zn<sub>2</sub>FN can be synthesized as an analogue to ZnO to tune the band gap and photocatalytic properties<sup>13</sup>, V and O can be simultaneous replaced in PbVO<sub>2</sub>(SeO<sub>3</sub>)<sub>2</sub>Cl and  $\beta$ -Ba<sub>2</sub>[VO<sub>2</sub>F<sub>2</sub>(IO<sub>3</sub>)<sub>2</sub>](IO<sub>3</sub>) by Ga and F to synthesize PbGaF<sub>2</sub>(SeO<sub>3</sub>)Cl<sup>14</sup> and  $\beta$ -Ba<sub>2</sub>[GaF<sub>4</sub>(IO<sub>3</sub>)<sub>2</sub>](IO<sub>3</sub>)<sup>15</sup> to engineer the nonlinear optical properties.

Aliovalent anion substitution in materials allows for a different tuning of properties than either isovalent anion or cation substitution, as materials with different anion groups (e.g. halides vs. chalcogenides) tend to have very different band gaps and applications due to the large differences in orbital energies in the groups. Full aliovalent substitution, in which an anion is continuously replaced by another is somewhat rare, but has been demonstrated in some zincblende type photovoltaic materials<sup>16</sup>, with the extreme case of InP-CdS solid solution allowing for band gap tuning from 1.3 eV to 2.6 eV, which occurs in a nonlinear fashion<sup>17</sup>. Tuning the band gap from a narrow band gap (solar absorber) to wide gap (photocatalyst) is of interest, as materials that have intermediate or overlapping properties have unique applications e.g. for two photon absorption in photocatalysis and photovoltaics. Aliovalent substitution is a good candidate for this type of materials tuning.

Here we demonstrate full aliovalent substitution of the narrow gap (1.2 eV) layered multiple anion semiconductor Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub>, a natural heterostructure of BiOCl and Bi<sub>2</sub>O<sub>2</sub>Se with possible solar absorber applications<sup>18</sup>, to the wide gap (2.7 eV) semiconductor SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> with applications in catalysis (photocatalytic water splitting<sup>19</sup> and ethane dehydrogenation<sup>20</sup>). Simultaneous Sr<sup>2+</sup> for Bi<sup>3+</sup> and Cl<sup>-</sup> for Se<sup>2-</sup> substitution is shown to be possible all the way to the Se<sup>2-</sup> free compound SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>. The aliovalent substitution is associated with the layersegregation of the Se<sup>2-</sup> and Sr<sup>2+</sup> ions. Despite the large band gap difference of the two end members ( $\Delta E_G = 1.5 \text{ eV}$ ), the band gap increases modestly with substitution until compositions where two band gap transitions are observed, allowing for the possibility of two photon absorption. The effect of substitution of the alkali earth on the cation site was also investigated, with synthesis and characterisation of the compound CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, demonstrating an increase in band gap and alkali earth independent thickness of the ionic Bi<sub>2</sub>O<sub>2</sub>Se type layer, indicating that aspects of the structure are primarily dependent on anion composition. The Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> structure is therefore open to multiple axes of compositional tuning, establishing a paradigm of aliovalent substitution in multiple anion compounds for materials design.

# **Experimental section**

# Synthesis

Compositions of  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  for x = 0, 0.25, 0.5, 0.75, 0.95, 0.99 were synthesized via a stochiometric combination of  $Bi_2O_3$ , Bi, Se, BiOCl and  $SrBiO_2Cl$ . Powders were ground in a mortar in pestle, then sealed in an evacuated quartz ampoule at pressures  $< 1 \times 10^{-2}$  torr. The ampoules were heated at 700 °C for 12 h in a muffle furnace, then brought to room temperature at 5°C/min. The x = 1.0 sample ( $SrBi_3O_4Cl_3$ ) was synthesized through a stochiometric combination of  $SrBiO_2Cl$  and BiOCl, ground in a mortar and pestle and heated in an alumina crucible in air at 700 °C. CaBi\_3O\_4Cl\_3 was synthesized through a stochiometric combination of  $SrBiO_2Cl$  and BiOCl, ground in a mortar and pestle and heated in an alumina crucible in air at 700 °C. CaBi\_3O\_4Cl\_3 was synthesized through a stochiometric mixture of  $SrBiO_2Cl$  and BiOCl, ground in a mortar and pestle and heated in an alumina crucible, and heated in air at 800 °C for 12 h followed by a second identical grinding and heating step. The CaBiO\_2Cl precursor was synthesized from a stochiometric mixture of CaCO\_3 and BiOCl, which were ground together in a mortar and pestle, placed in an alumina crucible, and heated in air at 800 °C for 12 h followed by a two more identical grinding and heating steps.

Powder diffraction measurements were collected on a PANalytical Empyrean powder diffractometer with a Cu K $\alpha$  tube and a K $\alpha$ 1 monochromator. Data were collected in the range 5 ° to 120 °. Rietveld refinements were performed using GSAS-II <sup>21</sup>.

Diffuse Reflectance measurements were performed on an Agilent Technologies Cary 60 UV-Vis spectrometer with a Harrick Scientific VideoBarrelino Diffuse Reflectance attachment, using BaSO<sub>4</sub> as a 100% reflectance background standard. For the plotting of the indirect gap, the background at low energies (between 1.1 and 1.15 eV) was subtracted for better comparison and for extraction of the band gap energy

Secondary Electron Microscopy (SEM) and Energy Dispersive X-Ray spectroscopy (EDX) was performed using a Carl Zeiss Gemini SEM 300 with a field emission. EDX was analysed using an Oxford Instruments Aztec Energy EDS analysis system with an XMax 80 detector. The Oxford Instruments Aztec Energy software suite was used for analysis. Samples were coated with 15nm of carbon prior to measurement to prevent charging. Samples were imaged and analysed using an accelerating voltage of 15 kV.

Density functional theory (DFT) calculations of the energy and electronic structure of  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  and  $CaBi_3O_4Cl_3$  compounds were performed using the projector augmented wave (PAW) approach in the VASP code <sup>22</sup>. Non-spin polarised calculations were performed using the Perdew-Burke-Ernzerhof (PBE) functional <sup>23</sup>. Geometry optimisations were performed using a plane-wave cut-off of 520 eV and a gamma centred k-point mesh with a density of  $\geq 28$  Å.

For the end member SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> (x=1) structure in the Sr<sub>x</sub>Bi<sub>4-x</sub>O<sub>4</sub>Se<sub>1-x</sub>Cl<sub>2+x</sub> series, a single unit cell structure was considered with 50 % occupancy of Sr and Bi on the Bi2 site. The same Ca/Bi ordering was used for the CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> unit cell structure. For the Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> (x=0) end member, and intermediate Sr<sub>0.25</sub>Bi<sub>3.75</sub>O<sub>4</sub>Se<sub>0.75</sub>Cl<sub>2.25</sub> (x=0.25) and Sr<sub>0.75</sub>Bi<sub>3.25</sub>O<sub>4</sub>Se<sub>0.25</sub>Cl<sub>2.75</sub> (x=0.75) systems, a  $\sqrt{2} \times \sqrt{2} \times 1$  supercell expansion of the initial unit cell was used to explore different Se/Cl orderings. For the end member SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> and CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> structures, the lattice parameters and atomic positions were optimised until the force on any atom fell below 0.005 eV/Å, with and energy converged of 10<sup>-7</sup> eV. For intermediate compositions, x=0.25 and 0.75, the lattice parameters were initially fixed those of the lowest energy x=0 and x=1 phases, respectively, and the energies of different Se/Cl orderings were compared, after optimisation of the lowest energy x=0.25 and 0.75 structures predicted under fixed cell conditions were then fully optimised before calculation of the electronic structure.

Density of states (DOS) plots were produced for the lowest energy  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  and  $CaBi_3O_4Cl_3$  structures using a higher plane wave cut off of 600 eV and a gamma centred k-point mesh with a density of  $\geq$ 56 Å. All DOS plots in this work were visualised in the Sumo package<sup>24</sup>. The formation energy ( $E_{form,x}$ ) per formula unit of the x=0.25 and 0.75 phases relative to the Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> and SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> end members was calculated via the equation:

$$E_{form,x} = E_x - x E_{SrBi304Cl} - (1-x) E_{Bi404SeCl}$$

Where  $E_x$  is the energy of the intermediate composition, and  $E_{SrBi3O4Cl3}$  and  $E_{Bi4O4SeCl2}$  are the energies of the end member phases.

### **Results and Discussion**

#### Composition and Structure

All compounds in the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  for x = 0, 0.25, 0.5, 0.75, 0.95, 0.99 and 1.0 were identified from X-ray diffraction as having the same I4/mmm unit cell reported for the x = 0 and 1.0 end members ( $Bi_4O_4SeCl_2$  and  $SrBi_3O_4Cl_3$ ). SEM-EDX was used to check the actual composition versus the nominal value of x. All samples showed small plate-like crystals, as expected from the van der Waals gap containing structure. One key difference is that for x = 0, platelike crystals with approximate in plane dimensions of 10  $\mu$ m were observed (Figure 1a), whereas for all other compositions, crystallites with in-plane dimensions of one order of magnitude smaller were observed (Figure 1b). This indicates that that a small change in the components involved in synthesis affects the nucleation and crystal growth kinetics in a way that favours smaller particle sizes in the same experimental conditions. This could be an important consideration when either designing these materials for photovoltaic or photocatalytic applications. The experimental value for x was calculated both from the Se/Cl ratio and the Sr/Bi ratio averaged from 5 measurements for each composition and compared to the nominal value. Figure 1c shows good agreement between the experimental and nominal values, with the values calculated by Sr/Bi and Se/Cl falling within error of each other and within error of the nominal composition. Along with the preservation of the unit cell, this suggests that the composition was successfully tuned by aliovalent substitution for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$ . A large uncertainty is observed for x = 0.25 likely due to the difficulty of finding sufficiently flat surfaces. It is worth noting that the value for x calculated by the Sr/Bi ratio cannot be less than zero due to zero being the minimum content of Sr, while the value of x calculated by the Se/Cl ratio can go below zero as x = 0 corresponds to a ratio of 0.5 Se/Cl. The composition wasn't measured for x = 0.99due to the amount of Se being below the detection limit of the instrument.



Figure 1. SEM images for (a) x = 0 Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> and (b) Sr<sub>0.5</sub>Bi<sub>3.5</sub>O<sub>4</sub>Se<sub>0.5</sub>Cl<sub>2.5</sub> on the same scale, demonstrating the difference in particle size. (c) comparison of the value for x calculated by the Sr/Bi ratio and Se/Cl ratio as determined by EDX to the nominal value of x. The dashed line shows the expected trend if the experimental equals the nominal.

All compositions had their lattice parameters and full structure modelled by Rietveld refinements. Figure 2(a) shows the diffraction patterns for the series and Figure 2(b) shows

an example Rietveld refinement for x = 0.75. Full Rietveld refinements for the whole series are shown in the supporting information. The diffraction patterns show the same I4/mmm pattern for every x, with small shifts in the lattice parameters observable. The peaks are also broader for any composition with alkali earth on Bismuth substitution than for the x = 0phase, due to the addition of Sr/Bi disorder into the system.



Figure 2 (a) Diffraction patterns for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$ . x = 0.99 was omitted due to its similarity x = 1.0 Patterns are offset from each other for better visibility. Inset : a close up of the (110) and (107) pair of peaks, showing peak shift as a function of x as well as the shift towards higher angle for CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> compared to all Sr containing materials. (b) Example Rietveld refinement for x = 0.75 (Sr<sub>0.75</sub>Bi<sub>3.25</sub>O<sub>4</sub>Se<sub>0.25</sub>Cl<sub>2.75</sub>), with a  $\chi^2 = 5.65$ , an  $R_W = 8.24$  % and goodness of fit = 2.37.

Figure 3 shows the full modelled structure for the series as determined by Rietveld refinements of powder XRD data. Compositions were constrained to the nominal composition due to the agreement of the nominal and experimental compositions shown in Figure 1 (b). The structure of the series overall is defined by Bi<sub>2</sub>O<sub>2</sub> fluorite type layers separated alternatively by a ionic bridging layer (Se1/Cl1) and a van der Waals layer (Se2/Cl2). Refining the Sr occupancy on both the Bi1 (adjacent to the ionic bridging layer) and Bi2 (adjacent to the van der Waals layer) sites in the Bi<sub>2</sub>O<sub>2</sub> demonstrated that within error, all Sr occupies the Bi2 position at every composition, consistent with the reported structure for SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>. For x = 0, the Se is distributed both across the ionic bridging layer and van der Waals layer, with a statistical site preference for the ionic bridging layer. Upon Sr substitution, this site preference gets more marked; at compositions of x = 0.75 and larger, Se only occupies the ionic bridging layer to within error of the model, refining to a slightly negative value when freely refined, though a small amount of Se on the Se2 site cannot be ruled out.



Figure 3. Crystal structures of  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  for x = 0, 0.25, 0.50, 0.75, 0.95 and 1.0 as modelled by Rietveld refinements from powder data. Partial occupancies are shown by a partial colouring in of an atomic site.

Lattice parameter trends are shown in Figure 4(a). The in-plane lattice parameter *a* varies linearly with *x* across the series, consistent with Vegard's law and the larger size of  $Sr^{2+}$  compared to  $Bi^{3+}$ . By contrast, the lattice parameter *c* varies non-monotonically with *x*. The *c* lattice parameter depends on the thickness of the ionic bridging layer, the van der Waals layer and the  $Bi_2O_2$  fluorite type layer. These layers are being affected simultaneously in different ways, with the total amount of Se being less with *x*, the site preference of Se for the Se1 site increasing with *x* and the amount of Sr increasing on the Bi2 site. The site preference can be seen when the ratio of the occupancy of Se in the Se2 site versus the Se1 site is plotted as a function of *x* in Figure 4(b). A quick drop off is observed around x = 0.5, after which, within uncertainty of modelling the diffraction data, all the Se occupies the Se1 site. Therefore, the amount of Se in the Se1 site is not directly proportional to *x*. The effect of this on the lattice

parameter *c* can be seen when plotting the thickness of the ionic bridging layer, as defined by the cross-plane Bi1-Bi1 distance (Figure 4 (c)). This value changes monotonically but not linearly with *x*. By instead plotting it is a function of the occupancy of Se in the Se1 site,  $x_{Se1}$ , a linear trend is observed (Figure 4(d)). Indeed, this layer thickness for CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> fits on this linear trend as well, despite the smaller overall *c* lattice parameter of CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> compared to SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> (26.6398(5) Å and 26.9997(4) Å respectively). This demonstrates that the thickness of the ionic bridging layer is dependent only on the anion composition at the bridging site, a consequence of the tendency of the alkali earth to only sit at the Bi2 site. The smaller *c* axis of CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> compared to SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> is therefore related to a contraction of the Bi<sub>2</sub>O<sub>2</sub> and van der Waals layers due to the smaller Ca<sup>2+</sup> cation. The ionic bridging layer can therefore be tuned by the anion composition at the bridging site, and the other layers tuned by choice of alkali earth, allowing for different compositional degrees of freedom for modifying the layer thicknesses at different points in the structure. Given the importance of these layers for e.g. thermal conductivity, the ability to tune the bonding at each layer in this type of natural heterostructure could be another method of introducing phonon engineering.

That the presence of Sr on the Bi2 site increases the site preference of Se for the Se1 site is consistent with electrostatics. A lower Coulomb energy is achieved by  $Se^{2-}$  having  $Bi^{3+}$  for its nearest neighbours, and  $Sr^{2+}$  with Cl<sup>-</sup> than compared with the converse. Thus the confinement of  $Sr^{2+}$  to the layer defined by the Bi2 site leads to the confinement of the Se<sup>2-</sup> to the layer defined by the Bi1 site. The effect of doping on the structure is therefore nontrivial as the Sr and Se occupancies are correlated.



Figure 4 (a) lattice parameter trends for *a* (black) and *c* (red) as a function of *x* in Sr<sub>x</sub>Bi<sub>4-x</sub>O<sub>4</sub>Se<sub>1-x</sub>Cl<sub>2+x</sub>. A linear fit is shown for *a* and a trend guide line is shown for *c*. (b) ratio of Se on the Se2 site to the Se1 site as a function of *x* in Sr<sub>x</sub>Bi<sub>4-x</sub>O<sub>4</sub>Se<sub>1-x</sub>Cl<sub>2+x</sub>. A trend guide line is shown as a dashed line. The red point is the ratio from published crystal structure determined from single crystal diffraction in <sup>18</sup>. This value and the corresponding value modelled by powder data here are within error of each other, 0.47(3) and 0.46(2) respectively. (c) the thickness of the bridging ionic layer, as defined by the Bi1-Bi1 distance as a function of Sr<sub>x</sub>Bi<sub>4-x</sub>O<sub>4</sub>Se<sub>1-x</sub>Cl<sub>2+x</sub> and (d) as a function of *x*<sub>Se1</sub> (the Se occupancy of the Se1 site). For (c) a trend guide line is shown, and for (d) a linear fit is shown. The data point for CaBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> is shown in red in (d). For all plots, where error bars are not visible, they are smaller than the size of the data points.

# Band gaps and Electronic Structure

The band gaps were measured via diffuse reflectance UV-Vis spectroscopy on powders of samples for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  and  $CaBi_3O_4Cl_3$ . Figures 5 (a) and (b) show tauc plots as a function of x for the direct and indirect gap respectively. For the values of x = 0.75, x = 0.95 and x = 0.99 two onset features are observed in different energy ranges; these were extracted as  $E_G$  direct,  $E_G$  indirect,  $E_G$  direct 2 and  $E_G$  indirect 2. The observation of two transitions for x = 0.75, x = 0.95 and x = 0.95 and x = 0.99 is of particular interest due to the application of SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, in photocatalysis. SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, is a known photocatalyst, the introduction of ingap states with Se addition may allow for two-photon absorption processes that allow for photocatalytic activities across a broader spectrum of incident light.

A clear shift towards higher energies can also be observed as a function of x. Figures 5 (a) and (b) show the extracted band gap as a function of x. There is a monotonic, linear increase in both the direct and indirect gaps from x = 0 to x = 0.75, with the direct gap increasing by 0.25 eV and the indirect gap increasing by 0.20 eV. Above x = 0.75, this linear relationship breaks down, with the indirect gap decreasing to lower values for x = 0.95 and x = 0.99. At the same time, the band gap associated with the second transition approaches the value observed for x = 1.0 (SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>). For x = 0.99, the higher energy band gaps are within error of that of SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, and that the indirect and direct gaps for the smaller energy transition are within error of each other. This supports a picture of a localised defect-like Se state 1.36(8) eV below the conduction band minimum for x = 0.99. The overall trends are consistent with the introduction of a semi-isolated Se p band upon introduction of Se into SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, which has poor orbital mixing with the O and Cl p states, as corroborated by density of states calculations (Figure 6). The linear relationship in gap between from x = 0and x = 0.75 is evidence of some orbital mixng, however the very modest change (0.2 eV) given the large difference in band gap between x = 0 and x = 1.0 is evidence that this orbital mixing is weak. This is because the Se p states sit at considerably higher energy than the Cl or O p states.

In the DOS calculations (Figure 6), for the SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> (x=1) end member, the top of the valence band is primarily of O 2p character, and the bottom of the conduction band is dominated by Bi 6p states. The energy gap between the valence and conduction band predicted by DFT is 1.60 eV, which is smaller than the experimentally observed indirect gap for SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> of 2.58 eV. The PBE functional used in this work is well known to lead to an underestimate of experimentally observed band gaps but allows for a qualitative comparison with other compounds in the series. As Se is introduced into the structure to Sr0.75Bi3.25O4Se0.25Cl2.75 (x=0.75), the valence band becomes dominated by Se 4p states whereas there is little change to the character of the conduction band. The introduction of the Se 4p states results in a significant reduction in the PBE energy gap to 0.65 eV. This 0.95 eV drop in the band gap as Se is introduced into the structure is consistent with the experimental measurements, which demonstrate a drop from 2.58 eV at x=1 to 1.47 eV for x= 0.75, or a 1.11 eV drop. As the fraction of Se increases in the structure, the number of Se states at the valence band edge increases, but there is only a small change in the energy gap from x=0.75 to x=0, again consistent with the only modest change in band gap observed experimentally across this range. In experiment, the band gap will be modified slightly by disorder, as orderings other than the lowest energy one are accessible as demonstrated by a lack of superstructure ordering and Se occupation of both anion sites observed across the series. Overall, the computational and experimental results support the interpretation of a semi-isolated Se state being introduced in the band gap, where its DOS and bandwidth depend on the amount of Se introduced into the system. The separated Se orbital manifold in the x = 0.75 supports the interpretation of a likely isolated Se orbital manifold in the x = 0.95 and x = 0.99 compositions; however, there is some level of Se-O hybridization in the in-gap states that must be taken into account, as evidenced by the non-trivial O contribution to the in-gap Se states.

The effect of the alkali earth is seen when comparing the band gaps of  $SrBi_3O_4Cl_3$  with CaBi\_3O\_4Cl\_3, which are both indirect and 2.58(7) eV and 2.72(8) eV respectively (Supplementary Figure 14). The direct gaps are 2.80(6) and 2.90(4) eV respectively as well. In the DOS calculations (Supplementary Figure 15), when Sr is swapped for Ca, the computed

energy gap increases from 1.60 to 1.67 eV, an increase that is within error of the experimentally observed increase. In both structures, the valence band edge is dominated by O 2p states and the conduction band by Bi 6p states. The increase in the gap from Sr to Ca is primarily related to the increase in the ionicity of the latter cation. This demonstrates the alkali earth cation to be a minor but independent source of tuning the electronic structure in this series; replacing Sr with the smaller and less electropositive Ca leads to a larger band gap allowing for another mechanism to tune the band gap in this structure type.



Figure 5. (a) Tauc plot for the indirect band gap from diffuse reflectance data for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  (b) Tauc plot for the direct band gap from diffuse reflectance data for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  (c) Extracted indirect and direct band gap energies for the series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$ . x = 0.75, x = 0.95 and x = 0.99 display two onset features in different energy ranges; these were extracted as  $E_G$  direct,  $E_G$  indirect,  $E_G$  direct 2 and  $E_G$  indirect 2.



Figure 6. Density of states plots for low energy  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$  structures. Positions of valence band maximum and conduction band minimum are shown for each system as dashed and dotted lines, respectively, with the corresponding energy gap in eV. Zoom-ins around the Fermi energy are shown in Supporting Figure 15.

Overall, the results presented here differentiate this aliovalent anionic substitution from the usual isovalent substitution; by going from one group to another, the energy difference in the orbital energy levels is increased more than by going from e.g. Cl to Br to I. For example, the band gap difference between  $Bi_2O_2Se (0.8 \text{ eV})^{25}$  and  $BiOCl (3.5 \text{ eV})^{26}$  is much larger than the difference between BiOCl (3.5 eV) and BiOBr (2.9 eV)<sup>27</sup>. Thus, aliovalent anion substitution has qualitatively different effects on the electronic structure compared with isovalent anion substitution. The ability to synthesize this series demonstrate that Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> has significant compositional and structural flexibility, with full aliovalent substitution possible all the way up to SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub>, and substitution of Ca possible for Sr. The existence of photocatalytic PbBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub><sup>28</sup>as well as analogous bromides and other stacking homologues such as Bi<sub>6</sub>O<sub>6</sub>Se<sub>2</sub>Cl<sub>2</sub><sup>29,30</sup> indicates that the level of tunability in terms of compositions and properties in this family of multiple anion and layered materials is vast, providing an alternative paradigm for properties design by anion substitution. A generalised formula can be written as  $A_xBi_{2+2n-x}O_{2+2n}Se_{n-x}X_{2+x}$  where A = (Ca, Sr, Pb) and X = (Cl, Br). It is also worth investigating if Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub> can be doped aliovalently in the other direction, e.g. M<sub>x</sub>Bi<sub>4-</sub>  $_{x}O_{4}Se_{1+x}Cl_{2-x}$  where *M* is a tetravalent element such as Zr, Hf or possibly Ge/Sn.

## Conclusions

Two materials with similar structures but differing band gaps,  $SrBi_3O_4Cl_3$  and  $Bi_4O_4SeCl_2$ , can be tuned between each other across the complex solid solution series  $Sr_xBi_{4-x}O_4Se_{1-x}Cl_{2+x}$ . Further, the alkali earth cation can be replaced by Ca, demonstrating this family of multiple anion Bi-based layered materials to exhibit a large amount of chemical flexibility. Due to the very different electronegativities, any amount of Se for Cl substitution leads to a collapse of the band gap by about 1.2 eV, and at small amounts of Se, two band-gap type transitions are observed in the diffuse reflectance. At larger amounts of Se, a small but linear change in band gap is observed with composition. The structure behaves as more complex than a typical solid solution, with the presence of Sr affecting the distribution of Se across the anion sites. Overall, these results demonstrate that aliovalent anion substitution can be done across a wide range of composition for multiple anion layered materials, and leads to a tuning of the electronic structure and crystal structure that is complex but still follows chemical rules, leading to different types of properties from either aliovalent cation substitution or isovalent anion substitution. Aliovalent anion substitution is therefore a complementary approach to structural and electronic tuning, particularly in layered multiple anion solids.

# **Supporting Information Description**

The supporting information contains four sections :

- 1. Secondary Electron Microscopy (SEM) and Energy Dispersive X-ray Spectroscopy (EDX)
- 2. Powder Diffraction and Rietveld Refinements
- 3. Diffuse Reflectance
- 4. Density Functional Theory Calculations

Crystallographic information files for all compounds for which Rietveld refinements were performed are also included as supporting information.

# References

- Takahashi, H.; Igawa, K.; Arii, K.; Kamihara, Y.; Hirano, M.; Hosono, H. Superconductivity at 43 K in an Iron-Based Layered Compound LaO<sub>1-x</sub>F<sub>x</sub>FeAs. *Nature* 2008, 453 (7193), 376–378.
- Han, G.; Vasylenko, A.; Daniels, L. M.; Collins, C. M.; Corti, L.; Chen, R.; Niu, H.; Manning, T. D.; Antypov, D.; Dyer, M. S.; Lim, J.; Zanella, M.; Sonni, M.; Bahri, M.; Jo, H.; Dang, Y.; Robertson, C. M.; Blanc, F.; Hardwick, L. J.; Browning, N. D.; Claridge, J. B.; Rosseinsky, M. J. Superionic Lithium Transport via Multiple Coordination Environments Defined by Two-Anion Packing. *Science* 2024, 383(6684), 739-745.
- Gibson, Q. D.; Zhao, T.; Daniels, L. M.; Walker, H. C.; Daou, R.; Hébert, S.; Zanella, M.; Dyer, M. S.; Claridge, J. B.; Slater, B.; Gaultois, M. W.; Corà, F.; Alaria, J.; Rosseinsky, M. J. Low Thermal Conductivity in a Modular Inorganic Material with Bonding Anisotropy and Mismatch. *Science* 2021, 373(6558), 1017-1022.
- Hawkins, C. J.; Newnham, J. A.; Almoussawi, B.; Gulay, N. L.; Goodwin, S. L.;
  Zanella, M.; Manning, T. D.; Daniels, L. M.; Dyer, M. S.; Veal, T. D.; Claridge, J. B.;
  Rosseinsky, M. J. Synthesis, Structure, and Properties of CuBiSeCl<sub>2</sub> : A Chalcohalide
  Material with Low Thermal Conductivity. *Chem. Mater.* 2024, *36* (9), 4530–4541.
- (5) Hodges, J. M.; Xia, Y.; Malliakas, C. D.; Alexander, G. C. B.; Chan, M. K. Y.; Kanatzidis, M. G. Two-Dimensional CsAg<sub>5</sub>Te<sub>3-x</sub>S<sub>x</sub> Semiconductors: Multi-Anion Chalcogenides with Dynamic Disorder and Ultralow Thermal Conductivity. *Chem. Mater.* 2018, *30* (20), 7245–7254.
- (6) Thomas, J. M.; Ueda, W.; Williams, J.; Harris, K. D. M. New Families of Catalysts for the Selective Oxidation of Methane. *Faraday Discussions of the Chemical Society* 1989, 87, 33-45.

- (7) Hirai, D. Pinalites: Optical Properties and Quantum Magnetism of Heteroanionic A<sub>3</sub>MO<sub>5</sub>X<sub>2</sub> Compounds. *Inorg. Chem.* **2024**, pp 4001–4010.
- (8) Liu, Y.; Son, W. J.; Lu, J.; Huang, B.; Dai, Y.; Whangbo, M. H. Composition Dependence of the Photocatalytic Activities of BiOCl<sub>1-x</sub>Br<sub>x</sub> Solid Solutions under Visible Light. *Chemistry - A European Journal* **2011**, *17* (34), 9342–9349.
- (9) Wang, Z.; Shi, Z.; Li, T.; Chen, Y.; Huang, W. Stabilität von Perowskit-Solarzellen: Einfluss Der Substitution von A-Kation Und X-Anion. *Angew. Chemie* 2017, *129* (5), 1210–1233.
- (10) Ghaithan, H. M.; Qaid, S. M. H.; Alahmed, Z. A.; Hezam, M.; Lyras, A.; Amer, M.; Aldwayyan, A. S. Anion Substitution Effects on the Structural, Electronic, and Optical Properties of Inorganic CsPb(I1-XBrx)3 and CsPb(Br1-XClx)3 Perovskites: Theoretical and Experimental Approaches. J. Phys. Chem. C 2021, 125 (1), 886–897.
- (11) Kageyama, H.; Hayashi, K.; Maeda, K.; Attfield, J. P.; Hiroi, Z.; Rondinelli, J. M.; Poeppelmeier, K. R. Expanding Frontiers in Materials Chemistry and Physics with Multiple Anions. *Nature Commun.* 2018, 9 (1), 772.
- (12) Charles, N.; Saballos, R. J.; Rondinelli, J. M. Structural Diversity from Anion Order in Heteroanionic Materials. *Chem. Mater.* **2018**, *30* (10), 3528–3537.
- (13) Lingampalli, S. R.; Manjunath, K.; Shenoy, S.; Waghmare, U. V.; Rao, C. N. R. Zn<sub>2</sub>NF and Related Analogues of ZnO. *J. Am. Chem. Soc.* **2016**, *138* (26), 8228–8234.
- (14) You, F.; Liang, F.; Huang, Q.; Hu, Z.; Wu, Y.; Lin, Z. Pb 2 GaF 2 (SeO 3 ) 2 Cl: Band Engineering Strategy by Aliovalent Substitution for Enlarging Bandgap While Keeping Strong Second Harmonic Generation Response. J. Am. Chem. Soc. 2019, 141 (2), 748– 752.
- (15) Chen, J.; Hu, C.; Mao, F.; Feng, J.; Mao, J. A Facile Route to Nonlinear Optical Materials: Three-Site Aliovalent Substitution Involving One Cation and Two Anions. *Angew. Chemie* 2019, 131 (7), 2120–2124.
- (16) Yang, W.; Liu, B.; Yang, B.; Wang, J.; Sekiguchi, T.; Thorsten, S.; Jiang, X. Pseudobinary Solid-Solution: An Alternative Way for the Bandgap Engineering of Semiconductor Nanowires in the Case of GaP-ZnSe. *Adv. Funct. Mater.* 2015, *25* (17), 2543–2551.
- (17) Glicksman, M.; Kraeft, W. D. Effect of High Intrinsic Ion Concentrations on Electron Energies in Solid Solutions of III-V and II-VI Semiconductors. *Solid State Electronics* 1985, 28 (1–2), 151–161.
- (18) Gibson, Q. D.; Manning, T. D.; Zanella, M.; Zhao, T.; Murgatroyd, P. A. E.; Robertson, C. M.; Jones, L. A. H.; McBride, F.; Raval, R.; Cora, F.; Slater, B.; Claridge, J. B.; Dhanak, V. R.; Dyer, M. S.; Alaria, J.; Rosseinsky, M. J. Modular Design via Multiple Anion Chemistry of the High Mobility van Der Waals Semiconductor Bi<sub>4</sub>O<sub>4</sub>SeCl<sub>2</sub>. *J. Am. Chem. Soc.* 2020, *142* (2), 847–856.
- (19) Suzuki, H.; Ozaki, D.; Ishii, Y.; Tomita, O.; Kato, D.; Nozawa, S.; Nakashima, K.; Saeki, A.; Kageyama, H.; Abe, R. A Sillén Oxyhalide SrBi<sub>3</sub>O<sub>4</sub>Cl<sub>3</sub> as a Promising

Photocatalyst for Water Splitting: Impact of the Asymmetric Structure on Light Absorption and Charge Carrier Dynamics. J. Mater. Chem. A **2023**, 11 (28), 15159–15167.

- (20) Ueda, W.; Lin, S.-W.; Tohmoto, I. Highly Selective Oxidative Dehydrogenation of Ethane to Ethene over Layered Complex Metal Chloride Oxide Catalysts. *Catalysis Lett.* 1997, 44, 241-245.
- (21) Toby, B. H.; Von Dreele, R. B. GSAS-II: The Genesis of a Modern Open-Source All Purpose Crystallography Software Package. J. Appl. Crystallogr. 2013, 46 (2), 544– 549.
- (22) Kresse, G.; Joubert, D. From Ultrasoft Pseudopotentials to the Projector Augmented-Wave Method. *Phys. Rev. B* 1999, 4 9(3), 1758
- (23) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple. *Phys. Rev. Lett.* **1996**, 77(18), 3865.
- M Ganose, A.; J Jackson, A.; O Scanlon, D. Sumo: Command-Line Tools for Plotting and Analysis of Periodic Ab Initio Calculations. *J. Open Source Software* 2018, *3* (28), 717.
- (25) Sun, Y.; Zhang, J.; Ye, S.; Song, J.; Qu, J. Progress Report on Property, Preparation, and Application of Bi<sub>2</sub>O<sub>2</sub>Se. *Adv. Func. Mater.* **2020**, 30(49), 2004480.
- (26) Cui, D.; Wang, L.; Xu, K.; Ren, L.; Weng, L.; Yu, Y.; Du, Y.; Hao, W. Band-Gap Engineering of BiOCl with Oxygen Vacancies for Efficient Photooxidation Properties under Visible-Light Irradiation. J. Mater. Chem. A 2018, 6 (5), 2193–2199.
- (27) Wang, Y.; Shi, Z.; Fan, C.; Wang, X.; Hao, X.; Chi, Y. Synthesis, Characterization, and Photocatalytic Properties of BiOBr Catalyst. J. Solid State Chem. **2013**, 199, 224–229.
- (28) Suzuki, H.; Higashi, M.; Tomita, O.; Ishii, Y.; Yamamoto, T.; Kato, D.; Kotani, T.; Ozaki, D.; Nozawa, S.; Nakashima, K.; Fujita, K.; Saeki, A.; Kageyama, H.; Abe, R. PbBi<sub>3</sub>O<sub>4</sub>X<sub>3</sub> (X = Cl, Br) with Single/Double Halogen Layers as a Photocatalyst for Visible-Light-Driven Water Splitting: Impact of a Halogen Layer on the Band Structure and Stability. *Chem. Mater.* 2021, *33* (24), 9580–9587.
- Ji, R.; Lei, M.; Genevois, C.; Zhang, W.; Ming, X.; He, L.; Allix, M.; Yin, C.; Kuang, X.; Xing, X. Multiple Anion Chemistry for Ionic Layer Thickness Tailoring in Bi<sub>2+2n</sub>O<sub>2+2n</sub>Se<sub>n</sub>X<sub>2</sub> (X = Cl, Br) van Der Waals Semiconductors with Low Thermal Conductivities. *Chem. Mater.* 2022, *34* (10), 4751–4764.
- (30) Gibson, Q. D.; Newnham, J. A.; Dyer, M. S.; Robertson, C. M.; Zanella, M.; Surta, T. W.; Daniels, L. M.; Alaria, J.; Claridge, J. B.; Rosseinsky, M. J. Expanding Multiple Anion Superlattice Chemistry: Synthesis, Structure and Properties of Bi<sub>4</sub>O<sub>4</sub>SeBr<sub>2</sub> and Bi<sub>6</sub>O<sub>6</sub>Se<sub>2</sub>Cl<sub>2</sub>. *J. Solid State Chem.* 2022, *312*.

https://doi.org/10.26434/chemrxiv-2024-rrpfv ORCID: https://orcid.org/0000-0001-7020-199X Content not peer-reviewed by ChemRxiv. License: CC BY 4.0